95-004

DIAMOND DRILLING REPORT

on the

RUSTY SPRINGS PROPERTY
Yukon Territory
N.T.S. 116 K/8 and 116 K/9
Latitude 66° 30' N, Longitude 140° 25' W

prepared for

EAGLE PLAINS RESOURCES LTD.

3010, 300 - 5TH AVENUE SOUTHWEST
CALGARY, ALBERTA
T2P 3C4

by

T.J. Termuende, P.Geo.
of
TOKLAT RESOURCES INC.
2720-17TH STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

February 21st, 1996

DIAMOND DRILLING REPORT

on the

RUSTY SPRINGS PROPERTY

Yukon Territory

N.T.S. 116 K/8 and 116 K/9

Latitude 66° 30' N, Longitude 140° 25' W

prepared for

EAGLE PLAINS RESOURCES LTD.

3010, 300 - 5TH AVENUE SOUTHWEST
CALGARY, ALBERTA
T2P 3C4

by

T.J. Termuende, P.Geo.
of
TOKLAT RESOURCES INC.
2720-17TH STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

February 21st, 1996

TABLE OF CONTENTS

SUMMARY 3

INTRODUCTION 5

LOCATION AND ACCESS 6

PROPERTY TENURE 7

HISTORY OF EXPLORATION 9

REGIONAL GEOLOGY AND MINERALIZATION 12

1995 PROGRAM AND RESULTS 14

CONCLUSIONS AND RECOMMENDATIONS 18

REFERNCES 21

LIST OF FIGURES

FIGURE 1 - PROPERTY LOCATION MAP ..... after page 6

FIGURE 2 - REGIONAL GEOLOGY MAP ..... after page 12

FIGURE 3 BIG ONION TRENCH LOCATION MAP ..... after page 17

FIGURE 4 BIG ONION GRID- AG IN SOILS ..... in pocket

FIGURE 5 BIG ONION GRID- PB IN SOILS ..... in pocket

FIGURE 6 BIG ONION GRID- ZN IN SOILS ..... in pocket

FIGURES 7-13 DIAMOND DRILL SECTIONS ..... in pocket

MAP 1 - PROPERTY COMPILATION MAP ..... in pocket

LIST OF APPENDICES

APPENDIX I: CERTIFICATE OF QUALIFICATION

APPENDIX II: ANALYTICAL RESULTS

APPENDIX III: DRILL LOGS

APPENDIX IV: STATEMENT OF EXPENDITURES

SUMMARY

A two-phase trenching and diamond drilling program was carried out at the Rusty Springs property during the period June 4th to September 12th, 1995. Work was carried out by Toklat Resources Inc. at the request of the directors of Eagle Plains Resources Ltd. of Cranbrook, B.C.. 21 drillholes totalling 1658 meters (5440 feet) were completed in the Mike and Orma hill areas, and a total of 400m of bulldozer trenching carried out in the Big Onion area. In addition, a 339-sample soil geochemistry survey was undertaken proximal to the Big Onion showing. A further 35 claim units were added to the existing property, bring the total area to 71 units. In conjunction with geological work, improvements were made to the airstrip, and an all-weather road network was completed to access all areas of the property. The total cost of the 1995 program was $539,000.

Drilling in the Mike Hill area outlined a strong northeast-trending structure which contained high-grade secondary silver-lead-zinc mineralization over a total of 100m, open to the northeast. The mineralization encountered by this drilling was erratic, but indicated a high-temperature carbonate-hosted (manto/chimney) model with potential for primary sulphide minerals at depth. The most impressive mineralized interval to date occurred in hole RS95-M7, where 15.3m assayed 15.1 oz/ton silver, 3% copper, and 1.3% zinc, from 28.6-43.9m.

Five drillholes were completed in the Orma Hill area during 1995, and confirmed the high-grade tenor of mineralization there. The area, drilled extensively in the late 1970s, contains similar mineralogy to that seen at the Mike Hill, is defined over 700m of strike length, and is apparently open to the south. Recoveries from 1995 drilling were markedly improved from those seen in past drilling programs.

The Big Onion showing, a 1994 prospecting discovery, lies 1.6 km south-west of the Mike Hill zone. It is steeply dipping, and lies roughly parallel to the Orma Zone. Trenching was undertaken to test five soil geochemical anomalies delineated during the 1994 season. Though outcrop material was not reached in any trenches, mineralized subcrop was exposed, and found to contain silver, lead, zinc and copper within the groundmass of silicified dolomite breccia material. Further work is planned for the area during 1996.

All drilling and support equipment was left on the property over the winter, with Eagle Plains planning a 10,000' deep-hole drilling program during 1996 to test for deep-seated primary sulphide mineralization.

INTRODUCTION

The Rusty Springs Property area has seen sporadic exploration since 1975, when rusty ground seeps were recognised during regional oil and gas exploration programs. Subsequent ground examination revealed silver-lead-zinc mineralization nearby. Staking of the area by Rio Alto Exploration followed, with systematic exploration programs carried out over the years by various operators.

High-grade mineralization was discovered in the Orma Hill area in 1978, and the focus of exploration efforts were concentrated in this area. Virtually all drilling was aimed at the Orma Vein since this time. Preliminary work, previous to the Orma discovery however, outlined anomalous soil geochemical values in the Mike Hill area. Limited drilling was carried out to define the nature of this mineralization, but met only limited success. No drilling or trenching was done on the Mike Hill since 1978.

In 1992, the final core claims comprising the Rusty Springs Property were allowed to lapse. They were subsequently restaked, and optioned to Eagle Plains Resources.


Bulldozer trenching of the Mike Hill area in 1994 resulted in the discovery of high grade silver-lead-zinc mineralization within quartz veins and silicified carbonate material. Drilling carried out during 1995 was aimed at evaluating the mineralized zones exposed on the Mike Hill. Trenching and soil geochemical sampling completed at the Big Onion area was follow-up of geochemical work initiated during 1994.

LOCATION AND ACCESS

The Rusty Springs Ag/Pb/Zn/Cu prospect is situated in the north-western part of the Yukon Territory at approximately 66° 30' North latitude and 140° 25' West longitude in N.T.S. 116 K/8 and 116 K/9. The property is about 8 km south of the Arctic Circle and 29 km east of the Alaska border (see Figure 1; following).

Access to the property is via wheel or ski-equipped aircraft or by winter road. An all-weather, 530m (1800') airstrip was constructed in 1994. Supply centres are located at Dawson City, Yukon (274km), Circle, Alaska (175km), or Fairbanks, Alaska (365km). Airstrip staging areas to Rusty Springs are available along the Dempster Highway at Eagle Plains (164kms), or from the "150 Mile" airstrip (137km).

Road access has been previously developed for winter haulage from Mile 123 (Ogilvie Crossing) on the Dempster Highway over a distance of 193 km. The Dempster Highway is a government-maintained all-weather road providing access from the south. The winter road access traverses gently sloping terrain without any major topographic obstacles.



EAGLE PLAINS RESOURCES LTD.

RUSTY SPRINGS PROJECT

LOCATION MAP

Date: FEB 1996	Scale: 1:6,000,000	
Toklat Resources Inc.		Fig no. 1

PROPERTY TENURE

The claims consist of 71 quartz-claims, staked in accordance with existing Yukon Quartz Mining Act regulations. Relative claim and post locations are shown on Map 1, in pocket. A summary of pertinent tenure information is provided below:

Claim Name	Record No.	Units	Location Date	Expiry Date
Eric 1	YB41182	1	July 29, 1992	Dec. 10, 2003
Eric 2	YB41183	1	July 29, 1992	Dec. 10, 2003
Eric 3	YB41184	1	July 29, 1992	Dec. 10, 2003
Eric 4	YB41185	1	July 29, 1992	Dec. 10, 2003
Eric 5	YB41186	1	July 29, 1992	Dec. 10, 2003
Eric 6	YB41187	1	July 29, 1992	Dec. 10, 2003
Eric 7	YB48768	1	June 10, 1994	Dec. 10, 2003
Eric 8	YB48769	1	June 10, 1994	Dec. 10, 2003
Jessica 1	YB41188	1	July 29, 1992	Dec. 10, 2003
Jessica 2	YB41189	1	July 29, 1992	Dec. 10, 2003
Jessica 3	YB41190	1	July 29, 1992	Dec. 10, 2003
Jessica 4	YB41191	1	July 29, 1992	Dec. 10, 2003
Jessica 5	YB41192	1	July 29, 1992	Dec. 10, 2003
Jessica 6	YB41193	1	July 29, 1992	Dec. 10, 2003
Jessica 7	YB48750	1	June 10, 1994	Dec. 10, 2003
Jessica 8	YB48751	1	June 10, 1994	Dec. 10, 2003
Shelly 1	YB48752	1	June 10, 1994	Dec. 10, 2003
Shelly 2	YB48753	1	June 10, 1994	Dec. 10, 2003
Shelly 3	YB48754	1	June 10, 1994	Dec. 10, 2003
Shelly 4	YB48755	1	June 10, 1994	Dec. 10, 2003
Shelly 5	YB48756	1	June 10, 1994	Dec. 10, 2003
Shelly 6	YB48757	1	June 10, 1994	Dec. 10, 2003
Shelly 7	YB48758	1	June 10, 1994	Dec. 10, 2003
Shelly 8	YB48759	1	June 10, 1994	Dec. 10, 2003
Shelly 9	YB48760	1	June 10, 1994	Dec. 10, 2003
Shelly 10	YB48761	1	June 10, 1994	Dec. 10, 2003
Shelly 11	YB48762	1	June 10, 1994	Dec. 10, 2003
Shelly 12	YB48763	1	June 10, 1994	Dec. 10, 2003
Shelly 13	YB48764	1	June 10, 1994	Dec. 10, 2003
Shelly 14	YB48765	1	June 10, 1994	Dec. 10, 2003
Shelly 15	YB48766	1	June 10, 1994	Dec. 10, 2003
Shelly 16	YB48767	1	June 10, 1994	Dec. 10, 2003
Joel 1	YB52722	1	Aug. 27, 1994	Dec. 10, 1999
Joel 2	YB52723	1	Aug. 27, 1994	Dec. 10, 1999
Joel 3	YB52724	1	Aug. 27, 1994	Dec. 10, 1999
Joel 4	YB52725	1	Aug. 27, 1994	Dec. 10, 1999
Joel 5	YB53897	1	July 2, 1995	Dec. 10, 2000
Joel 6	YB53898	1	July 2, 1995	Dec. 10, 2000

Claim Name	Record No.	Units	Location Date	Expiry Date
Joel 7	YB53899	1	July 2, 1995	Dec. 10, 2000
Joel 8	YB53900	1	July 2, 1995	Dec. 10, 2000
Glen	YB53901	1	July 2, 1995	Dec. 10, 2000
Calli	YB53902	1	July 2, 1995	Dec. 10, 2000
Marlo	YB53903	1	July 2, 1995	Dec. 10, 2000
Katie	YB53904	1	July 2, 1995	Dec. 10, 2000
Alecia	YB53905	1	July 2, 1995	Dec. 10, 2000
Kelsey	YB53906	1	July 2, 1995	Dec. 10, 2000
Lauren	YB53907	1	July 2, 1995	Dec. 10, 2000
Tyler	YB53908	1	July 2, 1995	Dec. 10, 2000
Casey	YB53909	1	July 2, 1995	Dec. 10, 2000
Lane	YB53910	1	July 2, 1995	Dec. 10, 2000
Kayla	YB53911	1	June 16, 1995	Dec. 10, 2000
Ben	YB53912	1	June 16, 1995	Dec. 10, 2000
Trevor	YB53913	1	June 16, 1995	Dec. 10, 2000
James	YB53914	1	June 16, 1995	Dec. 10, 2000
Connor 1	YB54257	1	Sept. 7, 1995	Sept. 7, 1996
Connor 2	YB54258	1	Sept. 7, 1995	Sept. 7, 1996
Connor 3	YB54259	1	Sept. 7, 1995	Sept. 7, 1996
Connor 4	YB54260	1	Sept. 7, 1995	Sept. 7, 1996
Connor 5	YB54261	1	Sept. 7, 1995	Sept. 7, 1996
Connor 6	YB54262	1	Sept. 7, 1995	Sept. 7, 1996
Connor 7	YB54263	1	Sept. 7, 1995	Sept. 7, 1996
Connor 8	YB54264	1	Sept. 7, 1995	Sept. 7, 1996
Connor 9	YB54265	1	Sept. 7, 1995	Sept. 7, 1996
Matt 1	YB54266	1	Sept. 7, 1995	Sept. 7, 1996
Matt 2	YB54267	1	Sept. 7, 1995	Sept. 7, 1996
Matt 3	YB54268	1	Sept. 7, 1995	Sept. 7, 1996
Matt 4	YB54269	1	Sept. 7, 1995	Sept. 7, 1996
Diduck 1	YB54270	1	Sept. 7, 1995	Sept. 7, 1996
Diduck 2	YB54271	1	Sept. 7, 1995	Sept. 7, 1996
Diduck 3	YB54272	1	Sept. 7, 1995	Sept. 7, 1996
Diduck 4	YB54273	1	Sept. 7, 1995	Sept. 7, 1996

Total: 71 units

HISTORY OF EXPLORATION

During the fall of 1975, while investigating an oolitic iron formation, a rusty spring-seep was observed by M.N. Chernoff. Upon investigation, the spring was found to be associated with high-grade silver, lead, zinc, and copper mineralization. A total of 92 quartz claims and 15 iron claims were staked during the fall and winter seasons.

During the 1976 summer season, a preliminary investigation of the property was conducted by Rio Alto Exploration Ltd., under the supervision of M.N. Chernoff. Exploration completed included helicopter-supported geological mapping, prospecting, sampling of mineralized float, and limited soil geochemical sampling. This work established the structural setting, confirmed the presence of high-grade silver values, and demonstrated the usefulness of soil geochemistry. The mineral occurrences were considered to be hydrothermal vein systems with supergene enrichment possibilities.

Based on encouraging results from this preliminary reconnaissance, a follow-up field program consisting of geological mapping, soil geochemical sampling, and 975 metres (3200 feet) of diamond drilling was conducted in 1977. Again, the results were considered positive, even though poor drill core recoveries were obtained. Additional ground was staked to give a total of 380 quartz claims and 15 iron claims.

A geological thesis by G. Schoel concluded that the mineralization was probably Mississippi Valley type.

During the winter of 1978, fuel, drill equipment, and supplies were ferried to the property by tractor train. That summer, two picket grids (totalling 67 line km) were established over the claims. Further geological mapping, soil geochemical sampling, diamond drilling (1840 metres), and metallurgical sampling were also completed. Poor drill core recoveries once again hampered the effectiveness of the program.

A geological thesis was undertaken by D. Hansen, again emphasising a Mississippi Valley type model for the mineralization.

Exploration during the period 1975 to 1978 inclusive was funded by Rio Alto Exploration.

In 1979, detailed geological mapping, a soil geochemical survey, an Induced Polarization survey, and a gravity survey were completed. Joint funding of this work was by Rio Alto and E & B Explorations Ltd. of Calgary, Alberta.

A geological thesis by J. Bankowski indicated a hydrothermal exhalative nature.

In 1980, E & B Explorations Ltd. as operator, focused on the widespread mineralization discovered on the Orma Hill. Their program saw 1830 metres (6000 feet) of diamond drilling, bulldozer trenching, and some detailed geological mapping completed. Core recoveries were not significantly improved over previous years.

In 1982, Taiga Consultants Ltd. was contracted by Kenton Natural Resources to carry out a geological evaluation of the property and subsequently a comprehensive mineral exploration and diamond drilling program. During this period, 510 metres (1673 feet) of diamond drilling was completed, as well as a soil geochemical survey, a geophysical (VLF-EM) survey, detailed geological mapping of the property, and six trenches dug in order to define the style of mineralization.

The most recent research work, carried out by Jill Kirker (April 1982), strongly supports a hydrothermal origin for the mineralization.

In 1983, additional geophysical surveying and geochemical sampling were completed by Taiga Consultants Ltd. to detail geophysical conductors and geochemical zones previously outlined. During the fall of 1983, 488 metres (1600 feet) of diamond drilling were completed.

In 1986, Kenton Natural Resources Inc., as operator, drilled two holes in the valley bottom between the Mike and Orma Hills in order to test an I.P. anomaly delineated in 1979 by previous

operators. This program consisted of 404m (1326') of drilling, and failed to intersect any significant mineralization. The drill was removed from the property following this short program.

The claims were gradually allowed to lapse, and in the spring of 1992, all claims comprising the property had expired. R.W. Termuende restaked the core area of the property on July 29th, 1992. 12 quartz claims were recorded, consisting of the Eric 1-6 and Jessica 1-6 claims.

A $190,000 exploration program was completed during the 1994 season. The focus of the two-stage program was to carry-out further systematic exploration in the Mike Hill area, as well as undertake initial reconnaissance work in the region surrounding the claim area. A total of 531 soil, 67 rock, and 36 silt samples were taken, over two separate control grids that were established on the property, covering the Mike Hill and Big Onion areas. Concurrent with the geological program, efforts were made to improve the infrastructure of the property, and included construction of a 530m (1800') airstrip, a 3.4km permanent road connecting the airstrip and camp areas, and 10km of drill-tote trails throughout the property. Environmental work was also undertaken in the Orma Hill area, with 8 man days spent collecting some 140 used fuel drums, refuse-burning, and general clean-up activities in areas of past development.

REGIONAL GEOLOGY

The regional geology, as illustrated in Figure 2, following, is based on photogeologic interpretation by Taiga Consultants Ltd.. Bedrock exposures within this region range in age from Devonian to Cretaceous. The oldest rock units exposed in the Rusty Springs area are the carbonates of the Middle Devonian Ogilvie Formation. All of the mineral occurrences discovered in this area to date are hosted by this unit.

Disconformably overlying the Ogilvie Formation are the shale, siltstone, and minor limestone units which comprise the Carboniferous Hart River Formation. The Hart River is succeeded by the late Carboniferous Ettrain Formation which consists of shale and carbonate units.


The Ettrain is disconformably overlain by the Permian Jungle Creek Formation, which in turn has been subdivided into a lower carbonate and clastic sequence and an upper shale sequence.

The Jungle Creek is unconformably overlain by the Jurassic to lower Cretaceous Kingak Formation. The Kingak consists predominantly of shale with minor siltstone.

Structurally, the property lies along the axes of two northerly oriented anticlines. Locally, along the axes of the structures, a culmination or dome occurs in the Orma Hill and the Mike Hill areas. This domal structure may be the expression of one or more intrusives emplaced along the axial portion of these anticlines. Drilling indicates that a low-angle thrust fault likely displaces the Orma Vein system at depth.

Mineralization

Since 1976, approximately 4000 soil samples have been collected for geochemical analyses. These analytical results indicate that prominent, well-defined mineralized structures are present within the property area.



LEGEND

KJR	Kingak Fm. - shale
Pjc_2	Jungle Cr. Fm. (shale unit)
Pjc_1	Jungle Cr Fm. (carbonate unit)
Ce	Eltrain Fm - shale and limestone
Chr	Hart River Fm shale, siltstone and limestone
Do	Ogilvie Fm - limestone

15°	Strike and dip (estimated)
	Overturned dip
	Anticline
	Syncline
	Fault, lineament
	Thrust fault
	Geological contact

EAGLE PLAINS RESOURCES LTD.

RUSTY SPRINGS PROJECT

Regional Geology

(Geology after Taiga, 1983)

Scale	Date	N.T.S
see bar	FEB. 1996	116 K8, 116 K9

Toklat Resources Inc. Fig. no : 2

Significant lode mineralization has been recognised on the property in three specific areas, namely at the Orma Hill, Mike Hill, and Big Onion showings. Mineralization to date consists of primarily "Bonanza Grade" silver-lead-zinc-copper veins oriented NW/SE and NE/SW. Though the Orma Hill has seen extensive stripping and diamond drilling activity, mineralized outcrop in place at both the Mike Hill and Big Onion locations were not discovered until 1994.

A total of 35 locations of mineralized material (primarily float) have been outlined in the property area, and are shown on Map 1; in pocket.

1995 PROGRAM AND RESULTS

The primary focus of the 1995 exploration program at Rusty Springs was to evaluate mineralization discovered in trenches at the Mike Hill Zone, and to further explore by trenching and soil geochemistry in the area of the Big Onion showing. In addition, limited drilling was completed within the Orma Zone to confirm the tenor of mineralization and to try and improve on poor recoveries experienced by previous operators. Details of this work are outlined below:

MIKE HILL

A total of 16 holes were drilled along a 300m strike length in order to test a prominent 700m-long silver-lead-zinc soil geochemical anomaly discovered during previous programs. Drilling in the area had been carried out in the late 1970s by past operators, but all holes were vertical and drilled to shallow depths, providing inadequate and ambiguous results.

A summary of drillhole information in the Mike Hill Area is provided below:

HOLE NO.	LOCATION	AZIMUTH/DIP	DEPTH	RECOVERY
RS95-M1	L1+00N/1+25E	310°/-50°	187.8m	
RS95-M2	L1+00N/0+08E	130°/-45°	65.2m	
RS95-M3	L1+00N/0+40E	250°/-45°	55.5m	
RS95-M4	L1+00N/0+40E	250°/-70°	32.3m	
RS95-M5	L1+75N/0+15E	130°/-45°	77.7m	
RS95-M6	L1+75N/0+15E	130°/-80°	32.9m	
RS95-M7	L1+75N/0+15E	130°/-60°	43.9m	
RS95-M8	L1+75N/0+15E	130°/-60°	87.8m*	74.6%
RS95-M9	L1+75N/0+15E	130°/-85°	154.8m**	74.8%
RS95-M10	L1+00N/0+08E	130°/-65°	87.8m	92.6%
RS95-M11	L1+00N/0+08E	130°/-85°	97.2m	94.9%
RS95-M12	L0+00N/0+25W	130°/-45°	75.3m	98.0%

HOLE NO.	LOCATION	AZIMUTH/DIP	DEPTH	RECOVERY
RS95-M13	L0+00N/1+25W	130°/-45°	110.0m	86.8%
RS95-M14	L0+00N/1+25W	130°/-70°	130.5m	97.2%
RS95-M15	L1+75N/0+50E	310°/-60°	74.4m	92.1%
RS95-M16	2+75N/0+15W	130°/-60°	121.3m	99.0%
			Total: 1,435.4m	

* Re-drill of hole RS95-07

** Re-drill of hole RS95-06

Results

Drilling in the Mike Hill area revealed the presence of a vertcal, well-developed mineralized structure. Mineralization occurs in secondary (oxide) form, and is erratically distributed throughout the drilling area. See Diamond Drill Sections, Figures 7-11, in pocket.

Intervals grading as high as 9.8% Pb and 5.7% Zn over 15.5m from 6.0-21.5m were intersected in hole RS95-M3, while hole RS95-M4 returned 7.39% Zn and 3.47 oz/t Ag over 11.6m from 0.0- 11.6m, and a further 6.6m grading 7.8% Zn from 16.6-23.2m. The best mineralization encountered to date in the Mike Hill area was seen in hole RS95-M7, which yielded 15.3m bearing 15.1 oz/t Ag, 3.0% Cu, 1.3% Zn, and 0.77% Pb from 28.6m to the end of the hole at 43.9m. The high-grade nature of mineralization at Rusty Springs was demonstrated in hole RS95-M15, which returned 55.33 oz/t Ag, 7.59% Cu, and 2.61% Zn over 0.6m at 35.1-35.7m. In addition, interval 35.7-36.8m contained 6.29 oz/t Ag, 1.14% Cu, and 4.08% Zn.

ORMA HILL

A total of five drill holes were completed in the Orma Hill area, and were intended to confirm the tenor of mineralization reported by past operators. A summary of drilling particulars is given below:

HOLE NO.	LOCATION	AZIMUTH/DIP	DEPTH	RECOVERY
OR95-01	Trench 6 Area	065°/-45°	98.1m	
OR95-02	Trench 6 Area	065°/-70°	38.4m	
OR95-03	Trench 6 Area	065°/-89°	26.8m	
OR95-04	Trench 7 Area	065°/-45°	31.7m	
OR95-05	Trench 7 Area	065°/-90°	28.0m	
			Total: 223.0m	

Results

Significant results from Orma Hill drilling were obtained in hole OR95-1 which returned 12.8 oz/t Ag, 1.03% Cu, and 18.8% Pb over 1.7m from 17.3-19.0m, and in OR95-02 which contained 3.9 oz/t Ag, 1.31% Cu, and 11.4% Pb over 1.5m within the interval 15.4- 16.9m. See Diamond Drill Sections; Figures 12, 13, in pocket.

BIG ONION

The Big Onion showing was discovered during prospecting and regional stream-sediment sampling work carried out in 1994. Mineralization here consists of high-grade silver-lead-zinc (copper) within quartz vein material, hosted by vuggy dolomite rocks. Distinctive pyromorphite/copper material identical in appearance to that exposed in Mike Hill trenches located some 1.6km from the Big Onion area, suggesting coeval emplacement, and widespread mineralizing activity.

Trenching and soil geochemical sampling was carried out in the Big Onion area to further evaluate its economic potential (see Trench Location Map, Figure 3). Soil sampling in the area revealed a number of spot-highs, which were subsequently trenched with a D-7 bulldozer.

Results


A total of 475m of stripping was completed throughout the program, with results ambiguous and inconclusive. No outcrop exposures were uncovered in the area due to extensive cover, though numerous mineralized fragments were encountered, including Ag-Pb mineralized shear material from a trench at BL 1+50S which returned 18.18 oz/t Ag and 70.60% Pb (grab). Sample TTRS-32, taken of mineralized trench debris exposed 50m south of the Big Onion showing, returned 7.33 oz/t Ag and 1.18% Cu (grab). In a trench dug at L2+50S/1+25E, malachite-coated vugs were observed within silicified dolomitic breccia fragments unearthed.

A total of 339 soil samples were taken in the Big Onion area, over a grid extending to the south-east of the existing grid (see Figures 4-6, following) . A number of spot-anomalies were encountered, with consistent, moderate Ag-Pb-Zn enrichment evident over 300m from L1+00S/7+00E to L4+00S/7+00E.

All samples were shipped to Eco-Tech Laboratories of Kamloops, BC for analysis. Samples were analyzed by ICP and Au geochem methods, with standard fire assays carried out on high-grade material.

G.P.S. SURVEY

An extensive G.P.S. Survey was completed over the entire property area from August 20-25. Interior Reforestation of Cranbrook, B.C. was contracted to carry out the survey, with M. Honeyman as operator. All drillsites, trenches, roads, claimposts, core storage locations, and topographic features were tied in to a base-station established at the Rusty Springs camp. This information forms the base for Map 1, located in back pocket. Location accuracy is estimated to be ± 5cm.



TRENCH

EAGLE PLAINS RESOURCES LIMITED		
RUSTY SPRINGS PROJECT		
BIG ONION TRENCH LOCATION MAP		
DATE: FEB 1996	DRAWN / MAPPED: I. JONES / C. DOWNIE	N.T.S.: 116 K/8, 116 K/9
TOKLAT RESOURCES INC.		FIGURE No. 3

CONCLUSIONS

The Rusty Springs property encompasses numerous high-grade Ag/Pb/Zn/Cu occurrences exposed in outcrop and in float of apparent hydrothermal "fissure-vein" type setting in a mid-Devonian carbonate sequence. These occurrences occur over widespread distances, and emphasise the excellent mineral potential of the area.

The property has been actively explored since 1976. Prior to 1995, this exploration has consisted of 67 km of cut-and-picket grid, an Induced Polarization survey, a gravity survey, a VLF-E.M. survey, soil geochemistry, detailed mapping and prospecting, 'cat' trenching, and 5642 metres of diamond drilling.

Mineral deposits exist elsewhere in North America which reflect the same bigenetic Hydrothermal Vein/MVT mineral styles suggested by work thus far at Rusty Springs. Two such deposits, located at Prairie Creek, NWT, and Pioche, Nevada, demonstrate the significant potential of these systems for the development of multi-million ton orebodies. These areas have in common large tabular massive sulphide bodies tapped by steeply-dipping quartz vein systems containing galena, tetrahedrite, sphalerite, and minor copper minerals within Devonian strata well removed from any known intrusive activity.

On the Orma Hill, mineralization is exposed at the surface in trenches, in samples of diamond drill core, and inferred from geochemical surveys, over a distance of 760 metres in north-northwest direction. A steeply dipping north-south epithermal vein system appears to be the primary source of the mineralization. Grade and tonnage of this zone has not yet been defined. This structure has not been adequately tested by deep drilling for the possible presence of underlying MVT mineralization.

On the Mike Hill, a strong, steeply-dipping northeast trending structure hosts erratic high-grade mineralization, with soil enrichment occurring over 700m. Secondary (oxide) mineralization was noted to vertical depths of up to 64m (211') in hole RS95-M15, suggesting that the primary source lies to depth.

At the Big Onion area, mineralization apparently genetically related to Mike Hill material was discovered in 1994. Follow-up trenching and additional geochemical sampling has revealed widespread mineralization, but no economic concentrations have been located.

RECOMMENDATIONS

A 3000m (10,000'), six-to eight hole deep drilling program is recommended for the property to test for a deep-seated primary source for the widespread secondary mineralization located to date on the property. Additional bulldozer trenching with contingent follow-up diamond drilling is also recommended for the Big Onion area, where soil geochemical sampling has identified anomalous geochemical enrichment over 300m of strike length.

A budget for proposed work is included below:

PROPOSED BUDGET

Phase 1

Personnel	$ 50,000.00
Diamond-Drilling (10000 ft x $35/foot)	350,000.00
Helicopter Support	25,000.00
Heavy Equipment	20,000.00
Mob/Demob	25,000.00
Analytical	8,000.00
Meals/Grocery	10,000.00
Truck and Equipment Rentals	5,000.00
Fuel (Diesel, Gasoline, Propane)	4,000.00
Supplies	3,000.00

Continued

Miscellaneous	6,000.00
Report/Reproduction	4,000.00
Sub-Total:	$510,000.00
10% Contingency:	50,000.00
TOTAL:	**$560,000.00**

REFERENCES

Ager, C.A. (1979): Gravity & I.P. Survey Rusty Springs Prospect, private corporate report.

Bacon, Donaldson & Associates Ltd. (1979): Rusty Springs Prospect Metallurgical Testing Report, private corporate report.

Bankowski, J. & Rio Alto Exploration (1980): Report on 1980 exploration Progress on Rusty Springs, Y.T.

Bankowski, J. & D. Hoy (1980): Report in geochemical sampling, Rusty Springs, Y.T.

Beck, F.M. (1978): Rusty Springs Prospect 1978 Exploration Summary, private corporate report.

Chernoff, M.N. (1975): Geology of Rusty Springs Mineral Prospect.

Chernoff, M.N. (1976): Geology of the Rusty Springs Mineral Prospect.

Downie, C.C. (1994): Geological Report on the Rusty Springs Property.

Guilbert, J.M. & Park, C.F. (1986): The Geology of Ore Deposits; W.H. Freeman and Company, pp 158-162.

Hansen, D. (1979): A Geological Model of the Rusty Springs Prospect.

Hansen, D. & Bankowski J. (1979):
Report of Geological Program Rusty Springs Prospect.

Hilland, D.W. (1979): Rusty Springs Prospect - A Brief Summary, private corporate report.

Heard, R.T. (1980): Summary Report on Rusty Springs Mineral Prospect.

Kirker, J. (1980): Thesis Proposal (M.Sc.). University of Calgary

Schoel, G. (1978): Preliminary Report on the Rusty Springs Zn-Pb-Cu-Ag Prospect, private corporate report.

Tschanz, C.M. and Pampeyan, E.H. (1970): Geology and Mineral Deposits of Lincoln County, Nevada; Nevada Bureau of Mines and Geology, Bulletin #73.

White, P.S. (1978): Report of 1977 Exploration of Rusty Springs Prospect.

White, P.S. (1978): Interim Geologic Report Rusty Springs Prospect. Private corporate report.

White, P.S. (1979): Report of 1979 Exploration on Rusty Springs Mineral Prospect.

APPENDIX I

Certificate of Qualification

CERTIFICATE OF QUALIFICATION

I, Tim J. Termuende, of 2720-17th St. South in the City of Cranbrook in the Province of British Columbia do hereby certify that:

1) I am a Professional Geoscientist registered with the Association of Professional Engineers and Geoscientists of British Columbia.


2) I am a graduate of the University of British Columbia (1987) with a B.Sc. degree in Geology, and have practised my profession as geologist continuously since graduation.

3) This report is supported by data collected during fieldwork conducted from June 4th to September 12th, 1995.

4) I have no direct interest in the Rusty Springs claims. I presently hold 202,000 shares of Eagle Plains Resources.

Dated this 21st day of February, 1996 in Cranbrook, British Columbia.

TOKLAT RESOURCES INC.



Tim J. Termuende, P.Geo.
President

APPENDIX II

Analytical Results

Eco-Tech LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-433

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B C.
V1C 4H4

20-Jul-95

ATTENTION: TIM TERMUENDE

217 core samples received July 12, 1995
PROJECT #: "Rusty Springs"
SHIPMENT #: RS02

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Zn (%)
51	R95-01 62 5-64 0m	641 4	18.71	2 55	-
149	R95-02 22 6-23 7m	-	-	-	1.34
150	R95-02 23 7-25.1m	-	-	-	1.53
151	R95-02 25.1-25 5m	-	-	-	13.70
160	R95-02 34 6-35 6m	-	-	-	1.22
169	R95-02 42 8-44 5m	-	-	-	1.98
170	R95-02 44 5-46 1m	-	-	-	6.66
171	R95-02 46.1-46 8m	-	-	-	2.42
184	R95-02 59 0-59 9m	-	-	-	1.99
185	R95-02 59 9-62.3m	-	-	-	4.36
189	R95-03 26 6-27 6m	-	-	-	1.18
192	R95-03 29 4-30.0m	-	-	-	1 26
193	R95-03 30.0-30.5m	-	-	-	1.81
QC DATA:					
Standard:					
Mp-1A		70 0	2 04	-	19.04
HV-1		-	-	0 52	-

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

3/95Toklat

Eco-Tech LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-373

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

30-Jun-95

ATTENTION: TIM TERMUENDE

25 rock samples received June 27, 1995
PROJECT #: None Given
SHIPMENT #: None Given

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	R95-03 0-5'	47.3	1 38	-	-	1.87
2	R95-03 4 6-6 0M	82.1	2 39	-	-	-
3	R95-03 6.0-7.5M	-	-	-	-	8.37
4	R95-03 7 5-7.9M	-	-	-	-	21 30
5	R95-03 7.9-8.5M	-	-	-	-	30.80
7	R95-03 5.'-10'	282.3	8.23	-	-	2 72
8	R95-03 9 5-10.5M	-	-	-	-	2.98
9	R95-03 10 5-11 5M	-	-	1 01	1.52	10.30
10	R95-03 11 5-12 7M	-	-	1.42	11.30	1 42
11	R95-03 12 7-13 9M	-	-	-	15.20	-
12	R95-03 10'-15'	334.1	9.74	-	-	-
13	R95-03 13.9-15.1-M	56.3	1.64	-	45 80	-
15	R95-03 15 8-18.1M	-	-	-	19.60	5 63
16	R95-03 18 1-19.1M	34.3	1 00	-	2 71	7 42
17	R95-03 15-20'	134 6	3 93	-	-	-
18	R95-03 19 1-20.0M	234.9	6.85	1.08	13.30	3.23
19	R95-03 20 0-21.5M	30 4	0.89	-	2.92	7.08
20	R95-03 21 5-22.8M	-	-	-	-	2.06
23	R95-03 23 9-24 6M	-	-	-	-	1 78
	QC DATA:					
	Resplit					
RS1	R95-03 0-5'	47 6	1.39	-	-	1.93
	Standard:					
Mp-1A		-	-	1.44	4.32	-

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/95Toklat

Eco-Tech
LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-434

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

24-Jul-95

ATTENTION: TIM TERMUENDE

141 Core samples received July 11, 1995
PROJECT #: Rusty Springs
SHIPMENT #: RS02

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
1	R95 - 4 0 - 5'	40 3	1.18	-	-	9.03
2	R95 - 4 5' - 10'	50 3	1.47	-	-	4.77
3	R95 - 4 3.0 - 4 0m	-	-	-	-	16.80
4	R95 - 4 4.0 - 5.4m	418 6	12 21	-	-	5.73
5	R95 - 4 5.4 - 6 7m	210.4	6.14	-	-	
6	R95 - 4 6 7 - 7 5m	132.6	3.87	1 03	-	10.40
7	R95 - 4 7 5 - 9 1m	152.4	4 44	1.08	-	11.30
8	R95 - 4 9.1 - 10 3m	-	-	-	-	1.48
9	R95 - 4 10 3 - 11 0m	-	-	-	-	8.40
10	R95 - 4 11.0 - 11 6m	39 3	1.15	-	-	10 33
15	R95 - 4 15.6 - 16.6m	30 3	0 88	-	-	-
16	R95 - 4 16 6 - 17 6m	31.4	0 92	-	-	1.26
17	R95 - 4 17 6 - 19.1m	34 6	1.01	-	-	10.26
18	R95 - 4 19.1 - 20.1m	-	-	-	-	6.36
19	R95 - 4 20.1 - 20.9m	-	-	-	-	4.81
20	R95 - 4 20.9 - 23 2m	-	-	-	-	10.72
23	R95 - 4 25.9 - 26 9m	-	-	-	-	1.54
31	R95 - 5 10 - 15'	90.9	2 65	-	-	-
32	R95 - 5 15 - 20'	70.4	2.05	-	-	-
33	R95 - 5 20 - 25'	183 4	5.35	-	-	-
34	R95 - 5 25 - 27'	209 8	6.12	-	-	-
35	R95 - 5 8 2 - 9 3m	30 6	0.89	-	-	-
39	R95 - 5 13 5 - 14.2m	-	-	-	1.72	-
114	R95 - 7 14.5 - 15 6m	-	-	-	-	1.36
121	R95 - 7 22 5 - 23 5m	31.6	0 92	7 78	-	-
122	R95 - 7 23 5 - 24 5m	-	-	7 72	-	-
123	R95 - 7 24 5 - 25 5m	409 3	11.94	1.44	-	-

Frank J. Pezzotti, A.Sc.T. B.C. Certified Assayer

TOKLAT RESOURCES INC. AK 95-434 24-Jul-95

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Sb (%)	Zn (%)
124	R95 - 7 25.5 - 26 6m	31.2	0 91	1.49	-	-	-
127	R95 - 7 28 6 - 29.6m	283 6	8.27	1.33	-	-	2.06
128	R95 - 7 29.6 - 30.6m	760.4	22 18	1 01		1 02	-
129	R95 - 7 30.6 - 31 4m	1384.0	40.36	4.32	2.28	1.78	-
130	R95 - 7 31.4 - 32.4m	156.2	4.56	6.14	-	-	-
131	R95 - 7 32.4 - 33.8m	158.4	4.62	2.52	-	-	-
132	R95 - 7 33.8 - 34 8m	397.4	11.59	-	-	-	-
133	R95 - 7 34.8 - 35.8m	652 3	19 02	4 48	1.22	1.15	-
134	R95 - 7 35.8 - 36.8m	1198 2	34.94	2 23	7.01	1.68	1.37
135	R95 - 7 36 8 - 37.8m	233.6	6.81	1.36	-	-	-
136	R95 - 7 37.8 - 38 8m	984.6	28.71	8.46	-	1.56	3.66
137	R95 - 7 38 8 - 40 5m	129.4	3 77	-	-	-	-
138	R95 - 7 40 5 - 41.1m	33 4	0 97	-	-	-	-
139	R95 - 7 41.1 - 42 0m	797 6	23 26	4 27	2.03	1 02	1.44
140	R95 - 7 42 0 - 42.8m	249.4	7.27	2 18	-	-	3.36
141	R95 - 7 42 8 - 43 9m	694.3	20.25	7.29	-	-	7.60
QC/DATA:							
Standard:							
Mp-1A		70 0	2 04	-	-	-	19 00
HV-1		-	-	0 52	-	-	-

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A Sc.T.
B.C. Certified Assayer

XLS/95Toklat

Eco-Tech LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-840

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

5-Oct-95

ATTENTION: TIM TERMUENDE

154 Rock samples received Sept.16, 1995
PROJECT #: None given
SHIPMENT #: None given

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu %	Zn %
17	RS 95-M8 20.5-22.0m	-	-	-	2.26
21	RS 95-M8 26.8-28.0m	98.9	2.88	-	-
24	RS 95-M8 31.2-32.7m	91.3	2.66	-	-
26	RS 95-M8 33.9-34.9m	-	-	2.26	-
27	RS 95-M8 34.9-36.0m	33.7	0.98	-	-
34	RS 95-M8 42.0-42.7m	-	-	-	1.52
35	RS 95-M8 42.7-43.3m	-	-	1.14	-
	QC DATA:				
	Standard:				
	Mp-IA	70.0	2 04	-	-
	HVI	-	-	0.52	-
	Mp-IA	-	-	-	19.00

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/95Toklat#2

Eco-Tech
LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-869

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

6-Oct-95

ATTENTION: TIM TERMUENDE

120 Core samples received Sept. 16, 1995
PROJECT #: None given
SHIPMENT #: None given

ET #.	Tag #	Zn %
64	RS95-M12- 68.5-70 0 m	2.08
71	RS95-M13- 3.0-5.7m	2.58
99	RS95-M13- 42.1-43.6 m	2 06

QC DATA:
Standard:
Mp-IA 19.00

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/95Toklat#2

Eco-Tech
LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy, R R #2, Kamloops, B C V2C 6T4 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-894

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

5-Oct-95

ATTENTION: TIM TERMUENDE

76 Core/Rock samples received September 16, 1995
PROJECT #: Not Given
SHIPMENT #: Not Given

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	As %	Cu %	Sb %	Zn %
5	TTRS95- 31	-	-	-	-	-	2.48
6	TTRS95- 32	251.2	7.33	-	1.18	-	-
7	RS95-M15- 0-3'	-	-	-	-	-	1.32
16	RS95-M15- 6.1-7.1m	-	-	-	-	-	8.89
21	RS95-M15- 11.5-11.7 m	-	-	-	-	-	2.62
45	RS95-M15- 35.1-35.7 m	1897.2	55.33	1.37	7.59	4.20	2.61
46	RS95-M15- 35.7-36.8 m	215.6	6.29	-	1.14	-	4.08
48	RS95-M15- 38.1-39.0 m	-	-	-	2.31	-	-
76	RS95-M15- 72.5-74.4 m	104.8	3.06	-	-	-	-
	QC DATA:						
	Standard:						
	Mp-IA	70.0	2.04	0.84	-	-	19.00
	HVI	-	-	-	0.52	-	-
	CD-1	-	-	-	-	3.57	-

ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/95Toklat#2

Eco-Tech LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-435

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

26-Jul-95

ATTENTION: TIM TERMUENDE

89 Core samples received July 11, 1995
PROJECT #: Rusty Springs
SHIPMENT #: RS02

ET #.	Tag #		Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)
2	OR95 -1	5 - 10'	41.4	1.21	-	1.82
16	OR95 -1	17.3 - 19 0m	439.3	12.81	1.03	18 80
31	OR95 -2	15.4 - 16.9m	135.8	3 96	1 31	11.40
32	OR95 -2	16.9 - 18.7m	250.1	7.29	-	5.28
49	OR95 -3	20.7 - 23.8m	107.3	3.13	-	-
50	OR95 -3	23.8 - 26 8m	49.3	1.44	-	1.23
51	OR95 -4	0 - 5'	261 5	7.63	-	2 88
65	OR95 -4	15 8 - 16.1m	-	-	1.01	1 74
69	OR95 -5	0 - 5'	34.2	1.00	-	1.43
81	OR95 -5	14.9 - 16 4m	333 6	9 73	-	-
QC/DATA:						
Standard:						
Mp-1A			70 2	2.05	-	4.32

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B C. Certified Assayer

XLS/95Toklat

Eco-Tech LABORATORIES LTD.

ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E Trans Canada Hwy , R R #2, Kamloops, B C V2C 2J3 Phone (604) 573-5700
Fax (604) 573-4557

CERTIFICATE OF ASSAY AK 95-447

TOKLAT RESOURCES INC.
2720-17th STREET SOUTH
CRANBROOK, B.C.
V1C 4H4

31-Jul-95

ATTENTION: TIM TERMUENDE

51 Rock samples received July 11, 1995
PROJECT #: Rusty Springs
SHIPMENT #: RS02

ET #.	Tag #	Ag (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
10	TTRS 95 - 10	623 4	18.18	1.71	1.73	-
11	TTRS 95 - 11	1066 6	31.11	-	70.60	-
39	CDRS 95 - 8	148.3	4 33	-	-	-
51	NO TAG	142 6	4.16	-	-	27.80
QC/DATA:						
Standard:						
Mp-1A		70 0	2.04	-	-	19.00
HV-1		-	-	0.52	-	-

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc.T.
B C. Certified Assayer

XLS/95Toklat

19-Jul-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-433
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

217 core samples received July 12, 1995
PROJECT #: "Rusty Springs"
SHIPMENT # RS02

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	R95-01 0-5'	5	1 0	0 24	30	120	<5	0 06	<1	2	111	72	1 05	<10	0 02	79	28	< 01	23	310	112	10	<20	10	< 01	<10	60	<10	2	82
2	R95-01 5'-10'	5	0 6	0 33	35	135	<5	0 20	<1	4	111	142	1 26	<10	0 09	121	25	< 01	50	950	118	5	<20	12	< 01	<10	57	<10	5	178
3	R95-01 3 0-4 1m	5	0 4	0 30	50	245	<5	0 06	<1	<1	98	44	1 20	<10	< 01	15	48	< 01	38	1550	1798	<5	<20	22	< 01	<10	106	<10	8	81
4	R95-01 4 1-4 4m	5	1 4	0 33	35	380	<5	0 04	<1	<1	127	44	0 63	<10	< 01	16	41	< 01	19	1460	4188	15	<20	14	< 01	<10	56	<10	3	39
5	R95-01 4 4-4 7m	5	< 2	0 47	70	470	<5	0 11	<1	1	116	88	1 29	<10	0 02	19	50	< 01	66	1860	1694	5	<20	29	< 01	<10	129	<10	12	221
6	R95-01 4 7-5 4m	5	< 2	0 35	95	105	<5	0 09	<1	23	85	98	3 18	<10	0 02	59	118	< 01	257	400	54	20	<20	<1	< 01	<10	297	<10	18	687
7	R95-01 5 4-5 9m	5	< 2	0 43	85	110	<5	0 04	<1	5	78	69	1 35	<10	< 01	27	81	< 01	115	370	72	10	<20	4	< 01	<10	155	<10	16	301
8	R95-01 5 9-6 4m	5	< 2	2 30	160	680	<5	0 13	<1	69	69	313	8 33	<10	< 01	300	147	< 01	650	2380	38	<5	<20	38	< 01	<10	466	<10	71	2053
9	R95-01 6 4-8 0m	5	< 2	0 71	90	415	<5	0 23	<1	6	99	60	1 28	<10	0 02	49	52	< 01	137	1810	42	10	<20	6	< 01	<10	111	<10	21	295
10	R95-01 8 0-9 7m	5	< 2	1 87	105	155	<5	0 20	<1	23	72	86	1 96	<10	0 01	131	52	< 01	299	3110	26	<5	<20	4	< 01	<10	112	<10	24	486
11	R95-01 9 7-10 2m	5	< 2	1 99	60	435	<5	0 19	2	16	116	84	2 01	<10	0 01	98	46	< 01	297	2560	28	<5	<20	18	< 01	<10	91	<10	19	354
12	R95-01 10 2-10 7m	5	< 2	3 49	75	355	<5	0 24	1	15	77	73	1 15	<10	0 02	64	26	< 01	406	3100	30	<5	<20	9	< 01	<10	110	<10	35	436
13	R95-01 10 7-11 6m	5	< 2	2 21	105	430	<5	0 27	<1	16	66	130	1 36	<10	0 04	102	34	0 03	456	3010	72	5	<20	12	< 01	<10	116	<10	51	836
14	R95-01 11 6-12 5m	5	< 2	4 14	165	360	<5	1 46	4	112	32	472	2 19	<10	0 23	944	31	0 02	1102	>10000	106	10	<20	12	< 01	<10	82	<10	64	2738
15	R95-01 12 5-14 0m	5	< 2	> 15	185	1265	<5	0 71	5	12	130	301	0 76	<10	0 07	124	20	< 01	742	>10000	<2	10	<20	140	< 01	<10	388	<10	35	612
16	R95-01 14 0-15 5m	5	0 4	1 81	30	105	<5	14 90	13	11	51	41	0 62	<10	8 85	240	10	< 01	195	1390	20	50	<20	33	< 01	<10	76	<10	21	371
17	R95-01 15 5-17 0m	5	0 2	0 73	20	30	<5	> 15	34	14	7	16	0 76	<10	14 10	254	3	< 01	135	400	10	70	<20	50	< 01	<10	32	<10	18	512
18	R95-01 17 0-18 5m	5	< 2	1 09	20	40	<5	> 15	31	12	8	14	0 70	<10	14 20	223	3	< 01	147	390	2	60	<20	46	< 01	<10	29	<10	20	483
19	R95-01 18 5-20 0m	5	< 2	0 05	15	15	<5	> 15	3	4	3	<1	0 24	<10	> 15	134	<1	< 01	21	170	2	70	<20	50	< 01	<10	12	<10	7	100
20	R95-01 20 0-22 0m	5	< 2	0 06	10	15	10	> 15	2	4	5	<1	0 31	<10	> 15	172	<1	0 01	23	180	<2	70	<20	58	< 01	<10	16	<10	7	121
21	R95-01 22 0-23 6m	5	0 8	3 99	90	160	<5	8 15	19	17	40	112	2 01	<10	4 46	142	18	< 01	391	2110	102	75	<20	21	< 01	<10	96	<10	38	1539
22	R95-01 23 6-24 5m	5	2 0	1 93	95	65	<5	> 15	7	10	24	108	1 18	<10	9 79	156	2	< 01	172	480	138	95	<20	40	< 01	<10	36	<10	15	827
23	R95-01 24 5-26 0m	5	< 2	0 11	35	105	<5	> 15	2	3	22	4	0 49	<10	12 50	156	<1	< 01	22	310	82	65	<20	50	< 01	<10	12	<10	4	264
24	R95-01 26 0-27 5m	5	0 4	0 65	85	35	<5	> 15	3	4	16	16	0 62	<10	13 30	171	<1	0 01	56	510	80	85	<20	47	< 01	<10	24	<10	8	491
25	R95-01 27 5-28 6m	5	0 4	0 14	25	15	<5	> 15	1	3	4	6	0 35	<10	> 15	200	<1	0 02	23	210	52	65	<20	61	< 01	<10	17	<10	4	163
26	R95-01 28 6-30 1m	5	0 2	0 16	15	15	<5	> 15	2	3	5	2	0 31	<10	14 70	165	<1	0 01	25	310	10	70	<20	60	< 01	<10	14	<10	4	152
27	R95-01 30 1-31 6m	5	0 4	0 17	15	30	<5	> 15	3	3	5	<1	0 34	<10	14 80	162	<1	0 01	24	260	42	70	<20	61	< 01	<10	15	<10	4	166
28	R95-01 31 6-33 4m	5	0 2	0 18	20	30	10	> 15	3	3	6	<1	0 34	<10	14 90	163	<1	0 01	25	250	44	70	<20	64	< 01	<10	14	<10	4	165
29	R95-01 33 4-33 6m	5	0 2	0 06	20	20	10	> 15	1	4	9	<1	0 41	<10	> 15	155	<1	0 01	19	200	16	65	<20	60	< 01	<10	16	<10	3	164
30	R95-01 33 6-35 0m	5	2 2	0 16	45	15	<5	> 15	7	6	43	83	0 42	<10	13 40	134	<1	0 01	29	120	78	80	<20	54	< 01	<10	18	<10	2	1521
31	R95-01 35 0-35 2m	5	1 6	0 14	45	15	<5	> 15	5	6	18	102	0 35	<10	14 80	134	<1	0 01	19	110	46	90	<20	63	< 01	<10	17	<10	2	497
32	R95-01 35 2-36 4m	5	0 6	0 09	50	15	<5	> 15	3	7	67	88	0 61	<10	12 40	136	<1	0 01	20	110	8	95	<20	52	< 01	<10	11	<10	2	248

TOKLAT RESOURCES INC AK 95-433

ECO-TECH LABORATORIES LTD

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
33	R95-01 36 4-36 6m	5	0 6	0 12	40	15	<5	> 15	4	4	9	69	0 42	<10	> 15	126	<1	0 01	24	80	10	105	<20	63	< 01	<10	14	<10	2	421
34	R95-01 36 6-37 6m	5	0 4	0 15	10	15	<5	5 18	1	2	272	17	0 55	<10	2 98	72	2	< 01	23	30	6	40	<20	14	< 01	<10	6	<10	<1	220
35	R95-01 37 6-39 6m	5	< 2	0 30	85	20	<5	> 15	2	12	10	2	1 26	<10	14 20	206	1	< 01	73	150	30	100	<20	64	< 01	<10	20	<10	6	943
36	R95-01 39 6-41 2m	5	0 2	0 46	40	45	<5	12 70	1	23	103	3	1 13	<10	7 62	260	2	< 01	111	130	24	50	<20	42	< 01	<10	17	<10	10	862
37	R95-01 41 2-42 4m	5	< 2	0 96	<5	245	<5	2 34	<1	11	92	3	2 28	<10	1 64	543	2	0 04	29	840	10	15	<20	59	0 13	<10	42	<10	4	229
38	R95-01 42 4-44 3m	5	< 2	0 04	10	30	<5	14 60	<1	2	85	2	0 38	<10	8 77	112	4	< 01	13	200	14	50	<20	42	< 01	<10	15	<10	4	154
39	R95-01 44 3-46 0m	5	< 2	0 06	25	35	<5	> 15	<1	2	61	7	0 54	<10	9 65	148	5	< 01	24	360	10	55	<20	58	< 01	<10	24	<10	4	186
40	R95-01 46 0-47 6m	5	< 2	0 04	35	25	<5	> 15	<1	6	42	3	1 09	<10	12 00	176	3	0 01	34	350	4	60	<20	62	< 01	<10	17	<10	5	337
41	R95-01 47 6-49 1m	5	< 2	0 03	25	25	5	> 15	<1	16	24	<1	1 37	<10	12 80	225	<1	< 01	66	210	<2	55	<20	45	< 01	<10	21	<10	8	379
42	R95-01 49 1-50 7m	5	< 2	0 02	10	10	<5	> 15	<1	<1	23	<1	0 09	<10	13 40	129	<1	< 01	1	160	<2	65	<20	44	< 01	<10	11	<10	4	39
43	R95-01 50 7-52 2m	5	0 2	0 02	25	15	<5	> 15	<1	4	4	<1	0 33	<10	> 15	164	<1	0 01	17	230	<2	60	<20	71	< 01	<10	10	<10	2	179
44	R95-01 52 2-53 6m	5	< 2	0 02	20	20	<5	> 15	<1	3	6	<1	0 35	<10	> 15	145	<1	0 01	19	280	<2	70	<20	67	< 01	<10	9	<10	2	184
45	R95-01 53 6-55 1m	5	< 2	0 02	15	15	<5	> 15	<1	4	5	2	0 48	<10	> 15	150	<1	0 01	15	350	<2	65	<20	65	< 01	<10	8	<10	2	138
46	R95-01 55 1-56 3m	5	< 2	0 02	10	20	<5	> 15	<1	12	3	<1	0 90	<10	> 15	166	<1	0 01	42	140	<2	60	<20	67	< 01	<10	7	<10	1	134
47	R95-01 56 3-58 2m	5	< 2	0 02	15	30	10	> 15	3	52	6	22	3 27	<10	13 70	476	2	< 01	178	110	<2	50	<20	57	< 01	<10	6	<10	5	888
48	R95-01 58 2-59 7m	5	< 2	0 04	10	20	<5	> 15	2	9	18	61	0 65	<10	12 60	121	<1	< 01	36	170	4	55	<20	55	< 01	<10	9	<10	5	171
49	R95-01 59 7-60 1m	5	< 2	2 32	125	250	<5	2 06	9	19	109	1457	14 60	<10	1 12	46	13	< 01	379	2090	20	30	<20	38	< 01	<10	764	<10	13	4726
50	R95-01 60 1-62 5m	5	2 2	0 33	210	45	<5	> 15	<1	11	16	382	0 89	<10	13 00	135	<1	< 01	59	250	8	290	<20	52	< 01	<10	36	<10	5	753
51	R95-01 62 5-64 0m	5	>30	1 89	4500	300	<5	12 50	<1	25	45	>10000	6 56	<10	7 50	153	4	< 01	331	1220	234	6780	<20	57	0 01	<10	196	<10	5	5668
52	R95-01 64 0-65 5m	5	1 0	0 10	50	20	<5	> 15	10	7	14	182	0 96	<10	13 80	124	<1	0 01	46	120	2	115	<20	64	< 01	<10	9	<10	7	545
53	R95-01 65 5-67 0m	5	0 8	0 07	35	15	<5	> 15	4	4	3	84	0 36	<10	14 90	107	<1	0 01	18	120	<2	80	<20	75	< 01	<10	4	<10	3	255
54	R95-01 67 0-68 5m	5	0 4	0 04	15	15	<5	> 15	1	2	3	17	0 12	<10	14 60	89	<1	0 01	<1	100	<2	70	<20	84	< 01	<10	5	<10	<1	96
55	R95-01 68 5-70 0m	5	0 4	0 04	15	20	<5	> 15	1	<1	2	10	0 09	<10	14 90	88	<1	0 01	<1	140	<2	70	<20	85	< 01	<10	4	<10	1	127
56	R95-01 70 0-71 5m	5	0 2	0 10	50	25	<5	> 15	2	9	3	26	1 00	<10	14 10	169	<1	0 01	53	90	<2	90	<20	91	< 01	<10	6	<10	6	939
57	R95-01 71 5-73 0m	5	< 2	0 03	15	10	<5	> 15	<1	<1	6	5	0 13	<10	14 60	101	<1	0 01	<1	80	<2	70	<20	82	< 01	<10	2	<10	<1	87
58	R95-01 73 0-74 5m	5	< 2	0 04	20	15	<5	> 15	<1	<1	3	5	0 16	<10	13 90	109	<1	0 01	2	80	4	75	<20	91	< 01	<10	6	<10	<1	123
59	R95-01 74 5-76 0m	5	< 2	0 03	15	15	5	> 15	<1	<1	2	1	0 10	<10	14 10	92	<1	0 01	<1	70	<2	70	<20	92	< 01	<10	3	<10	<1	67
60	R95-01 76 0-77 5m	5	2 0	0 03	5	135	<5	> 15	<1	<1	3	12	0 09	<10	14 00	85	7	0 01	<1	70	<2	70	<20	111	< 01	<10	5	<10	<1	46
61	R95-01 77 5-79 0m	5	< 2	0 03	15	15	<5	> 15	<1	<1	3	2	0 07	<10	14 30	92	<1	0 01	<1	90	2	65	<20	99	< 01	<10	5	<10	<1	41
62	R95-01 79 0-80 5m	5	0 4	0 02	15	15	<5	> 15	<1	<1	3	3	0 06	<10	14 10	96	<1	0 01	<1	70	<2	65	<20	96	< 01	<10	3	<10	<1	41
63	R95-01 80 5-82 0m	5	0 2	0 03	20	15	<5	> 15	<1	<1	7	4	0 19	<10	14 20	125	<1	0 01	<1	100	<2	70	<20	101	< 01	<10	6	<10	<1	71
64	R95-01 82 0-83 5m	5	0 6	0 02	40	25	<5	> 15	<1	<1	3	26	0 27	<10	14 40	112	<1	0 01	2	80	8	105	<20	93	< 01	<10	6	<10	<1	114
65	R95-01 83 5-85 0m	5	1 0	0 02	20	15	<5	> 15	<1	<1	4	30	0 09	<10	14 60	96	<1	0 01	<1	130	4	85	<20	87	< 01	<10	3	<10	<1	44
66	R95-01 104 7-106 1m	5	0 2	0 03	5	15	<5	> 15	<1	<1	3	6	0 13	<10	14 90	81	<1	0 01	2	130	<2	70	<20	82	< 01	<10	5	<10	<1	57
67	R95-01 106 1-107 2m	5	0 4	0 05	20	20	<5	> 15	<1	2	18	25	0 58	<10	13 80	109	<1	0 01	18	130	6	70	<20	86	< 01	<10	5	<10	<1	196
68	R95-01 107.2-108 4m	5	0 4	0 03	20	25	<5	> 15	<1	3	8	22	0 40	<10	14 10	114	<1	0 01	2	70	<2	70	<20	90	< 01	<10	4	<10	<1	54
69	R95-01 108 4-108 6m	5	0 4	0 05	20	30	<5	> 15	<1	1	3	2	0 51	<10	14 10	168	<1	0 01	7	50	4	75	<20	101	< 01	<10	8	<10	<1	63
70	R95-01 108 6-109 8m	5	0 2	0 03	20	20	<5	> 15	<1	<1	3	<1	0 11	<10	14 10	107	<1	0 01	<1	70	<2	65	<20	103	< 01	<10	4	<10	<1	22
71	R95-01 109 8-111 3m	5	< 2	0 03	20	20	<5	> 15	<1	<1	2	<1	0 12	<10	13 90	98	<1	0 01	<1	100	<2	60	<20	119	< 01	<10	3	<10	<1	21
72	R95-01 111 3-112 8m	5	0 2	0 04	10	15	<5	> 15	<1	<1	1	2	0 12	<10	14 50	80	<1	0 01	<1	90	<2	70	<20	101	< 01	<10	2	<10	<1	65
73	R95-01 112.8-114 3m	5	0 2	0 04	10	15	<5	> 15	<1	<1	1	2	0 13	<10	14 20	88	<1	0 01	<1	80	<2	65	<20	93	< 01	<10	3	<10	<1	46
74	R95-01 114 3-115 8m	5	0 2	0 04	10	15	<5	> 15	<1	<1	2	<1	0 15	<10	14 50	87	<1	0 01	<1	70	<2	65	<20	88	< 01	<10	4	<10	<1	19

TOKLAT RESOURCES INC AK 95-433

ECO-TECH LABORATORIES LTD

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
75	R95-01 115 8-117 3m	5	0 2	0 04	10	15	<5	> 15	<1	<1	1	<1	0 13	<10	14 70	81	<1	0 01	<1	80	<2	70	<20	93	< 01	<10	5	<10	<1	15
76	R95-01 117 3-118 4m	5	< 2	0 05	5	20	<5	> 15	<1	<1	2	<1	0 14	<10	14 10	82	<1	0 01	<1	90	<2	60	<20	89	< 01	<10	3	<10	<1	13
77	R95-01 118 4-118 7m	5	< 2	0 08	20	30	<5	> 15	<1	<1	4	7	0 31	<10	14 00	149	<1	0 01	<1	80	8	70	<20	96	< 01	<10	6	<10	<1	53
78	R95-01 118 7-120 2m	5	0 6	0 05	15	20	<5	> 15	<1	<1	4	13	0 20	<10	14 20	130	<1	0 01	<1	120	<2	65	<20	92	< 01	<10	6	<10	<1	44
79	R95-01 120 2-121 7m	5	0 2	0 03	5	15	<5	> 15	<1	<1	1	4	0 11	<10	14 20	92	<1	0 01	<1	60	4	60	<20	84	< 01	<10	3	<10	<1	33
80	R95-01 121 7-123 2m	5	0 2	0 05	10	15	<5	> 15	<1	<1	2	2	0 24	<10	14 40	98	<1	0 01	<1	100	<2	65	<20	87	< 01	<10	4	<10	<1	34
81	R95-01 123 2-124 7m	5	0 4	0 05	15	20	5	> 15	<1	<1	2	7	0 47	<10	14 20	102	<1	0 02	3	120	102	65	<20	74	< 01	<10	5	<10	<1	99
82	R95-01 124 7-125 6m	5	0 2	0 05	20	15	<5	> 15	<1	1	<1	<1	0 29	<10	14 70	103	<1	0 01	2	60	<2	70	<20	88	< 01	<10	6	<10	<1	61
83	R95-01 125 6-126 0m	5	0 2	0 12	15	30	<5	> 15	2	4	1	2	1 06	<10	14 90	146	<1	0 01	32	80	4	65	<20	94	< 01	<10	6	<10	1	381
84	R95-01 126 0-127 5m	5	0 4	0 04	20	15	<5	> 15	<1	<1	4	6	0 35	<10	14 80	90	<1	0 01	1	90	<2	70	<20	67	< 01	<10	5	<10	<1	80
85	R95-01 127 5-129 0m	5	0 2	0 06	10	20	<5	> 15	<1	1	<1	1	0 36	<10	> 15	84	<1	0 01	4	70	<2	60	<20	73	< 01	<10	4	<10	<1	103
86	R95-01 129 0-130 5m	5	0 4	0 06	5	20	<5	> 15	<1	2	2	<1	0 41	<10	14 60	101	<1	0 01	7	70	<2	65	<20	74	< 01	<10	5	<10	<1	108
87	R95-01 130 5-132 0m	5	0 2	0 04	20	15	<5	> 15	<1	<1	<1	<1	0 42	<10	> 15	97	<1	0 01	3	90	<2	65	<20	86	< 01	<10	5	<10	<1	71
88	R95-01 132 0-132 5m	5	< 2	0 04	25	15	<5	> 15	<1	1	36	<1	0 57	<10	13 60	81	<1	0 01	3	90	<2	60	<20	56	< 01	<10	5	<10	<1	39
89	R95-01 132 5-134 0m	5	0 4	0 04	15	15	<5	> 15	<1	2	2	<1	0 46	<10	> 15	94	<1	0 01	8	90	<2	65	<20	78	< 01	<10	4	<10	<1	91
90	R95-01 134 0-135 5m	5	< 2	0 04	15	15	<5	> 15	<1	<1	4	<1	0 14	<10	15 00	92	<1	0 01	<1	80	<2	70	<20	87	< 01	<10	3	<10	<1	7
91	R95-01 135 5-137 0m	5	< 2	0 04	<5	20	5	> 15	<1	<1	2	2	0 22	<10	14 80	101	<1	0 01	<1	140	<2	65	<20	86	< 01	<10	3	<10	<1	13
92	R95-01 137 0-137 9m	5	0 2	0 04	20	15	<5	> 15	<1	<1	<1	<1	0 19	<10	> 15	83	<1	0 01	1	110	<2	65	<20	72	< 01	<10	2	<10	<1	33
93	R95-01 137 9-138 1m	5	0 2	0 16	10	15	5	> 15	<1	6	27	2	0 46	<10	13 20	185	<1	0 01	44	70	<2	60	<20	66	< 01	<10	4	<10	1	226
94	R95-01 138 1-139 5m	5	< 2	0 04	10	20	5	> 15	<1	1	2	1	0 31	<10	14 20	140	<1	0 01	1	120	<2	65	<20	93	< 01	<10	4	<10	<1	44
95	R95-01 139 5-141 0m	5	< 2	0 05	5	15	5	> 15	<1	<1	2	<1	0 22	<10	14 90	108	<1	0 01	4	70	<2	60	<20	82	< 01	<10	4	<10	<1	78
96	R95-01 141 0-142 5m	5	< 2	0 05	10	20	5	> 15	<1	<1	<1	<1	0 18	<10	14 70	121	<1	0 01	1	100	<2	70	<20	108	< 01	<10	4	<10	<1	52
97	R95-01 142 5-144 0m	5	< 2	0 05	5	20	<5	> 15	<1	<1	2	<1	0 20	<10	14 20	134	<1	0 01	<1	120	<2	70	<20	111	< 01	<10	3	<10	<1	24
98	R95-01 144 0-145 5m	5	< 2	0 04	<5	20	<5	> 15	<1	<1	<1	<1	0 16	<10	14 30	96	<1	0 01	<1	90	<2	70	<20	110	< 01	<10	3	<10	<1	14
99	R95-01 145 5-147 0m	5	0 2	0 04	10	20	<5	> 15	<1	<1	<1	<1	0 22	<10	14 20	90	<1	0 01	<1	60	<2	65	<20	101	< 01	<10	4	<10	<1	13
100	R95-01 147 0-148 5m	5	0 2	0 04	15	15	5	> 15	<1	<1	<1	<1	0 16	<10	14 10	81	<1	0 01	<1	80	<2	65	<20	111	< 01	<10	4	<10	<1	5
101	R95-01 148 5-150 0m	5	0 2	0 05	10	20	5	> 15	<1	<1	<1	<1	0 18	<10	13 80	79	<1	0 01	<1	90	<2	65	<20	108	< 01	<10	4	<10	<1	4
102	R95-01 150 0-151 5m	5	< 2	0 04	10	20	<5	> 15	<1	<1	<1	<1	0 17	<10	14 00	85	<1	0 01	<1	60	<2	65	<20	113	< 01	<10	3	<10	<1	8
103	R95-01 151 5-153 0m	5	< 2	0 05	15	20	<5	> 15	<1	<1	<1	<1	0 13	<10	13 90	97	<1	0 01	<1	90	<2	70	<20	99	< 01	<10	4	<10	<1	4
104	R95-01 153 0-154 5m	5	< 2	0 05	10	20	<5	> 15	<1	<1	<1	<1	0 14	<10	13 70	98	<1	0 01	<1	70	<2	65	<20	97	< 01	<10	3	<10	<1	5
105	R95-01 154 5-156 0m	5	< 2	0 03	15	20	<5	> 15	<1	<1	2	<1	0 14	<10	14 20	111	<1	0 01	<1	70	<2	65	<20	92	< 01	<10	4	<10	<1	12
106	R95-01 156 0-157 5m	5	< 2	0 06	10	20	<5	> 15	<1	1	1	<1	0 27	<10	14 00	122	<1	0 01	5	90	<2	65	<20	86	< 01	<10	5	<10	<1	65
107	R95-01 157 5-159 0m	5	0 4	0 04	10	20	<5	> 15	1	<1	4	2	0 15	<10	13 60	121	<1	0 01	1	80	8	60	<20	106	< 01	<10	6	<10	<1	47
108	R95-01 159 0-160 5m	5	0 4	0 03	15	20	5	> 15	<1	<1	3	2	0 14	<10	13 30	114	<1	0 01	<1	90	4	65	<20	95	< 01	<10	4	<10	<1	31
109	R95-01 160 5-162 0m	5	< 2	0 05	10	25	<5	> 15	<1	1	14	<1	0 24	<10	13 10	130	<1	0 01	5	120	4	60	<20	95	< 01	<10	4	<10	<1	90
110	R95-01 162.0-163 0m	5	1 2	0 04	15	35	<5	> 15	<1	<1	4	<1	0 26	<10	13 40	130	<1	0 02	2	210	<2	60	<20	115	< 01	<10	2	<10	<1	26
111	R95-01 163 0-164 0m	5	0 4	0 04	20	35	<5	> 15	2	<1	3	1	0 33	<10	12 70	152	<1	0 01	6	110	<2	65	<20	109	< 01	<10	3	<10	<1	90
112	R95-01 164 0-164 5m	5	1 6	0 04	15	40	<5	> 15	2	3	3	2	0 59	<10	13 50	163	<1	0 02	24	270	10	65	<20	82	< 01	<10	2	<10	<1	195
113	R95-01 164 5-166 0m	5	0 4	0 03	10	25	<5	> 15	2	1	1	<1	0 18	<10	14 00	159	<1	0 01	7	50	<2	65	<20	80	< 01	<10	6	<10	<1	68
114	R95-01 166 0-167 5m	5	< 2	0 02	15	25	<5	> 15	<1	<1	6	<1	0 17	<10	13 40	140	<1	0 01	3	50	4	65	<20	91	< 01	<10	6	<10	<1	36
115	R95-01 167 5-167 9m	5	0 6	1 78	50	135	<5	> 15	13	13	26	130	2 45	<10	8 95	220	3	< 01	217	80	20	60	<20	62	< 01	<10	46	<10	11	853
116	R95-01 167 9-169 5m	5	0 4	0 06	5	45	<5	> 15	3	2	4	1	0 46	<10	13 50	207	<1	0 01	20	80	8	60	<20	128	< 01	<10	5	<10	<1	130

TOKLAT RESOURCES INC AK 95-433

ECO-TECH LABORATORIES LTD

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
117	R95-01 169 5-171 0m	5	< 2	0 04	10	25	5	> 15	<1	<1	2	<1	0 15	<10	14 10	143	<1	0 01	3	180	4	60	<20	99	< 01	<10	3	<10	<1	38
118	R95-01 171 0-172 5m	5	0 4	0 06	10	40	<5	> 15	2	2	2	3	0 42	<10	14 30	176	<1	0 01	15	70	<2	65	<20	95	< 01	<10	4	<10	<1	107
119	R95-01 172 5-174 0m	5	0 2	0 05	15	35	<5	> 15	1	2	3	1	0 27	<10	13 70	173	<1	0 02	10	240	4	60	<20	101	< 01	<10	4	<10	<1	63
120	R95-01 174 0-175 5m	5	0 4	0 02	15	35	5	> 15	<1	<1	3	<1	0 13	<10	14 00	150	<1	0 01	2	60	<2	60	<20	91	< 01	<10	5	<10	<1	30
121	R95-01 175 5-177 0m	5	< 2	0 06	15	55	<5	> 15	1	1	6	2	0 45	<10	12 90	158	<1	0 01	7	100	<2	60	<20	86	< 01	<10	4	<10	<1	60
122	R95-01 177 0-178 5m	5	0 4	0 03	15	50	<5	> 15	2	1	2	1	0 37	<10	13 80	199	<1	0 02	9	100	<2	60	<20	110	< 01	<10	5	<10	<1	87
123	R95-01 178 5-180 0m	5	0 2	0 03	10	40	<5	> 15	<1	<1	4	6	0 15	<10	14 00	144	<1	0 01	<1	60	10	70	<20	80	< 01	<10	4	<10	<1	22
124	R95-01 180 0-181 5m	5	0 4	0 04	15	45	<5	> 15	<1	2	2	7	0 29	<10	14 10	144	<1	0 01	6	90	10	70	<20	76	< 01	<10	5	<10	<1	59
125	R95-01 181 5-183 0m	5	< 2	0 04	15	30	<5	> 15	<1	2	1	2	0 36	<10	13 90	140	<1	0 01	14	60	6	60	<20	86	< 01	<10	6	<10	<1	89
126	R95-01 183 0-184 5m	5	0 4	0 05	<5	40	5	> 15	1	4	<1	6	0 66	<10	13 40	204	<1	0 01	27	170	4	60	<20	92	< 01	<10	6	<10	2	227
127	R95-01 184 5-186 0m	5	0 2	0 07	10	50	<5	> 15	<1	4	2	6	0 69	<10	13 20	190	<1	0 01	24	210	2	65	<20	85	< 01	<10	7	<10	1	141
128	R95-01 186 0-187 8m	5	< 2	0 08	5	40	<5	> 15	<1	2	3	5	0 46	<10	13 50	154	<1	0 01	8	180	4	60	<20	84	< 01	<10	5	<10	<1	46
129	R95-02 0-5'	5	< 2	0 13	15	30	<5	> 15	1	3	14	25	0 20	<10	10 50	133	<1	0 01	20	120	56	60	<20	42	< 01	<10	7	<10	2	644
130	R95-02 1 5-3 0m	5	< 2	0 07	20	40	<5	> 15	1	6	4	30	0 13	<10	14 60	164	<1	0 01	32	170	52	60	<20	68	< 01	<10	8	<10	3	828
131	R95-02 3 0-4 3m	5	0 2	0 04	15	20	<5	> 15	2	6	6	44	0 21	<10	14 70	145	<1	0 01	19	220	70	60	<20	66	< 01	<10	10	<10	4	528
132	R95-02 4 3-4 6m	5	0 4	0 07	15	25	<5	> 15	3	5	22	81	0 27	<10	13 30	164	<1	0 01	39	380	72	65	<20	68	< 01	<10	6	<10	3	1742
133	R95-02 4 6-6 0m	5	1 6	0 03	10	20	<5	> 15	2	1	6	16	0 12	<10	> 15	99	<1	0 01	11	350	20	65	<20	76	< 01	<10	4	<10	3	451
134	R95-02 6 0-7 5m	5	4 6	0 03	20	20	<5	> 15	4	3	5	29	0 20	<10	> 15	124	<1	0 01	13	300	46	90	<20	76	< 01	<10	5	<10	3	474
135	R95-02 7 5-9 0m	5	3 4	0 03	15	30	<5	> 15	7	<1	5	28	0 16	<10	> 15	118	<1	0 02	14	280	40	65	<20	73	< 01	<10	6	<10	5	513
136	R95-02 9 0-10 0m	5	2 6	0 01	15	20	<5	> 15	<1	<1	6	14	0 06	<10	> 15	83	<1	0 01	<1	70	8	60	<20	53	< 01	<10	7	<10	<1	266
137	R95-02 10 0-10 7m	5	2 6	0 03	15	35	<5	> 15	4	<1	9	15	0 14	<10	14 00	123	<1	0 01	7	650	96	70	<20	62	< 01	<10	8	<10	5	302
138	R95-02 10 7-12.0m	5	1 0	0 09	10	35	<5	> 15	6	3	6	50	0 11	<10	14 40	177	<1	0 01	59	200	72	65	<20	67	< 01	<10	13	<10	4	2032
139	R95-02 12 0-13 5m	5	1 4	0 04	20	20	<5	> 15	24	3	13	121	0 20	<10	14 20	173	<1	0 01	12	160	58	70	<20	72	< 01	<10	15	<10	4	3355
140	R95-02 13 5-15 0m	5	3 2	0 02	20	15	<5	> 15	53	5	5	83	0 13	<10	> 15	136	<1	0 01	5	70	32	75	<20	69	< 01	<10	8	<10	2	441
141	R95-02 15 0-16 5m	5	2 6	0 01	10	20	<5	> 15	1	<1	5	14	0 06	<10	> 15	83	<1	0 01	<1	60	8	60	<20	53	< 01	<10	7	<10	<1	268
142	R95-02 16 5-17 5m	5	1 6	0 01	15	15	<5	> 15	1	1	4	29	0 12	<10	14 80	93	<1	0 01	5	100	20	65	<20	51	< 01	<10	7	<10	<1	1052
143	R95-02 17 5-18 2m	5	2 2	0 01	10	20	<5	> 15	<1	<1	6	19	0 08	<10	> 15	83	<1	0 01	<1	60	14	65	<20	54	< 01	<10	7	<10	<1	717
144	R95-02 18 2-18 6m	5	3 6	0 01	25	20	<5	> 15	<1	<1	34	26	0 12	<10	13 50	93	<1	0 01	2	60	36	70	<20	44	< 01	<10	9	<10	<1	810
145	R95-02 18 6-19 2m	5	0 8	0 01	15	10	<5	> 15	<1	<1	7	7	0 06	<10	> 15	59	<1	0 01	<1	80	6	75	<20	40	< 01	<10	8	<10	<1	157
146	R95-02 19 2-20 7m	5	1 2	0 01	15	10	<5	> 15	<1	<1	5	12	0 10	<10	> 15	82	<1	0 01	4	70	24	60	<20	42	< 01	<10	8	<10	<1	1183
147	R95-02 20 7-21 6m	5	0 6	< 01	<5	10	<5	> 15	<1	<1	1	13	0 05	<10	13 50	60	<1	0 01	<1	40	6	65	<20	34	< 01	<10	5	<10	<1	770
148	R95-02 21 6-22 6m	5	2 4	0 04	10	15	<5	> 15	5	2	5	81	0 16	<10	15 00	101	<1	0 01	19	110	24	65	<20	59	< 01	<10	6	<10	<1	1635
149	R95-02 22 6-23 7m	5	2 0	0 06	25	15	<5	> 15	47	8	4	146	0 26	<10	14 80	193	<1	0 01	35	220	20	65	<20	68	< 01	<10	6	<10	<1	>10000
150	R95-02 23 7-25 1m	5	2 2	0 14	35	20	<5	> 15	99	5	6	571	0 39	<10	14 40	174	<1	0 01	37	430	22	60	<20	65	< 01	<10	7	<10	<1	>10000
151	R95-02 25 1-25 5m	5	< 2	1 18	55	40	<5	> 15	154	15	6	2993	0 67	<10	9 98	215	<1	< 01	212	210	26	30	<20	48	< 01	<10	14	<10	<1	>10000
152	R95-02 25 5-27 0m	5	1 8	0 02	15	15	<5	> 15	4	2	6	30	0 29	<10	14 40	111	<1	0 01	9	70	6	65	<20	76	< 01	<10	2	<10	<1	3205
153	R95-02 27 0-28 5m	5	2 6	0 03	15	15	<5	> 15	2	4	6	33	0 44	<10	14 30	117	<1	0 01	18	120	10	65	<20	74	< 01	<10	5	<10	4	1311
154	R95-02 28 5-30 0m	5	3 8	0 02	<5	20	<5	> 15	<1	2	4	3	0 16	<10	14 90	96	<1	0 01	7	180	<2	70	<20	74	< 01	<10	5	<10	4	341
155	R95-02 30 0-31 2m	5	5 4	0 03	15	25	<5	> 15	<1	5	1	7	0 51	<10	> 15	227	<1	0 01	21	100	4	60	<20	75	< 01	<10	6	<10	3	712
156	R95-02 31 2-31 6m	5	24 6	1 80	45	150	<5	> 15	19	49	9	660	1 56	<10	12 80	828	<1	< 01	271	370	36	60	<20	58	< 01	<10	34	<10	24	4460
157	R95-02 31 6-32.6m	5	5 6	0 06	15	25	5	> 15	4	8	2	20	0 77	<10	14 90	175	<1	0 01	35	100	10	60	<20	64	< 01	<10	7	<10	3	1481
158	R95-02 32 6-33 6m	5	2 6	0 04	5	25	5	> 15	3	6	3	13	0 41	<10	> 15	197	<1	0 01	22	60	10	65	<20	71	< 01	<10	6	<10	<1	1426

TOKLAT RESOURCES INC AK 95-433

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
159	R95-02 33 6-34 6m	5	3 2	0 05	<5	25	<5	> 15	57	15	3	294	1 11	<10	14 40	240	<1	0 01	53	40	26	60	<20	73	< 01	<10	5	<10	6	4901
160	R95-02 34 6-35 6m	5	3 0	0 03	10	20	<5	> 15	79	16	4	585	1 64	<10	14 00	267	<1	0 01	70	40	30	55	<20	74	< 01	<10	4	<10	8	>10000
161	R95-02 35 6-36 6m	5	7 4	0 06	20	20	<5	> 15	147	4	10	1006	0 85	<10	14 60	165	<1	0 01	25	70	12	70	<20	76	< 01	<10	7	<10	9	3341
162	R95-02 36 6-37 6m	5	1 0	0 01	5	20	<5	> 15	13	2	33	57	0 33	<10	12 50	128	<1	0 01	8	60	<2	55	<20	69	< 01	<10	4	<10	<1	638
163	R95-02 37 6-38 2m	5	1 0	0 01	10	20	<5	> 15	14	6	7	91	0 54	<10	14 60	136	<1	0 01	22	60	<2	70	<20	65	< 01	<10	5	<10	1	1882
164	R95-02 38 2-38 6m	5	0 6	0 03	15	20	<5	> 15	55	11	7	4901	1 60	<10	14 30	140	<1	0 01	51	270	36	60	<20	64	< 01	<10	4	<10	12	4246
165	R95-02 38 6-39 6m	5	< 2	0 02	10	20	<5	> 15	3	1	2	70	0 20	<10	14 60	92	<1	0 01	7	210	4	65	<20	84	< 01	<10	3	<10	2	1477
166	R95-02 39 6-40 6m	5	0 4	0 03	5	20	<5	> 15	<1	2	2	31	0 26	<10	14 40	94	<1	0 01	9	140	6	60	<20	89	< 01	<10	3	<10	<1	783
167	R95-02 40 6-41 6m	5	3 6	0 03	15	20	<5	> 15	25	7	2	145	0 69	<10	14 80	151	<1	0 01	34	210	4	60	<20	65	< 01	<10	5	<10	3	4221
168	R95-02 41 6-42 8m	5	3 6	0 03	15	20	<5	> 15	63	6	<1	473	0 90	<10	14 80	127	<1	0 01	48	70	4	55	<20	67	< 01	<10	7	<10	5	8383
169	R95-02 42 8-44 5m	5	9 8	6 02	135	405	<5	13 20	127	24	26	710	4 23	<10	8 14	181	<1	< 01	573	430	126	55	<20	25	< 01	<10	41	<10	24	>10000
170	R95-02 44 5-46 1m	5	< 2	0 05	10	20	<5	> 15	605	18	<1	1001	1 04	<10	13 40	165	<1	< 01	160	170	38	45	<20	37	< 01	<10	9	<10	<1	>10000
171	R95-02 46 1-46 8m	5	5 8	0 04	20	25	<5	> 15	309	18	2	87	0 45	<10	14 60	236	<1	0 01	37	470	20	55	<20	56	< 01	<10	7	<10	<1	>10000
172	R95-02 46 8-47 7m	5	11 4	0 03	10	20	<5	> 15	97	6	1	35	0 50	<10	> 15	198	<1	0 01	31	200	28	60	<20	62	< 01	<10	6	<10	4	1753
173	R95-02 47 7-48 2m	5	21 2	2 58	30	215	<5	> 15	89	12	6	59	0 77	<10	12 30	229	<1	0 01	130	290	140	60	<20	47	< 01	<10	38	<10	19	4050
174	R95-02 48 2-49 7m	5	9 0	0 04	10	15	<5	> 15	24	5	<1	2	0 25	<10	> 15	125	<1	0 01	12	140	32	60	<20	57	< 01	<10	8	<10	<1	489
175	R95-02 49 7-50 7m	5	5 6	0 02	10	15	5	> 15	24	3	2	9	0 29	<10	> 15	144	<1	0 01	13	150	52	65	<20	66	< 01	<10	8	<10	2	566
176	R95-02 50 7-51 3m	5	2 6	0 03	10	15	<5	> 15	51	12	<1	78	0 94	<10	> 15	193	<1	0 01	48	200	46	60	<20	71	< 01	<10	7	<10	5	4725
177	R95-02 51 3-51 8m	5	0 8	0 03	5	20	<5	> 15	8	7	<1	46	0 63	<10	> 15	161	<1	0 01	34	240	8	60	<20	73	< 01	<10	8	<10	3	2244
177a	R95-02 51 8-52 8m	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s	n/s
178	R95-02 52 8-53 8m	5	0 8	0 02	15	20	<5	> 15	4	<1	2	6	0 08	<10	14 40	96	<1	0 01	3	130	<2	60	<20	84	< 01	<10	9	<10	1	216
179	R95-02 53 8-54 8m	5	2 0	0 02	10	15	<5	> 15	14	<1	2	12	0 14	<10	> 15	104	<1	0 01	3	130	4	65	<20	74	< 01	<10	7	<10	2	245
180	R95-02 54 8-55 8m	5	0 6	0 02	10	20	<5	> 15	<1	<1	9	7	0 13	<10	> 15	88	<1	0 01	3	130	<2	60	<20	74	< 01	<10	4	<10	<1	184
181	R95-02 55 8-56 8m	5	0 6	0 01	5	15	<5	> 15	2	2	4	8	0 25	<10	> 15	98	<1	0 01	11	110	<2	60	<20	52	< 01	<10	6	<10	<1	355
182	R95-02 56 8-57 9m	5	2 4	0 02	10	20	<5	> 15	5	4	2	20	0 30	<10	> 15	155	<1	0 01	14	180	<2	60	<20	74	< 01	<10	5	<10	2	688
183	R95-02 57 9-59 0m	5	7 2	0 02	15	25	<5	> 15	47	4	4	41	0 49	<10	> 15	147	<1	0 01	16	140	10	60	<20	64	< 01	<10	6	<10	3	1119
184	R95-02 59 0-59 9m	5	4 0	0 03	15	25	<5	> 15	64	20	2	104	1 05	<10	14 50	240	<1	0 01	55	150	18	60	<20	56	< 01	<10	7	<10	<1	>10000
185	R95-02 59 9-62 3m	5	0 4	0 05	30	25	<5	> 15	23	21	3	135	0 98	<10	14 00	285	<1	0 01	74	230	74	60	<20	65	< 01	<10	15	<10	<1	>10000
186	R95-02 62 3-63 3m	5	0 2	0 02	10	15	<5	> 15	3	<1	2	<1	0 09	<10	> 15	120	<1	0 02	1	180	8	60	<20	86	< 01	<10	6	<10	1	281
187	R95-02 63 3-64 3m	5	< 2	0 02	5	15	<5	> 15	<1	<1	2	2	0 07	<10	> 15	93	<1	0 01	2	270	12	60	<20	68	< 01	<10	6	<10	<1	277
188	R95-02 64 3-65 2m	5	0 4	0 02	10	20	<5	> 15	<1	<1	2	3	0 17	<10	> 15	109	<1	0 01	6	110	8	60	<20	71	< 01	<10	8	<10	<1	263
373-1	R95-03 0-5'	5	>30	2 58	920	1090	<5	0 49	43	30	95	2070	5 50	<10	0 22	392	1	< 01	215	1550	5298	1300	<20	21	< 01	10	121	<10	13	>10000
373-7	R95-03 5'-10'	20	>30	1 61	2555	605	<5	0 20	72	22	62	5478	8 14	<10	0 04	254	<1	< 01	269	810	8598	4500	<20	22	< 01	10	332	<10	7	>10000
373-12	R95-03 10'-15'	20	>30	0 77	5455	515	<5	0 16	4	9	26	1623	10 70	<10	< 01	55	3	< 01	142	830	2414	7315	<20	16	< 01	30	374	<10	<1	6715
373-17	R95-03 15-20'	10	>30	1 34	2170	935	<5	0 09	<1	3	21	957	4 23	<10	< 01	29	5	< 01	103	630	796	2845	<20	5	< 01	20	66	<10	2	2469
373-2	R95-03 4 6-6 0m	10	>30	2 78	1640	1340	<5	0 12	15	27	107	1701	3 35	<10	0 02	211	7	< 01	220	1590	138	2170	<20	8	< 01	<10	84	<10	13	5761
373-3	R95-03 6 0-7 5m	5	23 6	> 15	535	1105	<5	0 31	157	13	89	8377	3 03	<10	0 03	75	<1	< 01	1301	6450	<2	500	<20	39	< 01	40	168	<10	<1	>10000
373-4	R95-03 7 5-7 9m	5	14 2	2 13	65	145	<5	0 04	25	32	59	4651	1 26	<10	< 01	206	<1	< 01	444	180	44	<5	<20	<1	< 01	<10	19	<10	<1	>10000
373-5	R95-03 7 9-8 5m	5	19 8	4 80	215	260	<5	0 10	60	88	29	6141	2.48	<10	0 02	586	<1	< 01	814	1170	64	<5	<20	2	< 01	<10	80	<10	<1	>10000
373-6	R95-03 8 5-9 5m	5	8 0	6 84	155	1125	<5	0 33	140	15	99	1396	3 00	<10	0 03	83	15	< 01	307	5490	116	5	<20	127	< 01	20	137	<10	2	8884
373-8	R95-03 9 5-10 5m	5	6 0	2 83	70	300	<5	0 11	87	6	55	2219	1 32	<10	0 02	29	<1	< 01	286	1510	88	15	<20	19	< 01	<10	51	<10	<1	>10000
373-9	R95-03 10 5-11 5m	5	0 8	10 50	305	675	<5	0 15	73	16	52	>10000	3 17	<10	0 03	52	<1	< 01	1227	1520	>10000	10	<20	<1	< 01	30	191	<10	10	>10000

TOKLAT RESOURCES INC AK 95-433

ECO-TECH LABORATORIES LTD

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
373-10	R95-03 11 5-12 7m	5	4 2	2 78	295	260	<5	0 07	31	51	86	>10000	> 15	<10	< 01	822	4	< 01	175	880	>10000	<5	<20	<1	< 01	40	327	<10	<1	>10000
373-11	R95-03 12 7-13 9m	5	5 8	5 15	200	275	<5	0 11	8	24	49	6572	> 15	<10	< 01	338	<1	< 01	164	690	>10000	<5	<20	3	< 01	40	173	<10	<1	4703
373-13	R95-03 13 9-15 1m	5	>30	0 08	30	80	<5	0 02	1	49	20	963	1 75	<10	< 01	534	<1	< 01	71	110	>10000	30	<20	2	< 01	<10	20	<10	7	1310
373-14	R95-03 15 1-15 9m	5	17 4	0 03	25	35	<5	> 15	51	11	5	2667	0 26	<10	13 20	102	<1	0 01	81	20	9234	85	<20	41	< 01	<10	7	<10	5	4355
373-15	R95-03 15 8-18 1m	5	16 6	8 82	60	75	<5	0 22	16	80	26	6922	3 68	<10	0 08	1095	<1	< 01	1033	250	>10000	<5	<20	<1	< 01	<10	67	<10	41	>10000
373-16	R95-03 18 1-19 1m	10	>30	4 69	35	65	<5	0 14	11	40	28	4309	2 27	<10	0 05	367	<1	< 01	632	130	>10000	<5	<20	<1	< 01	10	38	<10	<1	>10000
373-18	R95-03 19 1-20 0m	10	>30	0 87	35	65	<5	0 20	6	113	114	>10000	2 35	<10	0 06	1136	<1	< 01	843	380	>10000	35	<20	4	< 01	<10	22	<10	13	>10000
373-19	R95-03 20 0-21 5m	5	>30	3 40	40	60	<5	10 20	134	89	10	8702	3 34	<10	5 96	797	<1	< 01	1619	270	>10000	25	<20	23	< 01	<10	23	<10	45	>10000
373-20	R95-03 21 5-22 8m	5	16 4	0 66	25	55	<5	> 15	365	85	18	1496	3 40	<10	11 40	662	<1	0 01	456	220	836	45	<20	49	< 01	<10	21	<10	85	>10000
373-21	R95-03 22 8-23 6m	5	15 4	0 08	10	20	<5	> 15	142	10	49	236	0 79	<10	12 40	160	<1	0 01	60	80	132	55	<20	41	< 01	<10	9	<10	13	2418
373-22	R95-03 23 6-23 9m	5	6 0	0 03	<5	20	<5	> 15	222	23	13	193	1 53	<10	13 80	226	<1	0 01	64	70	40	55	<20	71	< 01	<10	6	<10	8	1913
373-23	R95-03 23 9-24 6m	5	9 4	0 10	20	55	<5	> 15	228	40	26	427	1 76	<10	12 40	433	<1	0 01	155	140	716	55	<20	60	< 01	<10	9	<10	11	>10000
373-24	R95-03 24 6-25 6m	10	5 8	0 02	10	20	<5	> 15	143	13	13	85	0 72	<10	14 10	194	<1	0 01	40	210	16	50	<20	64	< 01	<10	6	<10	5	5641
373-25	R95-03 25 6-26 6m	5	7 2	0 04	10	25	<5	> 15	112	14	19	126	0 96	<10	14 20	225	<1	0 01	52	140	52	65	<20	69	< 01	<10	11	<10	8	3771
189	R95-03 26 6-27 6m	5	3 2	0 05	10	30	<5	> 15	44	23	27	218	0 96	<10	13 50	308	<1	0 01	81	110	14	60	<20	66	< 01	<10	12	<10	1	>10000
190	R95-03 27 6-28 6m	5	1 4	0 07	10	20	<5	> 15	19	52	17	229	0 68	<10	14 30	603	<1	0 01	106	120	16	65	<20	66	< 01	<10	8	<10	<1	9733
191	R95-03 28 6-29 4m	5	2 2	0 07	10	20	<5	> 15	17	27	2	170	0 43	<10	> 15	365	<1	0 01	64	60	16	60	<20	63	< 01	<10	8	<10	<1	5428
192	R95-03 29 4-30 0m	5	5 6	0 15	25	35	<5	> 15	31	61	6	242	0 59	<10	14 40	789	<1	0 01	210	60	130	85	<20	71	< 01	<10	9	<10	6	>10000
193	R95-03 30 0-30 5m	5	2 2	0 07	10	35	<5	> 15	34	111	3	294	1 26	<10	14 10	1028	<1	0 01	186	50	78	65	<20	66	< 01	<10	9	<10	2	>10000
194	R95-03 30 5-31 5m	5	4 0	0 05	15	20	<5	> 15	27	34	7	70	0 61	<10	> 15	485	<1	< 01	73	70	110	75	<20	68	< 01	<10	10	<10	7	2009
195	R95-03 31 5-32 5m	5	2 2	0 05	10	10	<5	> 15	18	12	4	42	0 30	<10	> 15	226	<1	< 01	37	60	22	75	<20	66	< 01	<10	6	<10	2	2429
196	R95-03 32 5-33 5m	5	1 8	0 06	10	15	<5	> 15	14	15	7	22	0 22	<10	> 15	221	<1	0 01	26	90	28	65	<20	57	< 01	<10	7	<10	2	948
197	R95-03 33 5-34 5m	5	2 2	0 02	5	15	<5	> 15	4	9	5	14	0 24	<10	> 15	148	<1	0 01	16	80	10	65	<20	53	< 01	<10	7	<10	2	1211
198	R95-03 34 5-35 5m	5	1 4	0 02	10	20	<5	> 15	4	6	5	12	0 27	<10	> 15	157	<1	0 01	12	190	12	65	<20	59	< 01	<10	6	<10	2	1069
199	R95-03 35 5-36 8m	5	0 6	0 03	15	20	<5	> 15	2	10	3	6	0 61	<10	> 15	178	<1	0 01	31	170	8	60	<20	70	< 01	<10	4	<10	2	1175
200	R95-03 36 8-38 2m	5	1 0	0 02	10	20	<5	> 15	<1	6	3	<1	0 50	<10	> 15	111	<1	0 01	20	180	<2	60	<20	59	< 01	<10	6	<10	<1	398
201	R95-03 38 2-39 2m	5	2 8	0 02	20	20	<5	> 15	2	13	6	43	0 74	<10	> 15	216	<1	< 01	30	80	64	75	<20	55	< 01	<10	9	<10	2	671
202	R95-03 39 2-40 0m	5	0 8	0 03	10	15	<5	> 15	<1	7	1	33	0 18	<10	> 15	140	<1	0 01	14	230	22	65	<20	54	< 01	<10	5	<10	2	428
203	R95-03 40 0-41 0m	5	3 0	0 06	15	10	<5	> 15	9	7	1	55	0 32	<10	> 15	147	<1	0 01	26	210	84	75	<20	44	< 01	<10	8	<10	2	2466
204	R95-03 41 0-42 0m	5	2 4	0 09	35	15	<5	> 15	7	13	1	71	0 70	<10	> 15	158	<1	0 01	52	540	82	110	<20	59	< 01	<10	8	<10	5	2601
205	R95-03 42 0-42 8m	5	0 8	3 09	90	150	<5	> 15	11	41	13	101	2 94	<10	12 10	318	<1	< 01	363	450	96	75	<20	51	< 01	<10	63	<10	26	8901
206	R95-03 42.8-43 4m	5	1 6	0 07	20	10	<5	> 15	3	9	3	12	0 44	<10	> 15	227	<1	0 01	38	360	22	65	<20	65	< 01	<10	6	<10	4	737
207	R95-03 43 4-44 2m	5	1 0	1 06	35	55	<5	> 15	5	19	7	40	2 38	<10	13 80	250	<1	0 01	163	370	64	70	<20	73	< 01	<10	30	<10	15	2266
208	R95-03 44 2-46 7m	5	0 6	0 49	25	25	<5	> 15	3	18	3	26	0 84	<10	14 80	311	<1	0 01	87	210	32	65	<20	69	< 01	<10	17	<10	9	964
209	R95-03 46 7-47 7m	5	0 8	0 07	15	65	<5	> 15	2	7	3	21	0 16	<10	> 15	148	<1	0 01	15	100	28	75	<20	71	< 01	<10	12	<10	3	295
210	R95-03 47 7-48 3m	5	< 2	0 03	10	20	<5	> 15	<1	6	1	4	0 08	<10	> 15	166	<1	0 01	5	50	<2	60	<20	78	< 01	<10	13	<10	4	106
211	R95-03 48 3-49 6m	5	0 8	0 05	20	15	<5	> 15	3	10	3	20	0 35	<10	> 15	180	<1	0 01	27	400	32	70	<20	67	< 01	<10	10	<10	5	518
212	R95-03 49 6-50 7m	5	0 4	0 05	10	20	<5	> 15	2	18	1	18	1 10	<10	> 15	234	<1	0 01	67	310	24	65	<20	73	< 01	<10	12	<10	4	1131
213	R95-03 50 7-51 7m	5	0 4	0 07	10	20	<5	> 15	<1	8	2	3	0 58	<10	14 70	159	<1	0 01	41	170	8	60	<20	71	< 01	<10	13	<10	3	727
214	R95-03 51 7-52 7m	5	1 0	0 07	30	15	<5	> 15	11	14	2	81	0 80	<10	14 70	242	<1	< 01	87	150	22	95	<20	66	< 01	<10	11	<10	3	3986
215	R95-03 52.7-53 7m	5	0 6	0 05	15	10	<5	> 15	2	11	1	14	0 37	<10	> 15	198	<1	0 01	39	120	<2	60	<20	60	< 01	<10	6	<10	<1	1056
216	R95-03 53 7-54 8m	5	0 2	0 05	10	15	5	> 15	<1	9	<1	2	0 51	<10	> 15	155	<1	0 01	33	130	<2	60	<20	57	< 01	<10	7	<10	<1	456
217	R95-03 54 8-55 5m	5	0 4	0 04	10	20	5	> 15	2	6	1	3	0 46	<10	> 15	171	<1	0 01	30	110	8	65	<20	81	< 01	<10	8	<10	2	319

TOKLAT RESOURCES INC. AK 95-433

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
Resplit #:																														
RS1	R95-01 0-5'	5	0 6	0 29	30	135	<5	0 22	<1	2	113	92	1 18	<10	0 11	88	30	< 01	33	360	116	5	<20	11	< 01	<10	60	<10	3	115
RS36	R95-01 39 6-41 2m	5	0 2	0 44	35	45	<5	12 10	<1	26	90	2	1 07	<10	7 33	271	4	< 01	113	130	24	50	<20	38	< 01	<10	18	<10	10	878
RS71	R95-01 109 8-111 3m	5	< 2	0 03	<5	20	<5	> 15	<1	<1	1	<1	0 11	<10	13 80	97	<1	0 01	<1	80	<2	60	<20	120	< 01	<10	3	<10	<1	21
RS106	R95-01 156 0-157 5m	-	0 4	0 06	10	25	5	> 15	<1	1	1	<1	0 26	<10	14 00	93	<1	0 01	3	80	4	65	<20	86	< 01	<10	5	<10	<1	69
RS141	R95-02 15 0-16 5m	5	2 6	0 01	20	20	<5	> 15	<1	<1	7	13	0 05	<10	> 15	80	<1	0 01	<1	70	8	70	<20	51	< 01	<10	7	<10	<1	274
RS176	R95-02 50 7-51 3m	5	3 0	0 03	5	15	<5	> 15	49	10	<1	70	0 91	<10	14 80	169	<1	0 01	42	180	44	55	<20	70	< 01	<10	7	<10	4	4345
RS211	R95-03 48 3-49 6m	5	0 8	0 04	20	15	<5	> 15	3	9	2	13	0 31	<10	> 15	176	<1	0 01	25	400	28	60	<20	66	< 01	<10	10	<10	5	489
RS373-1	R95-03 0-5'	5	>30	2 52	930	1050	<5	0 50	44	31	118	2037	5 44	<10	0 22	425	2	< 01	208	1630	5298	1315	<20	21	< 01	<10	120	<10	12	>10000
Repeat #:																														
1	R95-01 0-5'	5	1 0	0 24	35	120	<5	0 05	<1	2	114	88	1 09	<10	0 02	86	29	< 01	28	330	114	10	<20	10	< 01	<10	60	<10	2	90
10	R95-01 8 0-9 7m	5	< 2	1 87	105	155	<5	0 32	<1	23	71	85	1 96	<10	0 08	130	51	< 01	299	3230	24	5	<20	5	< 01	<10	110	<10	24	491
19	R95-01 18 5-20 0m	5	< 2	0 04	10	15	<5	> 15	3	4	3	<1	0 23	<10	> 15	134	<1	< 01	19	150	4	65	<20	49	< 01	<10	12	<10	7	99
36	R95-01 39 6-41 2m	5	< 2	0 46	45	45	<5	12 60	<1	23	101	3	1 12	<10	7 74	258	1	< 01	110	130	22	50	<20	40	< 01	<10	17	<10	10	859
45	R95-01 53 6-55 1m	5	0 4	0 02	20	15	<5	> 15	<1	4	4	4	0 48	<10	14 80	147	<1	0 01	16	340	<2	70	<20	64	< 01	<10	8	<10	3	138
54	R95-01 67 0-68 5m	5	0 2	0 04	20	15	<5	> 15	1	2	3	10	0 11	<10	14 70	89	<1	0 01	<1	90	<2	70	<20	84	< 01	<10	5	<10	<1	95
71	R95-01 109 8-111 3m	5	0 4	0 03	10	20	<5	> 15	<1	<1	1	<1	0 11	<10	13 80	97	<1	0 01	<1	90	<2	60	<20	119	< 01	<10	3	<10	<1	23
80	R95-01 121 7-123 2m	5	0 2	0 05	10	15	<5	> 15	<1	<1	2	3	0 24	<10	14 30	97	<1	0 01	<1	120	<2	65	<20	84	< 01	<10	4	<10	<1	33
89	R95-01 132 5-134 0m	5	0 4	0 04	15	15	<5	> 15	<1	2	2	<1	0 45	<10	14 90	93	<1	0 01	7	80	<2	75	<20	78	< 01	<10	4	<10	<1	90
106	R95-01 156 0-157 5m	5	0 2	0 06	15	20	<5	> 15	<1	1	1	<1	0 26	<10	13 80	120	<1	0 01	6	100	<2	60	<20	83	< 01	<10	5	<10	<1	65
115	R95-01 167 5-167 9m	5	0 6	1 87	60	150	<5	> 15	13	13	26	136	2.55	<10	9 32	230	3	< 01	227	90	22	55	<20	65	< 01	<10	48	<10	11	897
124	R95-01 180 0-181 5m	5	0 4	0 03	10	45	<5	> 15	<1	1	2	7	0 28	<10	14 20	144	<1	0 01	7	90	10	65	<20	78	< 01	<10	5	<10	<1	61
133	R95-02 4 6-6 0m	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
141	R95-02 15 0-16 5m	5	2 6	0 01	15	20	<5	> 15	<1	<1	6	14	0 05	<10	14 80	82	<1	0 01	1	70	8	65	<20	53	< 01	<10	7	<10	<1	267
150	R95-02 23 7-25 1m	5	2 4	0 14	25	20	<5	> 15	96	5	6	555	0 38	<10	14 10	170	<1	0 01	36	400	18	65	<20	66	< 01	<10	7	<10	<1	>10000
159	R95-02 33.6-34 6m	5	2 8	0 05	5	25	<5	> 15	57	15	3	295	1 10	<10	14 40	240	<1	0 01	52	30	24	55	<20	73	< 01	<10	5	<10	4	4902
176	R95-02 50 7-51 3m	5	3 0	0 03	5	15	<5	> 15	52	12	<1	79	0 94	<10	> 15	193	<1	0 01	47	190	48	55	<20	71	< 01	<10	7	<10	4	4624
185	R95-02 59 9-62 3m	5	0 2	0 05	30	25	<5	> 15	23	20	3	133	0 96	<10	13 70	281	<1	0 01	72	250	72	50	<20	64	< 01	<10	15	<10	<1	>10000
194	R95-03 30 5-31 5m	5	4 0	0 05	10	15	<5	> 15	26	34	6	68	0 61	<10	15 00	481	<1	0 01	73	80	110	70	<20	65	< 01	<10	10	<10	7	1995
211	R95-03 48 3-49 6m	5	0 6	0 04	20	15	<5	> 15	3	10	2	14	0 33	<10	> 15	176	<1	0 01	26	370	30	70	<20	66	< 01	<10	10	<10	5	510
373-1	R95-03 0-5'	5	>30	2 53	945	1035	<5	0 48	42	30	95	2105	5 47	<10	0 21	392	1	< 01	210	1560	5236	1290	<20	21	< 01	10	122	<10	13	>10000
373-10	R95-03 11 5-12.7m	5	4 6	2 65	305	255	<5	0 07	32	51	85	>10000	> 15	<10	< 01	817	8	< 01	178	960	>10000	<5	<20	<1	< 01	30	321	<10	<1	>10000
373-19	R95-03 20 0-21 5m	-	>30	3 35	45	60	<5	10 20	134	90	10	8412	3 38	<10	5 97	811	<1	< 01	1639	290	>10000	20	<20	22	< 01	<10	23	<10	45	>10000
373-20	R95-03 21 5-22 8m	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Standard:																														
GEO95		150	1 2	1 70	70	150	<5	1 68	<1	17	60	85	3 85	<10	0 97	635	<1	0 02	27	660	20	<5	<20	59	0 11	<10	77	<10	4	78
GEO95		150	1 4	1 67	65	155	<5	1 69	<1	18	60	85	3 89	<10	0 87	640	<1	0 02	30	620	20	5	<20	57	0 11	<10	76	<10	4	72
GEO95		145	1 2	1 78	70	155	<5	1 63	<1	18	62	88	3 75	<10	0 86	652	<1	0 02	27	630	22	10	<20	63	0 12	<10	80	<10	4	78
GEO95		150	1 2	1 71	60	150	<5	1 73	<1	18	60	85	3 88	<10	0 85	635	<1	0 02	26	670	18	10	<20	61	0 12	<10	77	<10	4	82
GEO95		145	1 2	1 72	55	150	<5	1 60	<1	18	61	86	3 71	<10	0 86	634	<1	0 02	28	620	18	<5	<20	61	0 12	<10	78	<10	6	76
GEO95		150	1 2	1 73	60	150	<5	1 75	<1	18	61	84	3 72	<10	0 85	634	<1	0 02	28	620	20	<5	<20	62	0 12	<10	78	<10	5	74
GEO95		155	1 4	1 66	60	150	<5	1 58	<1	17	60	86	3 74	<10	0 87	641	<1	0 02	27	600	18	10	<20	55	0 10	<10	75	<10	5	70

NOTE: ***n/s = no sample submitted***

df/365
XLS/95Toklat

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A Sc T
B C Certified Assayer

21-Jul-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-434
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION TIM TERMUENDE

141 Core samples received July 11, 1995
PROJECT # Rusty Springs
SHIPMENT # RS02

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	R95 - 4 0 - 5'	5	>30	1 12	625	1095	<5	0 60	143	22	107	3580	2 21	<10	0 29	224	<1	< 01	348	660	2670	830	<20	14	< 01	<10	50	>10000	<1	>10000
2	R95 - 4 5' - 10'	5	>30	0 21	560	905	<5	0 25	63	250	131	3168	0 95	<10	0 11	133	<1	< 01	180	240	7814	880	<20	4	< 01	<10	12	<10	<1	>10000
3	R95 - 4 3 0 - 4 0m	5	25 6	0 07	385	1430	<5	0 09	188	6	118	2419	0 41	<10	0 03	176	<1	< 01	149	170	2406	360	<20	1	< 01	<10	9	>10000	<1	>10000
4	R95 - 4 4 0 - 5 4m	20	>30	0 44	5800	165	<5	0 16	188	26	68	3670	10 10	<10	< 01	219	<1	0 02	184	700	4468	8125	<20	14	< 01	<10	76	<10	<1	>10000
5	R95 - 4 5 4 - 6 7m	5	>30	2 82	1725	1495	<5	0 09	<1	9	65	2148	3 10	<10	0 02	113	2	0 02	190	340	344	835	<20	3	< 01	<10	26	<10	37	7696
6	R95 - 4 6 7 - 7 5m	5	>30	0 64	1085	1250	<5	0 93	30	73	79	>10000	1 86	<10	0 47	705	<1	< 01	231	390	288	560	<20	4	< 01	<10	21	>10000	<1	>10000
7	R95 - 4 7 5 - 9 1m	5	>30	0 85	1365	1095	<5	0 71	73	84	57	>10000	2 36	<10	0 34	720	<1	< 01	270	380	376	710	<20	3	< 01	<10	24	>10000	<1	>10000
8	R95 - 4 9 1 - 10 3m	5	17 0	0 04	35	105	<5	> 15	239	11	28	462	0 42	<10	9 59	126	<1	< 01	65	80	18	75	<20	35	< 01	<10	7	<10	<1	>10000
9	R95 - 4 10 3 - 11 0m	5	4 0	0 16	40	40	<5	> 15	983	34	9	3608	0 59	<10	12 10	316	<1	< 01	194	40	10	60	<20	42	< 01	<10	10	<10	<1	>10000
10	R95 - 4 11 0 - 11 6m	5	>30	5 53	270	315	<5	9 48	166	16	28	8760	2 14	<10	5 35	124	<1	< 01	1028	290	44	60	<20	14	< 01	<10	75	>10000	<1	>10000
11	R95 - 4 11 6m -12 6m	5	10 0	0 04	10	20	<5	> 15	144	4	5	235	0 27	<10	13 20	83	<1	< 01	22	40	26	70	<20	37	< 01	<10	9	<10	<1	5092
12	R95 - 4 12 6 - 13 6m	5	10 8	0 03	10	20	<5	> 15	233	10	3	257	1 15	<10	13 70	119	<1	0 01	50	30	34	60	<20	46	< 01	<10	9	<10	1	4091
13	R95 - 4 13 6 - 14 6m	5	3 4	0 04	15	30	<5	> 15	130	6	2	448	0 38	<10	14 50	140	<1	0 01	20	190	18	60	<20	64	< 01	<10	4	<10	2	4488
14	R95 - 4 14 6 - 15 6m	5	7 0	0 03	10	25	<5	> 15	104	<1	1	119	0 12	<10	14 60	96	<1	0 01	6	150	12	70	<20	74	< 01	<10	3	<10	2	1120
15	R95 - 4 15 6 - 16 6m	5	>30	0 03	10	15	<5	> 15	645	<1	3	100	0 15	<10	14 50	89	<1	0 01	24	290	18	60	<20	67	< 01	<10	5	<10	1	4917
16	R95 - 4 16 6 - 17 6m	5	>30	0 02	10	15	<5	> 15	654	5	3	178	0 34	<10	14 00	140	<1	0 01	29	40	40	65	<20	66	< 01	<10	3	<10	<1	>10000
17	R95 - 4 17 6 - 19 1m	5	>30	0 12	15	35	<5	> 15	1000	34	7	3550	4 23	<10	10 10	265	<1	0 01	298	60	188	20	<20	43	< 01	<10	14	>10000	7	>10000
18	R95 - 4 19 1 - 20 1m	5	2 6	0 05	15	20	<5	> 15	853	12	5	1678	1 21	<10	12 70	135	<1	< 01	101	140	32	40	<20	43	< 01	<10	7	<10	<1	>10000
19	R95 - 4 20 1 - 20 9m	5	3 8	0 10	15	25	<5	> 15	568	37	2	1143	1 73	<10	13 10	340	<1	0 01	204	110	60	50	<20	61	< 01	<10	9	<10	5	>10000
20	R95 - 4 20 9 - 23 2m	5	9 8	1 77	20	90	<5	14 20	516	47	8	6480	3 59	<10	8 39	417	<1	0 01	2617	60	22	10	<20	32	< 01	<10	28	>10000	65	>10000
21	R95 - 4 23 2 - 24 9m	5	12 4	0 08	20	40	<5	> 15	198	11	5	342	0 71	<10	13 80	182	<1	0 01	89	70	48	65	<20	50	< 01	<10	5	<10	10	3010
22	R95 - 4 24 9 - 25 9m	5	6 8	0 01	15	15	<5	> 15	60	1	3	39	0 15	<10	14 90	81	<1	0 01	6	70	<2	60	<20	35	< 01	<10	4	<10	4	368
23	R95 - 4 25 9 - 26 9m	5	6 0	0 08	15	20	<5	> 15	73	10	5	299	0 69	<10	14 10	148	<1	0 01	129	110	<2	60	<20	35	< 01	<10	5	<10	5	>10000
24	R95 - 4 26 9 - 27 9m	5	13 6	0 02	10	20	<5	> 15	76	8	1	75	0 90	<10	14 80	145	<1	0 01	30	140	18	65	<20	68	< 01	<10	5	<10	8	852
25	R95 - 4 27 9 - 28 9m	5	9 0	0 02	10	25	<5	> 15	63	4	1	38	0 52	<10	14 80	117	<1	0 01	20	160	<2	65	<20	63	< 01	<10	7	<10	5	828

TOKLAT RESOURCES INC AK 95-434

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	R95 - 4 28 9 - 29 9m	5	8 4	0 01	15	15	<5	> 15	51	1	<1	39	0 24	<10	14 80	89	<1	0 01	8	220	26	65	<20	42	< 01	<10	6	<10	4	689
27	R95 - 4 29 9 - 30 9m	5	8 0	0 01	10	10	<5	> 15	59	2	1	55	0 29	<10	> 15	73	<1	0 01	9	200	20	70	<20	38	< 01	<10	5	<10	3	593
28	R95 - 4 30 9 - 32 3m	5	3 4	0 01	10	15	<5	> 15	52	5	<1	48	0 42	<10	> 15	122	<1	0 01	14	220	18	60	<20	47	< 01	<10	7	<10	4	773
29	R95 - 5 0 - 5'	10	23 6	0 98	95	395	<5	11 40	15	13	27	338	2 80	<10	6 60	295	56	< 01	157	460	924	135	<20	40	< 01	<10	59	<10	12	2622
30	R95 - 5 5 - 10'	5	1 6	0 90	20	145	<5	> 15	9	13	23	208	3 00	<10	9 48	269	14	0 01	135	410	164	50	<20	58	< 01	<10	67	<10	13	1034
31	R95 - 5 10 - 15'	5	>30	4 09	130	300	<5	10 40	9	17	36	627	4 05	<10	6 01	186	345	< 01	412	510	240	40	<20	34	< 01	<10	120	<10	24	1330
32	R95 - 5 15 - 20'	5	>30	3 89	180	215	<5	3 55	2	14	78	500	4 31	<10	1 92	105	277	< 01	369	520	154	20	<20	11	< 01	<10	180	<10	14	819
33	R95 - 5 20 - 25'	5	>30	6 95	160	790	<5	1 72	10	10	74	650	3 29	<10	0 86	48	442	0 01	382	1720	158	10	<20	85	< 01	<10	449	160	8	826
34	R95 - 5 25 - 27'	5	>30	5 59	150	455	<5	3 37	2	16	56	681	4 08	<10	1 81	94	297	< 01	452	890	170	15	<20	37	< 01	<10	259	230	13	925
35	R95 - 5 8 2 - 9 3m	5	>30	2 31	45	245	<5	0 32	<1	9	81	180	1 91	<10	0 15	37	48	< 01	152	500	56	<5	<20	11	< 01	<10	170	<10	3	542
36	R95 - 5 9 3 - 11 1m	5	0 6	5 88	330	395	<5	0 17	<1	16	45	673	6 58	<10	0 04	35	29	< 01	425	1380	398	15	<20	6	< 01	<10	304	<10	20	1243
37	R95 - 5 11 1 - 11 8m	5	25 0	0 22	1020	290	<5	0 04	<1	<1	173	209	1 35	<10	< 01	27	12	< 01	18	300	3016	970	<20	16	< 01	<10	39	<10	1	91
38	R95 - 5 11 8 - 13 5m	5	2 0	0 83	230	535	<5	0 09	<1	<1	112	380	1 99	<10	0 02	18	57	< 01	49	1280	3368	80	<20	61	< 01	<10	93	<10	3	300
39	R95 - 5 13 5 - 14 2m	5	18 6	1 12	430	320	<5	0 09	<1	1	107	1509	3 11	<10	< 01	12	90	< 01	44	2160	>10000	460	<20	78	< 01	<10	162	<10	10	456
40	R95 - 5 14 2 - 15 0m	5	0 4	4 04	185	415	<5	0 27	3	3	111	553	2 58	<10	0 04	19	23	< 01	196	3550	328	60	<20	68	< 01	<10	155	<10	6	872
41	R95 - 5 15 0 - 16 1m	5	0 6	5 17	180	415	<5	0 18	5	36	63	865	7 23	<10	< 01	137	62	< 01	615	1350	536	25	<20	20	< 01	<10	227	<10	55	2642
42	R95 - 5 16 1 - 17 1m	5	0 4	8 05	60	235	<5	0 22	11	57	41	808	4 83	<10	0 03	343	28	< 01	772	870	92	<5	<20	<1	< 01	<10	169	<10	51	1943
43	R95 - 5 17 1 - 18 6m	5	< 2	> 15	45	1055	<5	0 13	7	27	18	1380	13 20	<10	< 01	44	62	< 01	1184	490	<2	<5	<20	3	< 01	<10	158	<10	25	2266
44	R95 - 5 18 6 - 20 1m	5	< 2	6 14	60	505	<5	1 73	33	30	29	1082	4 37	<10	0 80	170	15	< 01	833	600	46	<5	<20	4	< 01	<10	135	<10	86	1702
45	R95 - 5 20 1 - 21 3m	5	< 2	7 25	85	300	<5	7 49	21	38	25	1040	2 43	<10	4 07	204	11	< 01	718	730	52	35	<20	22	< 01	<10	180	<10	86	1052
46	R95 - 5 21 3 - 22 3m	5	< 2	0 33	10	50	<5	> 15	15	22	11	82	0 96	<10	10 20	213	1	< 01	114	90	12	50	<20	58	< 01	<10	20	<10	14	346
47	R95 - 5 22 3 - 23 3m	5	< 2	2 28	50	250	<5	> 15	30	22	16	273	1 04	<10	8 79	197	2	< 01	405	290	34	55	<20	47	< 01	<10	56	<10	32	1080
48	R95 - 5 23 3 -24 3m	5	< 2	0 10	15	20	<5	> 15	4	6	16	21	0 39	<10	11 10	151	<1	< 01	45	300	8	55	<20	68	< 01	<10	20	<10	16	183
49	R95 - 5 24 3 - 25 3m	5	< 2	0 30	20	75	<5	> 15	5	13	8	47	0 66	<10	12 60	160	<1	< 01	94	150	12	60	<20	73	< 01	<10	15	<10	9	438
49a	R95 - 5 25 3 - 35 4	n/s	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
50	R95 - 5 35 4 - 36 5m	5	< 2	0 05	25	20	<5	> 15	<1	2	6	38	0 22	<10	14 00	108	<1	0 01	13	90	10	70	<20	45	< 01	<10	8	<10	4	143
51	R95 - 5 36 5 - 37 9m	5	0 8	0 59	50	70	<5	> 15	6	16	16	106	0 83	<10	13 40	237	2	0 01	100	200	34	85	<20	46	< 01	<10	18	<10	12	594
52	R95 - 5 37 9 - 39 1m	5	0 2	0 03	20	15	<5	> 15	2	5	7	12	0 40	<10	14 70	128	<1	0 01	20	250	6	70	<20	38	< 01	<10	7	<10	4	287
53	R95 - 5 39 1 - 41 4m	5	2 0	0 07	65	20	<5	> 15	9	14	10	57	0 80	<10	13 60	212	<1	0 01	58	210	22	110	<20	50	< 01	<10	7	<10	7	724
54	R95 - 5 41 4 - 42 9m	5	1 6	0 13	90	35	<5	> 15	13	27	2	52	0 88	<10	14 00	369	<1	0 01	82	300	30	110	<20	72	< 01	<10	10	<10	8	769
55	R95 - 5 42 9 - 44 2m	5	0 4	0 07	45	25	<5	> 15	<1	15	2	10	0 77	<10	14 30	216	<1	0 01	54	250	10	85	<20	70	< 01	<10	11	<10	6	505
56	R95 - 5 44 2 - 45 8m	5	0 8	0 04	130	30	<5	> 15	10	28	9	29	2 09	<10	13 20	308	<1	< 01	138	230	42	105	<20	68	< 01	<10	11	<10	10	1546
57	R95 - 5 45 8 - 46 7m	5	0 8	0 06	65	50	<5	> 15	9	37	2	16	3 66	<10	13 40	455	2	0 01	181	170	38	95	<20	75	< 01	<10	10	<10	17	1973
58	R95 - 5 46 7 - 48 2m	5	< 2	0 02	<5	20	<5	> 15	<1	12	3	2	0 99	<10	14 20	227	<1	0 01	54	210	8	55	<20	73	< 01	<10	9	<10	7	486
59	R95 - 5 48.2 - 49 7m	5	0 2	0 02	20	15	<5	> 15	<1	3	2	4	0 28	<10	14 90	152	<1	0 01	14	220	4	65	<20	58	< 01	<10	11	<10	4	171

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
60	R95 - 5 49 7 - 50 6m	5	< 2	0 02	<5	20	<5	> 15	1	13	1	<1	1 14	<10	14 80	253	<1	0 01	62	140	34	55	<20	65	< 01	<10	10	<10	8	570
61	R95 - 5 50 6 - 53 6m	5	0 2	0 02	25	25	<5	> 15	1	14	7	6	1 09	<10	14 20	287	<1	0 01	60	120	48	75	<20	63	< 01	<10	10	<10	7	582
62	R95 - 5 53 6 - 56 7m	5	1 0	0 04	20	25	<5	> 15	3	12	11	17	1 01	<10	13 60	239	<1	0 01	67	340	56	70	<20	61	< 01	<10	9	<10	8	611
63	R95 - 5 56 7 - 59 7m	5	0 6	0 03	40	30	<5	> 15	3	<1	12	12	0 42	<10	13 20	189	<1	0 01	17	160	70	65	<20	58	< 01	<10	11	<10	4	220
64	R95 - 5 59 7 - 61 2m	5	0 6	0 18	25	35	<5	> 15	4	2	9	19	0 43	<10	12 60	167	<1	0 03	35	130	90	65	<20	51	< 01	<10	10	<10	5	256
65	R95 - 5 61 2 - 62 8m	5	0 4	0 01	90	40	<5	14 20	<1	<1	50	5	1 31	<10	8 32	118	<1	0 01	27	60	242	55	<20	39	< 01	<10	8	<10	<1	533
66	R95 - 5 62 8 - 64 3m	5	0 8	0 02	30	20	<5	> 15	4	<1	23	5	0 45	<10	12 80	163	<1	0 01	8	100	80	65	<20	65	< 01	<10	10	<10	2	200
67	R95 - 5 64 3 - 65 8m	5	1 4	0 01	75	25	<5	> 15	2	<1	27	8	0 72	<10	12 20	215	<1	0 01	12	60	136	65	<20	53	< 01	<10	8	<10	1	257
68	R95 - 5 65 8 - 68 9m	5	0 6	0 04	35	30	<5	> 15	2	<1	18	11	0 38	<10	12 40	135	<1	0 01	12	60	136	65	<20	39	< 01	<10	8	<10	<1	234
69	R95 - 5 68 9 - 71 9m	5	0 4	0 05	10	25	<5	> 15	2	<1	18	10	0 16	<10	13 40	104	<1	0 02	4	70	48	65	<20	44	< 01	<10	5	<10	<1	116
70	R95 - 5 71 9 - 75 0m	5	0 8	0 22	20	30	<5	> 15	3	<1	9	127	0 14	<10	13 40	144	<1	0 01	30	140	24	60	<20	58	< 01	<10	10	<10	<1	1580
71	R95 - 5 75 0 - 77 7m	5	0 8	0 05	30	20	<5	> 15	<1	<1	22	11	0 30	<10	12 70	142	<1	0 01	9	160	30	70	<20	58	< 01	<10	12	<10	3	119
72	R95 - 6 0 - 5'	5	3 8	0 85	35	440	<5	11 00	9	12	17	173	3 11	<10	6 32	210	16	< 01	169	430	416	80	<20	39	< 01	<10	53	<10	13	1571
73	R95 - 6 5 - 10'	5	0 4	0 66	30	220	<5	> 15	6	12	9	136	3 19	<10	10 70	231	21	< 01	149	370	140	50	<20	65	< 01	<10	91	<10	14	726
74	R95 - 6 10 - 15'	5	< 2	1 41	20	125	<5	> 15	6	11	13	138	1 83	<10	10 30	213	10	0 01	167	490	56	50	<20	65	< 01	<10	70	<10	15	507
75	R95 - 6 4 6 - 4 9m	5	< 2	0 07	15	25	<5	> 15	3	4	12	11	0 37	<10	13 00	190	<1	0 01	24	270	10	60	<20	80	< 01	<10	32	<10	10	119
76	R95 - 6 4 9 - 5 2m	5	< 2	> 15	55	170	<5	1 26	22	46	14	920	2 70	<10	0 51	163	5	< 01	1695	860	<2	<5	<20	2	< 01	<10	126	<10	88	2957
77	R95 - 6 5 2 - 6 4m	5	< 2	3 32	20	210	<5	14 40	12	30	8	298	2 35	<10	8 51	248	10	< 01	530	450	34	40	<20	46	< 01	<10	91	<10	45	1120
78	R95 - 6 6 4 - 7 6m	5	< 2	4 95	20	130	<5	11 00	20	39	14	238	1 22	<10	6 10	332	4	< 01	544	480	20	40	<20	41	< 01	<10	56	<10	34	1073
79	R95 - 6 7 6 - 8 5m	5	< 2	6 17	35	345	<5	9 05	23	64	22	515	3 05	<10	5 12	572	14	< 01	850	1020	28	25	<20	32	< 01	<10	105	<10	101	2243
80	R95 - 6 8 5 - 9 1m	5	< 2	5 59	40	400	<5	0 73	21	48	32	599	10 10	<10	0 09	153	60	< 01	1012	2420	42	<5	<20	9	< 01	<10	168	<10	78	3860
81	R95 - 6 9 1 - 10 3m	5	< 2	2 51	40	235	<5	0 47	15	26	53	208	3 49	<10	0 03	115	32	< 01	601	1900	26	<5	<20	24	< 01	<10	93	<10	69	1945
82	R95 - 6 10 3 - 11 6m	5	0 2	2 41	50	280	<5	1 23	21	46	55	196	4 59	<10	0 31	266	37	< 01	671	2820	30	<5	<20	15	< 01	<10	88	<10	64	2067
83	R95 - 6 11 6 - 13 1m	5	< 2	2 96	40	345	<5	0 55	31	49	62	232	4 46	<10	0 09	387	40	< 01	704	1470	32	<5	<20	15	< 01	<10	105	<10	74	2140
84	R95 - 6 13 1 - 14 6m	5	< 2	1 51	75	210	<5	0 21	14	32	79	249	6 22	<10	< 01	139	70	< 01	523	1140	30	<5	<20	14	< 01	<10	173	<10	61	1875
85	R95 - 6 14 6 - 16 2m	5	0 4	1 89	70	120	<5	0 35	6	36	87	241	3 36	<10	< 01	223	49	< 01	492	1610	50	<5	<20	15	< 01	<10	97	<10	67	958
86	R95 - 6 16 2 - 17 7m	5	< 2	1 66	70	75	<5	0 46	3	32	91	248	4 40	<10	< 01	131	36	< 01	505	2450	114	<5	<20	31	< 01	<10	93	<10	71	1132
87	R95 - 6 17 7 - 17 9m	5	< 2	0 28	15	30	<5	> 15	3	5	29	28	0 48	<10	12 50	166	3	< 01	50	490	26	60	<20	71	< 01	<10	33	<10	12	185
88	R95 - 6 17 9 - 18 7m	5	< 2	1 51	95	90	<5	0 94	7	25	102	229	4 92	<10	0 08	165	40	< 01	567	3670	34	<5	<20	20	< 01	<10	85	<10	96	1402
89	R95 - 6 18 7 - 20 3m	5	< 2	1 45	130	150	<5	0 66	18	59	53	218	14 00	<10	< 01	189	62	< 01	958	2770	28	<5	<20	10	< 01	<10	110	<10	92	3715
90	R95 - 6 20 3 - 21 6m	5	< 2	4 52	120	380	<5	2 98	15	25	71	482	6 21	<10	1 51	122	28	< 01	781	2430	106	<5	<20	27	< 01	<10	165	<10	59	2205
91	R95 - 6 21 6 - 23 2m	5	0 4	1 39	115	185	<5	3 61	14	24	121	291	6 22	<10	1 97	169	23	< 01	401	1050	62	10	<20	32	< 01	<10	130	<10	45	1481
92	R95 - 6 23 2 - 24 3m	5	0 6	0 66	25	120	<5	0 09	4	9	131	87	2 03	<10	0 01	43	11	< 01	185	360	100	<5	<20	2	< 01	<10	28	<10	12	762
93	R95 - 6 24 3 - 26 1m	5	< 2	2 32	30	330	<5	0 12	22	55	67	484	11 30	<10	< 01	80	31	< 01	859	770	40	<5	<20	13	< 01	<10	151	<10	29	3441
94	R95 - 6 26 1 - 27 0m	5	1 0	0 11	10	30	<5	0 07	<1	2	201	35	0 59	<10	0 03	37	7	< 01	26	50	20	10	<20	1	< 01	<10	7	<10	<1	120

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
95	R95-6 27 0-28 3m	5	1 4	0 66	50	190	<5	6 73	7	10	108	176	2 95	<10	3 87	128	9	< 01	147	540	36	35	<20	26	< 01	<10	65	<10	3	652
96	R95-6 28 3-29 6m	5	3 4	0 84	215	85	<5	12 10	26	18	103	920	2 37	<10	7 14	213	7	< 01	147	370	90	140	<20	38	< 01	<10	37	<10	7	2991
97	R95-6 29 6-31 3m	5	2 0	0 27	145	270	<5	7 57	25	5	150	367	2 80	<10	4 37	92	7	< 01	73	200	38	50	<20	14	< 01	<10	42	<10	2	3374
98	R95-6 31 3-32 9m	5	0 2	0 66	90	150	<5	0 24	2	6	128	196	5 14	<10	0 10	22	10	< 01	85	390	34	35	<20	4	< 01	<10	68	<10	<1	670
99	R95-7 0-5'	5	< 2	1 78	35	205	<5	> 15	8	11	21	247	3 08	<10	9 80	166	17	< 01	247	420	72	45	<20	55	< 01	<10	143	<10	11	805
100	R95-7 5'-10'	5	0 4	1 76	25	340	<5	> 15	8	18	14	367	5 27	<10	9 57	200	28	< 01	324	390	156	40	<20	45	< 01	<10	112	<10	18	1420
101	R95-7 10'-14'	5	< 2	1 93	30	205	<5	> 15	6	11	14	245	3 24	<10	9 97	167	15	< 01	246	300	140	40	<20	55	< 01	<10	90	<10	13	846
102	R95-7 4 3-4 9m	5	< 2	0 16	40	40	<5	> 15	7	11	17	27	1 35	<10	9 28	240	3	< 01	70	250	144	45	<20	46	< 01	<10	28	<10	14	351
103	R95-7 4 9-5 2m	5	< 2	8 94	165	1510	<5	0 63	37	21	38	780	8 70	<10	0 23	69	44	< 01	1470	1240	488	<5	<20	17	< 01	<10	392	<10	77	3148
104	R95-7 5 2-5 9m	5	< 2	> 15	40	325	<5	0 47	5	29	55	460	1 48	<10	0 07	218	11	< 01	737	650	<2	<5	<20	2	< 01	<10	45	<10	57	1087
105	R95-7 5 9-6 9m	5	< 2	5 40	140	890	<5	0 15	3	9	60	193	3 96	<10	0 03	31	25	< 01	436	650	78	<5	<20	2	< 01	<10	229	<10	9	915
106	R95-7 6 9-8 1m	5	< 2	9 35	90	375	<5	0 22	14	34	34	488	4 04	<10	0 07	153	27	< 01	1039	770	76	<5	<20	<1	< 01	<10	237	<10	28	2411
107	R95-7 8 1-9 3m	5	< 2	6 95	185	805	<5	0 23	2	12	76	398	4 43	<10	0 03	46	30	< 01	515	3040	124	<5	<20	178	< 01	<10	456	<10	16	974
108	R95-7 9 3-10 0	5	0 2	2 20	55	790	<5	0 20	<1	9	70	203	2 76	<10	< 01	55	17	< 01	186	2580	88	<5	<20	313	< 01	<10	151	<10	16	665
109	R95-7 10 0-11 1m	5	0 2	0 53	90	955	<5	0 11	1	<1	79	77	1 35	<10	< 01	25	10	< 01	38	1390	142	<5	<20	72	< 01	<10	66	<10	4	104
110	R95-7 11 1-12 1m	5	0 8	0 59	35	1050	<5	0 13	<1	<1	93	101	1 18	<10	< 01	26	13	< 01	70	1390	96	<5	<20	69	< 01	<10	64	<10	12	226
111	R95-7 12 1-13 1m	5	1 6	0 40	45	365	<5	0 26	1	4	112	540	1 21	<10	0 10	45	30	< 01	70	740	38	5	<20	68	< 01	<10	84	<10	18	512
112	R95-7 13 1-13 7m	5	6 2	0 29	45	90	<5	0 29	3	13	125	1587	0 99	<10	0 04	138	10	< 01	147	1100	120	10	<20	10	< 01	<10	30	<10	20	1851
113	R95-7 13 7-14 5m	5	3 4	0 32	60	790	<5	0 55	3	29	63	970	1 76	20	< 01	208	14	< 01	174	2540	152	<5	<20	7	< 01	<10	22	<10	27	3354
114	R95-7 14 5-15 6m	5	5 0	3 83	105	1245	<5	0 45	10	49	45	3960	2 35	10	0 01	355	12	< 01	601	2570	356	<5	<20	6	< 01	<10	33	<10	63	>10000
115	R95-7 15 6-16 7m	5	0 8	0 22	55	80	<5	< 01	<1	1	108	120	0 82	<10	< 01	22	6	< 01	34	150	358	5	<20	8	< 01	<10	12	<10	1	263
116	R95-7 16 7-17 7m	5	0 4	0 11	25	30	<5	5 46	<1	<1	87	51	0 33	<10	2 92	42	2	< 01	12	130	250	35	<20	16	< 01	<10	8	<10	2	129
117	R95-7 17 7-19 1m	5	0 8	2 97	170	540	<5	0 12	2	12	25	1236	7 73	<10	< 01	13	50	< 01	311	800	3668	<5	<20	3	< 01	<10	85	<10	22	2398
118	R95-7 19 1-20 3m	5	5 4	1 40	195	340	<5	0 08	2	8	105	1435	5 76	<10	< 01	21	36	< 01	210	830	1060	20	<20	19	< 01	<10	42	<10	13	1779
119	R95-7 20 3-21 7m	5	3 0	0 75	275	260	<5	0 03	<1	2	98	847	2 63	<10	< 01	20	15	< 01	70	420	234	45	<20	27	< 01	<10	28	<10	2	695
120	R95-7 21 7-22 5m	5	11 6	2 20	720	380	<5	0 12	<1	6	93	4072	3 81	<10	< 01	33	14	< 01	143	1460	104	125	<20	128	< 01	<10	46	<10	22	1720
121	R95-7 22 5-23 5m	5	>30	2 43	1965	205	<5	0 18	<1	30	75	>10000	3 75	<10	0 01	219	11	< 01	378	>10000	128	1845	<20	75	< 01	<10	51	<10	65	5774
122	R95-7 23 5-24 5m	5	8 6	3 95	1025	235	<5	0 06	8	20	55	>10000	7 56	<10	< 01	77	17	< 01	549	>10000	102	360	<20	1	< 01	<10	32	<10	53	5102
123	R95-7 24 5-25 5m	5	>30	2 55	4945	150	<5	0 16	52	24	53	>10000	> 15	<10	< 01	34	29	< 01	554	100	594	6850	<20	3	< 01	<10	62	<10	38	7868
124	R95-7 25 5-26 6m	5	>30	2 62	1245	125	<5	2 84	<1	14	86	>10000	4 28	<10	1 54	71	10	< 01	459	170	150	2180	<20	9	< 01	<10	41	<10	24	4115
125	R95-7 26 6-27 6m	5	14 2	0 51	320	20	<5	1 40	5	10	117	3149	2 90	<10	0 72	63	7	< 01	162	140	134	480	<20	3	< 01	<10	10	<10	20	1333
126	R95-7 27 6-28 6m	5	11 2	0 06	150	10	<5	11 90	29	22	49	936	0 67	20	6 74	186	1	< 01	47	300	38	440	<20	31	< 01	<10	6	<10	6	2425
127	R95-7 28 6-29 6m	5	>30	1 20	3405	80	<5	2 67	11	41	85	>10000	2 66	10	1 41	280	10	< 01	284	420	6442	7250	<20	29	< 01	<10	43	<10	8	>10000
128	R95-7 29 6-30 6m	5	>30	1 03	6675	105	<5	0 17	<1	3	78	>10000	2 94	<10	0 01	12	5	< 01	64	480	6186	>10000	<20	30	< 01	<10	42	<10	3	2512
129	R95-7 30 6-31 4m	20	>30	1 69	>10000	165	<5	0 22	18	4	46	>10000	3 99	20	< 01	6	7	< 01	82	>10000	>10000	>10000	<20	36	< 01	<10	41	<10	17	3980

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
130	R95 - 7 31 4 - 32 4m	5	>30	1 58	4320	70	<5	0 16	<1	9	72	>10000	2 60	<10	0 04	57	2	< 01	136	>10000	512	5535	<20	3	< 01	<10	28	<10	14	7695
131	R95 - 7 32 4 - 33 8m	5	>30	4 83	6845	245	<5	0 17	<1	12	30	>10000	10 70	<10	< 01	14	10	< 01	279	<10	956	9750	<20	2	0 01	<10	67	<10	25	5957
132	R95 - 7 33 8 - 34 8m	5	>30	4 16	6225	295	<5	0 21	<1	8	58	9833	7 23	<10	< 01	13	8	< 01	298	570	1898	8950	<20	6	< 01	<10	127	<10	21	3584
133	R95 - 7 34 8 - 35 8m	25	>30	3 07	8990	175	<5	1 63	91	16	44	>10000	9 32	<10	0 73	116	11	< 01	521	>10000	>10000	>10000	<20	9	< 01	<10	71	<10	149	8287
134	R95 - 7 35 8 - 36 8m	50	>30	4 86	>10000	155	<5	0 47	125	12	50	>10000	8 69	<10	< 01	25	15	< 01	654	710	>10000	>10000	<20	19	< 01	<10	163	<10	49	>10000
135	R95 - 7 36 8 - 37 8m	5	>30	4 17	4690	150	<5	4 59	<1	14	33	>10000	6 07	<10	2 52	71	6	< 01	535	220	4760	8505	<20	10	< 01	<10	43	<10	34	5772
136	R95 - 7 37 8 - 38 8m	10	>30	0 97	>10000	125	<5	6 02	44	31	43	>10000	2 70	<10	3 21	273	<1	< 01	189	>10000	3986	>10000	<20	20	< 01	<10	8	<10	37	>10000
137	R95 - 7 38 8 - 40 5m	5	>30	0 23	1725	25	<5	12 20	11	14	61	9002	1 51	<10	7 00	198	<1	< 01	72	230	870	2630	<20	31	< 01	<10	6	<10	6	7684
138	R95 - 7 40 5 - 41 1m	5	>30	10 40	2845	215	<5	2 43	<1	52	19	9609	9 10	<10	1 20	206	8	< 01	1049	800	290	1020	<20	5	< 01	<10	55	<10	96	8795
139	R95 - 7 41 1 - 42 0m	30	>30	0 61	8245	105	<5	7 45	39	20	44	>10000	1 54	10	4 12	186	<1	< 01	71	>10000	>10000	>10000	<20	19	< 01	<10	12	<10	14	>10000
140	R95 - 7 42 0 - 42 8m	5	>30	3 83	3205	185	<5	7 62	44	23	51	>10000	2.11	<10	4 31	179	<1	< 01	403	<10	802	4530	<20	17	0 01	<10	42	<10	70	>10000
141	R95 - 7 42 8 - 43 9m	5	>30	4 14	5960	245	<5	3 43	103	37	36	>10000	2 15	10	1 79	305	<1	< 01	431	>10000	4854	8825	<20	7	< 01	<10	43	<10	22	>10000

TOKLAT RESOURCES INC AK 95-434

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
Resplit.																														
1	R95 - 4 0 - 5'	5	>30	1 11	635	1055	<5	0 60	130	22	97	3352	2 18	<10	0 29	250	<1	< 01	336	680	2758	860	<20	15	< 01	<10	51	>10000	<1	>10000
36	R95 - 5 9 3 - 11 1m	5	0 6	5 70	330	380	<5	0 26	<1	16	45	653	6 81	<10	0 21	32	28	< 01	416	1320	388	10	<20	7	< 01	<10	296	<10	21	1295
71	R95 - 5 75 0 - 77 7m	5	0 6	0 08	20	30	<5	> 15	1	<1	19	12	0 29	<10	13 30	135	<1	0 01	14	150	28	70	<20	58	< 01	<10	13	<10	3	124
106	R95 - 7 6 9 - 8 1m	5	0 2	10 02	100	360	<5	0 16	15	31	30	570	4 03	<10	0 03	122	27	< 01	1019	730	72	5	<20	<1	< 01	<10	239	<10	28	2506
141	R95 - 7 42 8 - 43 9m	5	>30	4 44	5950	250	<5	3 28	88	38	38	>10000	2.17	10	1 71	290	<1	< 01	439	>10000	3966	7950	<20	6	< 01	<10	45	<10	26	>10000
Repeat.																														
1	R95 - 4 0 - 5'	5	>30	1 11	630	1110	<5	0 60	142	22	107	3506	2 18	<10	0 29	220	<1	< 01	343	650	2672	835	<20	14	< 01	<10	50	>10000	<1	>10000
10	R95 - 4 11 0 - 11 6m	5	>30	5 51	270	310	<5	9 29	164	16	28	8681	2 15	<10	5 34	123	<1	< 01	1021	300	40	55	<20	15	< 01	<10	74	>10000	<1	>10000
19	R95 - 4 20 1 - 20 9m	5	4 2	0 09	15	25	<5	> 15	567	37	2	1123	1 74	<10	13 10	340	<1	0 01	205	110	60	50	<20	60	< 01	<10	9	<10	5	>10000
36	R95 - 5 9 3 - 11 1m	5	1 0	5 77	330	385	<5	0 17	<1	16	43	657	6 42	<10	0 04	33	28	< 01	420	1340	394	15	<20	8	< 01	<10	297	<10	19	1227
45	R95 - 5 20 1 - 21 3m	5	< 2	6 95	75	290	<5	7 49	21	37	24	992	2 31	<10	4 12	200	12	< 01	700	690	48	45	<20	23	< 01	<10	172	<10	83	1024
54	R95 - 5 41 4 - 42 9m	5	1 4	0 08	80	35	<5	> 15	13	27	1	40	0 87	<10	14 50	374	<1	0 01	74	290	30	105	<20	75	< 01	<10	8	<10	6	755
71	R95 - 5 75 0 - 77 7m	5	0 6	0 05	25	20	<5	> 15	1	<1	21	11	0 27	<10	13 50	138	<1	0 01	12	150	30	70	<20	59	< 01	<10	11	<10	3	123
80	R95 - 6 8 5 - 9 1m	5	< 2	5 61	40	405	<5	0 68	21	49	33	600	10 30	<10	0 06	154	63	< 01	1032	2500	44	<5	<20	8	< 01	<10	170	<10	78	3957
89	R95 - 6 18 7 - 20 3m	5	< 2	1 47	130	150	<5	0 72	18	60	54	223	14 20	<10	0 02	190	63	< 01	963	2840	32	<5	<20	10	< 01	<10	111	<10	93	3757
106	R95 - 7 6 9 - 8 1m	5	< 2	9 32	90	385	<5	0 13	15	35	33	512	4 07	<10	0 04	150	28	< 01	1059	790	82	<5	<20	<1	< 01	<10	238	<10	29	2539
115	R95 - 7 15 6 - 16 7m	5	0 1	0 14	70	75	<5	< 01	<1	<1	105	183	0 80	<10	< 01	24	6	< 01	24	150	366	10	<20	9	< 01	<10	9	<10	1	237
124	R95 - 7 25 5 - 26 6m	5	>30	2 55	1210	120	<5	2 81	<1	13	82	>10000	4 20	<10	1 51	69	9	< 01	455	190	144	2150	<20	9	< 01	<10	41	<10	23	4076
141	R95 - 7 42 8 - 43 9m	-	>30	4 27	6215	250	<5	3 53	103	38	38	>10000	2 18	10	1 85	308	<1	< 01	441	>10000	4850	9000	<20	8	< 01	<10	44	<10	24	>10000
Standard																														
GEO95		150	1 4	1 65	70	155	<5	1 51	<1	17	54	83	3 72	<10	0 86	626	<1	0 02	27	610	24	5	<20	52	0 09	<10	71	<10	4	76
GEO95		150	1 4	1 64	75	150	<5	1 58	<1	17	54	85	3 82	<10	0 91	630	<1	0 01	26	620	22	<5	<20	50	0 09	<10	74	<10	4	72
GEO95		150	1 2	1 60	60	150	<5	1 63	<1	17	55	83	3 71	<10	0 92	629	<1	0 02	28	620	20	<5	<20	53	0 09	<10	70	<10	4	79
GEO95		150	1 4	1 62	65	145	<5	1 54	<1	17	54	86	3 70	<10	0 88	631	<1	0 01	28	610	22	5	<20	52	0 09	<10	69	<10	4	76
GEO95		150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

n/s = No Sample

df/434
XLS/95Toklat

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B C Certified Assayer

24-Jul-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-435
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

89 Core samples received July 11, 1995
PROJECT # Rusty Springs
SHIPMENT #. RS02

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	R95 - 8 0 - 5'	5	28 8	2.37	355	460	<5	0 28	<1	83	59	1827	12 80	<10	0 07	2062	17	< 01	497	90	9096	15	<20	2	< 01	<10	244	<10	18	1649
2	R95 - 8 5 - 10'	5	>30	1 08	65	230	<5	0 07	8	84	13	1344	> 15	<10	< 01	1408	27	< 01	563	<10	>10000	<5	<20	1	< 01	<10	144	<10	46	2071
3	R95 - 8 3 0 - 3 4m	10	12 6	0 85	140	540	<5	0 06	6	91	24	1440	> 15	<10	< 01	1550	26	< 01	585	<10	2628	<5	<20	2	< 01	<10	110	<10	63	2173
4	R95 - 8 3 4 - 3 7m	10	5 8	0 09	<5	345	<5	0 04	7	83	5	465	> 15	<10	< 01	1341	28	< 01	677	<10	644	<5	<20	1	< 01	<10	39	<10	43	2198
5	R95 - 8 3 7 - 5 0m	10	8 8	0 14	290	525	<5	0 04	5	105	4	2550	> 15	<10	< 01	2329	33	< 01	660	<10	3192	<5	<20	3	< 01	<10	36	<10	41	2123
6	R95 - 8 5 0 - 6 2m	5	3 8	0 10	150	795	<5	0 04	7	111	7	3209	> 15	<10	< 01	2826	32	< 01	688	<10	3870	<5	<20	<1	< 01	<10	15	<10	42	1784
7	R95 - 8 6 2 - 7 5m	5	10 4	0 18	1640	600	<5	0 04	<1	86	41	4786	> 15	<10	< 01	2195	39	< 01	443	220	5998	160	<20	<1	< 01	<10	20	<10	16	1182
8	R95 - 8 7 5 - 8 7m	5	15 0	0 08	2125	685	<5	0 04	<1	79	63	5085	> 15	<10	< 01	2237	38	< 01	388	190	5806	385	<20	1	< 01	<10	18	<10	5	1151
9	R95 - 8 8 7 - 9 9m	5	5 6	0 10	865	385	<5	0 06	<1	106	81	2954	6 13	<10	< 01	8098	17	< 01	206	320	9902	245	<20	<1	0 01	<10	21	<10	17	524
10	R95 - 8 9 9 - 10 7m	5	2 4	< 01	125	45	<5	< 01	<1	6	112	226	1 28	<10	< 01	90	4	< 01	18	10	368	<5	<20	<1	< 01	<10	1	<10	<1	48
11	R95 - 8 10 7 - 11 9m	10	9 4	0 04	3290	250	<5	0,05	<1	77	64	6366	> 15	<10	< 01	2225	42	< 01	416	340	8294	570	<20	1	< 01	<10	16	<10	9	1212
12	R95 - 8 11 9 - 13 1m	5	8 6	0 01	2470	90	<5	0 04	<1	55	64	4430	13 10	<10	< 01	624	27	< 01	314	310	5140	500	<20	<1	< 01	<10	11	<10	4	953
13	R95 - 8 13 1 - 14 3m	5	5 8	0 05	2975	435	<5	0 07	<1	92	71	5269	14 80	<10	< 01	2394	29	< 01	487	470	8332	595	<20	<1	< 01	<10	28	<10	14	1425
14	R95 - 8 14 3 - 15 8m	5	6 4	0 05	1540	760	<5	0 06	<1	54	62	3134	8 51	<10	< 01	2313	16	< 01	220	210	5450	270	<20	<1	< 01	<10	12	<10	8	618
15	R95 - 8 15 8 - 17 3m	10	12 6	0 10	805	465	<5	0 07	<1	80	85	2330	4 67	<10	< 01	2789	11	< 01	167	270	4666	215	<20	<1	< 01	<10	18	<10	14	470
16	R95 - 8 17 3 - 19 0m	10	>30	0 17	>10000	375	<5	0 33	<1	26	47	>10000	8 10	10	< 01	475	20	< 01	165	1350	>10000	7490	<20	20	< 01	<10	29	<10	17	591
17	R95 - 8 19 0 - 20 5m	15	1 6	0 02	75	25	<5	> 15	<1	<1	2	45	0 14	<10	> 15	257	<1	0 02	<1	60	292	100	<20	95	< 01	<10	10	<10	<1	9
18	R95 - 9 0 - 5'	5	17 8	5 96	630	605	<5	0 40	<1	37	45	1477	3 77	<10	0 16	578	7	< 01	331	290	3870	120	<20	3	< 01	<10	537	<10	12	478
19	R95 - 9 5' - 10'	5	26 4	4 89	690	625	<5	0 45	<1	26	84	1524	5 07	<10	0 18	339	13	< 01	290	320	5162	105	<20	3	< 01	<10	489	<10	13	492
20	R95 - 9 10' - 15'	5	15 8	1 49	1360	900	<5	0 30	<1	102	18	4379	> 15	<10	0 04	1727	35	< 01	703	290	6122	75	<20	7	< 01	<10	149	<10	34	2141
21	R95 - 9 4 6 - 5 8m	5	8 0	0 11	105	345	<5	0 05	7	85	20	1076	> 15	<10	< 01	1341	31	< 01	606	<10	1496	<5	<20	1	< 01	<10	22	<10	28	1665
22	R95 - 9 5 8 - 7 1m	5	5 0	0 06	95	1060	<5	0 06	9	249	2	2356	> 15	<10	< 01	4799	34	< 01	696	<10	4584	<5	<20	6	< 01	<10	15	<10	58	1841
23	R95 - 9 7 1 - 8 2m	5	7 0	0 03	855	1440	<5	0 05	<1	91	15	3410	> 15	<10	< 01	1930	36	< 01	744	<10	5098	150	<20	5	< 01	<10	14	<10	23	1509
24	R95 - 9 8 2 - 9 8m	5	8 8	0 05	1085	1360	<5	0 05	<1	93	23	4152	> 15	<10	< 01	2017	44	< 01	673	<10	6280	240	<20	6	< 01	<10	18	<10	23	1624
25	R95 - 9 9 8 - 11 0m	5	7 6	0 06	1495	465	<5	0 04	<1	81	30	4708	> 15	<10	< 01	1202	41	< 01	587	<10	6516	170	<20	<1	< 01	<10	15	<10	26	1556

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
26	R95 - 9 11 0 - 11 7m	5	8 2	0 03	1065	790	<5	0 05	<1	135	53	2617	> 15	<10	< 01	3516	36	< 01	473	60	5932	415	<20	1	< 01	<10	16	<10	20	936
27	R95 - 9 11 7 - 13 1m	10	9 8	0 07	1210	220	<5	0 06	<1	53	54	3819	> 15	<10	< 01	491	43	< 01	528	10	5128	475	<20	<1	< 01	<10	24	<10	10	1121
28	R95 - 9 13 1 - 14 4m	10	11 2	0 06	795	215	<5	0 07	<1	58	24	2895	> 15	<10	< 01	646	29	< 01	405	60	4264	255	<20	<1	< 01	<10	21	<10	17	867
29	R95 - 9 14 4 - 15 2m	5	12 4	0 25	1290	595	<5	0 05	<1	39	39	2377	> 15	<10	< 01	209	34	< 01	273	400	4082	275	<20	1	< 01	<10	20	<10	<1	645
30	R95 - 9 15 2 - 15 4m	5	4 8	0 15	65	385	<5	0 02	<1	9	25	198	5 93	<10	< 01	12	8	< 01	52	170	324	<5	<20	<1	< 01	<10	4	<10	<1	142
31	R95 - 9 15 4 - 16 9m	5	>30	0 11	>10000	795	<5	0 11	<1	14	53	>10000	4 87	<10	< 01	97	25	< 01	59	610	>10000	4175	<20	8	< 01	<10	18	<10	11	151
32	R95 - 9 16 9 - 18 7m	10	>30	0 08	4680	355	<5	2 19	<1	12	72	2147	4 52	<10	0 51	387	7	< 01	75	500	>10000	1600	<20	12	< 01	<10	9	<10	6	289
33	R95 - 9 18 7 - 20 2m	5	2 2	0 02	55	40	<5	> 15	<1	1	5	27	0 36	<10	14 90	474	<1	0 01	4	50	220	75	<20	76	< 01	<10	7	<10	<1	19
34	R95 - 9 20 2 - 21 7m	5	2 8	0 13	140	195	<5	> 15	<1	11	19	70	2 00	<10	10 70	400	<1	0 01	82	1400	254	60	<20	77	< 01	<10	10	<10	6	77
35	R95 - 9 21 7 - 23 2m	5	0 8	0 02	15	20	<5	> 15	<1	1	1	<1	0 19	<10	14 70	271	<1	0 01	4	70	14	60	<20	104	< 01	<10	4	<10	<1	6
OR3 36	R95 - 10 0 - 5'	5	14 8	1 06	280	655	<5	0 24	<1	19	69	716	4 06	<10	0 09	337	6	< 01	146	150	1536	20	<20	5	< 01	<10	79	<10	11	358
↓ 37	R95 - 10 5' - 10'	5	19 0	2 02	270	505	<5	0 11	<1	12	69	721	1 85	<10	0 04	171	3	< 01	159	150	1636	45	<20	10	< 01	<10	154	<10	6	219
38	R95 - 10 3 0 - 3 9m	5	10 4	0 10	70	390	<5	0 10	<1	26	111	391	9 07	<10	< 01	487	11	< 01	154	20	548	<5	<20	3	< 01	<10	18	<10	17	641
39	R95 - 10 3 9 - 5 4m	10	6 0	0 06	<5	285	<5	0 07	8	66	35	460	> 15	<10	< 01	982	22	< 01	456	<10	630	<5	<20	<1	< 01	<10	15	<10	30	1558
40	R95 - 10 5 4 - 6 9m	5	5 6	0 04	<5	355	<5	0 06	10	100	20	489	> 15	<10	< 01	1544	29	< 01	677	<10	944	<5	<20	<1	< 01	<10	16	<10	38	1789
41	R95 - 10 6 9 - 8 5m	5	8 0	0 04	680	200	<5	0 07	<1	103	47	1741	> 15	<10	< 01	1831	26	< 01	489	<10	3148	175	<20	<1	< 01	<10	13	<10	20	1414
42	R95 - 10 8 5 - 10 0m	10	4 4	0 02	385	280	<5	0 05	4	75	13	1578	> 15	<10	< 01	1044	32	< 01	618	<10	2758	50	<20	<1	< 01	<10	11	<10	28	1460
43	R95 - 10 10 0 - 11 6m	5	9 2	0 04	1715	300	<5	0 05	<1	50	37	3190	> 15	<10	< 01	355	42	< 01	498	50	5044	380	<20	<1	< 01	<10	11	<10	8	1031
44	R95 - 10 11 6 - 13 1m	5	14 4	0 02	1795	115	<5	0 06	<1	61	48	3734	> 15	<10	< 01	230	47	< 01	696	150	5538	685	<20	<1	< 01	<10	9	<10	3	1270
45	R95 - 10 13 1 - 14 6m	5	6 4	0 03	670	225	<5	0 06	<1	65	40	1736	14 60	<10	< 01	459	23	< 01	402	<10	2856	270	<20	<1	< 01	<10	10	<10	12	985
46	R95 - 10 14 6 - 16 1m	5	16 2	0 03	145	475	<5	0 09	<1	13	133	429	5 48	<10	< 01	203	9	< 01	133	20	784	15	<20	<1	< 01	<10	6	<10	7	276
47	R95 - 10 16 1 - 17 7m	5	10 2	0 29	640	740	<5	0 06	<1	58	29	2791	> 15	<10	< 01	318	33	< 01	676	20	4146	180	<20	23	< 01	<10	46	<10	19	1155
48	R95 - 10 17 7 - 20 7m	10	5 8	0 03	150	175	<5	0 03	<1	12	123	131	2 04	<10	< 01	46	4	< 01	40	110	328	15	<20	<1	< 01	<10	5	<10	<1	54
49	R95 - 10 20 7 - 23 8m	5	>30	0 07	795	220	<5	0 07	<1	32	92	1629	6 00	<10	< 01	438	14	< 01	168	210	2930	290	<20	2	< 01	<10	8	<10	4	489
50	R95 - 10 23 8 - 26 8m	5	>30	0 03	1915	300	<5	9 80	<1	<1	88	511	0 66	10	5 39	125	2	0 01	11	200	>10000	900	<20	30	< 01	<10	4	<10	2	29
OR4 51	R95 - 11 0 - 5'	10	>30	4 49	2785	805	<5	0 93	<1	43	35	2549	13 30	<10	0 44	659	20	< 01	390	640	>10000	635	<20	39	< 01	<10	366	<10	40	1460
↓ 52	R95 - 11 1 5 - 1 6m	5	21 2	0 78	350	480	<5	0 64	2	67	19	2387	> 15	<10	0 24	822	26	< 01	494	<10	4536	165	<20	4	< 01	<10	95	<10	46	2393
53	R95 - 11 1 6 - 2 9m	5	2 2	5 07	445	525	<5	0 06	<1	62	21	3965	> 15	<10	< 01	607	26	< 01	625	440	2800	175	<20	<1	< 01	<10	347	<10	62	2617
54	R95 - 11 2 9 - 3 9m	5	1 2	1 88	595	840	<5	0 04	<1	62	16	3091	> 15	<10	< 01	452	27	< 01	721	290	3146	295	<20	2	< 01	<10	186	<10	41	2297
55	R95 - 11 3 9 - 5 0m	5	2 0	1 53	545	625	<5	0 05	<1	35	38	1793	11 10	<10	< 01	179	18	< 01	471	390	1828	225	<20	<1	< 01	<10	159	<10	28	1362
56	R95 - 11 5 0 - 6 5m	10	5 6	0 30	430	440	<5	0 06	<1	15	64	951	4 04	<10	< 01	75	10	< 01	214	370	1138	165	<20	<1	< 01	<10	44	<10	10	519
57	R95 - 11 6 5 - 7 4m	5	2 4	0 78	385	505	<5	0 05	<1	13	23	672	3 24	<10	< 01	41	7	< 01	236	690	1400	125	<20	<1	< 01	<10	74	<10	17	590
58	R95 - 11 7 4 - 8 5m	5	2 8	1 96	1055	765	<5	0 03	<1	61	35	3260	> 15	<10	< 01	453	23	< 01	500	60	3794	125	<20	<1	< 01	<10	394	<10	40	1607
59	R95 - 11 8 5 - 9 8m	10	3 2	0 73	1170	695	<5	1 61	<1	35	22	3906	12 10	<10	< 01	89	24	< 01	407	8540	4294	300	<20	20	< 01	<10	80	<10	29	1156
60	R95 - 11 9 8 - 11 6m	5	6 2	0 46	555	375	<5	0 04	<1	15	134	1457	4 21	<10	< 01	55	10	< 01	183	450	1644	155	<20	2	< 01	<10	54	<10	8	374

TOKLAT RESOURCES INC AK 95-435

ECO-TECH LABORATORIES LTD

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
61	R95 - 11 11 6 - 12 7m	5	6 6	0 11	260	65	<5	0 02	<1	8	114	317	2 31	<10	< 01	81	7	< 01	68	100	802	55	<20	<1	< 01	<10	25	<10	3	183
62	R95 - 11 12 7 - 13 4m	5	11 4	1 30	1010	675	<5	0 20	<1	29	80	2073	9 54	<10	< 01	270	18	< 01	323	850	6188	295	<20	6	< 01	<10	133	<10	22	1096
63	R95 - 11 13 4 - 14 6m	15	8 8	1 69	1455	240	<5	0 06	<1	71	24	3558	> 15	<10	< 01	487	27	< 01	878	290	6276	500	<20	<1	< 01	<10	103	<10	49	1914
64	R95 - 11 14 6 - 15 8m	5	26 4	0 59	1155	300	<5	0 32	<1	45	63	2703	> 15	<10	0 06	347	22	< 01	504	720	8492	365	<20	<1	< 01	<10	35	<10	43	1367
65	R95 - 11 15 8 - 16 1m	5	21 2	0 67	1500	270	<5	3 09	<1	70	22	>10000	> 15	<10	1 50	643	23	< 01	713	1960	>10000	700	<20	11	< 01	<10	74	<10	61	1698
66	R95 - 11 16 1 - 17 1m	5	2 6	0 03	35	35	<5	> 15	3	7	11	78	0 56	<10	13 70	648	<1	0 01	31	100	100	65	<20	88	< 01	<10	10	<10	<1	158
67	R95 - 11 17 1 - 18 5m	10	0 8	0 03	30	30	<5	> 15	<1	2	3	64	0 42	<10	13 80	712	<1	0 02	17	60	82	70	<20	125	< 01	<10	9	<10	<1	60
68	R95 - 11 18 5 - 19 5m	5	0 8	0 02	10	35	<5	> 15	<1	1	4	7	0 35	<10	13 90	746	<1	0 02	3	80	14	60	<20	143	< 01	<10	9	<10	<1	22
ORS 69	R95 - 12 0 - 5'	5	>30	2 88	1645	680	<5	0 61	<1	76	29	4979	> 15	<10	0 19	1013	29	< 01	599	390	>10000	275	<20	11	< 01	<10	301	<10	53	2999
↓ 70	R95 - 12 5 - 7'	5	7 4	2 03	780	685	<5	0 41	<1	87	14	3933	> 15	<10	0 08	1057	31	< 01	708	220	6212	250	<20	6	< 01	<10	187	<10	47	2421
71	R95 - 12 2 1 - 3 0m	5	3 0	1 10	485	830	<5	0 14	<1	91	27	3176	> 15	<10	< 01	1045	32	< 01	650	<10	3096	200	<20	3	< 01	<10	95	<10	39	2473
72	R95 - 12 3 0 - 4 6m	5	2 8	1 65	335	385	<5	0 07	<1	43	26	1738	> 15	<10	< 01	276	22	< 01	505	170	2012	50	<20	<1	< 01	<10	74	<10	36	1706
73	R95 - 12 4 6 - 6 1m	5	2 4	0 55	290	435	<5	0 11	<1	40	39	883	> 15	<10	< 01	266	23	< 01	425	590	1374	40	<20	2	< 01	<10	43	<10	38	1727
74	R95 - 12 6 1 - 7 6m	5	3 0	0 42	620	250	<5	0 16	<1	65	50	796	11 70	<10	< 01	305	26	< 01	415	890	1870	130	<20	<1	< 01	<10	55	<10	21	1275
75	R95 - 12 7 6 - 9 1m	5	2 8	0 17	275	485	<5	0 11	<1	24	60	472	8 61	<10	< 01	126	18	< 01	229	620	946	40	<20	<1	< 01	<10	27	<10	24	976
76	R95 - 12 9 1 - 10 6m	5	3 4	0 77	675	1030	<5	1 34	<1	40	52	1116	14 20	<10	0 65	306	24	< 01	406	170	1872	95	<20	6	< 01	<10	72	<10	18	1271
77	R95 - 12 10 6 - 12 1m	5	3 2	0 95	455	700	<5	0 06	<1	29	49	648	10 60	<10	< 01	122	21	< 01	345	80	1438	50	<20	20	< 01	<10	89	<10	21	1304
78	R95 - 12 12 1 - 13 1m	5	2 0	0 17	510	160	<5	0 09	<1	46	54	784	> 15	<10	< 01	215	28	< 01	423	80	2018	85	<20	2	< 01	<10	35	<10	40	1819
79	R95 - 12 13 1 - 14 0m	5	3 0	0 07	60	65	<5	0 03	<1	3	167	82	1 13	<10	< 01	31	8	< 01	37	70	290	<5	<20	<1	< 01	<10	6	<10	3	107
80	R95 - 12 14 0 - 14 9m	5	3 4	0 23	945	275	<5	0 03	<1	38	55	1172	> 15	<10	< 01	185	25	< 01	343	90	3288	100	<20	<1	< 01	<10	28	<10	35	1391
81	R95 - 12 14 9 - 16 4m	5	>30	0 05	3525	70	<5	0 01	<1	4	174	2497	1 27	<10	< 01	30	8	< 01	38	70	6276	1690	<20	<1	< 01	<10	3	<10	2	196
82	R95 - 12 16 4 - 18 0m	5	6 8	0 07	325	40	<5	0 02	<1	12	162	609	2 91	<10	< 01	71	7	< 01	98	20	928	65	<20	<1	< 01	<10	6	<10	11	246
83	R95 - 12 18 0 - 21 0m	5	12 8	0 33	990	410	<5	0 10	<1	64	34	2488	> 15	<10	< 01	431	37	< 01	603	200	5450	465	<20	14	< 01	<10	41	<10	53	1658
84	R95 - 12 21 0 - 22 1m	5	16 6	2 28	1010	375	<5	1 67	<1	164	20	1931	> 15	<10	0 81	432	47	< 01	1731	1110	4802	250	<20	6	< 01	<10	173	<10	73	4386
85	R95 - 12 22 1 - 23 6m	5	15 6	0 52	435	155	<5	> 15	<1	30	17	758	5 75	<10	11 20	344	10	0 01	346	190	3322	260	<20	48	< 01	<10	35	<10	13	784
86	R95 - 12 23 6 - 25 0m	5	0 4	0 05	30	45	<5	> 15	<1	2	2	10	0 47	<10	> 15	236	<1	0 02	28	90	70	60	<20	78	< 01	<10	6	<10	<1	76
87	R95 - 12 25 0 - 25 9m	5	0 6	0 04	25	50	<5	> 15	<1	1	2	<1	0 48	<10	14 70	296	<1	0 02	22	120	38	60	<20	68	< 01	<10	4	<10	<1	77
88	R95 - 12 25 9 - 27 1m	5	0 2	0 02	15	85	<5	> 15	<1	<1	<1	<1	0 32	<10	14 70	322	<1	0 02	21	60	16	60	<20	83	< 01	<10	4	<10	<1	82
89	R95 - 12 27 1 - 28 0m	5	0 2	0 04	30	50	<5	> 15	<1	1	4	33	0 60	<10	12 40	252	<1	0 01	22	210	60	55	<20	67	< 01	<10	6	<10	<1	63

TOKLAT RESOURCES INC AK 95-435

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																														
Resplit:																														
1	R95 - 8 0 - 5'	5	>30	2 31	375	425	<5	0 32	2	82	46	1760	11 80	<10	0 10	2109	16	< 01	471	100	9696	20	<20	3	< 01	<10	237	<10	17	1815
36	R95 - 10 0 - 5'	5	14 2	1 00	295	655	<5	0 22	<1	19	80	728	3 97	<10	0 08	318	7	< 01	151	140	1530	20	<20	3	< 01	<10	79	<10	11	362
71	R95 - 12 2 1 - 3 0m	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Repeat:																														
1	R95 - 8 0 - 5'	5	29 0	2.28	350	440	<5	0 28	<1	83	56	1767	12 90	<10	0 07	2053	17	< 01	478	80	9048	10	<20	3	< 01	<10	242	<10	19	1653
10	R95 - 8 9 9 - 10 7m	5	2 6	0 04	130	45	0 02	0 02	<1	6	108	224	1 24	<10	0 01	85	3	< 01	19	<10	368	5	<20	<1	< 01	<10	2	<10	<1	47
19	R95 - 9 5' - 10'	5	27 4	4 96	675	620	<5	0 44	<1	26	83	1568	5 13	<10	0 17	345	12	< 01	293	290	5130	105	<20	4	< 01	<10	498	<10	13	494
36	R95 - 10 0 - 5'	5	13 4	1 00	295	660	<5	0 20	<1	19	67	721	4 03	<10	0 07	336	6	< 01	149	150	1548	25	<20	5	< 01	<10	77	<10	11	367
45	R95 - 10 13 1 - 14 6m	5	6 0	0 06	640	220	<5	0 06	<1	64	38	1715	14 40	<10	< 01	450	23	< 01	400	<10	2824	270	<20	<1	< 01	<10	14	<10	12	978
54	R95 - 11 2 9 - 3 9m	5	1 2	1 92	605	835	<5	0 04	<1	63	16	3167	> 15	<10	< 01	459	27	< 01	736	310	3224	290	<20	1	< 01	<10	191	<10	41	2350
71	R95 - 12 2 1 - 3 0m	5	2 8	1 07	505	870	<5	0 10	<1	93	26	3214	> 15	<10	< 01	1050	34	< 01	664	<10	3136	205	<20	2	< 01	<10	95	<10	40	2531
80	R95 - 12 14 0 - 14 9m	5	3 2	0 22	910	265	<5	0 06	<1	37	54	1129	> 15	<10	< 01	170	25	< 01	329	100	3206	105	<20	<1	< 01	<10	26	<10	35	1342
89	R95 - 12 27 1 - 28 0m	-	< 2	0 03	20	40	<5	> 15	<1	1	3	23	0 49	<10	10 34	214	<1	0 01	18	180	48	50	<20	57	< 01	<10	4	<10	<1	52
Standard:																														
GEO95		150	1 4	1 60	65	150	<5	1 64	<1	17	56	86	3 75	<10	0 87	649	<1	0 02	27	650	16	<5	<20	53	0 10	<10	75	<10	6	73
GEO95		145	1 4	1 68	70	160	<5	1 60	<1	17	58	86	3 75	<10	0 87	641	<1	0 02	28	670	18	<5	<20	54	0 10	<10	74	<10	6	81
GEO95		150	1 4	1 69	65	150	<5	1 63	<1	17	58	81	3 71	<10	0 85	633	<1	0 02	25	640	20	<5	<20	53	0 10	<10	74	<10	5	72

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A Sc T
B C Certified Assayer

df/447
XLS/95Toklat

3-Oct-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC AK 95-840
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION. TIM TERMUENDE

154 Rock samples received Sept 16, 1995
PROJECT #: None given
SHIPMENT #: None given

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	RS 95-M8- 0'-5'	< 2	1 31	80	250	<5	> 15	10	21	26	251	5 36	<10	9 25	239	20	< 01	303	650	228	45	<20	56	< 01	<10	94	<10	28	1707
2	RS 95-M8- 5'-10'	0 2	1 28	40	125	<5	> 15	11	12	28	441	2 35	<10	9 50	209	8	< 01	220	610	136	50	<20	57	< 01	<10	70	<10	24	1083
3	RS 95-M8- 10'-15'	0 2	1 18	25	140	<5	> 15	9	85	15	5751	1 35	<10	10 30	149	4	< 01	1353	360	58	55	<20	53	< 01	<10	49	<10	14	1549
4	RS 95-M8- 15'-20'	< 2	3 97	125	705	<5	1 73	18	20	105	432	6 92	<10	0 89	84	37	< 01	708	410	124	<5	<20	5	< 01	<10	194	<10	23	1816
5	RS 95-M8- 20'-25'	< 2	1 48	80	600	<5	0 15	3	25	70	210	4 34	<10	0 03	98	16	< 01	325	230	64	<5	<20	<1	< 01	<10	42	<10	29	1199
6	RS 95-M8- 7 9-8 5m	0 4	1 10	45	295	<5	1 08	1	5	164	110	2 23	<10	0 55	38	14	< 01	168	300	20	<5	<20	13	< 01	<10	55	<10	9	465
7	RS 95-M8- 8 5-9 9m	0 2	1 28	75	945	<5	1 39	3	4	129	115	2 12	<10	0 66	63	13	< 01	137	1350	60	5	<20	92	< 01	<10	109	<10	9	587
8	RS 95-M8- 9 9-10 9m	1 4	1 15	110	1110	<5	0 13	<1	<1	102	207	2 49	<10	< 01	26	76	< 01	104	1480	622	15	<20	187	< 01	<10	174	<10	17	315
9	RS 95-M8- 10 9-11 9m	1 0	0 96	55	1270	<5	0 11	<1	<1	111	131	1 28	<10	< 01	23	43	< 01	85	1210	92	5	<20	134	< 01	<10	128	<10	11	149
10	RS 95-M8- 11 9-12 8m	1 8	0 92	60	485	<5	0 18	<1	5	71	351	1 63	<10	0 04	25	41	< 01	125	1040	116	<5	<20	103	< 01	<10	120	<10	23	316
11	RS 95-M8- 12 8-14 3m	2 8	1 20	95	300	<5	1 73	19	31	102	753	4 90	<10	0 69	228	30	< 01	358	2260	258	<5	<20	15	< 01	<10	52	<10	40	7618
12	RS 95-M8- 14 3-15 8m	0 4	0 17	45	95	<5	> 15	94	9	37	368	1 91	<10	8 49	160	6	< 01	142	1290	12	50	<20	55	< 01	<10	30	<10	17	3172
13	RS 95-M8- 15 8-16 4m	1 0	0 44	60	65	<5	11 20	155	13	72	2645	2 60	<10	6 25	158	4	< 01	200	830	46	40	<20	38	< 01	<10	38	<10	24	7740
14	RS 95-M8- 16 4-17 6m	2 0	3 19	940	450	<5	0 41	38	34	75	5428	> 15	<10	0 10	127	61	< 01	486	2290	2970	300	<20	12	< 01	<10	170	<10	57	6835
15	RS 95-M8- 17 6-19 2m	5 8	0 30	100	65	<5	0 08	3	11	161	1106	2 18	<10	< 01	111	15	< 01	73	280	726	10	<20	5	< 01	<10	14	<10	26	774
16	RS 95-M8- 19 2-20 5m	3 8	1 41	65	490	<5	3 90	51	20	71	4224	1 33	<10	2 05	174	6	< 01	381	530	182	40	<20	66	< 01	<10	44	<10	32	8299
17	RS 95-M8- 20 5-22 0m	9 2	2 13	35	140	<5	5 01	33	33	58	3051	2 23	<10	2 73	189	<1	< 01	682	280	58	35	<20	11	< 01	<10	54	<10	53	>10000
18	RS 95-M8- 22 0-23 8m	6 4	0 17	40	40	<5	0 63	6	10	146	854	1 13	<10	0 32	97	1	< 01	90	110	188	15	<20	7	< 01	<10	7	<10	1	9071
19	RS 95-M8- 23 8-25 3m	0 8	1 64	60	65	<5	12 60	25	9	57	563	1 35	<10	7 06	156	3	< 01	99	320	58	120	<20	35	< 01	<10	61	<10	11	1216
20	RS 95-M8- 25 3-26 8m	16 2	0 62	395	55	<5	12 30	13	25	88	1361	1 89	<10	6 87	239	5	< 01	96	250	60	750	<20	33	< 01	<10	32	<10	17	1400
21	RS 95-M8- 26 8-28 0m	>30	0 12	940	35	<5	10 40	38	35	65	6158	1 81	<10	5 70	305	3	< 01	76	100	346	1995	<20	28	< 01	<10	8	<10	29	1345
22	RS 95-M8- 28 0-29 9m	5 8	0 77	565	1040	<5	0 94	10	<1	198	555	1 73	<10	0 44	48	9	< 01	62	400	100	520	<20	21	< 01	<10	46	<10	1	1059
23	RS 95-M8- 29 9-31 2m	18 8	1 69	640	185	<5	12 30	24	11	59	3096	1 25	<10	6 88	146	4	< 01	159	420	190	730	<20	31	< 01	<10	43	<10	45	2698
24	RS 95-M8- 31 2-32 7m	>30	0 78	815	105	<5	12 70	28	7	82	2811	0 74	<10	7 17	116	2	< 01	52	170	822	1985	<20	40	< 01	<10	29	<10	11	779
25	RS 95-M8- 32 7-33 9m	6 8	9 58	915	345	<5	2 78	12	12	122	4732	1 78	<10	1 41	97	4	< 01	394	760	106	575	<20	7	< 01	<10	287	<10	34	2476

TOKLAT RESOURCES INC AK 95-840

Eco-Tech Laboratories Ltd

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	RS 95-M8- 33 9-34 9m	6 4	> 15	1420	280	<5	1 03	37	26	30	>10000	3 36	<10	0 33	132	1	< 01	845	30	<2	645	<20	2	< 01	<10	183	<10	52	5059
27	RS 95-M8- 34 9-36 0m	>30	10 20	1315	120	<5	4 64	9	20	80	4269	3 79	<10	2 44	117	6	< 01	471	780	230	1070	<20	9	< 01	<10	193	<10	31	3535
28	RS 95-M8- 36 0-37 0m	11 0	1 04	325	50	<5	> 15	8	12	46	1672	1 46	<10	8 90	227	2	< 01	101	270	100	475	<20	42	< 01	<10	21	<10	20	978
29	RS 95-M8- 37 0-38 0m	6 8	0 25	190	20	<5	> 15	20	11	38	933	0 74	<10	8 72	168	<1	< 01	41	300	54	480	<20	38	< 01	<10	9	<10	9	1248
30	RS 95-M8- 38 0-39 0m	5 8	0 08	90	20	<5	13 70	9	7	85	377	0 40	20	7 85	244	<1	< 01	17	80	64	180	<20	40	< 01	<10	5	<10	4	1027
31	RS 95-M8- 39 0-40 0m	2 4	0 05	65	20	<5	> 15	8	6	54	230	0 83	<10	8 81	322	<1	< 01	18	100	40	185	<20	47	< 01	<10	6	<10	2	623
32	RS 95-M8- 40 0-41 0m	2 4	0 07	75	50	<5	14 90	12	31	69	327	0 94	<10	8 58	357	<1	< 01	72	140	36	205	<20	41	< 01	<10	8	<10	2	4959
33	RS 95-M8- 41 0-42 0m	17 4	0 12	420	30	<5	11 80	9	8	67	2765	0 92	<10	6 67	220	1	< 01	25	280	144	610	<20	37	< 01	<10	7	<10	4	1083
34	RS 95-M8- 42 0-42 7m	4 2	0 07	130	30	<5	> 15	67	15	45	1363	0 72	<10	10 20	289	<1	< 01	42	110	16	170	<20	57	< 01	<10	6	<10	3	>10000
35	RS 95-M8- 42 7-43 3m	23 6	8 81	1540	335	<5	6 62	17	10	36	>10000	2 56	<10	3 67	89	<1	< 01	474	170	78	1510	<20	17	< 01	<10	95	<10	20	6131
36	RS 95-M8- 43 3-45 1m	1 6	0 08	85	20	<5	> 15	18	11	43	428	0 48	<10	11 50	183	<1	< 01	17	240	10	140	<20	48	< 01	<10	6	<10	7	955
37	RS 95-M8- 45 1-46 6m	0 6	0 05	100	25	<5	> 15	13	13	35	372	0 79	<10	12 00	215	<1	< 01	21	270	<2	155	<20	45	< 01	<10	7	<10	6	706
38	RS 95-M8- 46 6-48 2m	0 4	0 05	85	30	<5	> 15	17	17	11	334	0 97	<10	13 40	290	<1	< 01	34	330	8	175	<20	63	< 01	<10	10	<10	6	810
39	RS 95-M8- 48 2-49 5m	0 4	0 37	375	75	<5	> 15	48	93	9	1391	6 67	<10	12 70	749	4	< 01	318	210	4	460	<20	60	< 01	<10	12	<10	26	3318
40	RS 95-M8- 49 5-50 9m	0 4	0 15	115	40	<5	> 15	15	24	7	339	1 18	<10	13 40	300	<1	< 01	61	210	<2	140	<20	59	< 01	<10	12	<10	7	892
41	RS 95-M8- 50 9-51 9m	0 2	0 19	425	75	<5	> 15	22	62	5	690	5 49	<10	13 00	627	3	< 01	249	170	8	510	<20	64	< 01	<10	19	<10	22	3764
42	RS 95-M8- 51 9-52 9m	< 2	0 19	530	65	<5	> 15	23	49	5	269	4 84	<10	13 20	497	3	< 01	237	80	14	555	<20	69	< 01	<10	12	<10	22	3815
43	RS 95-M8- 52 9-54 3m	< 2	0 06	160	30	<5	> 15	17	10	3	73	1 23	<10	14 70	169	<1	< 01	58	90	8	175	<20	75	< 01	<10	10	<10	6	1099
44	RS 95-M8- 54 3-55 8m	< 2	0 04	115	25	<5	> 15	7	4	7	40	0 51	<10	14 70	129	<1	< 01	25	70	12	110	<20	61	< 01	<10	9	<10	1	502
45	RS 95-M8- 55 8-57 3m	0 2	0 02	110	30	<5	> 15	4	5	7	45	0 58	<10	> 15	148	<1	0 01	27	70	6	120	<20	64	< 01	<10	6	<10	<1	541
46	RS 95-M8- 57 3-58 8m	< 2	0 03	135	25	<5	> 15	7	6	2	111	0 61	<10	> 15	133	<1	< 01	26	80	10	125	<20	53	< 01	<10	7	<10	1	616
47	RS 95-M8- 58 8-60 4m	0 4	0 03	170	25	<5	> 15	8	9	2	105	0 90	<10	> 15	175	<1	< 01	39	80	20	165	<20	65	< 01	<10	7	<10	3	909
48	RS 95-M8- 60 4-61 9m	0 4	0 04	195	25	<5	> 15	10	9	24	155	1 12	<10	13 60	199	<1	< 01	51	70	26	200	<20	58	< 01	<10	7	<10	4	1149
49	RS 95-M8- 61 9-63 4m	1 2	0 04	140	40	<5	> 15	8	6	9	86	0 83	<10	> 15	222	<1	0 01	34	80	10	120	<20	73	< 01	<10	10	<10	3	910
50	RS 95-M8- 63 4-66 4m	0 6	0 02	170	45	<5	> 15	7	17	10	95	1 62	<10	> 15	353	<1	0 01	86	50	20	155	<20	78	< 01	<10	9	<10	4	1384
51	RS 95-M8- 66 4-68 0m	1 2	0 05	255	55	<5	> 15	5	28	22	234	2 52	<10	14 00	474	1	0 01	138	190	34	190	<20	71	< 01	<10	10	<10	9	2124
52	RS 95-M8- 68 0-69 5m	0 6	0 04	185	45	<5	> 15	5	22	4	118	2 03	<10	14 20	381	<1	0 01	107	160	28	140	<20	71	< 01	<10	9	<10	6	1675
53	RS 95-M8- 69 5-71 0m	0 8	0 03	170	50	<5	> 15	3	20	12	34	2 34	<10	13 80	440	<1	0 01	135	80	22	145	<20	72	< 01	<10	9	<10	8	1695
54	RS 95-M8- 71 0-72 5m	0 4	0 02	55	40	<5	> 15	3	13	2	8	1 53	<10	14 70	337	<1	0 01	82	110	60	130	<20	74	< 01	<10	7	<10	4	1009
55	RS 95-M8- 72 5-74 0m	0 6	0 03	50	45	10	> 15	2	15	3	8	2 57	<10	14 50	265	1	0 01	131	70	110	195	<20	73	< 01	<10	5	<10	7	1507
56	RS 95-M8- 74 0-75 6m	0 6	0 03	10	35	5	> 15	2	3	5	6	0 52	<10	14 80	230	<1	0 01	26	50	38	95	<20	71	< 01	<10	4	<10	2	306
57	RS 95-M8- 75 6-77 1m	0 2	0 02	15	35	<5	> 15	2	4	6	6	0 77	<10	14 80	191	<1	0 01	33	50	72	100	<20	76	< 01	<10	9	<10	3	387
58	RS 95-M8- 77 1-78 6m	< 2	0 02	10	35	<5	> 15	3	5	2	3	0 69	<10	> 15	296	<1	0 01	39	190	44	85	<20	73	< 01	<10	5	<10	3	337
59	RS 95-M8- 78 6-80 1m	0 2	0 03	15	40	<5	> 15	2	6	11	2	0 66	<10	14 60	285	<1	0 01	29	120	180	85	<20	74	< 01	<10	6	<10	2	252
60	RS 95-M8- 80 1-81 7m	< 2	0 02	20	35	<5	> 15	2	2	17	2	0 74	<10	14 20	226	<1	0 01	17	110	76	80	<20	67	< 01	<10	9	<10	1	156

Et #	Tag #.	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	RS 95-M8- 81 7-83 2m	< 2	0 02	15	30	<5	> 15	2	1	9	<1	0 43	<10	> 15	208	<1	0 01	8	80	44	70	<20	71	< 01	<10	7	<10	1	104
62	RS 95-M8- 83 2-84 7m	< 2	0 02	15	40	<5	> 15	2	3	14	2	0 61	<10	14 30	238	<1	0 01	17	90	28	70	<20	69	< 01	<10	10	<10	<1	155
63	RS 95-M8- 84 7-87 8m	0 6	0 02	150	30	<5	1 41	<1	4	229	7	1 93	<10	0 66	56	9	< 01	42	<10	26	10	<20	4	< 01	<10	3	<10	<1	238
64	RS 95-M9- 0'-5'	0 4	1 98	35	345	<5	13 00	9	23	33	241	6 54	<10	7 63	283	30	< 01	351	730	184	35	<20	48	0 01	<10	104	<10	33	1626
65	RS 95-M9- 5'-10'	< 2	0 72	25	85	<5	> 15	7	10	28	205	1 06	<10	12 20	238	3	< 01	138	300	20	55	<20	78	< 01	<10	38	<10	17	398
66	RS 95-M9- 10'-15'	< 2	1 85	30	150	<5	13 70	13	19	36	206	1 62	<10	7 39	244	6	< 01	255	330	42	45	<20	45	< 01	<10	55	<10	28	688
67	RS 95-M9- 15'-20'	< 2	0 10	5	35	<5	14 60	5	11	50	25	0 38	<10	8 13	186	2	< 01	40	310	4	45	<20	52	< 01	<10	24	<10	10	134
68	RS 95-M9- 6 1-7 6m	< 2	0 12	10	40	<5	> 15	8	20	26	29	1 27	<10	9 72	320	7	< 01	89	730	2	50	<20	72	< 01	<10	63	<10	21	408
69	RS 95-M9- 7 6-9 6m	0 4	0 54	60	155	<5	0 25	2	8	122	63	1 81	<10	0 08	61	36	< 01	130	670	36	<5	<20	84	< 01	<10	91	<10	26	424
70	RS 95-M9- 9 6-11 5m	< 2	0 48	45	160	<5	0 15	1	2	91	53	1 24	<10	0 04	22	31	< 01	79	860	62	<5	<20	123	< 01	<10	105	<10	14	165
71	RS 95-M9- 11 5-13 4m	0 6	0 37	55	135	<5	0 10	2	5	159	55	1 68	<10	0 02	33	51	< 01	106	380	58	<5	<20	43	< 01	<10	80	<10	12	276
72	RS 95-M9- 13 4-15 3m	0 4	0 68	60	115	<5	0 32	3	17	133	118	6 36	<10	< 01	30	61	< 01	278	1650	78	<5	<20	28	< 01	<10	97	<10	42	1301
73	RS 95-M9- 15 3-16 2m	< 2	0 10	50	25	<5	0 03	1	2	155	31	1 96	<10	< 01	27	18	< 01	37	340	148	<5	<20	14	< 01	<10	23	<10	3	150
74	RS 95-M9- 16 2-17 6m	0 8	0 35	155	85	<5	0 09	2	5	180	93	4 25	<10	< 01	30	22	< 01	94	970	424	5	<20	111	< 01	<10	52	<10	12	426
75	RS 95-M9- 17 6-20 5m	< 2	1 43	10	75	<5	> 15	25	31	33	135	3 56	<10	10 50	366	9	< 01	313	400	10	40	<20	64	< 01	<10	27	<10	37	1550
76	RS 95-M9- 20 5-23 8m	< 2	0 03	10	20	<5	0 87	1	2	210	12	0 60	<10	0 46	44	8	< 01	16	20	64	10	<20	6	< 01	<10	3	<10	<1	88
77	RS 95-M9- 23 8-26 8m	0 2	0 75	35	80	<5	0 29	5	7	128	111	1 90	<10	0 13	59	11	< 01	161	250	150	<5	<20	4	< 01	<10	30	<10	8	741
78	RS 95-M9- 26 8-29 8m	< 2	5 95	155	375	<5	12 20	83	132	21	328	12 10	<10	7 27	1204	17	< 01	905	530	10	30	<20	42	< 01	<10	101	<10	76	4270
79	RS 95-M9- 29 8-31 0m	1 4	3 03	95	140	<5	12 90	22	26	33	1631	8 71	<10	7 63	181	16	< 01	333	340	30	55	<20	47	< 01	<10	77	<10	18	2358
80	RS 95-M9- 31 0-32 0m	0 4	0 23	15	60	5	> 15	37	48	5	19	4 65	<10	13 70	407	4	< 01	222	100	<2	45	<20	57	< 01	<10	13	<10	33	1548
81	RS 95-M9- 32 0-33 1m	< 2	> 15	255	380	<5	4 67	22	79	45	558	7 57	<10	2 49	494	13	< 01	972	1550	<2	30	<20	49	< 01	<10	272	<10	41	2575
82	RS 95-M9- 33 1-34 0m	< 2	2 45	215	115	<5	> 15	40	92	22	150	7 18	<10	11 00	768	13	< 01	387	1180	<2	60	<20	67	< 01	<10	64	<10	37	1973
83	RS 95-M9- 34 0-36 0m	< 2	8 09	500	345	<5	8 99	21	74	50	935	> 15	<10	5 31	497	33	0 01	774	2530	78	385	<20	58	< 01	<10	279	<10	46	3670
84	RS 95-M9- 36 0-39 0m	< 2	> 15	370	285	<5	1 36	38	97	61	937	9 96	<10	0 40	595	15	0 01	1278	3380	<2	75	<20	154	< 01	<10	270	<10	128	3755
85	RS 95-M9- 39 0-40 8m	0 2	0 09	5	40	5	> 15	31	48	45	25	2 13	<10	14 60	568	5	0 02	135	200	<2	55	<20	67	< 01	<10	16	<10	15	1056
86	RS 95-M9- 40 8-42 3m	< 2	0 06	5	35	<5	> 15	10	31	8	4	1 31	<10	14 50	392	<1	0 01	90	200	<2	60	<20	74	< 01	<10	12	<10	8	994
87	RS 95-M9- 42 3-45 1m	< 2	0 05	10	40	5	> 15	5	29	12	4	0 70	<10	14 30	395	<1	0 01	77	220	<2	65	<20	65	< 01	<10	10	<10	5	759
88	RS 95-M9- 45 1-46 1m	< 2	0 11	10	35	<5	> 15	3	14	11	6	0 29	<10	> 15	297	<1	0 02	63	270	<2	60	<20	67	< 01	<10	7	<10	<1	603
89	RS 95-M9- 46 1-48 0m	< 2	5 79	90	95	<5	14 30	11	34	43	213	3 14	<10	8 23	327	4	0 02	481	920	14	45	<20	64	< 01	<10	87	<10	22	2037
90	RS 95-M9- 48 0-50 0m	< 2	0 36	20	35	<5	> 15	6	26	7	22	0 97	<10	14 00	396	<1	0 02	101	440	<2	55	<20	69	< 01	<10	13	<10	9	685
91	RS 95-M9- 50 0-51 2m	< 2	0 05	5	35	<5	> 15	3	20	5	8	1 08	<10	14 70	388	<1	0 02	85	150	<2	60	<20	69	< 01	<10	9	<10	3	1297
92	RS 95-M9- 51 2-54 3m	< 2	0 45	25	50	<5	> 15	6	38	21	151	1 57	<10	13 00	431	<1	0 02	181	120	8	55	<20	53	< 01	<10	14	<10	10	2759
93	RS 95-M9- 54 3-56 3m	0 2	0 57	15	35	<5	> 15	9	13	14	354	0 95	<10	13 70	142	<1	0 02	104	90	12	55	<20	50	< 01	<10	9	<10	8	955
94	RS 95-M9- 56 3-57 3m	< 2	0 05	5	25	<5	> 15	22	26	6	182	0 51	<10	14 20	158	<1	0 01	39	50	8	60	<20	52	< 01	<10	9	<10	4	527
95	RS 95-M9- 57 3-58 3m	< 2	9 02	35	225	<5	10 80	18	21	11	5847	0 85	<10	6 34	113	<1	0 02	1901	110	42	35	<20	19	< 01	<10	12	<10	55	5110

Et #.	Tag #.	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
96	RS 95-M9- 58 3-59 1m	< 2	1 32	15	60	<5	> 15	11	9	32	1266	0 90	<10	12 40	95	<1	0 02	345	50	12	55	<20	35	< 01	<10	10	<10	22	1239
97	RS 95-M9- 59 1-61 9m	< 2	0 07	15	25	<5	> 15	10	6	5	93	0 37	<10	> 15	139	<1	0 02	28	80	<2	60	<20	52	< 01	<10	8	<10	3	345
98	RS 95-M9- 61 9-64 4m	< 2	0 06	10	30	<5	> 15	6	12	8	50	1 71	<10	14 30	187	<1	0 01	86	160	<2	55	<20	75	< 01	<10	8	<10	7	981
99	RS 95-M9- 64 4-64 9m	< 2	0 35	10	40	<5	> 15	10	17	10	210	1 79	<10	13 80	221	<1	0 01	179	100	4	55	<20	67	< 01	<10	10	<10	16	1342
100	RS 95-M9- 64 9-66 8m	< 2	0 08	<5	25	<5	> 15	12	23	5	188	3 06	<10	13 80	172	<1	0 01	150	180	<2	55	<20	66	< 01	<10	9	<10	15	1756
101	RS 95-M9- 66 8-67 5m	< 2	0 03	10	20	<5	> 15	9	10	7	76	1 25	<10	14 60	163	<1	0 01	69	150	<2	55	<20	70	< 01	<10	10	<10	9	756
102	RS 95-M9- 67 5-69 5m	< 2	0 08	10	25	<5	> 15	9	7	2	71	0 95	<10	> 15	156	<1	0 01	58	90	<2	60	<20	75	< 01	<10	11	<10	7	603
103	RS 95-M9- 69 5-69 8m	0 2	0 53	10	40	<5	> 15	11	11	4	257	1 84	<10	14 30	148	<1	0 02	130	120	10	55	<20	63	< 01	<10	11	<10	9	1122
104	RS 95-M9- 69 8-70 5m	0 4	0 18	5	35	<5	> 15	48	11	6	373	1 47	<10	14 40	157	<1	0 01	83	40	6	65	<20	53	< 01	<10	5	<10	7	1001
105	RS 95-M9- 70 5-71 3m	0 4	> 15	100	70	<5	5 82	36	16	25	4151	3 44	<10	3 29	72	2	0 01	802	260	<2	45	<20	12	< 01	<10	16	<10	48	6346
106	RS 95-M9- 71 3-72 5m	1 0	0 74	15	40	<5	> 15	22	10	17	572	1 77	<10	14 20	144	1	0 02	114	80	30	70	<20	38	< 01	<10	9	<10	12	1196
107	RS 95-M9- 72 5-73 4m	2 4	1 88	90	205	<5	> 15	19	27	8	1071	6 71	<10	11 00	282	6	0 03	532	230	136	70	<20	64	< 01	<10	28	<10	41	3763
108	RS 95-M9- 73 4-75 6m	< 2	0 15	10	30	<5	> 15	23	13	8	598	2 84	<10	14 50	165	<1	0 02	113	140	32	60	<20	65	< 01	<10	14	<10	17	1728
109	RS 95-M9- 75 6-77 0m	0 6	0 04	20	40	<5	> 15	13	12	<1	252	2 11	<10	14 80	203	<1	0 02	84	620	6	75	<20	72	< 01	<10	8	<10	8	1332
110	RS 95-M9- 77 0-80 1m	0 4	1 15	35	65	<5	> 15	11	18	9	480	2 18	<10	13 20	461	<1	0 02	211	230	34	60	<20	51	< 01	<10	9	<10	19	1863
111	RS 95-M9- 80 1-81 7m	< 2	1 16	20	165	<5	> 15	28	134	4	1994	13 00	<10	10 30	1746	15	0 02	617	<10	80	40	<20	40	< 01	<10	14	<10	80	8815
112	RS 95-M9- 81 7-84 7m	0 6	0 04	10	75	<5	> 15	5	10	5	83	0 88	<10	> 15	376	<1	0 02	43	80	18	65	<20	61	< 01	<10	7	<10	4	542
113	RS 95-M9- 84 7-87 8m	0 4	0 08	15	45	<5	> 15	11	18	3	280	3 77	<10	13 90	232	3	0 02	135	100	26	50	<20	61	< 01	<10	10	<10	17	1947
114	RS 95-M9- 87 8-90 8m	1 2	0 05	15	85	<5	> 15	9	25	17	154	3 60	<10	13 90	387	3	0 02	145	170	28	55	<20	56	< 01	<10	11	<10	15	1832
115	RS 95-M9- 90 8-93 9m	1 2	0 13	40	115	<5	> 15	9	20	5	252	2 65	<10	14 10	578	3	0 02	132	180	30	65	<20	56	< 01	<10	15	<10	15	1519
116	RS 95-M9- 93 9-96 9m	1 8	0 03	20	100	<5	> 15	7	23	5	138	1 88	<10	14 70	561	<1	0 02	86	140	26	60	<20	62	< 01	<10	11	<10	10	967
117	RS 95-M9- 96 9-100 0m	1 0	0 15	20	50	<5	> 15	7	14	4	115	1 69	<10	13 80	244	<1	0 02	85	340	32	60	<20	68	< 01	<10	10	<10	9	695
118	RS 95-M9- 100 0-101 2m	1 4	0 66	30	80	<5	> 15	11	26	7	396	5 33	<10	12 50	225	4	0 02	275	330	66	55	<20	70	< 01	<10	15	<10	26	2344
119	RS 95-M9- 101 2-102 7m	0 8	0 10	15	40	<5	> 15	30	16	2	1254	3 72	<10	14 60	186	3	0 01	140	230	34	80	<20	58	< 01	<10	15	<10	17	2245
120	RS 95-M9- 102 7-106 0m	4 2	3 38	135	110	<5	2 55	19	32	59	1263	9 93	<10	1 40	118	11	< 01	765	220	264	25	<20	31	< 01	<10	29	<10	51	5651
121	RS 95-M9- 106 0-106 7m	0 6	0 37	20	60	<5	12 00	8	18	40	452	3 04	<10	6 96	504	4	0 01	192	40	34	45	<20	47	< 01	<10	10	<10	16	1342
122	RS 95-M9- 106 7-107 5m	0 2	3 57	30	125	<5	11 90	18	75	27	1241	9 66	<10	7 15	734	9	0 01	755	70	88	25	<20	47	< 01	<10	17	<10	57	4407
123	RS 95-M9- 107 5-108 6m	< 2	12 20	135	85	<5	7 94	29	47	38	2431	7 41	<10	4 56	657	7	0 01	773	390	142	35	<20	30	< 01	<10	28	<10	58	4704
124	RS 95-M9- 108 6-109 1	1 0	0 92	85	85	<5	> 15	12	16	49	1120	3 70	<10	9 93	1000	6	0 01	349	150	84	60	<20	58	< 01	<10	21	<10	25	1827
125	RS 95-M9- 109 1-110 6m	1 6	0 19	35	110	<5	> 15	8	11	25	526	2 30	<10	13 20	1071	2	0 02	194	80	46	60	<20	72	< 01	<10	13	<10	13	1023
126	RS 95-M9- 110 6-112 2m	1 8	0 10	25	105	<5	> 15	8	14	21	320	1 86	<10	13 50	826	1	0 02	133	130	44	60	<20	79	< 01	<10	12	<10	9	781
127	RS 95-M9- 112 2-113 7m	1 2	0 09	15	70	<5	> 15	8	5	4	220	1 24	<10	14 20	563	<1	0 02	99	140	18	55	<20	67	< 01	<10	8	<10	7	554
128	RS 95-M9- 113 7-115 5m	0 8	0 19	115	85	<5	> 15	13	48	15	484	6 21	<10	12 20	697	12	0 01	491	140	118	80	<20	55	< 01	<10	21	<10	34	2332
129	RS 95-M9- 115 5-118 3m	1 0	0 03	10	45	<5	> 15	7	4	5	59	0 70	<10	> 15	279	<1	0 02	39	90	4	65	<20	72	< 01	<10	10	<10	3	273
130	RS 95-M9- 118 3-119 8m	2 0	0 07	50	55	<5	> 15	11	18	4	314	3 47	<10	13 70	304	3	0 02	189	120	50	50	<20	68	< 01	<10	13	<10	13	1134

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
131	RS 95-M9- 119 8-121 0m	1 0	0 08	55	130	<5	> 15	10	38	2	176	2 42	<10	13 90	895	2	0 02	194	90	50	70	<20	66	< 01	<10	12	<10	9	923
132	RS 95-M9- 121 0-122 3m	1 2	0 15	60	145	<5	> 15	10	41	5	328	2 44	<10	13 60	1229	4	0 02	286	140	70	60	<20	69	< 01	<10	16	<10	13	1051
133	RS 95-M9- 122 3-122 8m	0 4	0 04	15	40	<5	> 15	7	2	6	31	0 40	<10	14 50	187	<1	0 02	31	60	<2	60	<20	72	< 01	<10	6	<10	1	154
134	RS 95-M9- 122 8-124 4m	0 4	0 04	15	45	<5	> 15	7	2	7	17	0 32	<10	14 30	245	<1	0 02	24	80	<2	65	<20	86	< 01	<10	8	<10	1	116
135	RS 95-M9- 124 4-126 4m	0 4	0 07	25	125	<5	> 15	8	15	52	79	1 49	<10	13 80	645	5	0 02	115	160	14	60	<20	69	< 01	<10	16	<10	3	491
136	RS 95-M9- 126 4-127 5m	0 2	0 03	20	50	<5	> 15	12	10	8	21	1 44	<10	14 50	319	<1	0 02	80	70	8	60	<20	66	< 01	<10	8	<10	7	561
137	RS 95-M9- 127 5-130 5m	0 6	0 13	85	235	<5	> 15	28	42	18	97	3 45	<10	12 20	1554	6	0 01	347	100	60	65	<20	70	< 01	<10	17	<10	16	1415
138	RS 95-M9- 130 5-132 0m	< 2	0 07	155	65	<5	> 15	9	19	26	65	3 72	<10	12 90	538	4	0 02	218	80	62	75	<20	68	< 01	<10	25	<10	11	1169
139	RS 95-M9- 132 0-133 5m	< 2	0 05	110	55	<5	> 15	5	9	8	36	1 97	<10	13 90	590	1	0 02	172	80	30	80	<20	68	< 01	<10	16	<10	3	489
140	RS 95-M9- 133 5-134 8m	0 2	0 07	255	70	<5	> 15	112	20	22	72	4 64	<10	9 72	339	6	0 01	240	100	82	65	<20	64	< 01	<10	26	<10	18	1292
141	RS 95-M9- 134 8-136 6m	0 4	0 05	55	75	<5	> 15	22	5	7	21	1 17	<10	13 80	331	<1	0 02	85	80	12	65	<20	84	< 01	<10	10	<10	6	296
142	RS 95-M9- 136 6-138 2m	0 2	0 06	120	255	<5	> 15	10	17	12	68	3 28	<10	13 10	740	3	0 02	277	120	32	75	<20	70	< 01	<10	18	<10	7	924
143	RS 95-M9- 138 2-139 9m	0 4	0 05	55	85	<5	> 15	15	23	10	46	3 20	<10	13 30	636	3	0 02	226	100	10	65	<20	73	< 01	<10	18	<10	11	1065
144	RS 95-M9- 139 9-142 6m	0 6	0 06	50	245	<5	> 15	22	12	5	21	2 29	<10	12 70	284	2	0 02	128	100	10	60	<20	78	< 01	<10	13	<10	5	619
145	RS 95-M9- 142 6-143 8m	0 4	0 04	20	80	10	> 15	6	3	10	2	0 69	<10	14 10	210	<1	0 02	29	80	<2	60	<20	85	< 01	<10	6	<10	<1	152
146	RS 95-M9- 143 8-144 3m	0 2	0 07	20	75	<5	> 15	7	8	6	10	1 43	<10	13 90	234	1	0 02	52	150	8	60	<20	81	< 01	<10	12	<10	3	305
147	RS 95-M9- 144 3-145 7m	0 6	0 04	20	85	5	> 15	21	4	11	8	1 09	<10	13 40	235	<1	0 02	46	90	8	60	<20	92	< 01	<10	8	<10	1	213
148	RS 95-M9- 145 7-147 2m	0 4	0 03	20	65	<5	> 15	14	3	10	4	0 78	<10	13 50	239	<1	0 02	34	80	<2	60	<20	86	< 01	<10	7	<10	<1	181
149	RS 95-M9- 147 2-148 6m	0 6	0 04	30	115	5	> 15	17	9	3	6	1 06	<10	13 50	258	<1	0 02	64	60	<2	60	<20	74	< 01	<10	9	<10	4	321
150	RS 95-M9- 148 6-149 6m	0 2	0 05	15	110	<5	> 15	14	<1	3	3	0 32	<10	13 40	209	<1	0 02	14	150	<2	65	<20	106	< 01	<10	8	<10	2	73
151	RS 95-M9- 149 6-150 3m	0 2	0 05	35	190	<5	> 15	23	5	2	14	1 33	<10	13 60	350	1	0 02	79	100	2	65	<20	73	< 01	<10	10	<10	3	294
152	RS 95-M9- 150 3-151 8m	0 4	0 07	100	395	<5	> 15	64	23	3	51	4 66	<10	11 70	509	7	0 02	271	570	6	65	<20	66	< 01	<10	17	<10	15	1015
153	RS 95-M9- 151 8-153 3m	0 2	0 06	315	195	<5	> 15	30	37	4	123	6 64	<10	12 10	1151	13	0 02	507	120	16	90	<20	53	< 01	<10	44	<10	8	1294
154	RS 95-M9- 153 3-154 8m	< 2	0 12	390	205	<5	> 15	40	56	13	157	11 80	<10	10 00	844	24	0 01	644	180	36	110	<20	54	< 01	<10	68	<10	18	2062

Et #.	Tag #.	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																													
Resplit:																													
RS1	RS 95-M8- 0'-5'	0 2	1 38	80	255	<5	> 15	10	23	32	241	5 61	<10	9 42	247	21	< 01	315	650	248	40	<20	60	< 01	<10	97	<10	27	1761
RS36	RS 95-M8- 43 3-45 1m	2 0	0 10	100	25	<5	> 15	18	11	40	453	0 50	<10	11 20	178	<1	< 01	20	230	12	150	<20	49	< 01	<10	9	<10	7	1016
RS71	RS 95-M9- 11 5-13 4m	0 6	0 36	50	130	<5	0 09	1	5	150	55	1 69	<10	0 02	31	47	< 01	106	420	58	<5	<20	46	< 01	<10	78	<10	12	285
RS106	RS 95-M9- 71 3-72 5m	1 0	0 72	20	45	<5	> 15	22	10	16	583	1 84	<10	14 10	144	2	0 02	115	60	28	70	<20	39	< 01	<10	9	<10	12	1182
RS141	RS 95-M9- 134 8-136 6m	0 2	0 04	55	70	<5	> 15	22	5	10	20	1 16	<10	13 60	327	2	0 02	81	70	14	65	<20	83	< 01	<10	10	<10	4	296
Repeat:																													
1	RS 95-M8- 0'-5'	< 2	1 31	80	245	<5	> 15	10	21	27	244	5 26	<10	9 11	233	20	< 01	299	630	228	50	<20	57	< 01	<10	93	<10	27	1683
10	RS 95-M8- 11 9-12 8m	1 8	0 93	60	500	<5	0 11	<1	5	70	351	1 60	<10	0 02	25	41	< 01	127	1040	118	<5	<20	102	< 01	<10	123	<10	23	311
19	RS 95-M8- 34 9-36 0m	0 8	1 67	65	65	<5	12 50	25	9	59	569	1 35	<10	7 04	155	4	< 01	100	330	58	130	<20	33	< 01	<10	60	<10	12	1206
36	RS 95-M8- 43 3-45 1m	2 0	0 07	85	25	<5	> 15	18	11	43	421	0 47	<10	11 40	180	<1	< 01	17	230	10	130	<20	50	< 01	<10	6	<10	7	938
45	RS 95-M8- 55 8-57 3m	< 2	0 02	110	30	<5	> 15	4	5	6	42	0 56	<10	14 70	144	<1	0 01	26	70	6	120	<20	61	< 01	<10	6	<10	<1	530
54	RS 95-M8- 71 0-72 5m	0 2	0 02	60	40	<5	> 15	3	13	2	7	1 54	<10	14 70	339	<1	0 01	84	110	58	125	<20	74	< 01	<10	8	<10	5	1014
71	RS 95-M9- 11 5-13 4m	0 6	0 37	50	130	<5	0 14	1	5	148	58	1 66	<10	0 04	30	49	< 01	105	370	56	<5	<20	44	< 01	<10	77	<10	12	280
80	RS 95-M9- 31 0-32 0m	0 2	0 23	20	55	<5	> 15	36	48	5	19	4 65	<10	13 60	409	3	< 01	222	90	<2	40	<20	55	< 01	<10	13	<10	33	1559
89	RS 95-M9- 46 1-48 0m	< 2	5 82	95	95	<5	14 50	11	35	43	216	3 17	<10	8 37	330	6	0 02	482	930	14	55	<20	64	< 01	<10	88	<10	23	2061
106	RS 95-M9- 71 3-72 5m	0 8	0 71	20	40	<5	> 15	22	10	16	561	1 74	<10	14 00	141	1	0 02	112	70	28	65	<20	37	< 01	<10	9	<10	12	1180
115	RS 95-M9- 90 8-93 9m	1 4	0 18	35	110	<5	> 15	10	20	11	263	2 64	<10	13 60	571	3	0 02	135	190	30	65	<20	54	< 01	<10	15	<10	14	1511
124	RS 95-M9- 108 6-109 1	1 0	0 93	75	85	<5	> 15	12	16	49	1136	3 73	<10	10 10	1015	6	0 01	353	150	84	60	<20	59	< 01	<10	21	<10	26	1832
141	RS 95-M9- 134 8-136 6m	0 4	0 04	65	75	<5	> 15	21	5	5	20	1 16	<10	13 70	326	<1	0 02	80	70	12	70	<20	85	< 01	<10	9	<10	4	296
150	RS 95-M9- 148 6-149 6m	0 4	0 05	15	110	<5	> 15	14	<1	3	3	0 37	<10	13 50	212	<1	0 02	17	140	<2	60	<20	106	< 01	<10	8	<10	3	80
Standard:																													
GEO-95		1 4	1 67	60	160	<5	1 61	<1	19	64	84	3 75	<10	0 89	638	<1	0 02	24	570	16	<5	<20	50	0 12	<10	65	<10	6	66
GEO-95		1 2	1 79	65	165	<5	1 78	<1	19	64	84	3 69	<10	0 87	642	<1	0 02	24	580	18	<5	<20	52	0 12	<10	64	<10	6	65
GEO-95		1 2	1 71	65	170	<5	1 63	<1	18	58	86	3 76	<10	0 93	644	<1	0 02	26	570	20	<5	<20	58	0 10	<10	64	<10	5	64
GEO-95		1 4	1 66	60	175	<5	1 62	<1	19	58	84	3 84	<10	0 89	646	<1	0 02	24	580	22	10	<20	52	0 12	<10	65	<10	4	66
GEO-95		1 2	1 66	60	160	<5	1 60	<1	19	56	86	3 78	<10	0 87	638	<1	0 03	27	590	22	<5	<20	51	0 12	<10	66	<10	4	65

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B C Certified Assayer

df/840
XLS/95Toklat

2-Oct-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC AK 95-853
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION TIM TERMUENDE

93 Rock/Core samples received Sept. 16, 1995
PROJECT #- None given
SHIPMENT #. None given

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	RS95-M10 0 0-5'	< 2	0 03	10	25	<5	> 15	<1	2	44	12	0 17	<10	13 80	135	2	< 01	9	140	26	65	<20	62	< 01	<10	6	<10	1	298
2	RS95-M10 5'-10'	< 2	0 03	10	25	<5	> 15	<1	1	23	11	0 16	<10	14 90	124	<1	< 01	9	150	20	65	<20	73	< 01	<10	6	<10	2	276
3	RS95-M10 3 0-4 2 m	< 2	0 03	5	30	<5	> 15	<1	1	16	10	0 17	<10	> 15	117	<1	0 01	11	290	8	65	<20	80	< 01	<10	7	<10	3	251
4	RS95-M10 4 2-5 5m	< 2	0 03	5	25	<5	> 15	<1	<1	52	9	0 14	<10	> 15	110	4	0 01	10	370	10	65	<20	82	< 01	<10	6	<10	2	212
5	RS95-M10 5 5-7 0m	< 2	0 03	15	25	<5	> 15	72	<1	20	12	0 20	<10	> 15	104	<1	0 01	13	300	18	60	<20	79	< 01	<10	5	<10	2	212
6	RS95-M10 7 0-8 5m	< 2	0 04	20	40	<5	> 15	<1	<1	6	10	0 20	<10	> 15	139	<1	0 01	17	220	12	60	<20	81	< 01	<10	8	<10	3	335
7	RS95-M10 8 5-10 0m	< 2	0 03	10	35	<5	> 15	<1	<1	6	4	0 09	<10	> 15	121	<1	0 01	11	170	8	65	<20	83	< 01	<10	7	<10	<1	283
8	RS95-M10 10 0-11 6m	< 2	0 02	10	35	<5	> 15	<1	<1	16	6	0 10	<10	14 50	122	<1	0 01	7	250	10	60	<20	87	< 01	<10	5	<10	2	238
9	RS95-M10 11 6-12 8m	0 6	0 04	20	40	<5	> 15	<1	1	3	35	0 18	<10	> 15	118	<1	0 01	15	140	62	70	<20	89	< 01	<10	4	<10	<1	527
10	RS95-M10 12 8-14 2m	0 2	0 04	15	40	<5	> 15	2	<1	4	29	0 20	<10	> 15	129	<1	0 01	8	170	60	65	<20	89	< 01	<10	6	<10	2	429
11	RS95-M10 14 2-15 2m	< 2	0 07	15	30	<5	> 15	2	2	7	22	0 29	<10	> 15	143	<1	0 01	25	100	30	60	<20	72	< 01	<10	11	<10	1	552
12	RS95-M10 15 2-16 2m	0 2	0 17	15	35	<5	> 15	2	1	3	70	0 14	<10	> 15	130	<1	< 01	38	110	30	70	<20	64	< 01	<10	13	<10	2	921
13	RS95-M10 16 2-17 5m	0 4	0 07	10	30	<5	> 15	3	1	2	29	0 08	<10	> 15	112	<1	0 01	18	80	38	70	<20	58	< 01	<10	9	<10	<1	746
14	RS95-M10 17 5-18 5m	< 2	0 04	15	30	<5	> 15	<1	<1	10	15	0 11	<10	14 10	124	<1	< 01	14	60	48	70	<20	50	< 01	<10	10	<10	1	493
15	RS95-M10 18 5-19 5m	< 2	0 20	10	30	<5	> 15	2	1	10	41	0 10	<10	14 30	100	<1	0 01	32	70	40	60	<20	40	< 01	<10	11	<10	1	615
16	RS95-M10 19 5-20 7m	< 2	0 08	15	25	<5	> 15	<1	<1	22	13	0 10	<10	12.40	109	<1	< 01	10	70	54	65	<20	41	< 01	<10	9	<10	1	201
17	RS95-M10 20 7-22 2m	1 4	0 06	15	20	<5	> 15	<1	2	11	42	0 15	<10	14 30	129	<1	0 01	22	100	406	65	<20	69	< 01	<10	7	<10	3	522
18	RS95-M10 22 2-23 8m	1 4	0 04	10	10	<5	> 15	4	5	5	87	0 24	<10	14 30	126	<1	< 01	27	140	78	65	<20	62	< 01	<10	8	<10	4	1444
19	RS95-M10 23 8-25 3m	< 2	0 05	15	15	<5	> 15	2	3	1	16	0 27	<10	14 30	127	<1	< 01	27	110	16	70	<20	61	< 01	<10	6	<10	<1	1766
20	RS95-M10 25 3-26 8m	1 8	0 15	20	20	<5	> 15	2	3	7	32	0 21	<10	13 90	109	<1	< 01	27	60	18	85	<20	64	< 01	<10	6	<10	<1	1072
21	RS95-M10 26 8-28 3m	< 2	0 02	10	20	5	> 15	5	<1	2	7	0 11	<10	13 50	137	<1	0 01	6	50	<2	65	<20	84	< 01	<10	3	<10	<1	192
22	RS95-M10 28 3-29 9m	0 4	0 02	15	15	<5	> 15	11	3	6	14	0 20	<10	14 80	132	<1	< 01	11	60	16	65	<20	64	< 01	<10	4	<10	<1	352
23	RS95-M10 29 9-30 9m	< 2	0 04	10	15	<5	> 15	8	2	2	8	0 14	<10	14 90	104	<1	< 01	13	130	4	65	<20	50	< 01	<10	6	<10	<1	387
24	RS95-M10 30 9-31 9m	1 0	1 20	25	30	<5	> 15	6	8	8	51	0 41	<10	14 10	164	<1	< 01	126	260	28	60	<20	70	< 01	<10	22	<10	7	1589
25	RS95-M10 31 9-32 9m	2.0	0 18	15	20	<5	> 15	5	4	4	65	0 44	<10	14 60	116	<1	< 01	36	200	6	75	<20	64	< 01	<10	7	<10	3	1086

TOKLAT RESOURCES INC AK 95-853

ECO-TECH LABORATORIES LTD

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	RS95-M10 32 9-34 4m	2 2	0 04	25	25	<5	> 15	12	5	2	58	0 41	<10	14 70	171	<1	0 01	21	240	10	75	<20	66	< 01	<10	7	<10	<1	1252
27	RS95-M10 34 4-36 0m	< 2	0 01	<5	25	<5	> 15	2	<1	2	17	0 12	<10	14 80	90	<1	0 01	1	180	14	65	<20	53	< 01	<10	5	<10	<1	227
28	RS95-M10 36 0-37 5m	< 2	0 02	5	20	<5	> 15	2	<1	2	11	0 15	<10	14 60	103	<1	0 01	2	270	24	65	<20	60	< 01	<10	6	<10	<1	189
29	RS95-M10 37 5-39 0m	< 2	0 02	10	20	<5	> 15	<1	<1	2	2	0 11	<10	14 80	94	<1	0 01	<1	280	4	60	<20	55	< 01	<10	6	<10	<1	400
30	RS95-M10 39 0-40 5m	< 2	0 02	10	20	5	> 15	<1	2	3	<1	0 20	<10	14 20	107	<1	0 01	5	120	10	60	<20	68	< 01	<10	5	<10	<1	141
31	RS95-M10 63 4-65 0m	< 2	0 03	10	30	<5	> 15	2	2	5	21	0 34	<10	14 40	484	<1	0 01	6	130	<2	70	<20	95	< 01	<10	3	<10	<1	179
32	RS95-M10 65 0-66 5m	0 4	0 03	30	25	<5	> 15	1	3	2	60	0 67	<10	14 80	483	<1	0 01	17	70	14	75	<20	98	< 01	<10	4	<10	<1	395
33	RS95-M10 66 5-67 5m	< 2	0 03	40	25	<5	> 15	3	2	14	16	0 82	<10	14 30	380	<1	< 01	17	40	<2	75	<20	78	< 01	<10	6	<10	<1	322
34	RS95-M10 67 5-68 5m	< 2	0 03	30	25	<5	> 15	1	2	14	20	0 82	<10	14 10	433	<1	< 01	18	60	8	70	<20	81	< 01	<10	5	<10	<1	309
35	RS95-M10 68 5-69 5m	1 0	0 24	35	30	<5	> 15	3	3	4	32	0 80	<10	14 70	163	<1	< 01	50	70	6	70	<20	91	< 01	<10	7	<10	2	606
36	RS95-M10 69 5-70 5m	0 2	0 09	15	25	5	> 15	1	2	11	18	0 57	<10	13 70	129	<1	< 01	26	90	4	70	<20	78	< 01	<10	8	<10	2	362
37	RS95-M10 70 5-71 5m	< 2	0 22	10	25	<5	> 15	2	1	6	13	0 39	<10	14 40	144	<1	< 01	34	100	4	70	<20	93	< 01	<10	8	<10	3	324
38	RS95-M10 71 5-72.6m	< 2	2.31	45	450	<5	> 15	4	1	51	190	0 83	<10	10 70	116	<1	< 01	354	210	14	70	<20	57	< 01	<10	26	<10	16	1462
39	RS95-M10 72 6-73 6m	0 4	0 12	25	20	<5	> 15	2	2	5	58	0 78	<10	14 30	137	<1	< 01	35	100	18	70	<20	85	< 01	<10	8	<10	3	476
40	RS95-M10 73 6-74 6m	2 0	1 43	65	125	<5	> 15	3	8	19	252	2 11	<10	13 50	188	<1	0 01	190	160	24	80	<20	75	< 01	<10	24	<10	13	1219
41	RS95-M10 74 6-75 6m	1 6	1 48	160	115	<5	> 15	5	13	9	671	4 31	<10	12 00	152	7	0 01	243	480	28	85	<20	79	< 01	<10	43	<10	18	1705
42	RS95-M10 75 6-76 6m	0 4	0 89	20	65	<5	> 15	2	4	6	88	0 93	<10	13 40	142	<1	0 01	81	120	44	65	<20	80	< 01	<10	12	<10	6	584
43	RS95-M10 76 6-77 6m	< 2	0 11	10	20	5	> 15	1	5	3	20	0 84	<10	14 40	137	<1	< 01	53	130	4	65	<20	77	< 01	<10	9	<10	3	450
44	RS95-M10 77 6-78 7m	< 2	0 04	20	20	<5	> 15	<1	2	5	4	0 45	<10	14 40	135	<1	0 01	17	90	24	65	<20	74	< 01	<10	5	<10	<1	217
45	RS95-M10 78 7-80 2m	< 2	0 25	25	40	<5	> 15	1	2	7	51	0 72	<10	13 60	131	<1	< 01	39	180	10	65	<20	75	< 01	<10	12	<10	3	404
46	RS95-M10 80 2-82 5m	< 2	2 28	40	115	<5	> 15	3	5	15	346	1 11	<10	12 50	96	1	< 01	127	650	42	55	<20	98	< 01	<10	35	<10	3	1043
47	RS95-M10 82 5-83 3m	< 2	0 09	<5	20	<5	> 15	<1	<1	<1	39	0 14	<10	10 30	149	<1	< 01	7	80	<2	55	<20	79	< 01	<10	4	<10	<1	98
48	RS95-M10 83 3-84 8m	0 2	0 12	10	20	<5	> 15	<1	3	4	47	0 43	<10	14 20	93	<1	< 01	18	120	<2	60	<20	83	< 01	<10	6	<10	<1	242
49	RS95-M10 84 8-86 3m	< 2	0 04	<5	10	<5	> 15	<1	<1	1	9	0 13	<10	14 60	91	<1	< 01	1	100	<2	65	<20	77	< 01	<10	4	<10	<1	64
50	RS95-M10 86 3-87 8m	0 4	0 06	10	15	<5	> 15	1	1	2	20	0 27	<10	14 30	91	<1	< 01	9	70	<2	60	<20	81	< 01	<10	6	<10	<1	165
51	RS95-M11 0 0-2'	< 2	0 30	10	60	<5	> 15	<1	5	20	110	0 58	<10	11 90	189	<1	0 01	46	200	88	55	<20	57	< 01	<10	14	<10	2	877
52	RS95-M11 2-3'	< 2	0 07	5	30	<5	> 15	<1	3	8	24	0 21	<10	14 20	155	<1	0 01	24	110	42	65	<20	72	< 01	<10	7	<10	<1	729
53	RS95-M11 3-4'	< 2	0 09	5	30	<5	> 15	<1	2	11	25	0 21	<10	13 70	136	<1	0 01	18	130	44	60	<20	69	< 01	<10	7	<10	1	448
54	RS95-M11 4-5'	< 2	0 03	5	20	<5	> 15	<1	1	5	5	0 11	<10	14 30	108	<1	0 01	10	160	20	65	<20	77	< 01	<10	4	<10	1	251
55	RS95-M11 5-6,	< 2	0 04	<5	30	<5	> 15	<1	2	15	19	0 17	<10	13 90	131	<1	< 01	18	130	38	65	<20	66	< 01	<10	6	<10	1	445
56	RS95-M11 6-7'	< 2	0 04	5	25	<5	> 15	<1	2	6	17	0 15	<10	14 20	118	<1	0 01	12	140	24	60	<20	70	< 01	<10	5	<10	<1	296
57	RS95-M11 7-8'	< 2	0 03	<5	20	<5	> 15	<1	<1	12	5	0 12	<10	14 70	94	<1	< 01	10	120	8	65	<20	63	< 01	<10	6	<10	2	206
58	RS96-M11 8-9'	< 2	0 03	10	25	<5	> 15	3	<1	7	6	0 11	<10	14 20	99	<1	0 01	9	210	2	60	<20	71	< 01	<10	6	<10	2	202
59	RS95-M11 9-10'	<.2	0 03	10	35	<5	> 15	<1	<1	6	4	0 14	<10	14 80	127	<1	0 01	11	270	16	60	<20	81	< 01	<10	8	<10	3	240
60	RS95-M11 13 6-14 9m	< 2	0 05	10	35	<5	> 15	<1	1	6	16	0 27	<10	14 40	160	<1	0 01	25	100	28	60	<20	76	< 01	<10	7	<10	1	512
61	RS95-M11 14 9-16 5m	< 2	0 06	15	35	<5	> 15	<1	<1	10	5	0 13	<10	14 80	139	<1	0 01	9	80	48	65	<20	59	< 01	<10	11	<10	<1	181
62	RS95-M11 16 5-18 5m	< 2	0 08	15	35	<5	> 15	2	<1	6	6	0 10	<10	14 30	139	<1	0 01	15	60	44	65	<20	61	< 01	<10	8	<10	<1	321
63	RS95-M11 18 5-19 5m	< 2	0 02	15	25	<5	> 15	<1	2	3	4	0 13	<10	14 70	130	<1	< 01	8	70	44	65	<20	63	< 01	<10	6	<10	<1	205
64	RS95-M11 19 5-20 5m	< 2	0 02	10	25	<5	> 15	1	2	6	10	0 15	<10	> 15	127	<1	< 01	13	50	58	70	<20	63	< 01	<10	9	<10	2	239
65	RS95-M11 20 5-21 5m	< 2	0 08	15	30	<5	> 15	2	3	4	23	0 18	<10	14 80	122	<1	0 01	44	70	80	70	<20	61	< 01	<10	9	<10	2	381

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
66	RS95-M11 21 5-24 1m	< 2	0 20	15	50	<5	> 15	2	2	2	38	0 19	<10	> 15	118	<1	0 01	86	60	92	65	<20	57	< 01	<10	12	<10	1	674
67	RS95-M11 24 1-25 1m	< 2	0 13	15	35	<5	> 15	2	1	9	4	0 27	<10	> 15	147	<1	0 01	44	180	104	65	<20	68	< 01	<10	9	<10	4	748
68	RS95-M11 25 1-26 1m	< 2	0 24	15	40	<5	> 15	2	2	6	5	0 40	<10	14 40	155	<1	0 01	74	370	184	60	<20	70	< 01	<10	13	<10	4	905
69	RS95-M11 26 1-27 1m	< 2	1 26	70	100	<5	> 15	5	9	12	34	1 74	<10	13 60	179	2	0 01	292	810	600	60	<20	70	< 01	<10	26	<10	9	2510
70	RS95-M11 27 1-28 1m	< 2	0 93	50	65	<5	> 15	4	10	16	24	1 79	<10	11 30	105	1	< 01	249	470	298	55	<20	47	< 01	<10	22	<10	8	2117
71	RS95-M11 28 1-29 1m	< 2	11 90	255	360	<5	5 83	37	7	130	50	0 91	<10	1 80	46	<1	< 01	387	5410	2922	40	<20	157	< 01	<10	111	<10	60	4672
72	RS95-M11 29 1-30 2m	< 2	> 15	265	495	<5	5 63	11	20	177	45	4 23	<10	' 0 85	45	3	< 01	689	5000	748	<5	<20	460	< 01	<10	189	<10	68	5205
73	RS95-M11 30 2-31 2m	< 2	2 48	30	260	5	1 27	1	8	73	8	2 25	<10	0 56	391	<1	0 02	108	1500	234	5	<20	112	0 09	<10	57	<10	10	857
74	RS95-M11 31 2-32.2m	< 2	3 97	60	55	<5	> 15	8	7	26	23	0 57	<10	11 60	103	<1	< 01	256	540	480	65	<20	60	< 01	<10	55	<10	31	1829
75	RS95-M11 32 2-33 2m	< 2	5 40	90	160	5	> 15	11	18	25	20	0 97	<10	10 10	194	<1	< 01	341	540	862	60	<20	47	< 01	<10	104	<10	37	2600
76	RS95-M11 33 2-33 7m	3 4	0 13	85	50	<5	> 15	2	8	8	6	1 75	<10	13 50	213	2	0 01	85	180	768	70	<20	63	< 01	<10	28	<10	9	1012
77	RS95-M11 33 7-35 3m	1 0	0 05	20	35	5	> 15	5	3	8	14	0 53	<10	14 20	177	<1	0 01	23	130	238	65	<20	62	< 01	<10	21	<10	3	666
78	RS95-M11 35 3-36 3m	0 6	0 04	20	35	<5	> 15	10	3	2	20	0 70	<10	14 60	133	<1	0 01	33	460	192	70	<20	58	< 01	<10	11	<10	3	1120
79	RS95-M11 36 3-37 3m	< 2	0 02	15	30	<5	> 15	2	2	1	14	0 51	<10	15 00	136	<1	0 01	15	180	64	65	<20	69	< 01	<10	7	<10	3	430
80	RS95-M11 37 3-38 3m	0 2	0 07	25	35	<5	> 15	7	2	4	57	0 57	<10	14 20	122	<1	0 01	21	190	52	70	<20	54	< 01	<10	7	<10	<1	672
81	RS95-M11 38 3-39 3m	2.0	0 02	45	30	<5	> 15	39	1	10	538	0 37	<10	13 70	193	<1	0 01	15	140	58	95	<20	48	< 01	<10	10	<10	<1	9551
82	RS95-M11 39 3-40 8m	2 4	0 02	20	35	<5	> 15	2	<1	1	85	0 28	<10	14 60	203	<1	0 01	7	170	50	70	<20	63	< 01	<10	13	<10	2	472
83	RS95-M11 40 8-42 4m	0 8	0 02	20	50	<5	> 15	<1	<1	2	78	0 24	<10	14 70	159	<1	0 01	9	80	10	65	<20	74	< 01	<10	9	<10	<1	388
84	RS95-M11 42 4-43 9m	1 0	0 02	10	40	<5	> 15	2	2	6	47	0 19	<10	> 15	158	<1	0 01	11	100	4	65	<20	64	< 01	<10	9	<10	<1	374
85	RS95-M11 43 9-45 4m	1 0	0 02	10	40	<5	> 15	4	1	2	45	0 19	<10	> 15	147	<1	0 01	12	120	20	70	<20	61	< 01	<10	8	<10	<1	469
86	RS95-M11 45 4-46 9m	< 2	0 02	10	35	<5	> 15	3	<1	4	41	0 13	<10	> 15	118	<1	0 01	10	110	2	75	<20	51	< 01	<10	6	<10	<1	631
87	RS95-M11 64 6-66 1m	0 6	0 02	25	20	<5	> 15	<1	<1	6	58	0 33	<10	13 70	230	<1	< 01	3	60	46	80	<20	75	< 01	<10	3	<10	<1	231
88	RS95-M11 66 1-67 6m	1 0	0 02	55	35	<5	> 15	<1	<1	8	102	0 95	<10	14 30	199	<1	0 01	12	50	36	100	<20	77	< 01	<10	8	<10	<1	499
89	RS95-M11 67 6-69 1m	2.2	0 02	65	25	<5	> 15	1	<1	5	169	0 80	<10	13 20	177	<1	< 01	12	60	58	105	<20	77	< 01	<10	13	<10	<1	524
90	RS95-M11 69 1-70 6m	0 4	0 02	15	30	<5	> 15	1	<1	1	30	0 19	<10	13 70	179	<1	0 01	1	60	14	70	<20	92	< 01	<10	5	<10	<1	176
91	RS95-M11 70 6-72 1m	0 2	0 02	10	30	<5	> 15	<1	<1	<1	11	0 06	<10	14 10	155	<1	0 01	<1	60	2	60	<20	93	< 01	<10	2	<10	<1	122
92	RS95-M11 72 1-73 6m	< 2	0 02	10	40	<5	> 15	<1	<1	2	15	0 16	<10	14 00	180	<1	0 01	1	90	6	60	<20	81	< 01	<10	4	<10	<1	141
93	RS95-M11 73 6-75 1m	< 2	0 02	10	25	<5	> 15	<1	<1	5	3	0 10	<10	13 90	150	<1	0 01	<1	80	12	60	<20	77	< 01	<10	6	<10	<1	124

TOKLAT RESOURCES INC AK 95-853

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																													
Resplit:																													
R/S1	RS95-M10 0 0-5'	< 2	0 03	5	30	<5	> 15	1	2	53	10	0 16	<10	13 80	131	3	< 01	10	140	28	60	<20	67	< 01	<10	6	<10	1	304
R/S36	RS95-M10 69 5-70 5m	< 2	0 09	15	20	<5	> 15	<1	2	13	18	0 56	<10	13 70	125	<1	< 01	28	90	2	65	<20	76	< 01	<10	8	<10	2	369
R/S71	RS95-M11 28 1-29 1m	< 2	14 80	255	380	<5	5 49	36	7	138	61	0 91	<10	1 50	44	<1	< 01	375	5610	2880	35	<20	163	< 01	<10	114	<10	64	4819
Repeat:																													
1	RS95-M10 0 0-5'	< 2	0 03	5	25	<5	> 15	<1	1	46	12	0 15	<10	14 10	133	2	< 01	10	140	26	60	<20	68	< 01	<10	6	<10	1	301
10	RS95-M10 12 8-14 2m	< 2	0 03	10	35	<5	> 15	1	1	3	20	0 18	<10	14 20	122	<1	0 01	6	160	40	60	<20	88	< 01	<10	6	<10	1	397
19	RS95-M10 23 8-25 3m	0 2	0 05	10	20	<5	> 15	2	3	2	17	0 28	<10	14 60	129	<1	< 01	28	110	16	65	<20	66	< 01	<10	6	<10	<1	1792
36	RS95-M10 69 5-70 5m	< 2	0 09	15	20	<5	> 15	<1	2	11	18	0 56	<10	13 80	127	<1	< 01	27	90	2	65	<20	78	< 01	<10	8	<10	3	360
45	RS95-M10 78 7-80 2m	< 2	0 25	20	40	<5	> 15	1	3	7	51	0 72	<10	13 80	131	<1	< 01	39	190	8	65	<20	78	< 01	<10	12	<10	2	409
54	RS95-M11 4-5'	< 2	0 03	10	20	<5	> 15	<1	2	5	5	0 10	<10	14 20	108	<1	0 01	9	160	22	65	<20	74	< 01	<10	4	<10	1	250
71	RS95-M11 28 1-29 1m	< 2	11 30	240	345	<5	5 77	33	6	123	47	0 84	<10	1 80	43	<1	< 01	369	5120	2802	35	<20	148	< 01	<10	105	<10	58	4498
80	RS95-M11 37 3-38 3m	0 4	0 06	30	30	<5	> 15	6	2	3	58	0 60	<10	14 50	124	<1	0 01	20	180	44	75	<20	50	< 01	<10	7	<10	<1	673
Standard:																													
GEO'95		1 0	1 63	60	160	<5	1 59	<1	16	53	76	3 55	<10	0 93	638	<1	0 01	23	590	18	<5	<20	54	0 09	<10	67	<10	8	64
GEO'95		1 2	1 60	60	155	<5	1 60	<1	17	56	86	3 73	<10	0 89	638	<1	0 01	25	580	20	<5	<20	55	0 09	<10	64	<10	7	66

df/853
XLS/95Toklat#2

ECO-TECH LABORATORIES LTD
Frank J Pezzotti, A.Sc T
B C Certified Assayer

6-Oct-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC AK 95-869
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION. TIM TERMUENDE

120 Core samples received Sept. 16, 1995
PROJECT #. None given
SHIPMENT # None given

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	RS95-M12- 0-2'	4 4	0 35	15	60	<5	> 15	21	11	26	79	0 74	<10	12 00	274	<1	0 01	80	240	3804	65	<20	70	0 01	<10	19	<10	7	2575
2	RS95-M12- 2-3'	2 8	0.15	15	65	<5	> 15	23	7	20	67	0 43	<10	13 00	218	<1	< 01	70	230	1800	65	<20	82	< 01	<10	17	<10	7	1538
3	RS95-M12- 3-4'	0 4	0 03	10	25	<5	> 15	19	2	6	17	0 18	<10	14 30	197	<1	< 01	22	170	174	70	<20	81	< 01	<10	8	<10	3	1010
4	RS95-M12- 4-5'	0 6	0 09	5	30	<5	> 15	15	5	16	36	0 29	<10	13 90	220	<1	< 01	34	160	436	65	<20	82	< 01	<10	11	<10	4	850
5	RS95-M12- 5-6'	3 6	0 09	10	35	<5	> 15	16	3	8	27	0 26	<10	14 20	167	<1	< 01	31	170	2094	75	<20	66	< 01	<10	10	<10	3	626
6	RS95-M12- 6-7'	2 4	0 04	10	25	<5	> 15	14	4	10	18	0 18	<10	14 50	216	<1	< 01	21	120	1512	70	<20	81	< 01	<10	9	<10	3	558
7	RS95-M12- 7-8'	0 6	0 04	10	20	<5	> 15	18	3	17	17	0 19	<10	14 50	179	<1	< 01	22	120	204	65	<20	68	< 01	<10	10	<10	4	304
8	RS95-M12- 8-10'	1 0	0 03	15	20	<5	> 15	16	2	6	37	0 20	<10	14 70	131	<1	< 01	20	150	174	80	<20	71	< 01	<10	9	<10	3	426
9	RS95-M12- 3 0-4 1m	1 4	0 03	20	20	<5	> 15	10	2	10	50	0 19	<10	14 80	125	<1	< 01	28	260	470	80	<20	78	< 01	<10	8	<10	2	377
10	RS95-M12- 4 1-5 2m	1 2	0 02	20	25	<5	> 15	10	3	9	48	0 13	<10	14 50	117	<1	0 01	19	280	50	85	<20	81	< 01	<10	6	<10	3	288
11	RS95-M12- 5 2-6 2m	0 2	0 03	10	20	<5	> 15	14	4	9	12	0 13	<10	14 40	108	<1	0 01	24	250	40	70	<20	76	< 01	<10	6	<10	2	734
12	RS95-M12- 6 2-7 2m	0 4	0 04	15	20	<5	> 15	10	2	12	9	0 14	<10	14 20	117	<1	0 01	24	430	272	70	<20	81	< 01	<10	7	<10	2	268
13	RS95-M12- 7 2-8 2m	0 6	0 02	5	25	<5	> 15	11	3	23	9	0 16	<10	13 40	133	<1	0 01	19	240	278	65	<20	77	< 01	<10	6	<10	5	212
14	RS95-M12- 8 2-9 2m	1 2	0 03	15	25	<5	> 15	12	1	27	35	0 19	<10	13 80	128	<1	0 01	16	300	92	70	<20	80	< 01	<10	6	<10	3	170
15	RS95-M12- 9 2-10 2m	2 2	0 03	20	25	<5	> 15	11	<1	28	41	0 17	<10	13 90	141	<1	0 01	11	230	1130	90	<20	84	< 01	<10	6	<10	2	1369
16	RS95-M12- 10 2-11 3 m	0 8	0 05	20	30	<5	> 15	7	<1	12	48	0 18	<10	14 60	112	<1	0 01	26	210	90	80	<20	88	< 01	<10	7	<10	<1	576
17	RS95-M12- 11 3-12.3 m	0 6	0 03	10	30	<5	> 15	6	<1	9	18	0 21	<10	14 50	139	<1	0 01	7	330	72	70	<20	87	< 01	<10	7	<10	2	195
18	RS95-M12- 12 3-13 3 m	0 4	0 02	15	25	<5	> 15	5	<1	11	53	0 22	<10	> 15	124	<1	0 01	7	120	56	70	<20	77	< 01	<10	9	<10	<1	178
19	RS95-M12- 13 3-14 3 m	< 2	0 03	10	25	<5	> 15	7	<1	6	17	0 13	<10	15 00	123	<1	0 01	1	140	36	70	<20	84	< 01	<10	8	<10	<1	116
20	RS95-M12- 14 3-15 3 m	< 2	0 03	5	20	<5	> 15	6	<1	5	17	0 11	<10	14 90	107	<1	0 01	<1	240	20	65	<20	72	< 01	<10	7	<10	<1	100
21	RS95-M12- 15 3-16 3 m	1 4	0 03	15	20	<5	> 15	13	<1	8	43	0 18	<10	> 15	112	<1	0 01	3	300	84	80	<20	75	< 01	<10	5	<10	<1	166
22	RS95-M12- 16 3-17 4 m	< 2	0 02	20	30	<5	> 15	48	<1	6	48	0 17	<10	14 30	129	<1	0 01	6	210	96	75	<20	88	< 01	<10	6	<10	<1	7168
23	RS95-M12- 17 4-18 4 m	0 6	0 03	15	25	<5	> 15	6	<1	7	28	0 28	<10	14 50	124	<1	0 01	5	170	112	70	<20	87	< 01	<10	5	<10	<1	242
24	RS95-M12- 18 4-19 4 m	0 4	0 04	10	15	<5	> 15	5	<1	2	29	0 15	<10	14 10	102	<1	0 01	4	170	94	65	<20	91	< 01	<10	4	<10	<1	256
25	RS95-M12- 19 4-20 4 m	1 8	0 03	45	50	<5	> 15	16	<1	24	128	0 54	<10	13 00	171	<1	< 01	13	170	484	100	<20	88	< 01	<10	5	<10	<1	890
26	RS95-M12- 20 4-21 4 m	0 4	0 03	10	25	<5	> 15	2	<1	6	31	0 17	<10	14 30	98	<1	0 01	4	110	110	70	<20	79	< 01	<10	6	<10	<1	184
27	RS95-M12- 21 4-22.4 m	1 0	0 02	25	25	<5	> 15	5	<1	36	78	0 44	<10	12 90	95	<1	< 01	13	80	226	95	<20	69	< 01	<10	7	<10	<1	1134
28	RS95-M12- 22 4-23 5 m	< 2	0 03	20	25	<5	> 15	2	<1	9	34	0 25	<10	14 90	118	<1	< 01	5	110	66	70	<20	74	< 01	<10	7	<10	<1	218
29	RS95-M12- 23 5-24 5 m	0 6	0 02	25	35	<5	> 15	17	<1	22	42	0 40	<10	13 90	169	<1	0 01	14	90	276	75	<20	79	< 01	<10	10	<10	<1	4343

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
30	RS95-M12- 24 5-25 5 m	< 2	0 01	10	40	<5	> 15	3	<1	9	22	0 10	<10	14 60	153	<1	0 01	2	100	34	65	<20	78	< 01	<10	10	<10	<1	2846
31	RS95-M12- 25 5-26 5 m	0 4	0 01	15	35	<5	> 15	1	<1	18	16	0 11	<10	14 70	154	<1	0 02	<1	90	30	70	<20	84	< 01	<10	10	<10	<1	114
32	RS95-M12- 26 5-27 5 m	0 2	0 01	5	35	<5	> 15	1	<1	12	10	0 11	<10	14 90	157	<1	0 02	<1	70	36	65	<20	82	< 01	<10	8	<10	<1	81
33	RS95-M12- 27 5-28 5 m	< 2	0 02	20	50	<5	> 15	<1	<1	5	12	0 20	<10	14 30	129	<1	0 01	3	80	14	65	<20	94	< 01	<10	8	<10	<1	97
34	RS95-M12- 28 5-29 6 m	< 2	0 02	15	25	<5	> 15	7	<1	3	23	0 20	<10	14 90	104	<1	0 01	2	70	58	70	<20	82	< 01	<10	7	<10	<1	1496
35	RS95-M12- 29 6-31 1 m	0 4	0 02	15	25	<5	> 15	2	<1	14	24	0 29	<10	14 50	128	<1	< 01	3	70	106	70	<20	74	< 01	<10	9	<10	<1	167
36	RS95-M12- 31 1-32.6 m	0 2	0 02	10	20	<5	> 15	1	<1	4	18	0 16	<10	14 80	161	<1	< 01	<1	80	32	60	<20	84	< 01	<10	10	<10	<1	145
37	RS95-M12- 32 6-33 6 m	1 2	0 02	25	10	<5	> 15	2	<1	4	84	0 16	<10	> 15	141	<1	< 01	3	100	92	90	<20	91	< 01	<10	9	<10	1	170
38	RS95-M12- 33 6-34 6 m	0 2	0 03	20	15	<5	> 15	6	<1	5	58	0 21	<10	14 80	136	<1	< 01	4	100	60	75	<20	91	< 01	<10	12	<10	2	205
39	RS95-M12- 34 6-35 7 m	0 4	0 02	55	15	<5	> 15	6	<1	11	183	0 78	<10	14 30	174	<1	< 01	20	90	14	100	<20	93	< 01	<10	15	<10	2	567
40	RS95-M12- 35 7-36 7 m	25 8	0 02	265	15	<5	> 15	<1	<1	17	1068	0 36	<10	14 00	194	<1	< 01	6	40	166	375	<20	93	< 01	<10	15	<10	3	273
41	RS95-M12- 36 7-37 7 m	< 2	0 02	10	15	<5	> 15	<1	<1	3	6	0 09	<10	14 80	145	<1	< 01	<1	50	<2	60	<20	98	< 01	<10	11	<10	2	79
42	RS95-M12- 37 7-38 7 m	< 2	0 01	15	20	5	> 15	<1	<1	5	9	0 06	<10	14 40	116	<1	< 01	<1	70	<2	65	<20	92	< 01	<10	8	<10	<1	66
43	RS95-M12- 38 7-40 2 m	< 2	0 03	30	20	<5	> 15	<1	<1	4	21	0 52	<10	15 00	149	<1	< 01	11	230	2	70	<20	87	< 01	<10	8	<10	1	292
44	RS95-M12- 40 2-41 8 m	< 2	0 03	25	20	<5	> 15	8	<1	4	18	0 46	<10	> 15	179	<1	< 01	8	120	6	70	<20	86	< 01	<10	7	<10	2	373
45	RS95-M12- 41 8-43 3 m	0 4	0 02	15	15	<5	> 15	2	<1	8	14	0 23	<10	14 00	154	<1	< 01	1	90	12	65	<20	83	< 01	<10	5	<10	<1	156
46	RS95-M12- 43 3-44 3 m	< 2	0 03	30	15	<5	> 15	2	<1	8	23	0 40	<10	14 60	153	<1	< 01	4	130	10	75	<20	92	< 01	<10	10	<10	1	295
47	RS95-M12- 44 3-46 3 m	< 2	0 02	25	20	<5	> 15	3	<1	4	39	0 29	<10	14 50	156	<1	< 01	3	110	6	75	<20	88	< 01	<10	9	<10	<1	273
48	RS95-M12- 46 3-47 9 m	< 2	0 02	20	20	<5	> 15	8	<1	14	35	0 21	<10	13 90	105	<1	< 01	2	50	14	80	<20	85	< 01	<10	5	<10	<1	410
49	RS95-M12- 47 9-49 4 m	< 2	0 02	10	15	<5	> 15	<1	<1	5	4	0 09	<10	14 30	108	<1	< 01	<1	30	<2	60	<20	82	< 01	<10	5	<10	<1	93
50	RS95-M12- 49 4-50 9 m	< 2	0 01	15	15	<5	> 15	<1	<1	4	3	0 05	<10	> 15	76	<1	< 01	<1	60	<2	60	<20	55	< 01	<10	4	<10	<1	83
51	RS95-M12- 50 9-52 4 m	< 2	0 02	10	20	5	> 15	<1	<1	3	3	0 05	<10	14 40	91	<1	< 01	<1	60	<2	65	<20	81	< 01	<10	4	<10	<1	81
52	RS95-M12- 52.4-53 9 m	< 2	0 02	15	25	<5	> 15	3	<1	8	13	0 22	<10	13 90	127	<1	0 01	3	170	14	65	<20	87	< 01	<10	7	<10	<1	387
53	RS95-M12- 53 9-55 4 m	< 2	0 02	15	15	<5	> 15	2	<1	6	14	0 17	<10	14 00	76	<1	< 01	4	160	10	70	<20	74	< 01	<10	5	<10	<1	258
54	RS95-M12- 55 4-57 0 m	< 2	0 02	25	15	<5	> 15	1	<1	6	15	0 18	<10	14 30	79	<1	< 01	3	180	14	70	<20	76	< 01	<10	5	<10	<1	264
55	RS95-M12- 57 0-58 5 m	< 2	0 02	15	20	<5	> 15	<1	<1	5	13	0 15	<10	14 50	86	<1	0 01	3	170	2	70	<20	85	< 01	<10	8	<10	<1	268
56	RS95-M12- 58 5-59 5 m	< 2	0 03	90	25	<5	> 15	3	<1	7	154	0 85	<10	14 30	134	<1	< 01	12	390	26	155	<20	86	< 01	<10	10	<10	<1	779
57	RS95-M12- 59 5-61 0 m	14 0	0 02	245	20	<5	> 15	24	<1	17	1416	0 18	<10	13 60	91	<1	< 01	3	130	88	390	<20	71	< 01	<10	6	<10	<1	5833
58	RS95-M12- 61 0-62 5 m	0 6	0 02	35	20	<5	> 15	2	<1	4	47	0 30	<10	14 30	104	<1	< 01	3	190	22	95	<20	77	< 01	<10	7	<10	<1	572
59	RS95-M12- 62 5-63 5 m	1 6	0 03	50	15	<5	> 15	<1	<1	10	77	0 52	<10	14 30	124	<1	< 01	5	270	12	100	<20	82	< 01	<10	6	<10	<1	438
60	RS95-M12- 63 5-64 5 m	0 4	0 03	30	25	<5	> 15	2	<1	15	40	0 40	<10	14 10	108	<1	< 01	5	320	38	95	<20	75	< 01	<10	8	<10	1	407
61	RS95-M12- 64 5-65 5 m	0 6	0 02	60	20	<5	> 15	54	<1	6	185	0 55	<10	14 60	124	<1	< 01	9	200	52	135	<20	79	< 01	<10	7	<10	<1	9564
62	RS95-M12- 65 5-67 0 m	1 0	0 02	25	20	<5	> 15	2	<1	12	44	0 21	<10	14 70	119	<1	0 01	1	140	10	85	<20	72	< 01	<10	7	<10	<1	265
63	RS95-M12- 67 0-68 5 m	1 2	0 02	60	15	<5	> 15	3	<1	5	165	0 58	<10	14 60	94	<1	< 01	9	210	44	125	<20	75	< 01	<10	7	<10	<1	551
64	RS95-M12- 68 5-70 0 m	5 8	0 03	275	30	<5	> 15	58	<1	7	608	1 63	<10	14 00	138	<1	< 01	31	130	52	385	<20	66	< 01	<10	13	<10	<1	>10000
65	RS95-M12- 70 0-71 5 m	3 4	0 03	145	15	<5	> 15	24	<1	7	406	1 06	<10	14 80	103	<1	< 01	12	100	64	250	<20	74	< 01	<10	10	<10	<1	2707
66	RS95-M12- 71 5-73 0 m	2 0	0 02	45	20	<5	> 15	1	<1	7	100	0 36	<10	15 00	114	<1	0 01	3	130	14	105	<20	79	< 01	<10	5	<10	<1	461
67	RS95-M12- 73 0-74 5 m	< 2	0 02	30	20	<5	> 15	<1	<1	3	25	0 23	<10	14 70	104	<1	0 01	3	130	4	75	<20	86	< 01	<10	5	<10	<1	186
68	RS95-M13- 74 5-75 3 m	7 6	0 03	195	30	<5	> 15	5	<1	5	626	1 14	<10	13 70	217	<1	0 01	8	60	162	235	<20	82	< 01	<10	9	<10	<1	843
69	RS95-M13- 0-5'	5 8	0 46	40	80	<5	8 67	11	8	123	158	2 30	<10	4 83	176	27	< 01	59	300	2456	150	<20	27	< 01	<10	78	<10	2	845

TOKLAT RESOURCES INC. AK 95-869

ECO-TECH LABORATORIES LTD

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
70	RS95-M13- 5-10'	1 8	0 22	10	60	5	14 10	12	11	80	74	3 78	<10	7 85	187	35	< 01	71	340	1052	95	<20	42	< 01	<10	95	<10	<1	2105
71	RS95-M13- 3 0-5 7m	9 8	0 34	130	35	<5	> 15	144	12	54	1417	0 51	<10	11 70	250	<1	< 01	129	120	370	205	<20	59	< 01	<10	27	<10	<1	>10000
72	RS95-M13- 5 7-7 1m	6 2	0 08	50	60	<5	> 15	14	32	5	199	0 40	<10	14 80	352	<1	0 01	67	240	218	115	<20	87	< 01	<10	21	<10	13	3134
73	RS95-M13- 7 1-8 5m	4 4	0 07	20	40	<5	> 15	9	28	8	41	0 18	<10	> 15	281	<1	0 01	72	250	172	80	<20	85	< 01	<10	13	<10	10	2844
74	RS95-M13- 8 5-10 0m	2 2	0 03	20	30	<5	> 15	4	18	4	21	0 16	<10	> 15	262	<1	0 01	27	160	114	75	<20	83	< 01	<10	13	<10	10	238
75	RS95-M13- 10 0-11 6 m	< 2	0 02	10	20	<5	> 15	5	4	4	7	0 14	<10	> 15	175	<1	0 01	8	170	60	75	<20	66	< 01	<10	23	<10	12	165
76	RS95-M13- 11 6-13 1 m	< 2	0 02	5	20	5	> 15	6	5	4	5	0 09	<10	> 15	148	<1	0 01	8	90	54	75	<20	46	< 01	<10	22	<10	12	128
77	RS95-M13- 13 1-14 6 m	< 2	0 02	15	10	<5	> 15	3	2	5	5	0 09	<10	> 15	146	<1	< 01	10	260	56	75	<20	62	< 01	<10	16	<10	10	154
78	RS95-M13- 14 6-16 1 m	< 2	0 02	10	25	<5	> 15	1	1	11	8	0 11	<10	14 60	145	<1	0 01	11	350	62	80	<20	84	< 01	<10	10	<10	7	126
79	RS95-M13- 16 1-17 7 m	< 2	0 03	15	15	<5	> 15	3	3	4	11	0 14	<10	15 00	157	<1	0 01	15	200	80	75	<20	84	< 01	<10	7	<10	9	206
80	RS95-M13- 17 7-19 2 m	< 2	0 03	10	10	<5	> 15	5	3	6	12	0 15	<10	14 90	140	<1	< 01	20	360	106	75	<20	72	< 01	<10	6	<10	7	211
81	RS95-M13- 19 2-20 7 m	0 4	0 02	10	15	<5	> 15	4	2	5	12	0 10	<10	> 15	132	<1	< 01	14	150	112	80	<20	76	< 01	<10	7	<10	8	171
82	RS95-M13- 20 7-21 7 m	< 2	0 02	10	30	<5	> 15	2	1	4	11	0 15	<10	15 00	162	<1	< 01	23	210	130	70	<20	68	< 01	<10	10	<10	10	302
83	RS95-M13- 21 7-22 7 m	< 2	0 02	5	25	<5	> 15	4	1	5	9	0 12	<10	> 15	142	<1	0 01	14	200	94	80	<20	79	< 01	<10	7	<10	8	265
84	RS95-M13- 22 7-23 8 m	< 2	0 03	10	20	<5	> 15	4	2	44	18	0 22	<10	12.20	122	<1	< 01	22	140	158	70	<20	61	< 01	<10	5	<10	8	335
85	RS95-M13- 23 8-24 2 m	0 2	0 02	10	35	<5	> 15	2	2	4	10	0 17	<10	> 15	146	<1	0 01	19	380	242	80	<20	69	< 01	<10	4	<10	9	228
86	RS95-M13- 24 2-25 2 m	0 2	0 02	15	30	<5	> 15	<1	<1	5	5	0 15	<10	> 15	156	<1	0 01	16	200	192	75	<20	68	< 01	<10	7	<10	8	243
87	RS95-M13- 25 2-26 2 m	< 2	0 02	<5	30	<5	> 15	<1	<1	4	<1	0 10	<10	> 15	165	<1	0 01	11	120	98	75	<20	66	< 01	<10	8	<10	6	237
88	RS95-M13- 26 2-27 2 m	0 8	0 03	10	30	<5	> 15	4	2	4	17	0 12	<10	> 15	206	<1	0 01	29	140	208	75	<20	72	< 01	<10	9	<10	6	532
89	RS95-M13- 27 2-28 2 m	0 8	0 03	25	35	<5	> 15	4	15	5	27	1 31	<10	14 60	401	2	< 01	103	80	812	80	<20	73	< 01	<10	15	<10	10	1185
90	RS95-M13- 28 2-29 9 m	< 2	0 16	25	35	<5	> 15	3	24	7	22	1 96	<10	14 50	296	1	< 01	296	170	648	75	<20	65	< 01	<10	11	<10	10	4197
91	RS95-M13- 29 9-31 4 m	0 2	0 07	15	30	<5	> 15	2	11	7	16	0 94	<10	14 80	204	<1	< 01	128	250	276	75	<20	70	< 01	<10	9	<10	6	1663
92	RS95-M13- 31 4-32 9 m	< 2	0 03	15	25	<5	> 15	1	7	5	2	0 79	<10	> 15	182	<1	< 01	49	120	86	75	<20	73	< 01	<10	8	<10	3	494
93	RS95-M13- 32 9-34 4 m	< 2	0 03	10	25	<5	> 15	<1	6	4	5	0 48	<10	> 15	152	<1	< 01	52	190	62	80	<20	67	< 01	<10	6	<10	4	566
94	RS95-M13- 34 4-36 0 m	< 2	0 09	15	15	<5	> 15	1	9	2	18	0 64	<10	> 15	161	<1	< 01	83	210	36	75	<20	66	< 01	<10	8	<10	5	985
95	RS95-M13- 36 0-37 5 m	< 2	0 05	15	15	<5	> 15	2	6	6	27	0 41	<10	14 80	164	<1	< 01	46	190	74	75	<20	67	< 01	<10	8	<10	4	682
96	RS95-M13- 37 5-39 0 m	1 2	0 05	15	15	<5	> 15	5	4	7	54	0 18	<10	> 15	155	<1	< 01	23	450	44	80	<20	84	< 01	<10	6	<10	5	671
97	RS95-M13- 39 0-40 5 m	0 6	0 03	10	20	<5	> 15	2	2	3	14	0 17	<10	> 15	140	<1	< 01	18	180	32	80	<20	64	< 01	<10	6	<10	3	352
98	RS95-M13- 40 5-42 1 m	0 4	0 03	15	15	<5	> 15	2	2	3	8	0 21	<10	> 15	137	<1	< 01	35	210	28	85	<20	70	< 01	<10	5	<10	3	613
99	RS95-M13- 42 1-43 6 m	3 4	0 10	30	20	<5	> 15	136	9	5	409	0 62	<10	14 30	176	<1	< 01	82	100	116	105	<20	55	< 01	<10	9	<10	<1	>10000
100	RS95-M13- 43 6-45 1 m	< 2	0 06	20	40	<5	> 15	5	17	10	19	1 84	<10	14 50	269	2	0 01	151	130	22	75	<20	73	< 01	<10	6	<10	9	1190
101	RS95-M13- 45 1-46 6 m	0 6	0 02	5	15	<5	> 15	10	10	13	49	0 30	<10	14 50	219	<1	< 01	63	170	24	75	<20	53	< 01	<10	9	<10	2	3441
102	RS95-M13- 46 6-48 2 m	0 4	0 01	10	20	<5	> 15	3	5	6	14	0 43	<10	> 15	208	<1	< 01	42	110	32	80	<20	54	< 01	<10	10	<10	4	550
103	RS95-M13- 48 2-49 7 m	1 0	0 03	15	20	<5	> 15	5	13	10	14	0 56	<10	> 15	255	<1	< 01	64	80	124	85	<20	66	< 01	<10	10	<10	4	671
104	RS95-M13- 49 7-51 2 m	< 2	0 03	15	25	10	> 15	<1	18	7	8	1 43	<10	> 15	249	<1	< 01	173	60	36	75	<20	52	< 01	<10	11	<10	2	1128
105	RS95-M13- 51 2-54 2 m	< 2	0 03	10	25	<5	> 15	2	25	10	8	0 62	<10	> 15	418	<1	< 01	94	90	6	85	<20	54	< 01	<10	7	<10	<1	264
106	RS95-M13- 54 2-54 8 m	0 8	0 05	10	160	<5	> 15	8	218	5	32	2.60	<10	15 00	2965	7	< 01	575	240	40	80	<20	55	< 01	<10	16	<10	6	1113
107	RS95-M13- 54 8-56 0 m	< 2	0 03	10	15	<5	> 15	<1	6	5	<1	0 39	<10	> 15	221	<1	< 01	28	140	36	85	<20	64	< 01	<10	11	<10	<1	144
108	RS95-M13- 56 0-57 3 m	< 2	0 02	5	15	5	> 15	<1	5	2	<1	0 30	<10	> 15	189	<1	< 01	30	220	10	75	<20	67	< 01	<10	6	<10	<1	148
109	RS95-M13- 57 3-58 8 m	< 2	0 02	20	20	<5	> 15	<1	8	2	6	1 47	<10	> 15	172	1	< 01	112	180	40	85	<20	60	< 01	<10	7	<10	3	616

TOKLAT RESOURCES INC. AK 95-869

ECO-TECH LABORATORIES LTD

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
110	RS95-M13- 58 8-60 4 m	< 2	0 03	20	15	<5	> 15	<1	3	5	3	0 42	<10	> 15	229	<1	< 01	27	280	36	90	<20	77	< 01	<10	6	<10	<1	227
111	RS95-M13- 60 4-61 9 m	0 4	0 03	25	15	<5	> 15	2	3	4	15	0 43	<10	> 15	144	<1	< 01	32	270	36	90	<20	66	< 01	<10	6	<10	<1	290
112	RS95-M13- 61 9-63 4 m	0 4	0 02	25	15	<5	> 15	2	4	5	19	0 55	<10	> 15	141	<1	< 01	42	140	14	90	<20	61	< 01	<10	7	<10	<1	309
113	RS95-M13- 63 4-64 9 m	0 6	0 02	40	15	<5	> 15	2	4	1	35	0 45	<10	> 15	143	<1	< 01	27	160	56	95	<20	67	< 01	<10	8	<10	2	293
114	RS95-M13- 64 9-66 4 m	5 0	0 03	60	15	<5	> 15	23	6	5	147	1 02	<10	> 15	196	<1	< 01	68	160	252	110	<20	66	< 01	<10	12	<10	2	2243
115	RS95-M13- 66 4-67 9 m	2 4	0 02	35	10	<5	> 15	14	1	16	73	0 28	<10	> 15	159	<1	< 01	8	100	428	105	<20	55	< 01	<10	9	<10	<1	714
116	RS95-M13- 67 9-69 5 m	1 2	0 02	45	15	<5	> 15	4	1	10	75	0 33	<10	> 15	195	<1	< 01	11	100	122	125	<20	63	< 01	<10	5	<10	<1	219
117	RS95-M13- 69 5-71 0 m	0 6	0 02	30	20	<5	> 15	3	<1	3	34	0 19	<10	> 15	160	<1	< 01	5	160	46	105	<20	62	< 01	<10	5	<10	<1	148
118	RS95-M13- 71 0-72 5 m	< 2	0 02	20	10	<5	> 15	3	2	3	44	0 34	<10	> 15	159	<1	< 01	12	100	44	105	<20	59	< 01	<10	6	<10	<1	254
119	RS95-M13- 106 1-107 6 m	< 2	0 02	15	10	5	> 15	<1	<1	3	<1	0 06	<10	14 80	85	<1	< 01	<1	140	<2	80	<20	84	< 01	<10	4	<10	<1	31
120	RS95-M13- 109 1-110 0 m	< 2	0 02	15	10	<5	> 15	<1	<1	5	<1	0 11	<10	14 50	90	<1	< 01	3	110	2	85	<20	86	< 01	<10	5	<10	<1	43
QC/DATA																													
Resplit #.																													
RS1	RS95-M12- 0-2'	3 2	0 37	15	60	<5	> 15	20	11	25	82	0 75	<10	12 30	281	<1	0 01	83	250	3472	60	<20	74	0 01	<10	20	<10	6	2492
RS36	RS95-M12- 31 1-32 6 m	< 2	0 02	15	20	<5	> 15	1	<1	4	18	0 16	<10	> 15	160	<1	< 01	<1	80	28	65	<20	88	< 01	<10	10	<10	<1	144
RS71	RS95-M13- 3 0-5 7m	9 4	0 30	105	35	<5	> 15	136	13	62	1343	0 49	<10	11 00	252	<1	< 01	121	120	362	195	<20	58	< 01	<10	23	<10	<1	>10000
RS106	RS95-M13- 54 2-54 8 m	0 8	0 03	10	155	<5	> 15	7	213	8	27	2 49	<10	14 40	2857	5	< 01	567	210	36	80	<20	54	< 01	<10	14	<10	4	1079
Repeat #.																													
1	RS95-M12- 0-2'	4 2	0 35	15	60	<5	> 15	20	11	26	86	0 72	<10	12 10	270	<1	0 01	80	230	3774	60	<20	71	0 01	<10	19	<10	6	2543
19	RS95-M12- 13 3-14 3 m	< 2	0 03	5	25	<5	> 15	7	<1	5	16	0 13	<10	14 80	121	<1	0 01	1	150	36	65	<20	82	< 01	<10	7	<10	<1	116
36	RS95-M12- 31 1-32 6 m	0 4	0 02	15	20	<5	> 15	1	<1	4	17	0 15	<10	> 15	163	<1	< 01	1	70	30	65	<20	88	< 01	<10	10	<10	<1	144
45	RS95-M12- 41 8-43 3 m	< 2	0 02	15	20	<5	> 15	<1	<1	7	3	0 13	<10	14 40	121	<1	< 01	<1	150	<2	65	<20	88	< 01	<10	7	<10	3	126
54	RS95-M12- 55 4-57 0 m	< 2	0 03	10	20	<5	> 15	2	<1	6	15	0 17	<10	14 20	78	<1	< 01	4	170	12	75	<20	78	< 01	<10	5	<10	<1	261
63	RS95-M12- 67 0-68 5 m	1 0	0 03	60	20	<5	> 15	3	<1	6	164	0 58	<10	14 40	94	<1	< 01	9	200	60	125	<20	76	< 01	<10	7	<10	<1	544
70	RS95-M13- 5-10'	2 0	0 22	20	60	<5	14 70	12	12	81	77	3 95	<10	8 32	193	37	<.01	74	350	1120	95	<20	45	< 01	<10	99	<10	<1	2252
79	RS95-M13- 16 1-17 7 m	< 2	0 03	15	20	<5	> 15	3	3	5	11	0 13	<10	> 15	158	<1	0 01	15	200	78	70	<20	87	< 01	<10	7	<10	8	207
88	RS95-M13- 26 2-27 2 m	0 6	0 02	5	30	<5	> 15	4	2	3	15	0 10	<10	12.90	194	<1	0 01	27	120	194	80	<20	69	< 01	<10	7	<10	4	514
105	RS95-M13- 51 2-54 2 m	< 2	0 02	10	20	10	> 15	2	24	6	6	0 58	<10	14 90	404	<1	< 01	91	100	6	70	<20	50	< 01	<10	7	<10	<1	239
114	RS95-M13- 64 9-66 4 m	4 8	0 03	60	20	<5	> 15	22	6	5	147	1 00	<10	> 15	191	<1	< 01	67	160	252	110	<20	68	< 01	<10	12	<10	2	2239
Standard:																													
GEO-95		1 2	1 60	60	170	<5	1 62	<1	19	54	84	3 69	<10	1 10	644	<1	0 02	22	580	18	<5	<20	50	0 12	<10	66	<10	3	64
GEO-95		1 2	1 82	70	165	10	1 95	<1	19	64	92	4 13	<10	1 11	683	<1	0 02	28	670	24	10	<20	62	0 12	<10	81	<10	4	78
GEO-95		1 4	1 54	70	160	<5	1 61	<1	17	55	91	3 79	<10	0 87	656	1	< 01	28	590	20	5	<20	58	0 08	<10	69	<10	5	70
GEO-95		1 4	1 57	65	160	<5	1 69	<1	19	55	91	3 82	<10	0 85	647	<1	0 01	31	610	22	5	<20	50	0 09	<10	70	<10	4	72

ECO-TECH LABORATORIES LTD.
per Frank J Pezzotti, A.Sc T
B C Certified Assayer

df/840/869a
XLS/95Toklat

4-Oct-95

ECO-TECH LABORATORIES LTD
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-893
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

37 Core samples received September 16, 1995
PROJECT #. Not Given
SHIPMENT # Not Given

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	RS95- M14- 0'-5'	0 2	0 11	10	75	<5	> 15	<1	4	58	23	1 08	<10	8 56	214	20	0 01	18	190	106	50	<20	45	< 01	<10	49	<10	5	185
2	RS95- M14- 5'-10'	0 4	0 08	50	50	<5	> 15	4	3	30	26	1 23	<10	11 10	185	23	0 01	24	350	162	65	<20	66	< 01	<10	58	<10	5	421
3	RS95- M14- 34 4-35 9	0 4	0 03	<5	25	<5	> 15	6	7	5	13	0 47	<10	> 15	192	<1	0 01	48	250	86	65	<20	63	< 01	<10	6	<10	3	427
4	RS95- M14- 35 9-36 5	1 8	0 01	5	15	<5	9 45	2	4	109	16	0 28	<10	5 08	100	3	0 01	17	90	496	60	<20	24	< 01	<10	3	<10	<1	138
5	RS95- M14- 36 5-37 5	0 8	0 03	10	35	<5	> 15	2	3	5	14	0 10	<10	14 50	144	<1	0 02	18	220	30	65	<20	79	< 01	<10	6	<10	1	186
6	RS95- M14- 37 5-39 0	< 2	0 03	10	30	5	> 15	3	5	6	7	0 20	<10	> 15	229	<1	0 02	41	170	20	65	<20	81	< 01	<10	12	<10	3	322
7	RS95- M14- 39 0-40 5	< 2	0 03	10	30	<5	> 15	1	8	2	2	0 24	<10	> 15	276	<1	0 01	51	190	8	60	<20	83	< 01	<10	8	<10	2	409
8	RS95- M14- 40 5-42 0	< 2	0 03	5	30	<5	> 15	<1	4	6	1	0 16	<10	14 50	183	<1	0 02	26	110	12	60	<20	89	< 01	<10	10	<10	<1	230
9	RS95- M14- 42 0-44 5	0 2	0 02	5	35	<5	> 15	1	5	4	5	0 41	<10	> 15	220	<1	0 02	37	110	74	70	<20	73	< 01	<10	20	<10	3	308
10	RS95- M14- 44 5-46 0	0 4	0 02	5	35	<5	> 15	1	1	4	<1	0 14	<10	> 15	166	<1	0 02	10	70	42	65	<20	75	< 01	<10	8	<10	<1	130
11	RS95- M14- 46 0-47 5	0 4	0 02	20	35	<5	> 15	2	4	11	11	0 55	<10	> 15	186	<1	0 02	37	70	114	65	<20	62	< 01	<10	9	<10	2	307
12	RS95- M14- 47 5-49 0	0 2	0 01	10	30	<5	> 15	1	1	6	3	0 14	<10	> 15	176	<1	0 02	9	70	42	70	<20	69	< 01	<10	9	<10	<1	120
13	RS95- M14- 49 0-50 0	0 6	0 02	15	30	<5	> 15	3	3	5	10	0 50	<10	> 15	186	<1	0 02	30	60	86	65	<20	70	< 01	<10	22	<10	4	268
14	RS95- M14- 50 0-51 2	0 4	0 02	20	60	<5	> 15	4	37	30	64	0 57	<10	13 30	1759	<1	0 02	281	60	448	70	<20	51	< 01	<10	16	<10	3	962
15	RS95- M14- 51 2-53 6	0 4	0 03	35	60	<5	> 15	3	69	22	87	1 73	<10	13 80	1077	3	0 02	244	110	538	80	<20	59	< 01	<10	20	<10	6	1139
16	RS95- M14- 53 6-54 6	< 2	0 01	<5	35	<5	> 15	<1	1	100	8	0 44	<10	8 82	201	5	0 02	16	90	54	50	<20	43	< 01	<10	10	<10	1	144
17	RS95- M14- 54 6-57 3	4 4	0 01	15	45	<5	> 15	<1	1	17	27	0 38	<10	12 40	281	<1	0 01	30	60	1950	70	<20	63	< 01	<10	20	<10	3	386
18	RS95- M14- 57 3-58 4	< 2	0 02	220	75	<5	> 15	4	88	4	729	9 53	<10	12 20	818	13	0 01	676	<10	1514	145	<20	61	< 01	<10	14	<10	29	3682
19	RS95- M14- 58 4-60 0	0 6	0 02	40	40	<5	> 15	3	9	5	100	1 40	<10	> 15	329	<1	0 02	124	200	172	80	<20	67	< 01	<10	10	<10	7	704
20	RS95- M14- 60 0-61 2	0 8	0 02	60	70	<5	> 15	3	23	4	186	2 40	<10	14 40	441	2	0 01	201	230	142	85	<20	59	< 01	<10	8	<10	9	1195
21	RS95- M14- 61 2-63 4	0 6	0 02	25	35	<5	> 15	2	4	11	55	0 55	<10	> 15	202	<1	0 01	42	270	44	70	<20	62	< 01	<10	7	<10	3	402
22	RS95- M14- 63 4-65 0	1 6	0 02	25	30	<5	> 15	2	7	4	53	0 42	<10	> 15	257	<1	0 01	36	270	48	70	<20	48	< 01	<10	6	<10	3	405
23	RS95- M14- 107 6-109 1	0 4	0 04	10	30	<5	> 15	<1	1	3	2	0 30	<10	> 15	193	<1	0 02	8	60	2	65	<20	58	< 01	<10	9	<10	<1	84
24	RS95- M14- 109 1-110 6	0 8	0 04	40	30	<5	> 15	<1	<1	3	48	0 56	<10	> 15	210	<1	0 02	7	70	8	70	<20	64	< 01	<10	9	<10	<1	82
25	RS95- M14- 110 6-112 2	2 0	0 04	35	30	<5	> 15	<1	1	5	71	0 43	<10	> 15	255	<1	0 02	11	70	14	70	<20	62	< 01	<10	14	<10	1	111

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	RS95- M14- 112 2-113 7	< 2	0 03	25	35	<5	> 15	3	3	6	13	0 66	<10	14 30	332	<1	0 02	28	60	6	70	<20	60	< 01	<10	11	<10	<1	223
27	RS95- M14- 113 7-115 2	0 4	0 05	30	45	<5	> 15	3	7	4	4	1 21	<10	14 60	315	<1	0 01	60	70	40	60	<20	68	< 01	<10	21	<10	4	423
28	RS95- M14- 115 2-116 7	< 2	0 04	10	30	<5	> 15	4	6	2	1	0 81	<10	14 50	184	<1	0 01	41	70	4	65	<20	62	< 01	<10	8	<10	3	271
29	RS95- M14- 116 7-118 3	< 2	0 04	10	35	<5	> 15	3	3	1	<1	0 45	<10	> 15	196	<1	0 02	17	60	<2	65	<20	86	< 01	<10	11	<10	2	134
30	RS95- M14- 118 3-119 8	0 4	0 04	25	90	<5	> 15	6	16	2	6	1 09	<10	14 60	541	<1	0 01	74	70	6	60	<20	88	< 01	<10	9	<10	3	376
31	RS95- M14- 119 8-121 3	< 2	0 04	15	35	<5	> 15	<1	2	1	<1	0 44	<10	14 40	202	<1	0 02	14	60	<2	60	<20	78	< 01	<10	5	<10	<1	152
32	RS95- M14- 121 3-122 8	0 4	0 04	10	35	<5	> 15	1	1	3	2	0 35	<10	14 70	141	<1	0 01	6	90	<2	60	<20	70	< 01	<10	5	<10	<1	96
33	RS95- M14- 122 8-124 4	0 4	0 04	20	40	5	> 15	3	3	2	4	0 59	<10	14 40	185	<1	0 01	21	70	<2	60	<20	81	< 01	<10	5	<10	<1	181
34	RS95- M14- 124 4-125 9	0 6	0 03	30	40	<5	> 15	4	4	2	8	0 75	<10	14 50	258	<1	0 01	27	100	<2	65	<20	78	< 01	<10	9	<10	1	258
35	RS95- M14- 125 9-127 4	0 4	0 03	15	45	<5	> 15	2	5	9	3	0 82	<10	13 80	241	<1	0 02	25	80	<2	60	<20	78	< 01	<10	7	<10	<1	225
36	RS95- M14- 127 4-128 9	0 4	0 05	30	45	5	> 15	<1	1	2	<1	0 86	<10	13 30	231	<1	0 02	8	70	<2	60	<20	77	< 01	<10	6	<10	<1	76
37	RS95- M14- 128 9-130 5	0 2	0 04	25	45	<5	> 15	<1	<1	2	<1	0 78	<10	13 40	245	<1	0 02	5	80	<2	65	<20	112	< 01	<10	5	<10	<1	59
QC/DATA																													
Resplit #.																													
RS1	RS95- M14- 0'-5'	0 6	0 10	15	65	<5	> 15	<1	3	61	28	0 97	<10	9 06	201	18	0 01	21	180	90	50	<20	47	< 01	<10	48	<10	5	177
RS36	RS95- M14- 127 4-128 9	0 4	0 04	30	45	<5	> 15	<1	1	3	<1	0 90	<10	13 20	238	<1	0 02	9	70	<2	60	<20	80	< 01	<10	6	<10	<1	78
Repeat #.																													
1	RS95- M14- 0'-5'	0 4	0 11	15	80	<5	> 15	<1	3	55	34	1 02	<10	8 53	204	19	0 01	20	170	104	55	<20	46	< 01	<10	48	<10	4	185
10	RS95- M14- 44 5-46 0	< 2	0 01	10	35	<5	> 15	1	1	4	3	0 16	<10	> 15	166	<1	0 02	11	80	46	60	<20	75	< 01	<10	8	<10	<1	139
19	RS95- M14- 58 4-60 0	0 6	0 02	40	40	<5	> 15	3	8	4	98	1 39	<10	15 00	328	<1	0 02	124	190	172	75	<20	66	< 01	<10	10	<10	6	700
36	RS95- M14- 127 4-128 9	< 2	0 04	30	45	<5	> 15	<1	<1	2	<1	0 86	<10	13 40	231	<1	0 02	7	70	<2	65	<20	81	< 01	<10	6	<10	<1	76
Standard.																													
GEO-95		1 4	1 76	70	160	<5	1 65	<1	18	61	90	3 69	<10	0 88	676	<1	0 02	28	600	22	<5	<20	62	0 11	<10	65	<10	6	75
GEO-95		1 2	1 73	70	160	5	1 66	<1	18	62	84	3 70	<10	0 88	663	<1	0 02	25	590	20	<5	<20	59	0 11	<10	66	<10	7	72

ECO-TECH LABORATORIES LTD
Frank J Pezzotti, A.Sc T
B C Certified Assayer

df/869
XLS/95Toklat

4-Oct-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC AK 95-894
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION. TIM TERMUENDE

76 Core/Rock samples received September 16, 1995
PROJECT # Not Given
SHIPMENT #. Not Given

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	MBSR95- 4	< 2	0 19	85	210	15	0 18	<1	4	105	49	9 55	<10	0 04	30	87	< 01	29	1670	20	<5	60	111	< 01	10	173	<10	<1	141
2	MBSR95- 5	< 2	0 09	<5	360	15	0 05	1	7	154	75	12 80	<10	< 01	105	103	< 01	42	1070	<2	<5	100	31	< 01	30	203	<10	<1	278
3	MBSR95- 6	< 2	0 09	35	345	<5	0 02	<1	<1	52	20	4 65	<10	< 01	6	37	< 01	3	460	24	<5	20	10	< 01	10	126	<10	<1	24
4	MBSR95- 7	< 2	0 12	<5	235	15	0 03	1	5	50	48	12 40	<10	< 01	8	30	< 01	5	900	218	<5	80	6	< 01	30	254	<10	<1	77
5	TTRS95- 31	2 8	10 2	140	925	<5	2 52	172	67	10	5400	> 15	<10	1 28	343	12	< 01	1497	810	1138	5	40	11	< 01	10	36	<10	309	>10000
6	TTRS95- 32	>30	0 24	4150	160	<5	0 69	19	4	153	>10000	1 01	<10	0 34	75	4	< 01	46	100	1780	4820	40	2	< 01	<10	6	<10	7	2897
7	RS95-M15- 0-3'	27 4	1 73	280	1170	<5	3 4	44	14	81	2119	2 86	<10	1 98	501	<1	0 01	139	740	2524	385	<20	23	0 02	<10	59	<10	9	>10000
8	RS95-M15- 3-4'	14 2	2 01	210	1615	<5	4 13	27	16	87	1029	2 88	<10	2 38	472	7	0 01	167	640	2138	270	<20	23	0 02	<10	60	<10	11	6347
9	RS95-M15- 4-6'	11 2	> 15	220	1195	<5	2 75	24	24	37	1303	2 14	<10	1 47	321	1	< 01	643	1090	1358	190	<20	14	0 01	<10	82	<10	26	5907
10	RS95-M15- 6-7'	3 6	7 10	145	960	<5	0 31	6	34	68	492	2 62	<10	0 12	480	4	< 01	294	410	1382	40	40	3	< 01	<10	37	<10	9	1802
11	RS95-M15- 7-8'	4 4	> 15	180	960	<5	0 82	13	14	37	1015	1 65	<10	0 39	141	2	< 01	380	1010	1424	115	40	2	< 01	30	197	<10	24	3151
12	RS95-M15- 8-9'	10 0	9 11	235	995	<5	2 64	17	16	45	1219	1 93	<10	1 39	275	1	< 01	395	1020	2734	200	<20	12	< 01	10	71	<10	34	4116
13	RS95-M15- 9-10'	10 6	9 82	345	1120	<5	1 03	10	23	60	1321	1 75	<10	0 50	304	2	< 01	499	910	2108	205	20	6	< 01	10	60	<10	41	4185
14	RS95-M15- 10-11'	24 8	5 90	190	830	<5	4 57	17	171	81	2613	1 76	<10	2 46	1407	<1	< 01	639	750	1918	165	<20	12	< 01	<10	53	<10	56	4376
15	RS95-M15- 11-20'	23 2	6 05	190	775	<5	4 06	16	175	71	2584	1 79	<10	2 18	1426	1	< 01	633	750	1888	155	<20	10	< 01	<10	53	<10	56	4233
16	RS95-M15- 6 1-7 1m	4 6	0 97	390	95	<5	11 7	150	23	63	3318	1 65	<10	6 74	369	<1	< 01	281	190	646	325	<20	25	< 01	<10	17	<10	<1	>10000
17	RS95-M15- 7 1-8 1m	5 4	1 80	395	100	<5	> 15	36	15	54	1797	1 13	<10	10 20	180	<1	0 01	217	240	256	300	<20	35	< 01	<10	36	<10	14	6169
18	RS95-M15- 8 1-9 5m	1 4	0 28	145	50	<5	> 15	17	10	17	294	1 14	<10	13 20	208	<1	0 01	85	310	242	170	<20	47	< 01	<10	11	<10	10	1252
19	RS95-M15- 9 5-10 5m	0 6	0 12	65	55	<5	> 15	68	56	17	342	1 13	<10	12 90	602	<1	0 01	154	140	218	125	<20	48	< 01	<10	8	<10	7	9222
20	RS95-M15- 10 5-11 5 m	0 8	0 34	85	85	<5	> 15	23	5	11	260	0 43	<10	14 10	146	<1	0 01	81	130	192	90	<20	49	< 01	<10	11	<10	7	3361
21	RS95-M15- 11 5-11 7 m	1 8	0 38	355	140	<5	3 89	46	21	141	427	3 86	<10	2 16	201	<1	< 01	105	50	280	160	<20	11	< 01	<10	11	<10	<1	>10000
22	RS95-M15- 11 7-12 7 m	0 6	0 50	85	65	<5	> 15	20	5	10	156	0 56	<10	13 40	171	<1	0 02	57	170	78	90	<20	54	< 01	<10	18	<10	9	1374
23	RS95-M15- 12 7-13 7 m	0 6	0 35	45	55	<5	> 15	12	5	14	188	0 41	<10	13 50	120	<1	0 01	40	110	70	85	<20	43	< 01	<10	15	<10	10	521
24	RS95-M15- 13 7-14 7 m	7 2	0 20	120	40	<5	> 15	9	10	20	654	1 01	<10	13 10	155	<1	0 01	74	200	120	200	<20	53	< 01	<10	10	<10	9	1821
25	RS95-M15- 14 7-15 7 m	0 8	0 05	65	35	<5	> 15	42	12	16	214	0 78	<10	13 80	217	<1	0 01	64	240	104	100	<20	61	< 01	<10	8	<10	6	2008

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	RS95-M15- 15 7-16 6 m	< 2	0 08	95	180	<5	> 15	18	70	10	311	4 35	<10	12 40	721	<1	< 01	342	130	84	115	<20	56	< 01	<10	10	<10	12	8567
27	RS95-M15- 16 6-17 6 m	6 8	0 44	345	120	<5	> 15	5	8	28	1241	0 78	<10	11 90	166	<1	0 01	64	140	134	355	<20	45	< 01	<10	16	<10	6	1518
28	RS95-M15- 17 6-18 5 m	0 2	0 08	35	80	<5	> 15	2	3	11	85	0 34	<10	13 80	124	<1	0 01	21	110	8	80	<20	51	< 01	<10	10	<10	4	421
29	RS95-M15- 18 5-19 5 m	4 8	1 56	155	175	<5	> 15	12	11	51	459	0 99	<10	10 00	200	<1	0 01	154	510	158	165	<20	47	< 01	<10	32	<10	19	1299
30	RS95-M15- 19 5-20 5 m	0 2	0 22	45	45	<5	> 15	8	9	7	69	0 87	<10	14 00	187	<1	0 01	80	130	24	70	<20	60	< 01	<10	12	<10	12	629
31	RS95-M15- 20 5-21 5 m	0 6	1 23	90	100	<5	> 15	11	9	20	242	0 99	<10	11 90	176	<1	0 01	132	230	40	95	<20	57	< 01	<10	16	<10	9	876
32	RS95-M15- 21 5-22 5 m	1 2	0 18	65	65	<5	> 15	3	6	18	126	0 89	<10	13 70	242	<1	0 01	60	190	34	95	<20	79	< 01	<10	11	<10	4	522
33	RS95-M15- 22 5-23 5 m	7 4	0 03	35	45	<5	> 15	<1	1	16	29	0 29	<10	13 60	143	<1	0 01	11	120	34	75	<20	62	< 01	<10	8	<10	4	203
34	RS95-M15- 23 5-24 5 m	0 2	0 20	20	55	<5	> 15	1	2	15	27	0 22	<10	13 40	110	<1	0 01	49	190	12	65	<20	39	< 01	<10	9	<10	5	249
35	RS95-M15- 25 4-25 5 m	< 2	0 02	20	25	<5	> 15	2	2	12	20	0 24	<10	14 20	104	<1	0 01	14	540	6	70	<20	32	< 01	<10	9	<10	6	161
36	RS95-M15- 25 5-26 5 m	0 8	0 14	45	40	<5	> 15	3	12	6	97	0 35	<10	14 5	174	<1	0 01	42	100	8	100	<20	39	< 01	<10	10	<10	7	266
37	RS95-M15- 26 5-27 5 m	< 2	0 14	40	35	<5	> 15	1	7	7	46	0 44	<10	14 5	121	<1	0 01	46	180	10	75	<20	38	< 01	<10	9	<10	8	248
38	RS95-M15- 27 5-28 5 m	< 2	0 02	20	25	<5	> 15	<1	18	10	11	0 4	<10	14 5	173	<1	0 01	36	200	6	65	<20	36	< 01	<10	7	<10	6	179
39	RS95-M15- 28 5-29 5 m	< 2	0 02	25	25	<5	> 15	<1	5	7	2	0 23	<10	13 6	114	<1	0 01	19	110	4	65	<20	38	< 01	<10	6	<10	6	114
40	RS95-M15- 29 5-30 4 m	< 2	0 06	20	30	<5	> 15	12	16	5	22	1 03	<10	> 15	324	<1	0 01	113	270	12	70	<20	54	< 01	<10	7	<10	11	497
41	RS95-M15- 30 4-31 4 m	1 2	0 05	40	50	<5	> 15	26	42	2	177	5 35	<10	13 4	516	8	0 01	379	100	18	90	<20	53	< 01	<10	10	<10	27	1940
42	RS95-M15- 31 4-32 4 m	< 2	0 05	15	40	<5	> 15	22	29	3	8	2 05	<10	13 8	435	2	0 01	195	130	12	65	<20	62	< 01	<10	8	<10	17	933
43	RS95-M15- 32 4-33 4 m	1 8	0 09	15	45	15	> 15	21	41	8	22	4 79	<10	12 3	377	7	< 01	341	280	30	60	<20	54	< 01	<10	11	<10	27	1912
44	RS95-M15- 33 4-35 1 m	7 2	6 52	1020	155	<5	14 2	15	74	17	3235	5 38	<10	8 29	642	8	< 01	637	640	100	315	<20	37	< 01	<10	71	<10	90	3118
45	RS95-M15- 35 1-35 7 m	>30	0 80	>10000	160	<5	3 54	101	11	45	>10000	3 75	<10	1 75	68	<1	< 01	204	>10000	8928	>10000	<20	12	< 01	<10	8	<10	27	>10000
46	RS95-M15- 35 7-36 8 m	>30	0 25	2060	50	<5	14 9	28	14	44	>10000	0 99	<10	8 59	225	<1	< 01	64	<10	1276	5390	<20	32	< 01	<10	6	<10	<1	>10000
47	RS95-M15- 36 8-38 1 m	4 2	0 04	60	20	<5	> 15	5	7	56	263	0 39	<10	10 4	142	1	< 01	14	100	24	195	<20	38	< 01	<10	6	<10	3	548
48	RS95-M15- 38 1-39 0 m	26 6	6 90	320	510	<5	0 9	11	35	79	>10000	1 09	20	0 33	207	2	< 01	594	<10	396	610	<20	5	< 01	<10	110	<10	66	2418
49	RS95-M15- 39 0-40 0 m	2 0	3 68	95	120	<5	13	5	28	39	5511	1 85	<10	7 43	343	4	< 01	259	180	30	165	<20	27	< 01	<10	58	<10	34	914
50	RS95-M15- 40 0-40 5 m	3 0	2 23	85	65	<5	> 15	4	24	23	6417	1 55	<10	9 32	333	3	< 01	253	210	28	165	<20	32	< 01	<10	22	<10	42	709
51	RS95-M15- 40 5-41 5 m	< 2	8 13	90	270	<5	6 7	11	53	51	6617	1 53	<10	3 64	434	5	< 01	612	420	104	130	<20	18	< 01	<10	107	<10	135	1103
52	RS95-M15- 41 5-42 5 m	0 2	11 7	115	610	<5	0 68	13	22	68	3304	1 31	<10	0 21	168	3	< 01	677	970	122	80	40	7	< 01	10	184	<10	81	1373
53	RS95-M15- 42 5-43 5 m	0 4	3 37	115	90	<5	0 23	2	6	74	670	2 59	<10	0 07	26	7	< 01	184	690	56	40	20	25	< 01	<10	105	<10	4	666
54	RS95-M15- 43 5-44 2 m	< 2	13 0	165	130	<5	7 12	7	10	57	1117	2 61	<10	3 8	83	4	< 01	536	820	44	75	<20	24	< 01	<10	172	<10	14	1407
55	RS95-M15- 44 2-45 8 m	< 2	> 15	225	240	<5	0 74	18	54	47	2388	10 1	<10	0 2	267	14	< 01	976	520	<2	<5	60	16	< 01	40	272	<10	32	4456
56	RS95-M15- 45 8-47 3 m	< 2	0 40	35	65	<5	> 15	61	14	5	134	1 7	<10	14 2	417	<1	0 01	82	260	6	65	<20	63	< 01	<10	11	<10	28	1470
57	RS95-M15- 47 3-48 1 m	< 2	0 46	40	35	<5	> 15	12	9	4	123	1 27	<10	14 1	314	<1	0 01	66	140	4	70	<20	64	< 01	<10	11	<10	22	989
58	RS95-M15- 48 1-49 6 m	3 8	0 18	40	35	<5	> 15	47	13	5	174	1 72	<10	14 2	447	<1	0 01	86	170	4	75	<20	65	< 01	<10	6	<10	21	1047
59	RS95-M15- 49 6-51 2 m	6 0	0 10	25	35	<5	> 15	49	18	2	219	2 01	<10	14 3	579	<1	0 01	114	120	<2	75	<20	64	< 01	<10	10	<10	23	1069
60	RS95-M15- 51 2-52 7 m	2 6	0 32	80	30	<5	> 15	29	22	3	273	2 35	<10	13 9	495	2	0 01	145	150	34	100	<20	60	< 01	<10	15	<10	32	1213

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
61	RS95-M15- 52 7-53 7 m	6 2	0 19	255	40	<5	> 15	23	130	10	637	3 38	<10	13 9	1284	5	0 01	263	120	212	140	<20	60	< 01	<10	21	<10	47	2089
62	RS95-M15- 53 7-54 9 m	0 8	0 10	25	30	<5	> 15	15	25	5	53	1 05	<10	14 7	307	<1	0 01	65	100	<2	65	<20	59	< 01	<10	12	<10	10	568
63	RS95-M15- 54 9-56 4 m	0 8	0 17	30	25	<5	> 15	11	9	2	77	1 09	<10	14 5	199	<1	0 01	54	100	6	75	<20	57	< 01	<10	13	<10	8	543
64	RS95-M15- 56 4-57 9 m	< 2	0 14	40	25	<5	> 15	16	10	2	56	0 76	<10	14 8	209	<1	0 01	44	70	<2	70	<20	46	< 01	<10	8	<10	10	562
65	RS95-M15- 57 9-59 1 m	0 6	0 10	190	35	<5	> 15	15	17	12	69	1 55	<10	14 9	285	<1	0 01	74	60	<2	75	<20	50	< 01	<10	8	<10	12	968
66	RS95-M15- 59 1-59 5 m	0 8	0 03	20	25	<5	0 46	<1	2	196	37	0 47	<10	0 24	58	7	< 01	14	<10	<2	10	20	4	< 01	<10	<1	<10	<1	76
67	RS95-M15- 59 5-60 4 m	3 6	0 04	140	40	<5	> 15	8	10	19	128	1 25	<10	14 9	351	<1	0 01	69	60	18	80	<20	54	< 01	<10	7	<10	5	626
68	RS95-M15- 60 4-61 9 m	< 2	0 03	65	25	<5	> 15	5	11	16	22	0 85	<10	14 3	191	<1	0 01	58	60	<2	65	<20	49	< 01	<10	7	<10	3	655
69	RS95-M15- 61 9-63 4 m	< 2	0 02	40	215	5	> 15	<1	8	10	9	1 31	<10	14 6	224	<1	0 01	56	40	<2	65	<20	81	< 01	<10	8	<10	5	676
70	RS95-M15- 63 4-64 9 m	< 2	0 02	45	35	<5	> 15	2	11	14	3	1 21	<10	14 7	299	<1	0 01	67	60	<2	60	<20	64	< 01	<10	7	<10	3	797
71	RS95-M15- 64 9-66 4 m	< 2	0 07	30	45	10	> 15	8	26	7	19	3 73	<10	12 3	327	1	0 01	214	110	<2	55	<20	61	< 01	<10	6	<10	15	2524
72	RS95-M15- 66 4-68 0 m	0 8	0 03	65	35	<5	> 15	8	14	8	42	2 38	<10	13 4	242	<1	0 01	115	30	2	65	<20	60	< 01	<10	6	<10	8	1423
73	RS95-M15- 68 0-69 5 m	< 2	0 03	20	30	<5	> 15	13	7	6	33	1 18	<10	14	179	<1	0 01	68	150	2	60	<20	56	< 01	<10	7	<10	11	1041
74	RS95-M15- 69 5-71 0 m	0 2	0 03	30	35	<5	> 15	12	6	7	54	0 8	<10	13 9	177	<1	0 01	57	130	<2	65	<20	60	< 01	<10	8	<10	8	839
75	RS95-M15- 71 0-72 5 m	0 4	0 02	20	30	<5	> 15	5	2	2	24	0 41	<10	14 8	153	<1	0 01	28	160	<2	65	<20	78	< 01	<10	10	<10	5	507
76	RS95-M15- 72 5-74 4 m	>30	7 40	140	145	<5	12 8	10	17	16	1878	2 39	<10	7 51	214	<1	0 02	1173	160	62	55	<20	41	< 01	<10	37	<10	107	4307

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																													
Resplit #:																													
RS1	MBSR95- 4	< 2	0 21	90	225	15	0 20	<1	5	106	58	11 00	<10	0 06	25	91	< 01	33	1740	22	<5	40	121	< 01	20	184	<10	<1	155
RS36	RS95-M15- 25 5-26 5 m	1 0	0 14	50	35	<5	> 15	3	14	10	100	0 39	<10	> 15	180	<1	0 01	48	110	10	100	<20	40	< 01	<10	11	<10	8	287
RS71	RS95-M15- 64 9-66 4 m	< 2	0 07	25	45	10	> 15	8	24	8	18	3 4	<10	12 6	333	1	0 01	202	110	<2	50	<20	64	< 01	<10	6	<10	14	2357
Repeat #:																													
1	MBSR95- 4	< 2	0 18	80	215	15	0 17	<1	4	98	48	9 39	<10	0 03	28	86	< 01	29	1630	20	<5	60	109	< 01	<10	169	<10	<1	142
10	RS95-M15- 6-7'	3 6	6 84	145	965	<5	0 49	6	35	66	539	2 53	<10	0 18	492	4	< 01	297	380	1396	50	<20	3	< 01	<10	36	<10	9	1812
19	RS95-M15- 9 5-10 5m	0 4	0 08	65	45	<5	> 15	69	56	15	339	1 12	<10	13 10	597	<1	0 01	152	130	206	115	<20	47	< 01	<10	8	<10	6	9273
36	RS95-M15- 25 5-26 5 m	1 0	0 21	50	35	<5	> 15	3	13	6	109	0 41	<10	> 15	185	<1	0 01	51	110	8	105	<20	40	< 01	<10	11	<10	8	272
45	RS95-M15- 35 1-35 7 m	>30	0 82	>10000	165	<5	3 45	94	11	46	>10000	3 8	<10	1 66	68	<1	< 01	206	>10000	9068	>10000	<20	12	< 01	<10	9	<10	27	>10000
54	RS95-M15- 43 5-44 2 m	< 2	13 5	180	130	<5	7 39	8	11	59	1134	2 68	<10	4 01	87	7	< 01	550	890	42	70	<20	20	< 01	<10	177	<10	15	1427
71	RS95-M15- 64 9-66 4 m	0 2	0 08	30	40	5	> 15	8	26	8	22	3 76	<10	12 4	329	2	0 01	217	120	<2	50	<20	63	< 01	<10	6	<10	16	2532
Standard:																													
GEO-95		1 2	1 68	70	160	<5	1 64	<1	18	60	86	3 69	<10	0 87	647	<1	0 02	27	590	22	<5	<20	57	0 11	<10	64	<10	6	75
GEO-95		1 4	1 60	55	165	<5	1 85	<1	17	53	87	3 69	<10	1 03	649	<1	0 01	25	670	20	5	<20	52	0 08	<10	67	<10	6	72
GEO-95		1 2	1 68	60	170	<5	1 58	<1	17	53	85	3 65	<10	0 87	649	<1	0 01	25	580	20	10	<20	51	0 07	<10	66	<10	5	74

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B C Certified Assayer

df/869/894
XLS/95Toklat

4-Oct-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-896
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION. TIM TERMUENDE

15 Core/Rock samples received Sept. 16, 1995
PROJECT #. None given
SHIPMENT #· None given
Samples submitted by: Not Indicated

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	RS95-M16- 8 4-9 8	< 2	0 03	15	45	<5	> 15	<1	<1	13	<1	0 15	<10	14 4	181	<1	0 01	<1	140	4	70	<20	93	< 01	<10	16	<10	2	45
2	RS95-M16- 9 8-11 3	< 2	0 02	15	65	<5	> 15	<1	<1	26	<1	0 25	<10	12 9	166	<1	0 02	2	80	6	60	<20	87	< 01	<10	11	<10	2	69
3	RS95-M16- 11 3-12 6	0 8	< 01	50	35	<5	13 4	8	<1	105	78	0 46	<10	5 96	149	2	0 01	3	50	10	105	<20	38	< 01	<10	4	<10	<1	1777
4	RS95-M16- 12 6-14 0	0 2	0 02	25	45	<5	> 15	<1	<1	10	14	0 38	<10	14 3	128	<1	0 02	3	1100	4	70	<20	85	< 01	<10	9	<10	6	77
5	RS95-M16- 14 0-15 5	< 2	0 02	15	30	<5	> 15	<1	<1	8	<1	0 16	<10	14 5	149	<1	0 02	<1	150	<2	65	<20	97	< 01	<10	8	<10	<1	15
6	RS95-M16- 39 4-40 9	< 2	0 02	10	35	<5	> 15	<1	<1	4	<1	0 09	<10	> 15	125	<1	0 02	<1	140	10	70	<20	72	< 01	<10	8	<10	<1	15
7	RS95-M16- 40 9-41 7	< 2	< 01	<5	25	<5	4 99	<1	<1	196	<1	0 32	<10	2 51	55	7	0 01	4	20	20	35	<20	12	< 01	<10	2	<10	<1	16
8	RS95-M16- 41 7-43 2	< 2	0 02	5	30	5	> 15	<1	<1	5	<1	0 08	<10	14 9	121	<1	0 01	<1	120	10	70	<20	70	< 01	<10	7	<10	<1	16
9	RS95-M16- 93 1-94 6	< 2	0 03	20	35	5	> 15	<1	<1	9	<1	0 56	<10	14 2	247	<1	0 01	9	110	<2	55	<20	62	< 01	<10	9	<10	<1	51
10	RS95-M16- 94 6-96 0	< 2	< 01	20	40	<5	8 8	<1	1	148	1	0 9	<10	3 72	157	5	0 01	13	20	<2	35	<20	21	< 01	<10	3	<10	<1	74
11	RS95-M16- 96 0-97 3	< 2	0 03	25	35	<5	> 15	<1	<1	29	<1	0 66	<10	12 7	198	<1	0 01	7	40	<2	60	<20	61	< 01	<10	11	<10	<1	23
12	RS95-M16- 110 5-112 0	< 2	0 06	15	35	<5	> 15	<1	2	9	1	0 56	<10	12 7	167	<1	0 01	18	220	6	60	<20	46	< 01	<10	13	<10	<1	52
13	RS95-M16- 112.0-113 5	< 2	0 02	15	65	<5	> 15	<1	5	3	<1	0 29	<10	> 15	169	<1	0 01	12	50	12	65	<20	70	< 01	<10	4	<10	<1	70
14	RS95-M16- 118 3-119 8	< 2	0 04	20	40	<5	> 15	<1	<1	3	<1	0 43	<10	13 4	132	1	0 01	5	90	14	65	<20	63	< 01	<10	8	<10	<1	10
15	RS95-M16- 119 8-121 3	0 6	0 05	15	35	<5	> 15	<1	1	4	1	0 48	<10	13 7	152	<1	0 01	10	140	148	65	<20	60	< 01	<10	12	<10	<1	83
QC/DATA.																													
Resplit:																													
RS1	RS95-M16- 8 4-9 8	< 2	0 02	15	45	<5	> 15	<1	<1	8	<1	0 13	<10	14 6	179	<1	0 01	<1	160	2	70	<20	94	< 01	<10	16	<10	3	46
Repeat:																													
1	RS95-M16- 8 4-9 8	< 2	0 02	10	45	<5	> 15	<1	<1	13	<1	0 14	<10	14 5	181	<1	0 01	<1	140	2	65	<20	97	< 01	<10	16	<10	2	45
10	RS95-M16- 94 6-96 0	< 2	< 01	20	40	5	8 83	<1	1	151	1	0 91	<10	3 75	163	4	0 01	12	20	2	35	<20	23	< 01	<10	3	<10	<1	76
Standard:																													
GEO-95		1 2	1 66	60	170	<5	1 6	<1	17	54	87	3 73	<10	0 88	664	<1	0 01	25	590	20	<5	<20	52	0 08	<10	68	<10	7	67

df/894
XLS/95Toklat#2

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B·C Certified Assayer

27-Jul-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-437
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

250 Soil samples received July 11, 1995
PROJECT #: Rusty Springs
SHIPMENT #. RS02

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	L0 0+75E	0 4	0 33	10	660	<5	2 32	3	19	8	36	2 20	<10	0 37	3777	4	< 01	28	670	14	<5	<20	20	0 01	<10	23	<10	3	150
2	L0 1+00E	< 2	1 08	<5	315	<5	0 69	1	7	21	31	1 78	<10	0 37	187	2	0 01	26	590	20	5	<20	18	0 03	<10	43	<10	6	121
3	L0 1+25E	< 2	1 23	15	700	<5	0 37	<1	8	23	22	2 87	<10	0 29	364	24	< 01	22	800	22	<5	<20	16	0 02	<10	132	<10	3	106
4	L0 1+50E	0 4	1 31	15	720	<5	0 34	<1	5	24	19	2 61	<10	0 31	303	18	< 01	20	760	22	<5	<20	16	0 02	<10	100	<10	3	89
5	L0 1+75E	0 2	1 36	20	780	<5	0 89	1	10	26	37	3 14	<10	0 42	583	20	< 01	27	870	28	10	<20	21	0 02	<10	116	<10	5	149
6	L0 2+00E	< 2	0 94	15	510	<5	1 78	2	7	18	49	2 03	<10	0 46	507	7	< 01	25	730	20	15	<20	17	0 01	<10	63	<10	5	133
7	L0 2+25E	0 2	1 11	15	660	<5	1 30	1	8	23	36	2 51	<10	0 42	786	13	0 01	29	900	28	<5	<20	22	0 01	<10	81	<10	8	148
8	L0 2+50E	0 2	0 52	10	510	<5	2 34	4	3	10	48	1 22	<10	0 44	263	4	< 01	22	530	14	10	<20	18	< 01	<10	31	<10	4	195
9	L0 2+75E	0 8	0 89	25	810	<5	1 83	3	5	17	71	2 11	<10	0 46	323	9	< 01	32	760	38	20	<20	19	0 01	<10	62	<10	6	332
10	L0 3+00E	1 4	0 68	25	695	<5	1 79	2	4	13	81	1 68	<10	0 38	320	7	< 01	29	620	46	20	<20	18	0 01	<10	52	<10	6	286
11	L0 3+25E	1 2	1 07	40	765	<5	1 46	2	5	19	75	2 28	<10	0 40	315	11	< 01	41	780	68	25	<20	19	0 01	<10	77	<10	12	294
12	L0 3+50E	0 4	0 79	15	670	<5	1 38	4	4	14	45	1 69	<10	0 37	230	10	< 01	30	680	40	10	<20	23	< 01	<10	64	<10	9	160
13	L0 3+75E	< 2	1 20	20	695	<5	0 46	2	4	23	30	2 36	<10	0 30	177	20	< 01	37	850	106	5	<20	17	0 01	<10	121	<10	5	181
14	L0 4+00E	< 2	1 32	15	920	<5	0 82	1	7	25	45	2 67	<10	0 38	405	14	< 01	37	860	30	5	<20	20	0 02	<10	101	<10	10	182
15	L0 4+25E	< 2	0 48	10	845	<5	2 30	2	<1	9	32	1 02	<10	0 39	490	4	< 01	16	590	14	10	<20	18	< 01	<10	42	<10	5	76
16	L0 4+50E	0 2	0 49	10	750	<5	2 24	3	4	8	54	0 98	<10	0 36	784	7	< 01	24	550	16	10	<20	16	< 01	<10	36	<10	10	64
17	L0 4+75E	< 2	0 48	10	295	<5	2 11	1	3	10	27	1 13	<10	0 36	234	6	< 01	15	640	18	10	<20	17	< 01	<10	54	<10	7	59
18	L0 5+00E	< 2	0 31	5	240	<5	3 40	4	<1	4	55	0 65	<10	0 47	97	2	< 01	31	560	10	10	<20	23	< 01	<10	28	<10	7	66
19	L0 5+25E	< 2	0 31	10	140	<5	2 24	2	4	6	20	0 74	<10	0 36	205	3	< 01	16	480	18	5	<20	12	< 01	<10	34	<10	6	73
20	L0 5+50E	0 8	0 98	25	395	<5	1 70	7	12	19	68	2 33	<10	0 38	435	12	< 01	63	670	78	10	<20	19	0 01	<10	97	<10	16	320
21	L0 5+75E	0 4	0 30	<5	280	<5	3 22	3	<1	3	60	0 52	<10	0 49	223	<1	< 01	8	570	18	15	<20	15	< 01	<10	22	<10	5	88
22	L0 6+00E	0 8	0 66	15	175	<5	2 07	<1	4	13	61	1 35	<10	0 36	240	5	< 01	19	600	36	15	<20	18	0 01	<10	46	<10	8	115
23	L0 6+25E	< 2	1 26	20	165	<5	1 97	1	9	24	25	2 76	<10	0 66	430	14	0 01	35	580	48	5	<20	23	0 02	<10	92	<10	10	116
24	L0 6+50E	< 2	0 40	<5	75	<5	2 42	<1	2	5	9	0 60	<10	0 37	74	1	< 01	6	490	10	5	<20	14	< 01	<10	12	<10	4	48
25	L0 6+75E	< 2	1 06	15	185	<5	2 11	2	8	21	28	2 32	<10	0 45	635	14	< 01	39	890	60	5	<20	22	0 01	<10	77	<10	12	158

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	L2+00S 3+00E	< 2	1 13	15	880	<5	1 32	1	5	23	41	2 03	<10	0 44	216	6	< 01	28	740	30	10	<20	19	0 02	<10	75	<10	8	117
62	L2+00S 3+25E	< 2	0 86	35	640	<5	1 00	2	8	22	41	3 79	<10	0 27	602	29	< 01	36	730	90	5	<20	23	0 02	<10	143	<10	3	146
63	L2+00S 3+50E	0 6	0 91	20	1640	<5	2 10	3	7	22	57	3 21	<10	0 47	3752	24	0 01	32	820	30	5	<20	30	0 02	<10	108	<10	10	122
64	L2+00S 3+75E	< 2	1 02	15	1305	<5	1 64	<1	4	21	35	2 52	<10	0 48	1070	11	< 01	24	830	22	5	<20	24	0 01	<10	75	<10	6	104
65	L2+00S 4+00E	< 2	0 99	10	1135	<5	1 58	1	1	20	35	2 01	<10	0 46	249	6	< 01	24	750	20	<5	<20	23	0 01	<10	65	<10	5	100
66	L2+00S 4+25E	< 2	1 22	15	1090	<5	1 25	<1	3	23	31	2 86	<10	0 45	308	12	< 01	26	760	24	5	<20	24	0 02	<10	95	<10	5	110
67	L2+00S 4+50E	< 2	1 01	10	1355	<5	1 82	2	3	21	40	2 51	<10	0 48	567	10	< 01	32	860	36	5	<20	26	0 01	<10	70	<10	7	137
68	L2+00S 4+75E	< 2	1 00	25	1185	<5	1 68	2	5	21	40	2 77	<10	0 45	1016	15	< 01	34	820	40	5	<20	24	0 02	<10	94	<10	5	134
69	L2+00S 5+00E	< 2	0 47	15	1160	<5	2 45	2	5	10	27	1 86	<10	0 45	1996	7	< 01	19	630	20	5	<20	18	0 01	<10	43	<10	2	98
70	L2+00S 5+25E	< 2	0 55	10	960	<5	2 23	<1	1	11	26	1 63	<10	0 43	723	5	< 01	17	580	20	5	<20	17	< 01	<10	36	<10	3	93
71	L2+00S 5+50E	0 4	0 95	10	965	<5	1 77	1	3	19	45	2 23	<10	0 47	475	5	< 01	30	740	36	10	<20	21	0 02	<10	60	<10	7	112
72	L2+00S 5+75E	< 2	1 17	<5	705	<5	1 25	1	6	24	31	2 04	<10	0 56	214	4	0 01	33	740	36	10	<20	21	0 03	<10	62	<10	7	149
73	L2+00S 6+00E	< 2	0 65	55	1120	<5	2 17	<1	2	15	33	3 73	<10	0 38	476	12	< 01	23	660	36	<5	<20	19	0 01	<10	39	<10	3	114
74	L2+00S 6+25E	0 4	0 60	40	1170	<5	2 34	1	1	12	48	2 03	<10	0 34	156	5	< 01	27	710	38	5	<20	17	< 01	<10	39	<10	8	79
75	L2+00S 6+50E	0 6	0 80	30	995	<5	2 25	3	10	16	66	1 67	<10	0 41	646	6	< 01	60	800	54	10	<20	19	0 01	<10	59	<10	13	208
76	L2+00S 6+75E	< 2	0 38	5	770	<5	2 92	3	<1	6	32	0 72	<10	0 32	197	3	< 01	24	420	22	15	<20	33	< 01	<10	21	<10	5	91
77	L2+00S 7+00E	< 2	0 28	15	300	<5	4 24	4	1	5	14	0 74	<10	1 34	144	4	< 01	15	530	16	30	<20	23	< 01	<10	21	<10	3	123
78	L2+00S 7+25E	< 2	0 35	60	170	<5	1 53	4	5	8	39	2 43	<10	0 59	183	20	< 01	92	380	104	10	<20	13	< 01	<10	66	<10	2	474
79	L2+00S 7+50E	0 6	1 61	45	370	<5	5 35	14	36	19	83	2 71	<10	2 53	915	13	< 01	149	1080	78	25	<20	25	0 02	<10	70	<10	55	568
80	L2+00S 7+75E	0 8	2 19	40	280	<5	0 17	2	14	33	56	4 49	<10	0 27	263	24	< 01	79	620	36	<5	20	15	0 04	<10	112	<10	3	407
81	L2+00S 8+00E	< 2	1 44	30	190	<5	0 11	<1	8	33	36	4 83	<10	0 16	162	45	< 01	33	790	24	<5	20	29	0 04	<10	156	<10	<1	120
82	L2+00S 8+25E	< 2	2 87	15	180	5	0 12	<1	15	41	21	3 47	<10	0 49	314	3	0 02	31	310	26	<5	<20	12	0 05	<10	64	<10	1	1332
83	L3+00S 2+25E	1 0	0 71	80	345	<5	3 95	22	32	11	123	3 54	<10	1 21	891	6	0 01	221	800	102	25	<20	17	< 01	<10	30	<10	18	720
84	L3+00S 2+50E	< 2	0 29	10	175	<5	2 20	4	7	5	36	0 79	<10	0 33	559	2	< 01	35	570	22	15	<20	8	< 01	<10	12	<10	5	189
85	L3+00S 2+75E	0 4	1 11	<5	370	5	1 71	2	17	20	26	3 81	<10	0 48	1396	8	0 01	32	770	20	5	<20	14	0 01	<10	42	<10	3	180
86	L3+00S 3+25E	0 4	1 29	20	720	<5	0 98	1	11	25	48	3 29	<10	0 42	769	10	< 01	38	670	92	10	<20	19	0 02	<10	62	<10	7	181
87	L3+00S 3+50E	0 8	1 30	15	695	<5	1 00	2	9	25	43	2 59	<10	0 46	683	8	0 01	37	710	78	15	<20	18	0 02	<10	58	<10	6	197
88	L3+00S 3+75E	1 2	1 35	25	745	<5	0 88	4	14	27	53	2 78	<10	0 43	927	12	< 01	40	750	100	15	<20	18	0 02	<10	70	<10	6	222
89	L3+00S 4+00E	1 6	0 78	15	1510	<5	2 03	7	12	18	53	2 59	<10	0 40	8461	19	< 01	55	710	58	15	<20	20	0 02	<10	45	<10	5	192
90	L3+00S 4+25E	0 8	1 25	15	740	<5	1 52	3	6	25	61	1 80	<10	0 51	158	3	< 01	34	750	72	15	<20	20	0 02	<10	48	<10	9	216
91	L3+00S 4+50E	0 6	1 46	15	710	<5	1 14	3	15	28	75	2 92	<10	0 51	359	8	0 01	50	740	72	15	<20	20	0 02	<10	71	<10	13	189
92	L3+00S 4+75E	0 6	0 69	10	750	<5	2 59	5	14	13	53	1 63	<10	0 46	749	4	< 01	49	670	50	15	<20	19	0 01	<10	40	<10	8	141
93	L3+00S 5+00E	0 4	1 37	25	675	<5	1 49	3	10	25	45	2 73	<10	0 53	860	7	0 01	47	900	86	10	<20	20	0 02	<10	66	<10	11	195
94	L3+00S 5+25E	< 2	0 32	10	825	<5	3 74	3	4	5	36	0 93	<10	0 50	809	2	< 01	26	570	28	10	<20	19	< 01	<10	19	<10	5	109
95	L3+00S 5+50E	< 2	0 40	<5	530	<5	1 94	2	1	8	37	0 69	<10	0 33	74	<1	< 01	24	470	18	15	<20	12	< 01	<10	15	<10	3	52

TOKLAT RESOURCES INC AK 95-437

ECO-TECH LABORATORIES LTD

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
131	L1+00N 3+25E	< 2	1 20	30	965	<5	0 49	<1	2	24	22	2 61	<10	0 28	185	17	< 01	22	950	24	<5	<20	17	0 01	<10	137	<10	4	73
132	L1+00N 3+50E	< 2	0 27	<5	940	<5	0 73	1	<1	4	11	1 35	<10	0 17	37	9	< 01	6	1050	8	<5	<20	21	< 01	<10	10	<10	2	56
133	L1+00N 3+75E	< 2	0 12	10	1030	<5	1 42	<1	<1	2	12	0 60	<10	0 50	25	6	0 02	4	680	12	15	<20	37	< 01	<10	7	<10	<1	119
134	L1+00N 4+00E	< 2	0 21	<5	955	<5	1 49	<1	<1	4	12	0 48	<10	0 30	48	3	0 01	4	710	12	10	<20	33	< 01	<10	12	<10	1	59
135	L1+00N 4+25E	4 8	0 90	65	1255	<5	1 60	1	2	23	137	2 65	<10	0 29	261	35	0 01	47	1940	54	25	<20	27	< 01	<10	121	<10	12	298
136	L1+00N 4+50E	1 8	1 83	65	910	<5	1 41	<1	6	30	111	3 36	<10	0 43	240	24	< 01	63	800	52	55	<20	22	0 02	<10	120	<10	17	201
137	L1+00N 4+75E	< 2	0 92	45	235	<5	0 11	<1	6	25	25	5 74	<10	0 16	166	65	< 01	12	750	22	<5	40	12	0 04	<10	180	<10	<1	64
138	L1+00N 5+00E	< 2	0 75	15	315	<5	1 95	<1	2	10	31	1 30	<10	0 32	55	11	< 01	20	860	12	10	<20	23	< 01	<10	52	<10	11	119
139	L1+00N 5+25E	< 2	1 15	60	280	<5	0 13	<1	7	27	28	4 53	<10	0 27	170	78	< 01	20	840	36	<5	20	24	0 04	<10	126	<10	<1	63
140	L1+00N 5+50E	< 2	1 54	20	165	<5	0 10	<1	9	27	21	3 80	<10	0 26	218	45	< 01	19	500	22	<5	<20	12	0 04	<10	85	<10	<1	57
141	L1+00N 5+75E	< 2	2 19	15	155	<5	0 08	<1	13	36	23	3 85	<10	0 42	267	17	< 01	26	270	22	<5	<20	9	0 05	<10	75	<10	<1	71
142	L1+00N 6+00E	< 2	1 63	15	145	<5	0 06	<1	8	31	21	3 74	<10	0 31	254	18	< 01	18	200	22	<5	20	7	0 04	<10	86	<10	<1	63
143	L1+00N 6+25E	< 2	0 63	15	105	<5	0 04	<1	2	13	13	1 63	<10	0 03	65	8	< 01	5	270	16	<5	<20	5	0 03	<10	72	<10	<1	36
144	L1+00N 6+50E	< 2	1 50	<5	60	<5	0 05	<1	5	21	9	3 42	<10	0 14	116	6	< 01	9	150	16	<5	20	5	0 03	<10	84	<10	<1	35
145	L1+00N 6+75E	< 2	1 58	10	75	<5	0 05	<1	6	24	10	3 54	<10	0 20	131	10	< 01	11	200	16	<5	20	6	0 03	<10	68	<10	<1	42
146	L1+00N 7+00E	< 2	2 25	10	125	<5	0 07	<1	11	32	18	3 65	<10	0 33	219	9	< 01	22	260	20	<5	20	7	0 04	<10	73	<10	<1	62
147	L2+00N 0+25W	0 2	1 37	20	335	<5	1 54	4	20	26	53	2 92	<10	0 43	1479	9	< 01	61	930	92	<5	<20	18	0 02	<10	94	<10	9	215
148	L2+00N 0+50W	< 2	1 82	10	385	<5	1 11	3	12	31	72	2 41	<10	0 47	362	8	< 01	79	880	158	5	<20	19	0 02	<10	105	<10	10	230
149	L2+00N 0+75W	< 2	1 62	15	270	<5	0 93	2	8	29	55	2 35	<10	0 41	265	7	< 01	51	780	110	<5	<20	19	0 02	<10	83	<10	8	183
150	L2+00N 1+00W	< 2	1 59	10	245	<5	0 78	1	8	30	38	2 20	<10	0 44	150	5	< 01	35	690	52	5	<20	17	0 02	<10	75	<10	7	143
151	L2+00N 1+25W	< 2	1 60	10	295	<5	0 52	1	8	31	37	1 86	<10	0 42	118	3	< 01	34	560	48	5	<20	16	0 02	<10	86	<10	9	134
152	L2+00N 1+50W	< 2	1 52	20	345	<5	1 29	1	13	28	48	3 20	<10	0 44	648	10	< 01	56	880	132	<5	<20	19	0 01	<10	78	<10	9	223
153	L2+00N 1+75W	< 2	1 39	20	385	<5	0 83	<1	7	25	30	2 63	<10	0 41	209	5	< 01	31	700	46	<5	<20	18	0 02	<10	64	<10	5	143
154	L2+00N 2+00W	< 2	0 84	10	195	<5	0 72	<1	5	19	28	2 00	<10	0 24	134	3	< 01	23	570	20	<5	<20	25	0 01	<10	39	<10	6	88
155	L2+00N 0+25E	< 2	1 28	10	260	<5	1 26	2	10	25	30	2 70	<10	0 45	329	5	< 01	36	680	22	<5	<20	16	0 02	<10	75	<10	8	148
156	L2+00N 0+50E	0 6	0 88	5	505	<5	1 98	5	50	20	29	2 46	<10	0 41	5672	29	< 01	53	750	16	<5	<20	17	0 02	<10	76	<10	4	163
157	L2+00N 0+75E	< 2	1 00	10	230	<5	1 59	<1	10	21	22	2 14	<10	0 45	555	7	< 01	28	730	16	<5	<20	17	0 01	<10	73	<10	5	133
158	L2+00N 1+00E	< 2	1 12	15	200	<5	1 34	<1	10	23	21	2 63	<10	0 43	324	9	< 01	30	750	18	<5	<20	17	0 02	<10	87	<10	5	156
159	L2+00N 1+25E	< 2	1 05	15	235	<5	1 52	<1	9	22	28	2 32	<10	0 41	573	9	< 01	35	760	18	5	<20	17	0 02	<10	86	<10	6	142
160	L2+00N 1+50E	< 2	1 39	5	245	<5	0 88	1	7	30	40	1 75	<10	0 46	161	3	< 01	34	540	24	5	<20	18	0 02	<10	75	<10	9	160
161	L2+00N 1+75E	< 2	1 07	5	240	<5	1 40	2	7	23	39	1 96	<10	0 45	190	4	< 01	34	660	16	5	<20	17	0 02	<10	72	<10	8	138
162	L2+00N 2+00E	< 2	0 55	10	190	<5	2 50	1	5	11	24	1 24	<10	0 44	636	5	< 01	21	740	10	10	<20	17	< 01	<10	42	<10	4	108
163	L2+00N 2+25E	< 2	1 23	20	250	<5	1 08	2	12	25	31	2 66	<10	0 42	342	18	< 01	36	670	22	<5	<20	16	0 02	<10	95	<10	8	152
164	L2+00N 2+50E	< 2	1 54	40	460	<5	0 59	4	56	24	59	5 12	<10	0 13	2527	90	< 01	95	810	24	<5	20	18	0 02	<10	214	<10	4	246
165	L2+00N 2+75E	< 2	0 64	10	305	<5	2 97	4	24	7	58	1 50	<10	0 38	996	13	< 01	36	1120	6	10	<20	34	< 01	<10	48	<10	11	101

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
166	L2+00N 3+00E	< 2	0 52	10	315	<5	0 46	<1	2	8	14	1 91	<10	0 10	61	14	< 01	9	1090	10	<5	<20	18	< 01	<10	16	<10	4	73
167	L2+00N 3+25E	0 4	0 76	<5	360	<5	0 34	<1	<1	10	12	2 11	<10	0 09	12	13	< 01	6	1030	18	<5	<20	17	< 01	<10	20	<10	7	42
168	L2+00N 3+50E	0 4	2 77	40	330	<5	0 04	<1	1	31	52	3 12	30	0 04	44	38	< 01	15	1280	42	<5	<20	8	0 01	<10	114	<10	18	70
169	L2+00N 3+75E	< 2	2 07	190	355	<5	0 02	<1	6	34	70	6 82	<10	< 01	33	106	< 01	120	3930	76	<5	<20	28	0 01	<10	310	<10	8	649
170	L2+00N 4+00E	< 2	0 39	270	285	15	0 02	<1	5	38	37	12 40	<10	< 01	11	205	< 01	14	3950	28	<5	<20	17	0 01	<10	521	<10	<1	144
171	L2+00N 4+25E	< 2	1 18	15	110	<5	0 05	<1	5	22	15	4 09	<10	0 14	92	54	< 01	8	320	22	<5	<20	7	0 02	<10	120	<10	<1	40
172	L2+00N 4+50E	< 2	1 20	15	90	<5	0 05	<1	5	25	29	4 58	<10	0 11	129	84	< 01	9	400	32	<5	<20	5	0 02	<10	169	<10	<1	50
173	L2+00N 4+75E	< 2	1 97	15	70	<5	0 05	<1	7	28	13	3 89	<10	0 18	152	22	< 01	13	310	28	<5	<20	5	0 03	<10	96	<10	<1	47
174	L2+00N 5+00E	< 2	0 72	25	90	<5	0 02	<1	5	19	32	5 01	<10	0 02	113	68	< 01	8	310	16	<5	<20	4	0 04	<10	214	<10	<1	54
175	L2+00N 5+25E	< 2	1 48	15	70	<5	0 04	<1	5	24	11	3 27	<10	0 14	121	10	< 01	10	310	14	<5	<20	5	0 02	<10	77	<10	<1	47
176	L2+00N 5+50E	< 2	1 85	10	80	<5	0 05	<1	7	28	12	4 18	<10	0 26	177	6	< 01	14	240	16	<5	<20	5	0 02	<10	71	<10	<1	49
177	L3+00N 0+25W	< 2	1 40	15	305	<5	0 46	<1	9	24	22	2 71	<10	0 31	287	10	< 01	28	590	54	<5	<20	15	0 01	<10	96	<10	2	112
178	L3+00N 0+50W	< 2	1 13	10	365	<5	0 83	<1	23	20	30	2 41	<10	0 33	1291	16	< 01	25	800	38	<5	<20	20	0 01	<10	69	<10	4	103
179	L3+00N 0+75W	< 2	1 08	15	345	<5	0 83	<1	11	18	32	2 19	<10	0 32	615	12	< 01	25	830	32	<5	<20	22	0 01	<10	61	<10	5	89
180	L3+00N 1+00W	< 2	1 39	25	360	<5	0 75	1	14	24	43	3 66	<10	0 30	598	20	< 01	33	930	40	<5	<20	28	0 01	<10	99	<10	2	129
181	L3+00N 1+25W	< 2	1 37	15	320	<5	0 34	<1	6	23	24	2 53	<10	0 31	153	11	< 01	26	640	34	<5	<20	17	< 01	<10	81	<10	2	87
182	L3+00N 1+50W	< 2	1 37	15	340	<5	0 38	<1	11	23	24	2 92	<10	0 30	303	10	< 01	28	730	34	<5	<20	17	< 01	<10	77	<10	3	95
183	L3+00N 1+75W	< 2	1 30	5	350	<5	0 54	<1	19	22	26	2 60	<10	0 32	722	12	< 01	29	810	32	<5	<20	20	0 01	<10	71	<10	4	97
184	L3+00N 2+00W	< 2	1 06	10	255	<5	0 37	<1	6	18	15	1 87	<10	0 28	224	8	< 01	20	580	28	<5	<20	14	< 01	<10	55	<10	2	77
185	L3+00N 0+25E	< 2	1 05	10	280	<5	1 25	3	8	20	25	2 20	<10	0 41	367	8	< 01	26	670	34	<5	<20	17	0 01	<10	68	<10	3	164
186	L3+00N 0+50E	< 2	0 93	5	340	<5	1 64	4	8	19	32	2 05	<10	0 45	535	6	< 01	32	720	28	5	<20	18	0 01	<10	56	<10	6	152
187	L3+00N 0+75E	< 2	0 93	10	225	<5	1 59	2	6	19	23	1 88	<10	0 45	370	5	< 01	21	730	22	10	<20	17	< 01	<10	51	<10	5	131
188	L3+00N 1+00E	< 2	1 07	10	280	<5	1 17	3	12	22	29	2 09	<10	0 45	895	6	< 01	31	660	32	10	<20	16	0 01	<10	64	<10	6	145
189	L3+00N 1+25E	< 2	0 89	15	235	<5	2 13	3	7	18	34	1 99	<10	0 50	494	6	< 01	27	760	24	10	<20	18	< 01	<10	54	<10	6	133
190	L3+00N 1+50E	< 2	0 43	15	170	<5	3 59	4	4	9	24	1 02	<10	0 54	707	3	0 01	20	880	12	15	<20	17	< 01	<10	24	<10	3	129
191	L3+00N 1+75E	< 2	0 80	10	210	<5	2 86	3	5	15	35	1 68	<10	0 52	112	3	< 01	33	890	28	10	<20	17	< 01	<10	60	<10	8	142
192	L3+00N 2+00E	< 2	0 77	15	215	<5	3 50	6	10	15	56	1 98	<10	0 93	410	3	< 01	58	900	32	15	<20	17	< 01	<10	65	<10	11	246
193	L3+00N 2+25E	< 2	0 24	20	100	<5	8 44	3	3	4	25	0 79	<10	4 27	88	1	< 01	27	420	30	45	<20	22	< 01	<10	37	<10	8	191
194	L3+00N 2+50E	< 2	0 33	<5	145	<5	7 54	16	4	6	103	0 37	<10	3 73	49	<1	< 01	72	500	42	40	<20	24	< 01	<10	50	<10	20	331
195	L3+00N 2+75E	< 2	0 87	10	215	<5	4 54	7	14	15	66	1 94	<10	1 52	375	4	< 01	82	820	30	15	<20	18	< 01	<10	61	<10	16	365
196	L3+00N 3+00E	< 2	0 99	15	215	<5	2 77	7	17	19	51	2 47	<10	0 58	654	8	< 01	92	990	28	5	<20	17	0 01	<10	73	<10	14	461
197	L3+00N 3+25E	< 2	1 30	20	225	<5	1 44	3	16	25	38	2 70	<10	0 43	378	15	< 01	57	690	30	10	<20	16	0 01	<10	103	<10	10	177
198	L3+00N 3+50E	< 2	0 84	15	180	<5	1 98	3	7	18	28	1 89	<10	0 42	250	16	< 01	32	820	20	<5	<20	19	< 01	<10	102	<10	8	106
199	L3+00N 3+75E	< 2	0 48	15	165	<5	3 09	1	5	9	25	1 06	<10	0 47	271	9	0 01	18	660	16	10	<20	22	< 01	<10	75	<10	6	68
200	L3+00N 4+00E	< 2	0 45	10	155	<5	1 29	<1	3	12	15	1 03	<10	0 28	33	7	< 01	14	550	16	5	<20	15	< 01	<10	47	<10	3	156

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
201	L3+00N 4+25E	< 2	0 41	<5	140	<5	0 35	2	2	7	10	1 16	<10	0 05	40	15	< 01	9	590	10	<5	<20	10	< 01	<10	39	<10	<1	62
202	L3+00N 4+50E	< 2	0 87	30	125	5	0 06	<1	5	18	22	4 05	<10	0 09	140	41	< 01	11	440	18	<5	<20	6	0 03	<10	138	<10	<1	56
203	L3+00N 4+75E	< 2	1 18	<5	155	<5	0 07	<1	3	19	12	2 39	<10	0 05	32	11	< 01	8	550	18	<5	<20	6	< 01	<10	53	<10	<1	27
204	L3+00N 5+00E	< 2	2 07	15	95	<5	0 07	<1	10	33	17	4 36	<10	0 39	293	4	< 01	20	250	18	<5	<20	7	0 04	<10	63	<10	<1	61
205	L4+00N 0+25W	< 2	1 36	10	250	<5	0 64	<1	10	26	29	2 69	<10	0 40	166	5	< 01	31	550	32	<5	<20	15	0 01	<10	66	<10	7	127
206	L4+00N 0+50W	< 2	1 46	15	285	<5	0 85	<1	12	26	32	3 09	<10	0 41	347	8	< 01	35	800	40	<5	<20	19	0 01	<10	78	<10	6	108
207	L4+00N 0+75W	< 2	0 65	10	245	<5	2 11	2	4	14	28	1 53	<10	0 39	393	4	< 01	21	800	18	10	<20	22	< 01	<10	39	<10	4	77
208	L4+00N 1+00W	< 2	0 50	10	275	<5	3 08	2	6	9	36	1 31	<10	0 43	712	4	< 01	24	760	14	10	<20	32	< 01	<10	33	<10	6	85
209	L4+00N 1+25W	< 2	1 32	<5	275	<5	1 02	1	12	26	27	1 97	<10	0 39	453	6	< 01	28	800	40	<5	<20	26	0 01	<10	55	<10	7	98
210	L4+00N 1+50W	< 2	0 90	<5	285	<5	2 06	2	12	17	24	1 97	<10	0 45	1753	7	< 01	26	980	24	<5	<20	29	0 01	<10	38	<10	5	118
211	L4+00N 1+75W	< 2	0 89	<5	285	<5	1 69	2	18	17	25	2 80	<10	0 39	1855	11	< 01	23	800	24	<5	<20	27	0 01	<10	49	<10	4	120
212	L4+00N 2+00W	< 2	0 68	5	305	<5	2 23	1	15	14	29	1 81	<10	0 44	2228	10	< 01	20	1050	16	5	<20	27	< 01	<10	40	<10	5	78
213	L4+00N 0+25E	< 2	0 67	5	210	<5	2 76	1	8	13	24	1 59	<10	0 48	756	4	< 01	21	830	14	10	<20	21	< 01	<10	33	<10	4	83
214	L4+00N 0+50E	< 2	0 70	<5	295	<5	2 58	2	13	15	26	1 96	<10	0 49	2146	6	< 01	35	820	14	5	<20	20	0 01	<10	40	<10	3	156
215	L4+00N 0+75E	< 2	0 89	10	205	<5	2 13	1	9	16	27	2 10	<10	0 48	538	6	< 01	28	750	18	10	<20	18	0 01	<10	48	<10	4	116
216	L4+00N 1+00E	< 2	1 41	<5	260	<5	0 74	2	14	29	52	2 57	<10	0 48	127	6	< 01	52	610	34	<5	<20	16	0 02	<10	81	<10	12	152
217	L4+00N 1+25E	< 2	0 95	15	215	<5	2 20	1	17	18	33	2 31	<10	0 51	313	5	< 01	33	580	20	5	<20	16	0 01	<10	55	<10	7	125
218	L4+00N 1+50E	< 2	0 49	5	180	<5	3 41	2	5	9	30	1 02	<10	0 53	255	2	< 01	24	740	10	15	<20	21	< 01	<10	28	<10	4	67
219	L4+00N 1+75E	< 2	0 18	<5	135	<5	3 99	7	3	3	22	0 45	<10	0 54	267	3	< 01	15	560	2	15	<20	20	< 01	<10	9	<10	2	85
220	L4+00N 2+00E	< 2	0 19	<5	145	<5	4 07	4	5	3	44	0 40	<10	0 54	223	2	0 01	23	640	4	15	<20	19	< 01	<10	18	<10	4	78
221	L4+00N 2+25E	3 8	1 67	15	235	<5	3 49	5	30	24	118	3 00	20	1 56	197	8	< 01	130	920	62	20	<20	19	0 01	<10	79	<10	26	312
222	L4+00N 2+50E	< 2	0 44	5	150	<5	2 93	<1	2	5	27	0 86	<10	0 41	135	2	< 01	19	460	14	10	<20	13	< 01	<10	15	<10	3	67
223	L4+00N 2+75E	< 2	0 50	15	125	<5	0 09	<1	2	11	11	2 32	<10	0 01	39	20	< 01	6	420	14	<5	<20	2	0 02	<10	100	20	<1	21
224	L4+00N 3+00E	< 2	1 19	15	300	5	0 16	1	8	24	22	4 78	<10	0 22	179	27	< 01	25	700	22	<5	<20	10	0 02	<10	137	<10	<1	64
225	L4+00N 3+25E	< 2	0 75	10	75	<5	0 06	<1	3	11	5	1 84	10	0 07	45	6	< 01	5	180	14	<5	<20	<1	0 04	<10	64	<10	<1	25
226	L4+00N 3+50E	< 2	0 95	<5	105	5	0 14	<1	4	14	6	2 59	20	0 11	92	6	< 01	6	220	18	<5	<20	4	0 03	<10	66	<10	<1	31
227	L4+00N 3+75E	< 2	1 42	10	235	15	0 07	2	7	33	12	6 05	30	0 23	179	23	< 01	15	720	26	<5	<20	10	0 03	<10	99	<10	<1	57
228	L4+00N 4+00E	0 6	0 95	<5	220	<5	2 00	3	8	15	21	2 04	10	0 48	617	9	< 01	25	850	4	40	<20	44	< 01	10	38	<10	3	84
229	L4+00N 4+25E	< 2	0 47	10	200	<5	3 06	2	3	8	43	1 03	<10	0 48	473	4	< 01	25	600	8	10	<20	14	< 01	<10	38	<10	4	77
230	L4+00N 4+50E	0 8	1 52	15	185	<5	1 06	3	16	28	78	3 16	10	0 68	448	3	0 01	61	780	26	10	<20	14	0 02	<10	69	<10	16	331
231	L4+00N 4+75E	0 8	1 29	10	160	<5	2 54	7	19	21	85	2 64	10	0 94	651	6	< 01	86	790	32	25	<20	14	0 02	<10	68	<10	18	456
232	L4+00N 5+00E	< 2	0 92	<5	105	<5	2 80	2	6	12	19	1 84	<10	0 49	473	4	< 01	17	850	16	10	<20	12	0 01	<10	44	<10	7	163
233	L4+00N 5+25E	< 2	1 65	<5	195	<5	1 21	1	10	22	17	3 31	10	0 42	426	5	< 01	33	540	52	15	<20	12	0 02	<10	79	<10	6	146
234	L4+00N 5+50E	1 6	0 73	20	130	<5	7 61	6	9	13	56	1 25	10	3 65	484	7	< 01	79	1450	20	55	<20	23	< 01	<10	65	<10	21	304
235	BL 0+25N	< 2	0 39	10	95	5	5 55	4	5	6	20	1 03	<10	2 06	526	<1	< 01	27	660	48	35	<20	13	< 01	<10	21	<10	5	297

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
236	BL 0+50N	0 8	1 11	25	800	<5	1 79	9	31	20	58	7 41	<10	0 44	3174	12	< 01	43	780	26	<5	<20	14	0 01	<10	99	<10	3	489
237	BL 0+75N	0 4	1 30	10	690	10	1 23	4	28	22	30	9 31	<10	0 38	2669	21	< 01	36	710	20	<5	<20	18	0 01	<10	90	<10	<1	188
238	BL 1+00N	0 4	1 00	10	670	10	1 62	3	40	18	38	6 99	<10	0 34	2708	22	< 01	33	770	18	<5	<20	17	0 01	<10	82	<10	4	158
239	BL 1+25N	1 4	1 23	5	330	<5	1 52	2	12	24	87	1 87	<10	0 41	481	5	< 01	52	730	232	10	<20	17	0 01	<10	60	<10	7	194
240	BL 1+50N	< 2	1 14	10	220	<5	1 21	<1	7	24	36	2 38	<10	0 41	443	9	< 01	37	690	68	<5	<20	16	0 01	<10	63	<10	4	159
241	BL 1+75N	< 2	0 94	<5	215	<5	2 03	1	8	18	28	2 15	<10	0 49	457	6	< 01	30	740	28	5	<20	15	0 01	<10	66	<10	4	145
242	BL 2+00N	< 2	1 36	15	225	<5	1 51	2	10	22	44	2 57	<10	0 42	347	7	< 01	50	800	116	10	<20	13	0 01	<10	87	<10	8	181
243	BL 2+25N	< 2	1 12	<5	230	<5	1 58	3	11	22	32	2 28	<10	0 47	611	5	< 01	37	680	30	10	<20	12	0 01	<10	71	<10	8	165
244	BL 2+50N	< 2	1 11	<5	255	<5	1 15	2	11	22	25	2 97	<10	0 40	433	9	< 01	34	690	32	<5	<20	15	0 01	<10	74	<10	6	151
245	BL 2+75N	0 4	1 37	20	300	<5	1 18	2	10	23	30	2 54	<10	0 40	676	10	< 01	34	740	50	5	<20	17	0 01	<10	84	<10	5	149
246	BL 3+00N	< 2	1 55	<5	345	<5	0 82	1	11	24	27	2 68	<10	0 39	405	12	< 01	32	760	48	<5	<20	17	0 01	<10	87	<10	4	159
247	BL 3+25N	< 2	1 29	15	350	<5	0 81	1	11	21	28	2 52	<10	0 35	415	13	< 01	29	800	36	<5	<20	19	0 01	<10	81	<10	3	117
248	BL 3+50N	< 2	2 14	25	365	<5	0 68	<1	17	26	40	3 96	<10	0 35	407	18	< 01	46	910	46	<5	<20	15	0 01	<10	119	<10	2	130
249	BL 3+75N	< 2	0 83	<5	230	<5	2 00	<1	8	15	33	1 68	<10	0 42	366	4	< 01	30	710	16	10	<20	16	< 01	<10	45	<10	5	91
250	BL 4+00N	< 2	1 03	10	205	<5	1 86	<1	7	19	21	2 01	<10	0 46	389	4	< 01	24	810	18	<5	<20	16	0 01	<10	48	<10	4	97
QC/DATA:																													
Repeat #.																													
1	L0 0+75E	0 6	0 35	10	655	<5	2 58	4	21	7	33	2 30	<10	0 41	3980	4	0 01	30	690	12	<5	<20	22	0 01	<10	26	<10	4	157
10	L0 3+00E	1 2	0 71	30	690	<5	1 75	3	4	14	82	1 70	<10	0 39	308	8	< 01	30	630	48	20	<20	17	0 01	<10	54	<10	6	294
19	L0 5+25E	< 2	0 32	<5	135	<5	2 19	3	4	6	20	0 77	<10	0 35	204	3	< 01	16	460	18	10	<20	13	< 01	<10	35	<10	6	71
28	L0 7+50E	< 2	1 12	10	80	<5	0 05	<1	3	17	12	2 45	<10	0 06	63	10	< 01	8	210	20	<5	20	6	0 02	<10	82	<10	<1	40
36	L1+00S 3+25E	< 2	0 81	10	290	<5	2 33	2	6	17	41	1 83	<10	0 63	421	4	< 01	27	670	34	10	<20	18	0 01	<10	47	<10	8	158
45	L1+00S 5+50E	0 2	0 92	20	290	<5	1 92	2	6	19	51	1 97	<10	0 45	375	8	< 01	37	740	40	10	<20	18	0 01	<10	62	<10	11	178
54	L1+00S 7+75E	< 2	2 38	25	465	<5	0 11	<1	10	37	26	4 69	<10	0 33	251	19	< 01	31	700	22	<5	<20	17	0 03	<10	98	<10	<1	87
63	L2+00S 3+50E	0 6	0 87	25	1495	<5	2 19	2	7	21	59	3 11	<10	0 47	3741	22	0 01	32	840	28	5	<20	33	0 02	<10	104	<10	10	127
71	L2+00S 5+50E	< 2	0 89	15	970	<5	1 87	2	3	18	46	2 23	<10	0 49	506	7	< 01	31	700	36	10	<20	18	0 01	<10	59	<10	8	117
80	L2+00S 7+75E	0 8	2 17	45	290	<5	0 15	1	15	34	60	4 74	<10	0 26	280	26	< 01	85	660	42	5	40	15	0 03	<10	117	<10	3	441
89	L3+00S 4+00E	1 6	0 70	15	1540	<5	2 15	6	12	16	55	2 40	<10	0 41	8459	16	< 01	51	690	54	10	<20	21	0 02	<10	41	<10	5	187
98	L3+00S 6+25E	< 2	0 26	10	560	<5	2 50	2	2	5	26	0 64	<10	0 36	774	2	< 01	22	540	10	10	<20	16	< 01	<10	14	<10	3	115
106	L3+00S 8+25E	< 2	0 31	15	535	<5	2 66	9	<1	6	75	0 65	<10	0 40	193	1	< 01	31	490	26	15	<20	13	< 01	<10	16	<10	5	220
115	L1+00N 1+25W	< 2	1 11	10	350	<5	0 83	2	12	20	29	2 93	<10	0 38	576	5	< 01	29	610	24	<5	<20	16	0 02	<10	49	<10	5	140
124	L1+00N 1+50E	< 2	1 28	5	500	<5	0 24	<1	3	21	25	2 16	<10	0 25	85	9	< 01	25	620	28	<5	<20	15	0 01	<10	65	<10	3	99

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
133	L1+00N 3+75E	< 2	0 11	<5	1025	<5	1 43	<1	<1	2	11	0 58	<10	0 50	24	6	0 02	4	670	6	15	<20	36	< 01	<10	7	<10	<1	125
141	L1+00N 5+75E	< 2	2 17	15	160	<5	0 08	<1	13	36	23	3 83	<10	0 41	263	18	< 01	26	270	20	<5	20	8	0 05	<10	75	<10	<1	71
150	L2+00N 1+00W	< 2	1 46	<5	230	<5	0 73	1	7	28	36	2 05	<10	0 41	141	5	< 01	32	660	50	<5	<20	16	0 02	<10	71	<10	6	134
159	L2+00N 1+25E	< 2	1 11	5	255	<5	1 65	1	10	23	31	2 48	<10	0 43	660	10	< 01	36	800	18	<5	<20	19	0 01	<10	92	<10	7	147
168	L2+00N 3+50E	0 2	2 82	40	345	<5	0 03	<1	1	31	54	3 23	30	0 04	42	39	< 01	15	1290	42	<5	40	10	< 01	20	113	<10	18	71
176	L2+00N 5+50E	< 2	1 84	<5	80	5	0 05	<1	7	28	11	4 16	<10	0 26	177	7	< 01	13	250	16	<5	<20	5	0 02	<10	72	<10	<1	51
185	L3+00N 0+25E	< 2	1 07	15	280	<5	1 34	3	8	20	26	2 21	<10	0 44	371	8	< 01	27	670	34	<5	<20	17	0 01	<10	70	<10	3	166
194	L3+00N 2+50E	< 2	0 36	<5	145	<5	7 87	17	4	6	105	0 39	<10	3 81	52	<1	< 01	74	500	42	45	<20	22	< 01	<10	52	<10	20	331
203	L3+00N 4+75E	< 2	1 16	5	155	<5	0 05	<1	3	18	11	2 35	<10	0 03	38	10	< 01	7	550	16	<5	<20	7	< 01	<10	52	<10	<1	28
211	L4+00N 1+75W	< 2	0 91	<5	310	<5	1 74	2	21	17	30	2 91	<10	0 40	1976	12	< 01	26	830	24	<5	<20	30	0 01	<10	52	<10	5	123
220	L4+00N 2+00E	< 2	0 21	5	160	<5	4 22	3	6	3	50	0 46	<10	0 58	246	2	< 01	26	670	6	20	<20	22	< 01	<10	20	<10	6	82
229	L4+00N 4+25E	< 2	0 46	5	200	<5	3 07	3	3	8	41	1 08	<10	0 47	489	4	< 01	24	610	8	10	<20	12	< 01	<10	38	<10	3	78
238	BL 1+00N	0 6	0 94	20	680	5	1 73	3	40	17	38	7 21	<10	0 33	2751	24	< 01	32	740	16	<5	<20	21	0 01	<10	82	<10	3	152
246	BL 3+00N	0 2	1 53	5	335	<5	0 81	<1	11	24	27	2 67	<10	0 37	406	12	< 01	33	710	48	<5	<20	15	0 01	<10	87	<10	4	155
Standard:																													
GEO'95		1 4	1 75	65	160	<5	1 67	<1	18	62	88	4 05	<10	0 94	666	<1	0 02	26	660	22	<5	<20	58	0 12	<10	79	<10	5	72
GEO'95		1 0	1 63	70	165	<5	1 58	<1	17	58	83	3 83	<10	0 87	665	<1	0 02	26	610	20	<5	<20	55	0 11	<10	75	<10	5	73
GEO'95		1 0	1 57	65	155	<5	1 56	<1	17	57	81	3.78	<10	0 83	622	<1	0 02	26	620	18	<5	<20	54	0 11	<10	75	<10	4	75
GEO'95		1 0	1 69	70	155	<5	1 58	<1	18	58	86	3 93	<10	0 88	651	<1	0 02	25	590	24	<5	<20	54	0 11	<10	77	<10	4	73
GEO'95		1 0	1 62	65	150	<5	1 54	<1	17	53	84	3 73	<10	0 83	636	<1	0 01	24	590	20	<5	<20	52	0 09	<10	70	<10	6	72
GEO'95		1 0	1 61	55	155	<5	1 57	<1	18	55	84	3 85	<10	0 85	685	<1	0 01	27	590	18	5	<20	54	0 09	<10	71	<10	5	72
GEO'95		1 0	1 64	65	150	<5	1 54	<1	17	54	81	3 80	<10	0 82	652	<1	0 01	26	590	20	5	<20	54	0 09	<10	71	<10	6	71

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B C Certified Assayer

df/437A/B/C
XLS/95Toklat

6-Oct-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-852
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

89 Soil samples received Sept. 16, 1995
PROJECT #: None given
SHIPMENT #: None given

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	L2+00S-8+75E	< 2	2 10	30	180	<5	0 12	<1	13	33	20	3 21	<10	0 40	328	11	< 01	23	350	24	<5	<20	13	0 04	<10	59	<10	<1	61
2	L2+00S-9+00E	< 2	1 10	35	100	5	0 06	<1	7	24	17	3 59	<10	0 22	161	25	< 01	14	530	16	<5	<20	11	0 03	<10	131	<10	<1	63
3	L2+00S-9+25E	< 2	0 66	85	220	5	0 04	<1	4	22	21	4 74	<10	0 13	116	118	< 01	10	760	36	<5	<20	50	0 03	<10	204	<10	<1	36
4	L2+00S-9+50E	< 2	0 39	<5	65	<5	0 03	<1	1	7	9	0 87	<10	0 01	24	8	< 01	4	910	10	<5	<20	6	< 01	<10	21	<10	<1	38
5	L4+00S-5+00E	0 8	0 88	25	495	<5	2 46	3	8	18	50	1 82	<10	0 54	709	4	0 03	42	820	34	15	<20	23	0 01	<10	44	<10	7	192
6	L4+00S-5+25E	0 4	0 75	20	565	<5	2 40	2	5	15	52	1 51	<10	0 49	823	3	< 01	42	690	22	15	<20	21	< 01	<10	37	<10	6	182
7	L4+00S-5+50E	< 2	0 18	5	315	<5	3 50	3	2	3	28	0 48	<10	0 54	561	2	0 02	21	470	4	10	<20	19	< 01	<10	12	<10	2	141
8	L4+00S-5+75E	0 4	0 38	15	405	<5	3 48	2	4	7	27	1 10	<10	0 56	642	3	0 02	24	680	14	15	<20	18	< 01	<10	20	<10	3	194
9	L4+00S-6+00E	0 8	0 69	30	575	<5	4 44	4	7	13	74	1 72	<10	1 82	1090	2	< 01	48	780	32	30	<20	23	0 01	<10	36	<10	10	213
10	L4+00S-6+25E	1 0	1 06	20	375	<5	1 97	3	7	22	90	1 63	<10	0 64	119	2	< 01	63	880	50	20	<20	21	0 01	<10	61	<10	14	219
11	L4+00S-6+50E	0 8	0 58	15	495	<5	3 03	4	10	12	68	2 09	<10	0 50	909	5	< 01	62	810	24	10	<20	22	< 01	<10	34	<10	7	174
12	L4+00S-6+75E	< 2	0 21	5	325	<5	3 89	4	3	4	35	0 57	<10	0 61	943	2	0 02	36	740	8	20	<20	25	< 01	<10	11	<10	2	138
13	L4+00S-7+00E	0 4	0 40	10	340	<5	3 03	6	14	8	59	1 09	<10	0 49	1267	10	0 01	54	720	10	15	<20	29	< 01	<10	36	<10	7	193
14	L4+00S-7+25E	0 4	1 25	20	415	<5	1 25	1	11	29	59	2 50	<10	0 41	350	16	< 01	56	1170	24	<5	<20	32	0 01	<10	110	<10	10	167
15	L4+00S-7+50E	0 2	0 94	30	330	<5	0 12	<1	4	18	48	2 57	<10	0 09	124	25	< 01	34	470	32	<5	<20	23	0 02	<10	113	<10	1	140
16	L4+00S-7+75E	0 4	0 33	10	725	<5	1 78	9	2	4	18	0 67	<10	0 31	81	6	0 02	13	400	10	15	<20	25	< 01	<10	23	<10	4	165
17	L4+00S-8+00E	< 2	0 14	15	50	<5	3 60	9	<1	1	44	0 32	<10	0 49	174	2	0 01	16	570	<2	15	<20	<1	< 01	<10	10	<10	<1	241
18	L4+00S-8+25E	2.2	0 56	40	85	<5	3 90	3	4	8	123	1 12	<10	0 59	267	4	< 01	32	630	62	20	<20	21	< 01	<10	39	<10	8	134
19	L4+00S-8+50E	0 8	0 54	30	120	<5	3 79	4	4	9	100	0 89	<10	0 52	497	11	< 01	26	760	16	20	<20	23	< 01	<10	58	<10	7	103
20	L4+00S-8+75E	< 2	1 56	25	105	10	0 16	<1	7	31	24	4 30	<10	0 24	179	39	< 01	16	440	18	<5	<20	16	0 03	<10	137	<10	<1	57
21	L4+00S-9+00E	< 2	1 12	35	105	5	0 06	<1	6	26	30	4 93	<10	0 13	96	42	< 01	12	440	14	<5	<20	21	0 03	<10	204	<10	<1	56
22	L4+00S-9+25E	< 2	0 70	20	65	<5	0 05	<1	4	15	13	2 71	<10	0 09	70	22	< 01	7	210	10	<5	<20	12	0 04	<10	123	<10	<1	29
23	L4+00S-9+50E	< 2	1 73	50	185	5	0 09	<1	10	32	30	4 70	<10	0 30	306	25	< 01	18	740	18	<5	<20	19	0 03	<10	120	<10	<1	59
24	L4+00S-9+75E	< 2	1 11	60	95	10	0 04	<1	6	30	21	4 26	<10	0 14	106	30	< 01	11	500	16	<5	<20	18	0 03	<10	156	<10	<1	41
25	L4+00S-10+00E	< 2	0 68	20	95	5	0 03	<1	3	16	20	2 79	<10	0 03	55	22	< 01	7	340	16	<5	<20	9	0.02	<10	141	<10	<1	28

TOKLAT RESOURCES INC. AK 95-852

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	L4+00S-10+25E	< 2	0 85	50	160	5	0 05	<1	6	36	44	5 72	<10	0 15	131	70	< 01	11	920	18	<5	<20	33	0 03	<10	196	<10	<1	44
27	L5+00S-5+00E	< 2	1 11	5	375	5	0 63	1	6	22	33	2 22	<10	0 36	186	7	< 01	35	740	24	<5	<20	21	0 01	<10	61	<10	6	125
28	L5+00S-5+25E	< 2	1 40	15	425	<5	0 61	2	9	28	59	2 29	<10	0 38	187	6	< 01	51	610	32	<5	<20	15	0 01	<10	84	<10	6	148
29	L5+00S-5+50E	0 4	1 12	10	480	<5	1 08	2	9	24	35	2 34	<10	0 40	562	10	< 01	37	920	22	5	<20	24	0 01	<10	63	<10	6	147
30	L5+00S-5+75E	0 6	1 32	20	940	<5	0 74	<1	31	30	55	3 73	<10	0 37	2471	21	< 01	54	1000	26	<5	<20	25	0 02	<10	98	<10	12	141
31	L5+00S-6+00E	0 2	1 30	15	710	<5	0 59	1	5	27	50	2 07	<10	0 37	340	7	< 01	40	780	30	<5	<20	24	0 01	<10	74	<10	8	120
32	L5+00S-6+25E	0 2	0 99	30	795	<5	0 50	<1	3	22	35	2 44	<10	0 36	146	10	< 01	26	730	20	20	<20	21	0 02	<10	66	<10	4	108
33	L5+00S-6+50E	0 8	1 25	25	1075	<5	0 48	<1	2	27	47	2 44	<10	0 39	196	9	< 01	31	730	22	25	<20	22	0 02	<10	74	<10	6	125
34	L5+00S-6+75E	1 4	0 97	30	875	<5	1 59	3	1	21	60	2 65	<10	0 43	119	10	< 01	30	810	20	15	<20	22	< 01	<10	70	<10	5	101
35	L5+00S-7+00E	1 2	1 05	20	610	<5	1 67	2	4	22	83	1 89	<10	0 47	257	4	< 01	39	790	30	20	<20	21	0 01	<10	55	<10	10	144
36	L5+00S-7+25E	1 6	0 90	35	340	<5	3 42	5	15	19	102	3 58	<10	1 39	731	11	< 01	78	700	58	25	<20	22	0 01	<10	70	<10	13	324
37	L5+00S-7+50E	0 4	0 13	10	130	<5	3 27	5	1	3	35	0 35	<10	0 48	205	3	0 05	19	460	12	20	<20	12	< 01	<10	10	<10	1	68
38	L5+00S-7+75E	0 8	0 28	10	215	<5	3 21	7	1	6	123	0 57	<10	0 37	88	2	0 01	41	550	20	20	<20	14	< 01	20	27	<10	7	134
39	L5+00S-8+00E	3 2	0 41	50	125	<5	2 47	1	3	10	82	1 21	<10	0 34	214	6	0 01	26	640	86	35	<20	17	< 01	<10	49	<10	6	166
40	L5+00S-8+25E	0 4	0 25	10	120	<5	3 18	<1	2	6	18	0 54	<10	0 40	232	3	0 02	15	580	10	10	<20	20	< 01	<10	32	<10	3	103
41	L5+00S-8+50E	< 2	1 20	20	115	5	0 15	<1	7	28	18	4 30	<10	0 23	181	33	< 01	17	460	22	<5	<20	18	0 04	<10	148	<10	<1	79
42	L5+00S-8+75E	0 2	0 76	15	40	<5	0 05	<1	3	14	6	1 91	<10	0 05	46	10	< 01	4	170	14	<5	<20	5	0 06	<10	115	<10	<1	28
43	L5+00S-9+00E	< 2	1 29	30	100	<5	0 06	<1	7	34	23	5 67	<10	0 17	157	48	<.01	14	640	16	<5	<20	17	0 05	20	161	<10	<1	57
44	L5+00S-9+25E	< 2	1 64	25	130	<5	0 10	<1	9	35	23	4 71	<10	0 33	277	21	< 01	17	560	18	<5	<20	12	0 04	<10	98	<10	<1	62
45	L5+00S-9+50E	0 4	0 86	65	420	<5	0 27	<1	3	32	26	3 39	<10	0 21	69	54	< 01	16	1480	24	<5	<20	43	0 02	10	151	<10	1	56
46	L5+00S-9+75E	0 2	1 13	20	285	<5	0 60	<1	6	28	17	2 74	<10	0 39	173	16	< 01	21	930	24	<5	<20	27	0 03	<10	82	<10	3	87
47	L5+00S-10+00E	< 2	1 19	25	315	<5	0 43	<1	10	35	36	4 12	<10	0 39	248	29	< 01	25	880	20	<5	<20	31	0 05	<10	109	<10	4	94
48	L6+00S-5+00E	0 2	1 15	10	255	<5	0 16	<1	3	23	11	1 54	<10	0 24	70	3	< 01	13	350	20	<5	<20	14	0 02	<10	36	<10	2	58
49	L6+00S-5+25E	0 2	1 02	<5	250	<5	0 19	<1	3	20	10	1 32	<10	0 23	67	3	< 01	13	340	16	<5	<20	14	0 02	<10	39	<10	2	58
50	L6+00S-5+50E	< 2	1 16	5	255	5	0 19	<1	7	23	10	2 43	<10	0 26	193	10	< 01	15	500	18	<5	<20	15	0 02	<10	52	<10	1	60
51	L6+00S-5+75E	< 2	0 91	20	255	10	0 27	<1	5	19	9	5 33	<10	0 17	72	23	0 04	11	850	14	<5	<20	19	0 01	20	107	<10	<1	100
52	L6+00S-6+00E	0 6	0 50	<5	275	<5	0 43	2	5	8	13	3 66	<10	0 05	89	17	0 08	12	1100	12	<5	<20	26	< 01	10	31	<10	2	244
53	L6+00S-6+25E	0 4	1 14	5	235	<5	0 16	<1	3	24	12	2 36	<10	0 24	69	9	< 01	15	630	18	<5	<20	17	0 02	20	65	<10	2	69
54	L6+00S-6+50E	< 2	1 16	15	195	<5	0 13	<1	4	25	13	3 03	<10	0 22	65	14	< 01	14	670	18	<5	<20	14	0 02	<10	72	<10	<1	54
55	L6+00S-6+75E	< 2	1 09	5	215	<5	0 15	<1	3	22	11	2 12	<10	0 21	61	8	< 01	12	590	18	<5	<20	14	0 01	<10	44	<10	1	63
56	L6+00S-7+00E	< 2	1 08	15	180	<5	0 11	<1	3	22	10	2 58	<10	0 21	56	10	< 01	13	530	18	<5	<20	12	0 01	10	51	<10	<1	53
57	L6+00S-7+25E	< 2	1 04	5	190	<5	0 12	<1	2	21	9	1 52	<10	0 20	53	5	< 01	10	460	20	<5	<20	11	0 01	<10	41	<10	1	42
58	L6+00S-7+50E	< 2	1 00	<5	190	<5	0 16	<1	3	22	10	1 98	<10	0 20	61	9	< 01	11	510	18	<5	<20	14	0 01	10	34	<10	<1	47
59	L6+00S-7+75E	< 2	1 04	10	185	<5	0 16	<1	4	21	8	2.06	<10	0 23	82	7	< 01	12	420	16	<5	<20	14	0 02	10	46	<10	1	46
60	L6+00S-8+00E	< 2	1 00	<5	210	<5	0 21	<1	4	20	11	2 37	<10	0 21	69	8	< 01	14	680	16	<5	<20	15	0 01	<10	37	<10	1	76

TOKLAT RESOURCES INC. AK 95-852

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	L6+00S-8+25E	< 2	0 91	<5	180	<5	0 19	<1	4	18	8	1 61	<10	0 22	145	4	< 01	12	410	14	<5	<20	15	0.02	<10	34	<10	1	55
62	L6+00S-8+50E	< 2	1 04	10	180	<5	0 16	<1	4	21	8	1 90	<10	0 24	84	6	< 01	12	410	16	<5	<20	13	0 02	<10	45	<10	1	52
63	L6+00S-8+75E	0 2	0 91	<5	245	<5	0 24	<1	2	18	18	1.38	<10	0 21	48	5	< 01	13	380	14	<5	<20	14	0 01	10	27	<10	2	36
64	L6+00S-9+00E	1 4	1 15	20	570	<5	0 33	<1	1	26	16	1 85	<10	0 21	74	11	< 01	18	850	34	<5	<20	28	< 01	<10	76	<10	3	67
65	L6+00S-9+25E	2 4	1 45	55	765	<5	0 38	<1	10	31	25	3 95	<10	0 20	439	71	< 01	25	1430	50	<5	<20	39	< 01	<10	217	<10	5	79
66	L6+00S-9+50E	3 0	1 23	30	445	<5	1 00	1	9	30	32	2 73	<10	0 33	489	76	0 04	30	1220	56	15	<20	78	< 01	<10	160	<10	7	197
67	L6+00S-9+75E	0 4	0 66	10	140	<5	0 07	<1	2	12	12	1 39	<10	0 03	57	9	< 01	11	450	18	<5	<20	6	< 01	10	44	<10	<1	43
68	L6+00S-10+00E	< 2	1 68	20	95	<5	0 08	<1	8	29	12	3 55	<10	0 28	208	12	< 01	14	380	18	<5	<20	8	0 04	<10	94	<10	<1	55
69	L7S-5+00E	0 2	0 90	<5	175	<5	0 18	<1	4	19	9	3 25	<10	0 23	64	6	< 01	14	650	14	<5	<20	12	0 02	10	43	<10	<1	53
70	L7S-5+25E	< 2	1 08	<5	255	<5	0 26	<1	4	22	9	1 88	<10	0 32	99	4	< 01	14	530	18	<5	<20	15	0 02	<10	46	<10	2	64
71	L7S-5+50E	0 2	1 01	<5	375	<5	0 40	<1	9	21	9	4 28	<10	0 28	456	8	< 01	15	560	14	<5	<20	18	0 02	<10	41	<10	<1	63
72	L7S-5+75E	< 2	1 27	5	385	<5	0 31	<1	4	25	11	2 03	<10	0 34	114	4	< 01	17	480	20	<5	<20	15	0 02	10	55	<10	3	73
73	L7S-6+00E	0 2	1 15	<5	450	<5	0 43	<1	6	23	9	2.37	<10	0 37	304	9	< 01	17	610	18	<5	<20	20	0 02	<10	53	<10	2	80
74	L7S-6+25E	0 2	1 17	<5	525	<5	0 50	<1	6	24	13	2 04	<10	0 37	498	6	< 01	19	610	18	<5	<20	17	0 02	<10	50	<10	3	85
75	L7S-6+50E	0 2	1 29	<5	505	<5	0 35	<1	6	26	12	2 69	<10	0 37	245	8	< 01	20	560	20	<5	<20	14	0 02	<10	50	<10	3	88
76	L7S-6+75E	< 2	1 42	10	605	<5	0 40	1	6	29	18	2.44	<10	0 44	189	6	0 01	25	580	24	<5	<20	16	0 02	<10	61	<10	4	107
77	L7S-7+00E	< 2	1 31	10	660	<5	0 84	<1	7	27	15	2 67	<10	0 48	464	7	0 01	24	790	18	<5	<20	21	0 02	<10	58	<10	2	130
78	L7S-7+25E	< 2	1 16	5	670	<5	0 85	<1	6	24	12	2 48	<10	0 44	577	10	0 01	21	830	16	<5	<20	19	0 02	<10	50	<10	2	96
79	L7S-7+50E	0 4	1 08	<5	755	<5	0 78	2	13	22	15	3 44	<10	0 37	1115	18	0 01	23	800	16	<5	<20	20	0 02	<10	52	<10	2	103
80	L7S-7+75E	0 6	1 13	15	795	<5	0 92	1	15	24	20	4 14	<10	0 41	1512	26	0 01	28	820	20	<5	<20	22	0 02	<10	67	<10	3	145
81	L7S-8+00E	0 2	1 44	<5	865	<5	0 68	<1	12	29	27	3 87	<10	0 44	689	16	0 01	29	810	18	<5	<20	19	0 02	<10	72	<10	7	111
82	L7S-8+25E	0 2	1 39	10	740	<5	0 70	<1	8	29	20	3 14	<10	0 47	392	12	0 01	29	790	24	<5	<20	19	0 02	<10	73	<10	4	130
83	L7S-8+50E	0 4	0 34	<5	910	<5	3 50	3	8	5	31	1 06	<10	0 48	1203	6	0 01	33	800	6	10	<20	29	< 01	<10	14	<10	4	169
84	L7S-8+75E	0 6	0 87	10	1070	<5	1 98	3	28	17	27	3 36	<10	0 42	1426	18	< 01	57	970	22	<5	<20	21	0 01	<10	65	<10	10	325
85	L7S-9+00E	1 0	0 59	5	1305	<5	2 52	2	8	9	45	1 46	<10	0 37	2848	15	< 01	26	940	14	10	<20	25	< 01	<10	41	<10	9	67
86	L7S-9+25E	0 6	1 27	5	470	<5	0 30	<1	5	28	19	2 16	<10	0 41	154	12	< 01	24	620	22	<5	<20	20	0 03	<10	78	<10	4	96
87	L7S-9+50E	0 8	0 94	<5	535	<5	0.18	<1	<1	24	15	1 16	<10	0 24	65	5	< 01	15	320	20	<5	<20	15	0 02	<10	43	<10	3	49
88	L7S-9+75E	0 8	1 44	20	770	<5	0 39	<1	2	27	33	2 69	<10	0 33	91	21	0 01	53	650	20	<5	<20	25	0 02	<10	99	<10	6	109
89	L7S-10+00E	2 2	1 00	20	1165	<5	0 62	2	<1	22	34	2 61	<10	0 19	120	31	0 03	34	1680	22	<5	<20	43	< 01	10	108	<10	8	117

TOKLAT RESOURCES INC. AK 95-852

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																													
Repeat:																													
1	L2+00S-8+75E	< 2	2 01	25	195	<5	0 18	<1	11	31	19	3 03	<10	0 43	303	10	< 01	24	350	26	<5	<20	13	0 03	<10	57	<10	<1	64
10	L4+00S-6+25E	0 8	1 03	20	375	<5	2 09	4	7	22	95	1 59	<10	0 65	115	2	< 01	65	910	52	20	<20	20	0 01	<10	61	<10	14	223
19	L4+00S-8+50E	1.0	0 52	35	120	<5	3 64	4	4	8	96	0 91	<10	0 50	483	11	0 01	26	720	14	15	<20	23	< 01	<10	58	<10	6	99
28	L5+00S-5+25E	< 2	1 36	20	390	<5	0 52	2	8	25	53	2.06	<10	0 34	175	5	< 01	46	580	28	<5	<20	16	0 01	<10	80	<10	6	135
36	L5+00S-7+25E	1 8	1 10	40	380	<5	3 61	7	19	23	120	3 70	<10	1 52	765	15	< 01	88	800	70	35	<20	25	0 02	<10	80	<10	16	358
45	L5+00S-9+50E	0 2	0.84	70	420	<5	0 22	<1	2	32	22	3 37	<10	0 19	56	55	< 01	14	1470	24	<5	<20	40	0 02	10	151	<10	1	52
54	L6+00S-6+50E	< 2	1 17	15	195	<5	0 13	<1	4	25	14	3.05	<10	0 25	66	14	< 01	13	670	16	<5	<20	15	0 02	10	71	<10	<1	56
63	L6+00S-8+75E	0 2	0 90	<5	245	<5	0 24	<1	2	18	18	1 35	<10	0 21	48	5	< 01	13	370	14	<5	<20	15	0 01	<10	27	<10	2	36
71	L7S-5+50E	0 4	0 98	<5	380	<5	0 40	<1	9	21	9	4 27	<10	0 28	464	9	< 01	15	550	14	<5	<20	17	0 02	<10	39	<10	<1	63
80	L7S-7+75E	0 4	1 10	15	845	5	0 91	1	15	24	21	4 21	<10	0 40	1517	27	0 01	30	820	20	<5	<20	23	0 02	<10	68	<10	3	151
89	L7S-10+00E	2 2	0 96	20	1025	<5	0 62	1	<1	21	34	2 55	<10	0 18	110	31	0 03	33	1690	22	<5	<20	42	< 01	20	103	<10	8	117
Standard:																													
GEO'95		1 2	1 62	70	165	<5	1 56	<1	17	54	87	3 73	<10	0 87	635	<1	0 01	25	580	22	<5	<20	49	0 09	<10	70	<10	6	66
GEO'95		1 4	1 70	65	165	<5	1 58	<1	19	54	86	3 67	<10	0 86	625	<1	0 02	22	580	22	<5	<20	53	0 11	<10	77	<10	5	70
GEO'95		1 4	1 65	70	160	<5	1 60	<1	19	55	88	3 66	<10	0 87	650	<1	0 02	22	570	22	5	<20	59	0 12	<10	64	<10	5	72

df/882
XLS/95Toklat#2

ECO-TECH LABORATORIES LTD.
Frank J Pezzotti, A.Sc T
B C Certified Assayer

6-Oct-95

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B C
V2C 6T4

Phone 604-573-5700
Fax 604-573-4557

TOKLAT RESOURCES INC. AK 95-852
2720-17th STREET SOUTH
CRANBROOK, B C
V1C 4H4

ATTENTION: TIM TERMUENDE

89 Soil samples received Sept 16, 1995
PROJECT # None given
SHIPMENT #. None given

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	L2+00S-8+75E	< 2	2 10	30	180	<5	0 12	<1	13	33	20	3 21	<10	0 40	328	11	< 01	23	350	24	<5	<20	13	0 04	<10	59	<10	<1	61
2	L2+00S-9+00E	< 2	1 10	35	100	5	0 06	<1	7	24	17	3 59	<10	0 22	161	25	< 01	14	530	16	<5	<20	11	0 03	<10	131	<10	<1	63
3	L2+00S-9+25E	< 2	0 66	85	220	5	0 04	<1	4	22	21	4 74	<10	0 13	116	118	< 01	10	760	36	<5	<20	50	0 03	<10	204	<10	<1	36
4	L2+00S-9+50E	< 2	0 39	<5	65	<5	0 03	<1	1	7	9	0 87	<10	0 01	24	8	< 01	4	910	10	<5	<20	6	< 01	<10	21	<10	<1	38
5	L4+00S-5+00E	0 8	0 88	25	495	<5	2 46	3	8	18	50	1 82	<10	0 54	709	4	0 03	42	820	34	15	<20	23	0 01	<10	44	<10	7	192
6	L4+00S-5+25E	0 4	0 75	20	565	<5	2 40	2	5	15	52	1 51	<10	0 49	823	3	< 01	42	690	22	15	<20	21	< 01	<10	37	<10	6	182
7	L4+00S-5+50E	< 2	0 18	5	315	<5	3 50	3	2	3	28	0 48	<10	0 54	561	2	0 02	21	470	4	10	<20	19	< 01	<10	12	<10	2	141
8	L4+00S-5+75E	0 4	0 38	15	405	<5	3 48	2	4	7	27	1 10	<10	0 56	642	3	0 02	24	680	14	15	<20	18	< 01	<10	20	<10	3	194
9	L4+00S-6+00E	0 8	0 69	30	575	<5	4 44	4	7	13	74	1 72	<10	1 82	1090	2	< 01	48	780	32	30	<20	23	0 01	<10	36	<10	10	213
10	L4+00S-6+25E	1 0	1 06	20	375	<5	1 97	3	7	22	90	1 63	<10	0 64	119	2	< 01	63	880	50	20	<20	21	0 01	<10	61	<10	14	219
11	L4+00S-6+50E	0 8	0 58	15	495	<5	3 03	4	10	12	68	2 09	<10	0 50	909	5	< 01	62	810	24	10	<20	22	< 01	<10	34	<10	7	174
12	L4+00S-6+75E	< 2	0 21	5	325	<5	3 89	4	3	4	35	0 57	<10	0 61	943	2	0 02	36	740	8	20	<20	25	< 01	<10	11	<10	2	138
13	L4+00S-7+00E	0 4	0 40	10	340	<5	3 03	6	14	8	59	1 09	<10	0 49	1267	10	0 01	54	720	10	15	<20	29	< 01	<10	36	<10	7	193
14	L4+00S-7+25E	0 4	1 25	20	415	<5	1 25	1	11	29	59	2 50	<10	0 41	350	16	< 01	56	1170	24	<5	<20	32	0 01	<10	110	<10	10	167
15	L4+00S-7+50E	0 2	0 94	30	330	<5	0 12	<1	4	18	48	2 57	<10	0 09	124	25	< 01	34	470	32	<5	<20	23	0 02	<10	113	<10	1	140
16	L4+00S-7+75E	0 4	0 33	10	725	<5	1 78	9	2	4	18	0 67	<10	0 31	81	6	0 02	13	400	10	15	<20	25	< 01	<10	23	<10	4	165
17	L4+00S-8+00E	< 2	0 14	15	50	<5	3 60	9	<1	1	44	0 32	<10	0 49	174	2	0 01	16	570	<2	15	<20	<1	< 01	<10	10	<10	<1	241
18	L4+00S-8+25E	2 2	0 56	40	85	<5	3 90	3	4	8	123	1 12	<10	0 59	267	4	< 01	32	630	62	20	<20	21	< 01	<10	39	<10	8	134
19	L4+00S-8+50E	0 8	0 54	30	120	<5	3 79	4	4	9	100	0 89	<10	0 52	497	11	< 01	26	760	16	20	<20	23	< 01	<10	58	<10	7	103
20	L4+00S-8+75E	< 2	1 56	25	105	10	0 16	<1	7	31	24	4 30	<10	0 24	179	39	< 01	16	440	18	<5	<20	16	0 03	<10	137	<10	<1	57
21	L4+00S-9+00E	< 2	1 12	35	105	5	0 06	<1	6	26	30	4 93	<10	0 13	96	42	< 01	12	440	14	<5	<20	21	0 03	<10	204	<10	<1	56
22	L4+00S-9+25E	< 2	0 70	20	65	<5	0 05	<1	4	15	13	2 71	<10	0 09	70	22	< 01	7	210	10	<5	<20	12	0 04	<10	123	<10	<1	29
23	L4+00S-9+50E	< 2	1 73	50	185	5	0 09	<1	10	32	30	4 70	<10	0 30	306	25	< 01	18	740	18	<5	<20	19	0 03	<10	120	<10	<1	59
24	L4+00S-9+75E	< 2	1 11	60	95	10	0 04	<1	6	30	21	4 26	<10	0 14	106	30	< 01	11	500	16	<5	<20	18	0 03	<10	156	<10	<1	41
25	L4+00S-10+00E	< 2	0 68	20	95	5	0 03	<1	3	16	20	2 79	<10	0 03	55	22	< 01	7	340	16	<5	<20	9	0 02	<10	141	<10	<1	28

TOKLAT RESOURCES INC AK 95-852

ECO-TECH LABORATORIES LTD

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	L4+00S-10+25E	< 2	0 85	50	160	5	0 05	<1	6	36	44	5 72	<10	0 15	131	70	< 01	11	920	18	<5	<20	33	0 03	<10	196	<10	<1	44
27	L5+00S-5+00E	< 2	1 11	5	375	5	0 63	1	6	22	33	2 22	<10	0 36	186	7	< 01	35	740	24	<5	<20	21	0 01	<10	61	<10	6	125
28	L5+00S-5+25E	< 2	1 40	15	425	<5	0 61	2	9	28	59	2 29	<10	0 38	187	6	< 01	51	610	32	<5	<20	15	0 01	<10	84	<10	6	148
29	L5+00S-5+50E	0 4	1 12	10	480	<5	1 08	2	9	24	35	2 34	<10	0 40	562	10	< 01	37	920	22	5	<20	24	0 01	<10	63	<10	6	147
30	L5+00S-5+75E	0 6	1 32	20	940	<5	0 74	<1	31	30	55	3 73	<10	0 37	2471	21	< 01	54	1000	26	<5	<20	25	0 02	<10	98	<10	12	141
31	L5+00S-6+00E	0 2	1 30	15	710	<5	0 59	1	5	27	50	2 07	<10	0 37	340	7	< 01	40	780	30	<5	<20	24	0 01	<10	74	<10	8	120
32	L5+00S-6+25E	0 2	0 99	30	795	<5	0 50	<1	3	22	35	2 44	<10	0 36	146	10	< 01	26	730	20	20	<20	21	0 02	<10	66	<10	4	108
33	L5+00S-6+50E	0 8	1 25	25	1075	<5	0 48	<1	2	27	47	2 44	<10	0 39	196	9	< 01	31	730	22	25	<20	22	0 02	<10	74	<10	6	125
34	L5+00S-6+75E	1 4	0 97	30	875	<5	1 59	3	1	21	60	2 65	<10	0 43	119	10	< 01	30	810	20	15	<20	22	< 01	<10	70	<10	5	101
35	L5+00S-7+00E	1 2	1 05	20	610	<5	1 67	2	4	22	83	1 89	<10	0 47	257	4	< 01	39	790	30	20	<20	21	0 01	<10	55	<10	10	144
36	L5+00S-7+25E	1 6	0 90	35	340	<5	3 42	5	15	19	102	3 58	<10	1 39	731	11	< 01	78	700	58	25	<20	22	0 01	<10	70	<10	13	324
37	L5+00S-7+50E	0 4	0 13	10	130	<5	3 27	5	1	3	35	0 35	<10	0 48	205	3	0 05	19	460	12	20	<20	12	< 01	<10	10	<10	1	68
38	L5+00S-7+75E	0 8	0 28	10	215	<5	3 21	7	1	6	123	0 57	<10	0 37	88	2	0 01	41	550	20	20	<20	14	< 01	20	27	<10	7	134
39	L5+00S-8+00E	3 2	0 41	50	125	<5	2 47	1	3	10	82	1 21	<10	0 34	214	6	0 01	26	640	86	35	<20	17	< 01	<10	49	<10	6	166
40	L5+00S-8+25E	0 4	0 25	10	120	<5	3 18	<1	2	6	18	0 54	<10	0 40	232	3	0 02	15	580	10	10	<20	20	< 01	<10	32	<10	3	103
41	L5+00S-8+50E	< 2	1 20	20	115	5	0 15	<1	7	28	18	4 30	<10	0 23	181	33	< 01	17	460	22	<5	<20	18	0 04	<10	148	<10	<1	79
42	L5+00S-8+75E	0 2	0 76	15	40	<5	0 05	<1	3	14	6	1 91	<10	0 05	46	10	< 01	4	170	14	<5	<20	5	0 06	<10	115	<10	<1	28
43	L5+00S-9+00E	< 2	1 29	30	100	<5	0 06	<1	7	34	23	5 67	<10	0 17	157	48	< 01	14	640	16	<5	<20	17	0 05	20	161	<10	<1	57
44	L5+00S-9+25E	< 2	1 64	25	130	<5	0 10	<1	9	35	23	4 71	<10	0 33	277	21	< 01	17	560	18	<5	<20	12	0 04	<10	98	<10	<1	62
45	L5+00S-9+50E	0 4	0 86	65	420	<5	0 27	<1	3	32	26	3 39	<10	0 21	69	54	< 01	16	1480	24	<5	<20	43	0 02	10	151	<10	1	56
46	L5+00S-9+75E	0 2	1 13	20	285	<5	0 60	<1	6	28	17	2 74	<10	0 39	173	16	< 01	21	930	24	<5	<20	27	0 03	<10	82	<10	3	87
47	L5+00S-10+00E	< 2	1 19	25	315	<5	0 43	<1	10	35	36	4 12	<10	0 39	248	29	< 01	25	880	20	<5	<20	31	0 05	<10	109	<10	4	94
48	L6+00S-5+00E	0 2	1 15	10	255	<5	0 16	<1	3	23	11	1 54	<10	0 24	70	3	< 01	13	350	20	<5	<20	14	0 02	<10	36	<10	2	58
49	L6+00S-5+25E	0 2	1 02	<5	250	<5	0 19	<1	3	20	10	1 32	<10	0 23	67	3	< 01	13	340	16	<5	<20	14	0 02	<10	39	<10	2	58
50	L6+00S-5+50E	< 2	1 16	5	255	5	0 19	<1	7	23	10	2 43	<10	0 26	193	10	< 01	15	500	18	<5	<20	15	0 02	<10	52	<10	1	60
51	L6+00S-5+75E	< 2	0 91	20	255	10	0 27	<1	5	19	9	5 33	<10	0 17	72	23	0 04	11	850	14	<5	<20	19	0 01	20	107	<10	<1	100
52	L6+00S-6+00E	0 6	0 50	<5	275	<5	0 43	2	5	8	13	3 66	<10	0 05	89	17	0 08	12	1100	12	<5	<20	26	< 01	10	31	<10	2	244
53	L6+00S-6+25E	0 4	1 14	5	235	<5	0 16	<1	3	24	12	2 36	<10	0 24	69	9	< 01	15	630	18	<5	<20	17	0 02	20	65	<10	2	69
54	L6+00S-6+50E	< 2	1 16	15	195	<5	0 13	<1	4	25	13	3 03	<10	0 22	65	14	< 01	14	670	18	<5	<20	14	0 02	<10	72	<10	<1	54
55	L6+00S-6+75E	< 2	1 09	5	215	<5	0 15	<1	3	22	11	2 12	<10	0 21	61	8	< 01	12	590	18	<5	<20	14	0 01	<10	44	<10	1	63
56	L6+00S-7+00E	< 2	1 08	15	180	<5	0 11	<1	3	22	10	2 58	<10	0 21	56	10	< 01	13	530	18	<5	<20	12	0 01	10	51	<10	<1	53
57	L6+00S-7+25E	< 2	1 04	5	190	<5	0 12	<1	2	21	9	1 52	<10	0 20	53	5	< 01	10	460	20	<5	<20	11	0 01	<10	41	<10	1	42
58	L6+00S-7+50E	< 2	1 00	<5	190	<5	0 16	<1	3	22	10	1 98	<10	0 20	61	9	< 01	11	510	18	<5	<20	14	0 01	10	34	<10	<1	47
59	L6+00S-7+75E	< 2	1 04	10	185	<5	0 16	<1	4	21	8	2 06	<10	0 23	82	7	< 01	12	420	16	<5	<20	14	0 02	10	46	<10	1	46
60	L6+00S-8+00E	< 2	1 00	<5	210	<5	0 21	<1	4	20	11	2 37	<10	0 21	69	8	< 01	14	680	16	<5	<20	15	0 01	<10	37	<10	1	76

TOKLAT RESOURCES INC. AK 95-852

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
61	L6+00S-8+25E	< 2	0 91	<5	180	<5	0 19	<1	4	18	8	1 61	<10	0 22	145	4	< 01	12	410	14	<5	<20	15	0 02	<10	34	<10	1	55
62	L6+00S-8+50E	< 2	1 04	10	180	<5	0 16	<1	4	21	8	1 90	<10	0 24	84	6	< 01	12	410	16	<5	<20	13	0 02	<10	45	<10	1	52
63	L6+00S-8+75E	0 2	0 91	<5	245	<5	0 24	<1	2	18	18	1 38	<10	0 21	48	5	< 01	13	380	14	<5	<20	14	0 01	10	27	<10	2	36
64	L6+00S-9+00E	1 4	1 15	20	570	<5	0 33	<1	1	26	16	1 85	<10	0 21	74	11	< 01	18	850	34	<5	<20	28	< 01	<10	76	<10	3	67
65	L6+00S-9+25E	2 4	1 45	55	765	<5	0 38	<1	10	31	25	3 95	<10	0 20	439	71	< 01	25	1430	50	<5	<20	39	< 01	<10	217	<10	5	79
66	L6+00S-9+50E	3 0	1 23	30	445	<5	1 00	1	9	30	32	2 73	<10	0 33	489	76	0 04	30	1220	56	15	<20	78	< 01	<10	160	<10	7	197
67	L6+00S-9+75E	0 4	0 66	10	140	<5	0 07	<1	2	12	12	1 39	<10	0 03	57	9	< 01	11	450	18	<5	<20	6	< 01	10	44	<10	<1	43
68	L6+00S-10+00E	< 2	1 68	20	95	<5	0 08	<1	8	29	12	3 55	<10	0 28	208	12	< 01	14	380	18	<5	<20	8	0 04	<10	94	<10	<1	55
69	L7S-5+00E	0 2	0 90	<5	175	<5	0 18	<1	4	19	9	3 25	<10	0 23	64	6	< 01	14	650	14	<5	<20	12	0 02	10	43	<10	<1	53
70	L7S-5+25E	< 2	1 08	<5	255	<5	0 26	<1	4	22	9	1 88	<10	0 32	99	4	< 01	14	530	18	<5	<20	15	0 02	<10	46	<10	2	64
71	L7S-5+50E	0 2	1 01	<5	375	<5	0 40	<1	9	21	9	4 28	<10	0 28	456	8	< 01	15	560	14	<5	<20	18	0 02	<10	41	<10	<1	63
72	L7S-5+75E	< 2	1 27	5	385	<5	0 31	<1	4	25	11	2 03	<10	0 34	114	4	< 01	17	480	20	<5	<20	15	0 02	10	55	<10	3	73
73	L7S-6+00E	0 2	1 15	<5	450	<5	0 43	<1	6	23	9	2 37	<10	0 37	304	9	< 01	17	610	18	<5	<20	20	0 02	<10	53	<10	2	80
74	L7S-6+25E	0 2	1 17	<5	525	<5	0 50	<1	6	24	13	2 04	<10	0 37	498	6	< 01	19	610	18	<5	<20	17	0 02	<10	50	<10	3	85
75	L7S-6+50E	0 2	1 29	<5	505	<5	0 35	<1	6	26	12	2 69	<10	0 37	245	8	< 01	20	560	20	<5	<20	14	0 02	<10	50	<10	3	88
76	L7S-6+75E	< 2	1 42	10	605	<5	0 40	1	6	29	18	2 44	<10	0 44	189	6	0 01	25	580	24	<5	<20	16	0 02	<10	61	<10	4	107
77	L7S-7+00E	< 2	1 31	10	660	<5	0 84	<1	7	27	15	2 67	<10	0 48	464	7	0 01	24	790	18	<5	<20	21	0 02	<10	58	<10	2	130
78	L7S-7+25E	< 2	1 16	5	670	<5	0 85	<1	6	24	12	2 48	<10	0 44	577	10	0 01	21	830	16	<5	<20	19	0 02	<10	50	<10	2	96
79	L7S-7+50E	0 4	1 08	<5	755	<5	0 78	2	13	22	15	3 44	<10	0 37	1115	18	0 01	23	800	16	<5	<20	20	0 02	<10	52	<10	2	103
80	L7S-7+75E	0 6	1 13	15	795	<5	0 92	1	15	24	20	4 14	<10	0 41	1512	26	0 01	28	820	20	<5	<20	22	0 02	<10	67	<10	3	145
81	L7S-8+00E	0 2	1 44	<5	865	<5	0 68	<1	12	29	27	3 87	<10	0 44	689	16	0 01	29	810	18	<5	<20	19	0 02	<10	72	<10	7	111
82	L7S-8+25E	0 2	1 39	10	740	<5	0 70	<1	8	29	20	3 14	<10	0 47	392	12	0 01	29	790	24	<5	<20	19	0 02	<10	73	<10	4	130
83	L7S-8+50E	0 4	0 34	<5	910	<5	3 50	3	8	5	31	1 06	<10	0 48	1203	6	0 01	33	800	6	10	<20	29	< 01	<10	14	<10	4	169
84	L7S-8+75E	0 6	0 87	10	1070	<5	1 98	3	28	17	27	3 36	<10	0 42	1426	18	< 01	57	970	22	<5	<20	21	0 01	<10	65	<10	10	325
85	L7S-9+00E	1 0	0 59	5	1305	<5	2 52	2	8	9	45	1 46	<10	0 37	2848	15	< 01	26	940	14	10	<20	25	< 01	<10	41	<10	9	67
86	L7S-9+25E	0 6	1 27	5	470	<5	0 30	<1	5	28	19	2 16	<10	0 41	154	12	< 01	24	620	22	<5	<20	20	0 03	<10	78	<10	4	96
87	L7S-9+50E	0 8	0 94	<5	535	<5	0 18	<1	<1	24	15	1 16	<10	0 24	65	5	< 01	15	320	20	<5	<20	15	0 02	<10	43	<10	3	49
88	L7S-9+75E	0 8	1 44	20	770	<5	0 39	<1	2	27	33	2 69	<10	0 33	91	21	0 01	53	650	20	<5	<20	25	0 02	<10	99	<10	6	109
89	L7S-10+00E	2 2	1 00	20	1165	<5	0 62	2	<1	22	34	2 61	<10	0 19	120	31	0 03	34	1680	22	<5	<20	43	< 01	10	108	<10	8	117

TOKLAT RESOURCES INC. AK 95-852

ECO-TECH LABORATORIES LTD

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
QC/DATA:																													
Repeat.																													
1	L2+00S-8+75E	< 2	2 01	25	195	<5	0 18	<1	11	31	19	3 03	<10	0 43	303	10	< 01	24	350	26	<5	<20	13	0 03	<10	57	<10	<1	64
10	L4+00S-6+25E	0 8	1 03	20	375	<5	2 09	4	7	22	95	1 59	<10	0 65	115	2	< 01	65	910	52	20	<20	20	0 01	<10	61	<10	14	223
19	L4+00S-8+50E	1 0	0 52	35	120	<5	3 64	4	4	8	96	0 91	<10	0 50	483	11	0 01	26	720	14	15	<20	23	< 01	<10	58	<10	6	99
28	L5+00S-5+25E	< 2	1 36	20	390	<5	0 52	2	8	25	53	2 06	<10	0 34	175	5	< 01	46	580	28	<5	<20	16	0 01	<10	80	<10	6	135
36	L5+00S-7+25E	1 8	1 10	40	380	<5	3 61	7	19	23	120	3 70	<10	1 52	765	15	< 01	88	800	70	35	<20	25	0 02	<10	80	<10	16	358
45	L5+00S-9+50E	0 2	0 84	70	420	<5	0 22	<1	2	32	22	3 37	<10	0 19	56	55	< 01	14	1470	24	<5	<20	40	0 02	10	151	<10	1	52
54	L6+00S-6+50E	< 2	1 17	15	195	<5	0 13	<1	4	25	14	3 05	<10	0 25	66	14	< 01	13	670	16	<5	<20	15	0 02	10	71	<10	<1	56
63	L6+00S-8+75E	0 2	0 90	<5	245	<5	0 24	<1	2	18	18	1 35	<10	0 21	48	5	< 01	13	370	14	<5	<20	15	0 01	<10	27	<10	2	36
71	L7S-5+50E	0 4	0 98	<5	380	<5	0 40	<1	9	21	9	4 27	<10	0 28	464	9	< 01	15	550	14	<5	<20	17	0 02	<10	39	<10	<1	63
80	L7S-7+75E	0 4	1 10	15	845	5	0 91	1	15	24	21	4 21	<10	0 40	1517	27	0 01	30	820	20	<5	<20	23	0 02	<10	68	<10	3	151
89	L7S-10+00E	2 2	0 96	20	1025	<5	0 62	1	<1	21	34	2 55	<10	0 18	110	31	0 03	33	1690	22	<5	<20	42	< 01	20	103	<10	8	117
Standard:																													
GEO'95		1 2	1 62	70	165	<5	1 56	<1	17	54	87	3 73	<10	0 87	635	<1	0 01	25	580	22	<5	<20	49	0 09	<10	70	<10	6	66
GEO'95		1 4	1 70	65	165	<5	1 58	<1	19	54	86	3 67	<10	0 86	625	<1	0 02	22	580	22	<5	<20	53	0 11	<10	77	<10	5	70
GEO'95		1 4	1 65	70	160	<5	1 60	<1	19	55	88	3 66	<10	0 87	650	<1	0 02	22	570	22	5	<20	59	0 12	<10	64	<10	5	72

df/882
XLS/95Toklat#2

ECO-TECH LABORATORIES LTD
Frank J Pezzotti, A.Sc T
B C Certified Assayer

APPENDIX III

Diamond Drill Logs

DRILL HOLE LOG

LOCATION: MIKE HILL 11+00N/11+25E			DRILL HOLE NO.: RS95-M1
AZIMUTH: 310	ELEVATION: 2600'/793m		PROPERTY: RUSTY SPRINGS
INCLINATION: -50°	LENGTH: 187.8m/616'	SURVEYS	CLAIM NO.
RECOVERY:	CORE SIZE: BGM	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: 11+00N/11+25E
STARTED: JUNE 11/95		416' 126.8m / / / -51°	LOGGED BY: CHAS DOWNIE, TIM TERMENDE
COMPLETED:		616' 187.8m / / / -51°	DATED LOGGED: JUNE 15/95
PURPOSE: TEST CONTINUITY DOWNDIP OF MIKE HILL MINERALIZATION			DRILLING CO.: FALCON
			ASSAYED BY: ECOTECH

CORE RECOVERY:.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
00	3.0	OVERBURDEN		0	5'	5'	1.0	72	112	10	82
		dk grey clay/silt clay mixed with fragments lt. grey siltstone + cherty breccia		5'	10'	5'	0.6	142	118	5	178
30	12.5	BRECCIA		3.0	4.1	1.1	0.4	4.1	1798	<5	81
		- angular to subangular clasts of dk grey cherty siltstone and dk. grey dolomite in a		4.1	4.4	0.3	1.4	47	1123	15	39
		matrix of weakly to strongly rusty-oxidized		4.4	4.7	0.3	<.2	68	1694	5	221
		(-med grey med cement		4.7	5.4	0.7	<.2	78	54	20	687
		- in places the clasts are distinctly milled with		5.4	5.9	0.5	<.2	69	72	10	301
		the matrix clearly fine, crushed wallrock		5.9	6.4	0.5	<.2	31	36	<5	2053
		- inbound is weakly to str oxidized with		6.4	8.0	1.6	<.2	60	112	10	295
		orange to red oxides on fractures		8.0	9.7	1.7	<.2	86	26	<5	486
				9.7	10.2	0.5	<.2	84	28	<5	354
.5		- mod.-str. fractured		10.2	10.7	0.5	<.2	73	30	<5	436

Toklat Resources Inc.

18

Drill Hole No. RS95-01 | Page 1 of

SAMPLE INTERVALS ON BACK

DRILL HOLE LOG

LOCATION:			DRILL HOLE NO.: RS95-01
AZIMUTH:	ELEVATION:		PROPERTY:
INCLINATION:	LENGTH:	SURVEYS	CLAIM NO:
	CORE SIZE:	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION.
STARTED:			LOGGED BY:
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.:
			ASSAYED BY:
CORE RECOVERY:			

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		- 2-3% white ddspar as breccia cement and vera		10.7	11.6	0.9	<2	130	72	5	836
		rundomly oriented 0.1-2mm microveins		11.6	12.5	0.9	<2	472	106	10	2738
		40-41									
		- bright yellow clay alteration of breccia clasts									
		- weak sl. densides on lower contact to qtz vein									
		41-44 QTZ VEIN									
		coarse grained white to clear strongly oxidized qtz. vein;									
		sharp contacts at 45deg, str rust red to deep brown oxide									
		overprint									
44-5.4	5.9-6.4	STRONGLY OXIDIZED INTERVAL/GOUGE									
		red to orange gossan overprint; rock is str									
		altered with original rock textures completely									
		destroyed; 20% fine to med angular									

Toklat Resources Inc.

DRILL HOLE LOG

LOCATION:			DRILL HOLE NO.:
AZIMUTH:	ELEVATION:		PROPERTY:
INCLINATION:	LENGTH.	SURVEYS	CLAIM NO:
	CORE SIZE:	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY:
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.:
			ASSAYED BY:

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		gouge clasts, shear contacts at 50° tca									
		9.7-10.2 QUARTZ VEIN, QTZ FLOOD									
		10cm wide strongly fractured qtz. vein w orange									
		clay oxide infillings; margins have qtz repl-flood									
		of breccia clasts									
12.5	16.5	10.7-16.5 FAULT/SHEAR ZONE		12.[illegible]	14.0	1.5	<2	301	<2	10	612
		strongly fractured clasts of clay/silt/sand mixed		14.0	15.5	1.5	0.4	41	20	50	371
		with grey, yellow red, brown clay, fine crush,		15.5	17.0	1.5	0.2	16	10	70	512
		rare slickensides; fractures generally at 45° tca;									
		10.7-12.5 str red to orange oxide overprint									
		12.5-16.5 mod orange oxide stain, 25% white									
		chalky clay alteration									

Toklat Resources Inc.

DRILL HOLE LOG

LOCATION:			DRILL HOLE NO.: RS95-21
AZIMUTH:	ELEVATION:		PROPERTY:
INCLINATION:	LENGTH:	SURVEYS	CLAIM NO.
	CORE SIZE:	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY:
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.:
			ASSAYED BY:

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
165	91.4	BLOTCHY LIMESTONE/DOLOMITIC LIMESTONE		15.5	17.0		0.2	16	10	70	512
		med to dk grey; med grained weakly dolomitic		17.0	18.5		<.2	14	2	60	483
		limestone; weakly to moderately oxidized		18.5	20.0		<.2	<1	2	70	100
		fractures; 2% white spar reps st fossil debris		20.0	22.0		<.2	<1	<2	70	121
		rare 2mm microveins; local nodular textures destroyed		22.0	23.6		0.8	112	102	75	1539
		2-3% white dk2 in fractures and rare reps		23.6	24.5		2.0	108	138	95	827
		22.0 - 23.6 FAULT/SHEAR ZONE		24.5	26.0		<.2	4	82	65	264
		three different zones; upper is well carbonatized,		26.0	27.5		0.4	16	80	85	491
		strongly oxidized angular clast fragments; cut:		27.5	28.6		0.4	6	52	65	163
		22.6 sharp contact along 2cm wide dk2. vein		28.6	30.1		0.2	2	10	70	152
		at 60°ca with sand, red crush; at 231		30.1	31.6		0.4	<1	42	70	166
		str. fractured dolomite clasts mixed ± grey		31.6	33.4		0.2	<1	44	70	165
		clay.		33.4	33.6		0.2	<1	16	65	164
				33.6	35.0		2.2	83	78	80	1521

Toklat Resources Inc.

DRILL HOLE LOG

LOCATION:			DRILL HOLE NO.:
AZIMUTH:	ELEVATION:		PROPERTY:
INCLINATION:	LENGTH:	SURVEYS	CLAIM NO.
	CORE SIZE:	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY:
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.:
			ASSAYED BY:

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		24.0-24.2 QUARTZ VEIN, FAULT		35.0	35.2	0.2	1.6	102	46	90	497
		25% white to grey qtz repl of matrix,		35.2	36.4	1.2	0.6	88	8	95	248
		clasts in 75° to fault zone; str oxidized		36.4	36.6	.2	0.6	69	10	105	421
		25.0-25.1 QUARTZ VEIN, FAULT		36.6	37.6	1.0	0.4	17	6	40	220
		3cm wide 75° to qtz vein; lower		37.6	39.6	2.0	<.2	2	30	100	943
		contact .5 3 cm band of fine to		39.6	41.2	1.6	0.2	3	24	50	862
		med oxidized crush,		41.2	42.4	1.2	<.2	3	10	15	229
		25.3-41.4 increase in chlorite; 8% as rims									
		around nodules, clasts									
		26.8 3 cm band of sandy oxidized crush									
		28.6-41.4 red oxides on fractures and as mod pervasive									
		stain from 35.4-38.0									
		29.3-41.4 strongly fractured; maybe a FAULT									
		33.4-33.6 QTZ VEIN; barren, str fract									

Toklat Resources Inc.

Drill Hole No. | Page 6 of 18

DRILL HOLE LOG

LOCATION:			DRILL HOLE NO.:
AZIMUTH:	ELEVATION:		PROPERTY:
INCLINATION:	LENGTH:		CLAIM NO.
	CORE SIZE:		SECTION:
STARTED:			LOGGED BY:
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.:
			ASSAYED BY:

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		351-352 QTZ VEIN, str. oxidized:									
		364-366 QTZ VEIN/FAULT: white qtz w									
		tetrahedrite mixed with fine rusty sandy crush									
		376.4-414.3 QUARTZ FLOOD									
		20% qtz as repl. of clasts and matrix in									
		brecciated dolomite, local tetrahedrite									
		xtals - 2% over interval									
414	460	BRECCIA -		412	424	1.2	<.2	3	10	15	229
		angular clasts of med grey dolomite limestone,		424	443	1.9	<.2	2	14	50	154
		dolomite chert, siltstone in a fine grained		443	460	1.7	<.2	7	10	55	186
		argillaceous rich rusty matrix, 5% white dol spar									
		running of clasts									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
460	630	DOLOMITE		460	476	1.6	<.2	3	4	60	337
		f.-med gr vuggy ddomite; from 476-507		476	491	1.5	<.2	<1	<2	55	379
		ddomite is dk. grey to light brown moderate brecciation		491	507	1.6	<.2	<1	<2	65	39
		from 507-630 ddomite is bleached to light grey,		501	523	1.5	0.2	<1	<2	60	179
		mod. fractured, 30% mod oxide stain on oxide		522	536	1.4	<.2	<1	<2	70	184
		on fractures; weak to mod bx		536	551	1.5	<.2	2	<2	65	138
		508-550 FAULT, strongly fractured clasts		551	563	1.2	<.2	<1	<2	60	134
		of ddomite in local crush and mud,		563	582	1.9	<.2	22	<2	50	888
		fractures - coated w ~60° tco.		582	597	1.5	<.2	61	4	55	171
		597-601 FAULT/ STRONGLY OXIDIZED		597	601	0.4	<.2	1457	20	30	4726
		deep red-orange oxide stain on		601	625	2.4	2.2	382	8	240	753
		f.-med crushed ddomite fragments, local									
		goethite boxwork; local sand									
		625-640 FAULT/OXIDIZED/MINERALIZED									
		strongly fractured to f.-med crushed ddomite,									
		60% of interval has pervasive oxide overprint,									
		contacts undulose ~80° tco									
		mineralization - 625-628 azurite, mala-									
		chite, chrysocolla, tetrahedrite in vein									
		breccia with quartz, az-mal as repl									
		stain on ddomite clasts									
630	1215	MARLY LIMESTONE - DOLOMITIC LIMESTONE		625	640	1.5	641.4	(2.55)	234	6780	5668
		med. to dark grey fine to v. fine grained		640	655	1.5	1.0	182	2	115	545
		limestone, variable argillaceous content		655	670	1.5	0.8	84	<2	80	255

Toklat Resources Inc.

Drill Hole No. RS95-01 | Page 2 of 18

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		local weakly oxidized fractures									
		gives variation in color, local marly textures;		67.0	68.5	1.5	0.4	17	<2	70	96
		20% of interval is weakly dolomitic, 5% white		68.5	70.0	1.5	0.4	10	<2	70	111
		ddspar as repl of fossil debris burrows, rimming		70.0	71.5	1.5	0.2	26	<2	70	939
		of vugs, 1-2mm veins at 45-60° tca, 1% 1-2mm		71.5	73.0	1.5	<.2	5	<2	70	87
		white to clear qtz ± carbonate veinlets at 45-60° tca;		73.0	74.5	1.5	<.2	6	4	75	131
		± 708-709		74.5	76.0	1.5	<.2	1	<2	70	67
		well consolidated rusty fault gouge @ 80° tca		76.0	77.5	1.5	2	12	<2	70	466
		80.9-82.9 coarse vugs healed with white		77.5	79.0	1.5	<.2	2	2	65	71
		ddspar, calspar ± bitumen; abundant bio		79.0	80.5	1.5	0.4	3	<2	65	41
		debris - crinoids, burrows etc.		80.5	82.0	1.5	0.2	4	<2	70	21
		106.1-107.2 low angle (3-5° tca) fractures;		82.0	83.5	1.5	0.6	26	8	105	111
		red to orange oxides on fractures; altered		83.5	85.0	1.5	1.0	30	4	85	444
		as weak pervasive strain; 0.5 cm									
		quartz vein at 106.5; 3cm quartz vein									
		at 75° tca at 106.7 has shards of grey									
		dolomite									
		108.4-108.6 HEMATITIC SHEAR									
		1cm band of hematitic clay @ 55° tca;									
		margins have hematite alt of argillaceous									
		laminations									
		109.4-109.3 BRECCIA									
		subangular clasts of grey dolomitic									
		limestone in a matrix of white ddspar;									
		weakly vuggy healed with calcite									

Toklat Resources Inc.

Drill Hole No. RS95-01 | Page 9 2 of 18

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		115.2-116.0 BRECCIA									
		Shaley/clay to sbrounded clasts of med to									
		dark grey weakly ddomitic limestone in		104.7	106.1	1.4	0.2	6	<2	70	57
		a matrix of white to grey ddspar; + minor		106.1	107.2	1.1	0.4	25	6	70	196
		probably a solution breccia		107.2	108.4	1.2	0.4	22	<2	70	54
		116.9-117.0 FAULT		108.4	108.6	0.2	0.4	2	<1	75	6
		coarse grey ddomitic limestone rubble;		108.6	109.8	1.3	0.2	<1	<2	65	22
		sharp contacts at high angles (75°-85°),		109.8	111.3	1.5	<0.2	<1	<2	60	21
		hw; fw are similar marly grey ddomitic		111.3	112.8	1.5	0.2	2	<2	70	65
		limestone;		112.8	114.3	1.5	0.2	2	<2	65	416
		117.5-141.6		114.3	115.8	1.5	0.2	<1	<2	65	19
		local red hematite staining of		115.8	117.3	1.5	0.2	<1	<2	70	15
		fractures		117.3	118.4	1.1	<0.2	<1	<2	60	12
				118.4	118.7	0.3	<0.2	7	8	70	53
1215	1607	MARLY TO NODULAR DOLOMITE-DOLOMITIC		118.7	120.2	1.5	0.6	13	<2	65	44
		LIMESTONE		120.2	121.7	1.5	0.2	4	4	60	33
		med. brown to grey-brown, fine grained to locally									
		sandy ddomitic limestone and ddomite; local		120.2	121.7	1.5	0.2	4	4	60	33
		nodular textures; 10% argillaceous partings - marly		121.7	123.2	1.5	0.2	2	<2	65	34
		buildups; 1% small vugs; 2-3% white ddspar		123.2	124.7	1.5	0.4	7	102	65	99
		as veg healing, wispy stringers, in small solution brx		124.7	125.6	0.9	0.2	<1	<2	70	61
		zones, in 01-05 cm veins @ 90-60° tca, interval is		125.6	126.0	0.4	0.2	2	4	65	381
		moderately to strongly fractured; fractures commonly have		126.0	127.5	1.5	0.4	6	<2	70	80
		orange to red oxide stain; brecciated debris, burrows		127.5	129.0	1.5	0.2	1	<2	60	103

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		hematite ± white dolspar scattered throughout; occ		129.0	130.5	1.5	0.4	<1	<2	65	108
		stylolites ± argillite, hematite;		130.5	132.0	1.5	0.2	<1	<2	65	71
				132.0	132.5	0.5	<.2	<1	<2	60	39
		123.3 0.5 cm calcite vein ± manganese-		132.5	134.0	1.5	0.4	<1	<2	65	91
		goethite		134.0	135.5	1.5	<.2	<1	<2	70	7
		129.7 SHEAR/FAULT 2 cm banded		135.5	137.0	1.5	<.2	2	<2	65	15
		hematitic gouge - clay @ 35 tca; phyllite-		137.0	137.9	0.9	0.2	<1	<2	65	23
		sericite? along contact		137.9	138.1	0.2	0.2	2	<2	60	226
		125.3-125.4 FAULT strong fractured clasts		138.1	139.5	1.4	<.2	1	<2	65	44
		of ddamite mixed with orange to red mud;		139.5	141.0	1.5	<.2	<1	<2	60	78
		contacts @ 45 tca; upper margin has		141.0	142.5	1.5	<.2	<1	<2	70	52
		wispy hematitic laminations;		142.5	144.0	1.5	<.2	<1	<2	70	24
		125.6-126.0 mod to strong pervasive orange		144.0	145.5	1.5	<.2	<1	<2	70	14
		oxide stain; fractures have goethite-anterite;		145.5	147.0	1.5	0.2	<1	<2	65	13
		132.0, 132.5 QUARTZ VEINS 1.5 cm		147.0	148.5	1.5	0.2	<1	<2	65	5
		white quartz veins at 85 tca		148.5	150.0	1.5	0.2	<1	<2	65	4
		132.8-133.2 weak pervasive orange oxide		150.0	151.5	1.5	<.2	<1	<2	65	8
		stain on nodular ddamite		151.5	153.0	1.5	<.2	<1	<2	70	4
		138.0 QTZ VEIN 1.5 cm width white		153.0	154.5	1.5	<.2	<1	<2	65	5
		qtz vein @ 45 tca, contacts sharp-rusty;		154.5	156.0	1.5	<.2	<1	<2	65	12
		finely smeared silver metallic mineral in		156.0	157.5	1.5	<.2	<1	<2	65	65
		quartz is likely drill related		157.5	159.0	1.5	0.4	2	8	60	47
				159.0	160.5	1.5	0.4	2	4	65	31
				160.5	162.0	1.5	<.2	<1	4	60	40

Toklat Resources Inc.

Drill Hole No.	Page 10 of 18

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		1492 – 1607 interval becomes more carbonaceous; occ graphite on fractures, graphitic argillaceous partings throughout; stylolites; 1505 2cm band of argillic w.th kinetitic mud-clay												
		1562 SHEAR 55/1 imbricated thin argillaceous clast fragments @ 35°tca; marcasite have weak pervasive rusty oxide stain;												
		1564-1566 BRECCIA angular to subangular clasts of grey dolomite in a matrix of white spar, fragments have rust stain along margins; texture suggests a passive type of breccia - solution bx												
		1571 BEDDING 55°tca												
		1573m limestone is deep blue-marcasitic												
1		ath?												
1607	1618	ALTERNATING CARBONATE SEQUENCE		1605	1620	1.5	<.2	<1	4	60	90			
		alternating beds of laminated argillaceous		1620	1630	1.0	1.2	<1	<2	10	26			
		dolomitic limestone, grey-blue blotchy		1630	1640	10	0.4	1	<2	65	90			
		dolomitic limestone, brecciated dolomitic		1640	1645	0.5	1.6	2	10	65	195			
		limestone grey brown dolomite; locally		1645	1660	1.5	0.4	<1	<2	65	60			
		silicified; 5% white dolspar as infilling		1660	1675	1.5	<.2	<1	4	65	16			
		of solution breccia, infilling in crackle breccia,		1675	1679	0.4	0.6	130	20	60	853			
		in mm dimension cracks - fractures, in rare mm		1679	1695	1.6	0.4	1	8	60	130			

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		to 05cm veins @ 40-60°tca; moderately fractured		169.5	171.0	1.5	<.2	<1	4	60	38
		with weak to moderate oxidation on fracts;		171.0	172.5	1.5	0.4	3	<2	65	107
		locally oxide stain is more intense with oxide		172.5	174.0	1.5	0.2	1	4	60	63
		on sill/dike contacts; BEDDING 162.9-50°tcc		174.0	175.5	1.5	0.4	<1	<2	60	30
		166.0-40°tcc 173.7-50° in laminated fd lst;		175.5	177.0	1.5	<.2	2	<2	60	60
				177.0	178.5	1.5	0.4	1	<2	60	87
		164.0-164.5 lightly bleached rusty to grey		178.5	180.0	1.5	0.2	6	10	70	22
		sandy dolomite cut by 3 cm width ltly		180.0	181.5	1.5	0.4	7	10	70	59
		calcareous qtz veins 55°tcc; margins of		181.5	183.0	1.5	<.2	2	6	60	89
		vein are brecciated w/ white dolspar rich.		183.0	184.5	1.5	0.4	6	4	60	227
		165.5-165.9 moderately bleached fine grained,		184.5	186.0	1.5	0.2	6	2	65	141
		locally laminated dolomitic limestone cut by		186.0	187.8	1.8	<.2	5	4	60	46
		4cm width breccia - quartz; strongly oxidized									
		fragments									
		171.0-172.7 micro veins of white dolspar									
		supporting angular fragments of blue-grey dolomite;									
		fragments locally have weak oxide stain on									
		rims									
		180.7 sharp hiltidge contact between									
		fragmental-biclastic dolomite-phyllite;									
		blue grey med grained dolomite dominate									
		-40°tcc									

EOH 187.8m
G16'

Toklat Resources Inc.

Drill Hole No	Page 12 of 13

DRILL HOLE LOG

RS95-M2

LOCATION: 117m AT AZ 310° FROM RS95-01 (1+00N/0+78E)

DRILL HOLE NO.: RS95-M2

AZIMUTH: 130° | ELEVATION: 2380'

INCLINATION: -45° | LENGTH: 214' / 65.2m

RECOVERY: | CORE SIZE: BGM

STARTED: JUNE 18/95

COMPLETED: JUNE 19/95

PURPOSE: TEST ORIENTATION AND CONTINUITY OF MIKE HILL STRUCTURE

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

PROPERTY: RUSTY SPRINGS

CLAIM NO:

SECTION: 1+00N

LOGGED BY: CCD

DATED LOGGED:

DRILLING CO.: FALCON

ASSAYED BY: ECOTEC

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (a/b) Ag	Cu	Pb	Sb	Zn
0	5'	OVERBURDEN CASING		0	5'	5'	<.2	25	56	60	694
15	53.4	LIMESTONE/ DOLOMITIC LIMESTONE		1.5	3.0	1.5	<.2	30	52	60	828
		fine to med grained blue grey dolomitic limestone;		3.0	4.3	1.3	0.2	44	70	60	528
		3-5% white dolspar in rep. zones, often biodastic		4.3	4.6	0.3	0.4	81	72	65	1742
		debris in 1-3mm width anastomosing stringers		4.6	6.0	1.4	1.6	16	20	65	451
		generally from 20-50 deg; moderately to strongly		6.0	7.5	1.5	4.6	29	46	90	474
		fractured weak to moderate oxide stain on		7.5	9.0	1.5	3.4	28	40	65	513
		fractures; numerous fault zones as noted; local rusty oxide		9.0	10.0	1.0	2.6	14	8	60	266
		stain on argillite rich areas - laminations; local		10.0	10.7	0.7	2.6	15	96	70	302
		thinly bedded		10.7	12.0	1.3	1.0	50	72	65	2032
		28-31 FAULT med dd. lst fragments mixed		12.0	13.5	1.5	1.4	121	58	70	3355
		with fine crush; clay		13.5	15.0	1.5	3.2	83	32	75	441
				15.0	16.5	1.5	2.6	14	8	60	268

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		3.7-9.9 FAULT strongly fractured dol lst		16.5	17.5	1.0	1.6	29	20	65	1052
		fragments mixed w med crush, clay, weak		17.5	18.2	0.7	2.2	19	14	65	717
		patchy pervasive weathering stain; contacts;		18.2	18.6	0.4	3.6	26	36	70	810
		fractures at 60°tca;		18.6	19.2	0.6	0.8	7	6	75	157
		4.3-4.6 QUARTZ VEIN white quartz		19.2	20.7	1.5	1.2	12	24	60	118
		with angular internal fragments of		20.7	21.6	0.9	0.6	13	6	65	770
		dol lst - weak oxide on fractures;		21.6	22.6	1.0	2.4	81	24	65	1615
		4.9-11.6 3-4% quartz in 0.2-0.4 cm veins		22.6	23.7	1.1	2.0	146	20	65	(1.34)
		at 20-35°tca, local rep. fractures		23.7	25.1	1.4	2.2	571	22	60	(153)
		8.2-9.6 FAULT contacts at 25°tca, crs z'd		25.1	25.5	0.4	<.2	2993	26	30	(13.70)
		med angular clasts w local grey-mud,		25.5	27.0	1.5	1.8	30	6	65	3205
		v weakly oxidized		27.0	28.5	1.5	2.6	33	10	65	1311
		10.0-10.7 FAULT med to fine angular clasts		28.5	30.0	1.5	3.8	3	<2	70	341
		w sandy grey clay, contacts @ 30°tca		30.0	31.2	1.2	5.4	7	4	60	712
		11.6-11.7 FAULT med ang. lav crush, contacts		31.2	31.6	0.4	24.6	1660	36	60	4460
		@ 60°tca		31.6	32.6	1.0	5.6	20	10	60	1461
		18.3 MALACHITE 5 cm vuggy qtz - ddspar		32.6	33.6	1.0	2.6	13	10	65	1426
		float zone; single vug healed w malachite		33.6	34.6	1.0	3.2	294	26	60	4901
		19.2-20.7 FAULT crse angular ddomite		34.6	35.6	1.0	3.0	585	30	55	(1.22)
		lst fragments w clay + crush on fractures;		35.6	36.6	1.0	7.4	1006	12	70	3341
		contacts - fractures @ 50°tca; local strong Fe		36.6	37.6	1.0	1.0	57	<2	55	638
		oxide stain on fractures,		37.6	38.2	0.6	1.0	91	<2	70	1882
		21.6-22.6 FAULT med. to fine angular dol lst		38.2	38.6	0.4	0.6	4901	36	60	4246
		fragments mixed w sandy crush, fractures		38.6	39.6	1.0	<.2	70	4	65	1499

Toklat Resources Inc.

Drill Hole No. R995-02 | Page 2 of 65

4346

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		core variably Fe oxide stained;		396	406	1.0	0.4	31	6	60	783
		22.9-23.1 FAULT crse angular ddmtst fragments		406	41.6	1.0	3.6	145	4	60	4221
		mixed ± sandy crush, contacts 39°tca,		41.6	42.8	1.2	3.6	473	4	55	8385
		23.7-23.8 FAULT med to crse angular crush		42.8	44.5	1.7	9.8	710	126	55	(1.98)
		contacts 55°tca		44.5	46.1	1.6	<.2	1001	38	45	(6.66)
		24.4-33.6 increase in rusty zones on fractures		46.1	46.8	0.7	5.8	97	20	55	(2.42)
		in argillaceous laminations, med to strong		46.8	47.7	0.9	11.4	35	28	60	1755
		variable pervasive orange oxide stain		47.7	48.2	0.5	21.2	59	140	60	4050
		25.1-25.5 FAULT crse to med clasts of		48.2	49.7	1.5	9.0	2	32	60	484
		spary ddamtst mixed ± red-orange sandy		49.7	50.7	1.0	5.6	9	52	65	566
		crush, clasts are friable, sharp contacts		50.7	51.3	0.6	2.6	78	46	60	4725
		@ 75°tca;		51.3	51.8	0.5	0.8	46	8	60	2244
		27.2 qtz vein 0.5cm width at 25°tca;		51.8	52.8	1.0	N/S	N/S	N/S	N/S	N/S
		31.2-31.6 FAULT fine to medium sandy		52.8	53.8	1.0	0.8	6	<2	60	N/S
		ddamtst crush, variable pervasive yellow to rusty									
		yellow stain, contacts at 30°tca									
		33.5-33.6 FAULT rusty ddamtst fragments									
		mixed ± sandy crush									
		33.6-[illegible] MODERATELY TO STRONGLY OXIDIZED									
		DOLOMITIC LIMESTONE WITH DOLSPAR ±									
		QUARTZ REPLACEMENT-VEINING, LOCAL									
		MALACHITE-AZURITE									
		med to fine grained med argillaceous ddamtc									
		limestone; moderate to strong variable									

ASSAY INTERVALS ON BACK

Toklat Resources Inc.

Drill Hole No. RS95-02 | Page 3 of 63

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		rusty oxide staining, moderately fractured with rusty orange to red oxides on fractures, local fractures have weakly developed epidote-calcite bowenite, 10% rusty dolspar as floating replacement, 0.1-2 cm veins @ low angle to ca-10-35°, infilling of tension gashes, as saddle dolomite in vugs; 3-5% white to rusty quartz in local float-rich zones, as prismatic xtals in vugs, rare 0.2-0.5 cm veinse 20-45° to ca, broge 0.5-1.5 cm width vugs scattered throughout, rock is lightly bleached,					
		359 TETRAHEDRITE a few specks of disseminated tetrahedrite on 55° to ca str rusty fracture bisected by 0° to ca 0.2 cm width qtz veins					
		36.2-36.4 MALACHITE pale green-blue malachite coating on saddle dolomite in rusty vug with quartz and on rusty 45° and 75° to ca. fractures					
		38.2-38.6 MALACHITE-AZURITE mm width fracture fill; coarse crystalline recrystallized, fractures have deep red oxide & malachite film stepprint,					
		409 pale green acicular radiating xtals on deep red-brown metallic fine grained fracture fill;					

Toklat Resources Inc.

Drill Hole No.	Page 42 of 65

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
"		red-brown metallic mineral has soft brown streak - hematite? goethite?												
		422-428 red to brown to red silver metallic fine grained fill on low angle fractures, red-brown oxides have soft brown to red streak → hematite, red silver mineral is harder and has dendritic habit in places → boulangerite?												
		428-449 FAULT/CAVE 2m core loss, coarse to med. subangular clasts of rusty, sandy to fine grained dolomite, drillers report CAVE or void over this interval; upper contact has pale green radiating acicular mineral on fracture, contacts indistinct; NOTE: RECOVERY INCLUDES BAG OF RUSTY DOLOMITE SAND & QTZ FRAGMENTS												
		468-468 FAULT coarse to moderate subangular clasts of moderately to weakly rusty dolomite mixed with grey dolomite sand,												
		477-482 FAULT angular to subangular generally elongate, dolomite list clasts mixed in sandy earthy grey clay; contacts strong at 85° to CA;												
534	65.2	534-565: decrease in oxides, blue grey, f-med grained, oxidized fractures; no pervasive rusty straw like cleavage; 15% white spar-		52.8	53.8	1.0	0.8	6	<2	60	216			
				53.8	54.8	1.0	2.0	12	4	65	245			
				54.8	55.8	1.0	0.6	7	<2	60	184			

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		moderately fractured;		55.8	56.8	1.0	0.6	8	<2	60	355
		50.0 - 59.9 med grained dolomite = pervasive		56.8	57.9	1.1	2.4	20	<2	60	688
		rusty oxide stain; fracture have lemonite -		57.9	59.0	1.1	7.2	41	10	60	1114
		manganese oxide; oxide stain on argillaceous		59.0	59.9	0.9	4.0	104	18	60	(1.99)
		partings;		59.9	62.3	2.4	0.4	135	74	60	(4.36)
		59.9-62.3 FAULT moderately rusty, sandy		62.3	63.3	1.0	0.2	<1	8	60	281
		dolomite, sandy crush grading into		63.3	64.3	1.0	<2	2	12	60	271
		non rusty sandy dolomite, sandy crush;		64.3	65.2	0.9	0.4	3	8	60	263
		rock on downhole side of fault is									
		distinctly less weathered - oxidized									
		compared to interval above, 1.5m core									
		loss									
		EOH 65.2m / 214' June 19/95									

Toklat Resources Inc.

Drill Hole No.,	Page 6A of 6

DRILL HOLE LOG

RS95-M3

DRILL HOLE NO.: ~~R95-03~~

LOCATION: MIKE HILL 1+00N 0+40E	
AZIMUTH: 250°	ELEVATION: 2375'
INCLINATION: -45°	LENGTH: 55.5m / 182'
RECOVERY:	CORE SIZE: BGM
STARTED: JUNE 20/95	
COMPLETED: JUNE 21/95	
PURPOSE: TEST CONTINUITY & ORIENTATION OF MIKE VEIN STRUCTURE	

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.
55.5m			-46°

PROPERTY: RUSTY SPRINGS
CLAIM NO:
SECTION: 1+00N
LOGGED BY. CCD
DATED LOGGED:
DRILLING CO.: FALCON
ASSAYED BY: ECO TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH (m)	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	20	OVERBURDEN/RUBBLE		0	5'	5'	47.3	30.70	5298	1300	(1.87)
		angular to subangular clasts of rusty dolomite -		5'	10'	5'	282.3	5478	8598	4500	(2.72)
		quartz mixed w brown to rusty orange sandy		10'	15'	5'	334.1	1623	2414	7315	6715
		mud; rare malachite - azurite, dolomite fractures have		15'	20'	5'	134.6	957	796	2845	2469
		goethite - hematite - limonite;									
46	85	STRONGLY WEATHERED RUBBLE		46	60	1.4	230	1701	138	2170	5761
		yellow - brown to yellow to red rubble zone of		60	75	1.5	236	8377	42	110	(8.37)
		sandy to coarse dolomite chips, quartz fragments		75	79	0.4	14.2	4651	44	<5	(21.30)
		mixed with clay & sand; rare frags of		79	85	0.6	19.8	1641	64	<5	(30.80)
		malachite - azurite; orange-red sand @ 60m									
		tests positive for copper;									
		75-79 sandy dolomite cut ⊏ 4mm									
		qtz veins & coated malachite on rusty fractures									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
8.5	11.5	ALTERED DOLOMITE fine to med grained		8.5	9.5	1.0	8.0	1396	116	5	8884
		moderately to strongly bleached dolomite; clear		9.5	10.5	1.0	6.0	2.219	88	15	(2.98)
		varies from bleached grey to grey blue to		10.5	11.5	1.0	0.8	(1.01)	(1.52)	10	(10.30)
		brt red, strongly recrystallized to rusty									
		fracture fill; 2% white qtz in mm veinlets									
		@ 30-55° to c, rare qtz xtals on fractures;									
		5% white dolspar as fracture fill, mm									
		veinlets 30-55° to c, local repl. fractures;									
		pale green mineral in radiating acicular									
		habit on some fractures (rare) tests positive									
		for copper;									
		7.5-7.9 8 cm width breccia zone									
		@ 35° to c, margins have brecciated to									
		orange hematite stain, breccia is									
		strongly altered to original clasts masked,									
		containing qtz - 8%; also on split 0.5-1.5 cm									
		width veinlet of brindle brown to green sphalerite;		11.5	12.7	1.2	42	(1.42)	(1.30)	<5	(1.42)
11.5	15.1	RUBBLE ZONE bright orange to dark		12.7	13.9	1.2	5.8	6572	(15.20)	<5	4703
		grey-black rubble zone of sandy to med		13.9	15.1	1.2	>30	963	(45.80)	30	1310
		dolomite fragments mixed w qtz chips &									
		clay; orange zones test positive for									
		copper, 0.5 cm nodules of black mineral									
		with botryoidal habit, hardness 4, deep									
		brown streak scattered throughout;									

Toklat Resources Inc.

$\frac{1.4}{3.1} = \frac{.5}{x}$ $\frac{1.8}{2.9} = \frac{1.3}{x}$ $\frac{2.4}{3.0} = \frac{.75}{x}$

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		from 13.9-15.1 rubble. is grey in colour = dolomite sandy clay									
15.1	13.1	DOLOMITE light, bleached grey dolomite with pale green soft mineral on fractures - malachite, distinctly less rusty than surrounding rocks		15.1	15.9	0.8	17.4	2667	9234	85	4155
				15.8	18.1	2.3	16.6	6422	(19.60)	<5	(5.63)
13.1	23.6	RUBBLE ZONE bright orange to brown to grey-black dolomite sand mixed = qtz chips, dolomite fragments and mud, orange oxides, test positive for copper to 22.8m; soft pale green mineral on fractures from 17.0-18.2 m tests positive for copper, soft white mineral on fractures from 17.7-17.9 tests negative for copper.		18.1	19.1	1.0	34.3	4409	(2.71)	<5	(7.42)
				19.1	20.0	0.9	234.9	(1.08)	(13.30)	35	(3.23)
				20.0	21.5	1.5	30.4	8702	(2.92)	25	(7.08)
				21.5	22.8	1.3	16.4	1496	8.0	45	(2.06)
				22.8	23.6	0.8	15.4	236	1.2	55	2118
		19.1-20.0 dark grey-black dolomite sand = scattered arsenite-malachite chips, ~ 2% over interval.									
23.6	30.5	RUBBLE ZONE coarse to medium angular clasts of brown-grey to grey fine to med grained dolomite; 35% of interval is moderately bleached, interval is strongly fractured		23.6	23.9	0.3	6.0	193	40	55	1913
				23.9	24.6	0.5	9.4	427	716	55	(1.78)
				24.6	25.6	1.0	5.8	85	16	50	5641
				25.6	26.6	1.0	7.2	126	52	65	3971

Toklat Resources Inc.

Drill Hole No. RSRS-03 | Page 2 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Zn			
		with yellow to orange oxides on fracture		26.6	27.6	1.0	3.2	218	14	60	(1.18)		
		surfaces; fractures at 45-55 to c.a; moderate		27.6	28.6	1.0	1.4	229	16	65	9733		
		pervasive yellow stain over 45% of interval;		28.6	29.4	0.8	2.2	170	16	60	5428		
		grey-sand from 25.8-25.9 / 26.5 26.8 /		29.4	30.0	0.6	5.6	242	130	85	(1.26)		
		27.3-27.5 / 29.4-29.8 / 30.2-30.5		30.0	30.5	0.5	2.0	294	78	65	(1.81)		
		27.5-27.7 qtz veins e 55 to c.a with											
		qtz repl., breccia clasts, breccia clasts											
		have pervasive dusty stain											
30.5	55.5	WEAKLY TO MODERATELY OXIDIZED DOLOMITE,		30.5	31.5	1.0	4.0	70	110	75	1764		
		DOLOMITIC LIMESTONE		31.5	32.5	1.0	2.2	42	22	75	2429		
		fine to med grained grey-brown to blue grey		32.5	33.5	1.0	1.8	27	28	65	948		
		moderately calcareous dolomite; strongly fractured		33.5	34.5	1.0	2.2	14	10	65	1211		
		at 55 to c.a with 80% of fractures coated with		34.5	35.5	1.0	1.4	12	12	65	1011		
		red to orange oxide stain; argillaceous partings		35.5	36.8	1.3	0.6	6	8	60	1175		
		typically oxidized; dolomite hosts weak to		36.8	38.2	1.4	1.0	<1	22	60	398		
		moderate pervasive oxide stain; 5-8%		38.2	39.2	1.0	2.8	43	24	75	671		
		white to yellow spar as repl. of argillic blocks		39.2	40.0	0.8	0.8	33	22	65	428		
		tic debris, mm anastomosing stringers;		40.0	41.0	1.0	3.0	55	84	75	2466		
		dolomite hosts 20% small to med vugs healed w		41.0	42.0	1.0	3.4	71	82	116	2601		
		calspar, dolspar, red blebby mineral →		42.0	42.8	0.8	0.8	101	16	75	8901		
		hematite?		42.8	43.4	0.6	1.6	12	22	65	737		
		329° FAULT 5cm band of fine to medium		43.4	44.2	0.8	1.0	40	64	70	2266		
		dolomite crush mixed with black sand		44.2	46.7	2.5	0.6	26	32	65	964		

Toklat Resources Inc.

Drill Hole No. RS05-03 | Page 4 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Hg	Cu	Pb	Sb	Zn
		contacts at 55°tca;		46.7	47.7	1.0	0.8	21	28	75	295
		38.2-39.2 FAULT strongly oxidized dolomite;		47.7	48.3	0.6	<.2	4	<2	60	106
		strongly fractured angular fragments mixed in		48.3	49.6	1.3	0.8	20	3.2	70	518
		rusty sand, contacts indistinct at high angle		49.6	50.7	1.1	0.4	18	1.4	65	11.1
		(70-35°tca)		50.7	51.7	1.0	0.4	3	8	60	727
		42.5-42.3 FAULT strong red to orange to		51.7	52.7	1.0	1.0	81	<2	95	2446
		yellow oxide overprint on medium to fine		52.7	53.7	1.0	0.6	14	<2	60	1056
		dolomite crush, from 42.6-42.3 strong		53.7	54.8	1.1	0.2	2	<2	60	456
		oxide overprint is on medium grained		54.8	55.5	0.7	0.4	3	8	65	314
		dolomite, contacts at 35°tca;									
		43.4-46.7 FAULT fine to medium dolomite									
		fragments mixed with sandy crush, mud;									
		from 43.4-44.2 rubble has intense pervasive									
		red-orange-yellow oxide overprint; from									
		44.2-46.7 oxide overprint is less intense									
		and mainly yellow, NOTE: 1.0m core loss									
		over interval									
		FAULT 46.7-49.6 bleached dolomite with local									
		soft white clay alteration; interval is									
		strongly fractured with gouge clay, sand									
		scattered throughout; lower contact has									
		2cm band of fine grey sand @ 65°tca;									
		EOH 55.5m / 182'									

Toklat Resources Inc.

Drill Hole No. RSDS-03 | Page 5 of 55

DRILL HOLE LOG

RS95-M4

DRILL HOLE NO.: ~~RS95-M4~~

LOCATION: MIKE HILL 1+00N 10+40E		PROPERTY:	
AZIMUTH: 250°	ELEVATION: 2480	CLAIM NO:	
INCLINATION: -75°	LENGTH: 32.3m/106'	SECTION: 1+00N	
RECOVERY:	CORE SIZE: BGM	LOGGED BY: CCD	
STARTED: JUNE 21		DATED LOGGED:	
COMPLETED: JUNE 22		DRILLING CO.: FALCON	
PURPOSE: TEST FOR DIAMOND MINERALIZATION SEEN IN RS95-03		ASSAYED BY: ECOTECH	

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	10'	OVERBURDEN / RUBBLE angular fragments		0	5'	5'	40.3	3580	2670	830	(9.03)
		chips of white quartz, rusty dolomite, blue grey		5'	10'	5'	50.3	3168	7814	880	(4.77)
		dolomite; scattered malachite-azurite assoc w									
		qtz, in dolomite fractures									
3.0	4.0	RUBBLE coarse to medium angular to subangular		3.0	4.0	1.0	256	2419	2406	360	(16.80)
		fragments of rusty med. grained dolomite and									
		white quartz; qtz carries malachite-azurite; dolomite									
		has local qtz repl - qtz veining, thin films of pale									
		blue green copper mineral on fractures;									
4.0	5.4	SAND fine white quartz chips + rusty to		4.0	5.4	1.4	418.6	3670	4468	8125	(5.73)
		brown dolomite sand, fine grained galena and									
		marcasite-azurite scattered throughout sand - est									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		1% each, upper 10 cm in med dolomite rubble												
54	67	RUBBLE - medium to fine angular clasts & chips of dolomite mixed with sandy, qtz rich fragments; 1% diss malachite scattered over interval; interval is strongly oxidized with orange to yellow yellow stain, sharp contact with underlying zone is in muddy interval so no distinct angle		5.4	6.7	1.3	210.4	.2148	344	835	7696			
67	75	DOLOMITE - DOLOMITE SAND dark grey to grey-brown sandy dolomite - dolomite sand; 35% of interval has strong blue-green malachite-azurite alteration with corresponding strong positive copper tests; 2 cm quartz vein @ 69m has malachite on fracture;		6.7	7.5	0.8	132.6	(1.03)	288	560	(10.40)			
75	91	RUBBLE fine to coarse dolomite fragments, dolomite sand mixed with mud, clay, occ qtz fragments; moderate to weak orange to yellow oxide stain;		7.5	9.1	1.6	152.4	(1.08)	376	710	(11.30)			
91	323	DOLOMITE - DOLOMITIC LIMESTONE med to dark grey med. to fine grained fossiliferous, argillaceous, dolomite; locally calcareous, 5-8% white dolospar		9.1	10.3	1.2	17.0	462	18	75	(1.48)			
				10.3	11.0	0.7	4.0	3608	10	60	(8.40)			
				11.0	11.6	0.6	39.3	8760	44	60	(10.33)			

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		as fossil repl. in mm fracture fills - anastamos-		11.6	12.6	1.0	10.0	235	26	70	5092
		ing stringers, local matrix breccia infill; moderate-		12.6	13.6	1.0	10.8	257	34	60	4741
		ly fractured with red-orange oxide stain on		13.6	14.6	1.0	3.4	448	18	60	4182
		fractures, local pervasive oxide stain as		14.6	15.6	1.0	7.0	119	12	70	1130
		described below:		15.6	16.6	1.0	30.3	100	18	60	4112
		9.1-11.0 moderate to strong pervasive		16.6	17.6	1.0	31.4	178	40	65	(1.26)
		yellow to orange oxide stain, argillaceous		17.6	19.1	1.5	34.6	3250	188	20	(10.26)
		partings - fractures strongly reduced;		19.1	20.1	1.0	2.6	1678	<2	40	(6.36)
		from 10.3-11.0 5% pale blue green		20.1	20.9	0.8	3.8	1143	10	50	(4.81)
		soft botryoidal to reticulating mineral -		20.9	22.4	1.5	9.8	6480	22	10	(10.72)
		chrysocolla? that tests positive for copper		22.2	24.9	1.7	12.4	342	48	65	.010
		11.0-11.6 FAULT sandy dolomite fault gouge		24.9	25.9	1.0	6.8	39	<2	60	368
		with pervasive yellow oxide overprint, contacts		25.9	26.9	1.0	6.0	299	<2	60	(1.54)
		indistinct;		26.9	27.9	1.0	13.6	75	18	65	952
		17.2-17.3 FAULT rusty red dolomite sand mixed		27.9	28.9	1.0	9.0	38	<2	65	828
		with deep red hematite sand, green-blue		28.9	29.9	1.0	8.4	39	26	65	689
		copper mineral, sharp contacts @ 75°CA,		29.9	30.9	1.0	8.0	55	20	70	543
		17.6-24.8 FAULT ZONE medium to fine		30.9	32.3	1.4	3.4	48	18	60	773
		grained to sandy dolomite with pervasive									
		red-orange to yellow oxide stain, strongly									
		fractured; 35% of interval is fine to med									
		fragments of dolomite mixed with sandy mud,									
		fine to med grange, qtz fragments; 3% malachite									
		azurite scattered over interval; deep orange									

Toklat Resources Inc.

Drill Hole No.	Page 3 of 4

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		sandy mud zones test positive for copper to 23.2m, no distinct fault contact angles; 29.9-32.3 strongly fractured with strong red to red orange oxide stain in fractures and clay argillaceous partings; FAULTS from 26.2-26.3m, 26.9-27.1m, 29.0-29.1m, 29.9-30.0 m with contacts indistinct but generally at high angle tca (≥ 75° tca)					
		EOH 32.3m / 106'					

Toklat Resources Inc.

Drill Hole No. BS95-04 | Page 4 of 4

DRILL HOLE LOG

RS95-M5

LOCATION: RUSTY SPRINGS MIKE HILL 1+75N/01+15E			DRILL HOLE NO.: ~~RS95-05~~
AZIMUTH: ~~150°~~ 130°	ELEVATION: 2300'		PROPERTY:
INCLINATION: -45°	LENGTH: 255'/77.7m	SURVEYS	CLAIM NO:
RECOVERY:	CORE SIZE: BGM	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: ~~2300N~~ 1+75N
STARTED: JUNE 22			LOGGED BY: CLD
COMPLETED: JUNE 26			DATED LOGGED:
PURPOSE: TEST VEIN MINERALIZATION IN 200 TRENCH AND SOURCE OF GEOCHEM ANOMALY			DRILLING CO.: FALCON
			ASSAYED BY: ECOTECH

CORE RECOVERY.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	27	OVERBURDEN		0	5'	5'	23.6	338	924	135	2622
		0-5' brown dirt - organic debris mixed with		5'	10'	5'	1.6	208	164	50	1034
		medium to crse fragments of siliceous		10'	15'	5'	90.9	627	240	40	1330
		blue-grey dolomite		15'	20'	5'	70.4	500	154	20	819
		15-20' yellow brown clay + sand mixed with		20'	25'	5'	183.4	650	158	10	826
		medium to crse fragments of quartz + brown		25'	27'	2'	209.8	681	170	15	925
		sandy dolomite, quartz fragments have crse									
		well formed xtals of sphalerite + tetrahedrite									
		20-25' med brown clay + sand mixed with fragments									
		of brown sandy dolomite, blue-grey dolomite									
		white qtz									
		25-27' red-brown rusty sand + clay mixed with									
		fragments of sandy dolomite, blue-grey dolomite									
		quartz; quartz has crse xtals of sphalerite									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION
		16.8-19.3 well consol. dated, sl.
		yellow to orange sandy dolom
		clay alteration; 5% 0.1-0.5 cm
		veining.
		19.3-20.1 well developed med
		th sandy dolomite with per
		orange ox.de stain, wgs
		elongate perpend dur to ca;
		hematite, goethite, white cl
		20.1-21.3 med grained dol
		perv.s.te ox.de stain, lem
		clay alteration on fractures;
		21.1-21.3 FAULT ore
		rubble mixed with o
		e 33° to ca;
21.3	59.7	DOLOMITE light to medium
		fine to medium grained, fos
		dolomite, dense, moderately frac
		fractures have ox.de stain with
		hematite; argillaceous partings ar
		4% white dolospar as fossil repl

Toklat Resources

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH
		on fractures				
8.2	11.1	RUBBLE / FAULT? strongly weathered angular clasts		8.2	9.3	1.1
		of blue-grey dolomite, brown sandy to med. grained		9.3	11.1	1.8
		dolomite mixed with yellow to orange to brown				
		sand, med, 5% white qtz fragments, chips, 10 cm				
		qtz vein e 9.3m has strong hematite clay-oxide				
		margin with contact e 68° to ca, dolomite is cut by				
		mm qtz vein stockwork in places;				
11.1	11.8	QUARTZ VEIN strongly fractured, white to rusty,		11.1	11.8	0.7
		medium to coarse quartz fragments; upper +				
		lower contacts are with med grey strongly				
		microfractured shale, strong red-orange ox.de				
		stain on fractures; coarse pyrite bleb e 11.2 is altered				
		avg. fractures generally 45-55° to ca,				
11.8	15.0	RUBBLE, FAULT? med to coarse (up to 15 cm length)		11.8	13.5	1.7
		strongly fractured blue-grey to rusty brown med		13.5	14.2	0.7
		grained dolomite; fractures are ox.d. red, generally		14.2	15.0	0.8
		e 55-65 to ca, 2% white qtz fragments with				
		oxidized fractures, 10 cm qtz vein from 14.3-14.4				
		has sharp contacts 45 to ca;				
		13.5-13.7 FAULT fine shaly crush mixed				

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		29.1-29.3 FAULT med to crse clasts of oxidized dolomite mixed with sand, clay + qtz fragments; contacts @ 60°tca					
		30.0 FAULT similar to above with fine to medium dolomite crush mixed with qtz fragments, contacts @ 45°tca,					
		36.5-37.9 FAULT med. to crse oxidized sand, dolomite fragments mixed with sand + dolomite crush; 5% scattered qtz fragments, pervasive oxide stain is yellow to orange to red, contacts @ 65°tca,					
		39.1-39.3 2x3cm width white to clear qtz vein 50°tca,					
		39.2-51.0 moderate to strong pervasive red oxide stain + red oxide in fractures + in argillaceous partings					
		45.9-46.1 FAULT fractured fine to med dolomite crush, contacts indistinct, margins have intense pervasive red oxide stain;					
NOTE: PDE RECEIVED FROM Toklat Inc.		51-53.4 FAULT - RUBBLE zone medium angular fragments of dolomite and quartz mixed with sand + clay - weak pervasive oxide stain, contacts indistinct;					

Toklat Resources Inc.

Drill Hole No. RSDS-05 | Page 5 2 of 6

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		539 56.7 RUBBLE clean angular dolomite fragments + qtz fragments, rusty fractures									
		56.9-593 RUBBLE-FAULT dolomite sand mixed with quartz chips + fragments of bleached grey dolomite, contacts indistinct									
597	777	DOLOMITE BRECCIA strongly brecciated light to medium grey, moderately bleached dolomite, fine to medium to crse angular to subangular fragments in a matrix of white sparry dolomite; moderately to strongly fractured with rusty oxides on fractures;		59.7	61.2	1.5	0.6	19	90	65	256
				61.2	62.8	1.6	0.4	5	242	55	533
				62.8	64.3	1.5	0.8	5	80	65	200
				64.3	65.8	1.5	1.4	8	136	65	257
				65.8	68.9	3.1	0.6	11	136	65	234
				68.9	71.9	3.0	0.4	10	48	65	116
		62.7-62.8 5 cm width qtz vein @ 15° tca		71.9	75.0	3.1	0.8	127	24	60	1580
		with sphalerite, tetrahedrite in crse		75.0	77.7	2.7	0.8	11	30	70	119
		crystals.									
		643-777 RUBBLE fine to crse angular to subangular fragments of dolomite breccia, quartz vein fragments scattered throughout									
		EOH 777m/2551									
		HOLE STOPPED DUE TO DRILLING PROBLEMS - LOSS OF CIRCULATION									

Toklat Resources Inc.

Drill Hole No. RS95-05 | Page 6 of 6

RS95 27 -65°
50'-

DRILL HOLE LOG

RS95-M6

LOCATION: ~~2100W 0+25E~~ 1+75N/0+15E		DRILL HOLE NO.: RS95-6	
AZIMUTH: 130°	ELEVATION: ~~2300'~~	PROPERTY:	
INCLINATION: -80°	LENGTH: 108'/329m	CLAIM NO:	
	CORE SIZE: BGM	SECTION: 1+75N	
STARTED:		LOGGED BY: CCD	
COMPLETED:		DATED LOGGED:	
PURPOSE:		DRILLING CO.: FALCON	
		ASSAYED BY: ECO TECH	

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (oz) Ag	Cu	Pb	Sb	Zn
00	15'	O/B brown to rusty brown dirt mixed with		0	15	1.5	38	173	416	80	1571
		fragments of grey-blue ddomite, ddomite breccia		15	30	1.5	0.4	136	140	50	726
		multilithic ddomite-chert breccia and minor		30	4.5	1.5	<.2	138	56	50	507
		quartz.									
4.6	49	RUBBLE coarse angular to subangular clasts of		46	49	0.3	<.2	11	10	60	119
		med grey lightly bleached ddomite; fractures have									
		orange ox de stain, ddomite has 25% white									
		ddspar vein.									
49	5.2	FAULT fine to medium strongly oxidized-		4.9	5.2	0.3	<.2	920	<2	<5	2457
		weathered ddomite crush, contacts indistinct									
		but appear to be at high angle tco (>75°)									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
5.2	7.6	DOLOMITE BRECCIA strongly bleached light grey med		5.2	6.4	1.2	<.2	298	34	40	1120
		to fine subangular fragments of dolomite, bleaching		6.4	7.6	1.2	<.2	238	20	40	1073
		has destroyed original texture. Boundaries matrix									
		matrix unresolvable, 10% angular to subangular									
		white clay altered flecks; moderately fractured ss									
		tca : strong orange to purple red to less on fract.s -									
		limonite, goethite, hematite, fracture margins often									
		have pervasive oxide stain:									
		5.5-5.6, 5.9-6.1 strong orange to green-orange									
		gossanous rotten, porous rock riddled with									
		fine to coarse vugs; 2ee contacts sharp at									
		55° tca; white clay alteration in mm veinlets									
		on fractures,									
		6.6-7.3 fine to medium open boxwork on									
		moderately altered dolomite; mm stockwork of									
		carbonate veins removing resistant matrix soft									
		porous clay altered rock more weathered;									
		moderately fractured 0° tca - 55° tca with strong									
		deep orange oxide stain on fractures;									
7.6	21.6	MULTILITHIC BRECCIA angular to subangular fragments		7.6	8.5	0.9	<.2	515	28	25	2243
		of fine grained siltstone-shale (85%) and fine		8.5	9.1	0.6	<.2	599	42	<5	3860
		to med grained dolomite (<25%), matrix varies		9.1	10.3	1.2	<.2	208	26	<5	1945
		from fine tectonic crush to rusty argillite;		10.3	11.6	1.3	0.2	196	30	<5	2067

Toklat Resources Inc.

Drill Hole No. RS95-06 | Page 2 of 2

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		grey siltstone-shale cut by mm white spar veinlets		11.6	13.1	1.5	<.2	232	32	<5	1410
		that are pre brecciation matrix is replaced in		13.1	14.6	1.5	<.2	219	30	<5	1875
		part by white spar. 35% of interval has strong		14.6	16.2	1.6	0.4	241	50	<5	918
		to moderate pervasive sericite alteration which affects		16.2	17.7	1.5	<.2	248	114	<5	1[illegible]
		both individual clasts in some parts and in others		17.7	17.9	0.2	<.2	28	26	60	1[illegible]
		is pervasive over 15 cm intervals, colours range		17.9	18.7	0.8	<.2	229	34	<5	1102
		from pale yellow to orange to bright red-		18.7	20.3	1.6	<.2	218	28	<5	715
		orange aphanitic 25% of interval has vuggy		20.3	21.6	1.3	<.2	482	106	<5	2[illegible]5
		angular boxwork of carbonate veins or angular									
		boxwork in strong clay altered zones									
		12.5-14.3 strong rusty argillaceous									
		laminations 85-95 tca									
		16.2 16.4 2 x 4 cm width veins of white									
		quartz calcite;									
		NOTE REDUCE TO BQM at 17.7m									
		17.7 17.9 RUBBLE rounded pebbles of									
		dolomite, qtz, clean; drilling rubble to									
		reduction;									
		17.9-21.6 multilithic clasts become									
		dominantly sandy brown dolomite; mod									
		to strong pervasive oxidation with									
		goethite-hematite on fractures; strong									
		yellow-brown alteration at 19.7 may be limonite;									

Toklat Resources Inc.

Drill Hole No.	Page 32 of 45

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		± FAULT ZONE									
21.6	32.9	QUARTZ VEIN, QTZ VEIN STOCKWORK massive to stockwork white f. to grained to locally quartz, overall vein attitude is at low angle to CA (15-25° to CA), 35% of interval is strongly fractured/silicified to strongly oxidized medium to locally dolomite fragments are commonly mixed with dolomite sand and/or crush, in places fragments are rotten-vuggy with intense red-orange to yellow overprint; larger quartz veins carry tetrahedrite and sphalerite? in large crystals and rare patches, tetrahedrite kinds noted at 22.9, 26.2m, 29.7m		21.6	23.2	1.6	0.4	241	61	10	1481
				23.2	24.3	1.1	0.6	87	100	<5	762
				24.3	26.1	1.8	<.2	484	40	<5	441
				26.1	27.0	0.9	1.0	35	20	10	120
				27.0	28.3	1.3	1.4	176	36	35	652
				28.3	29.6	1.3	3.4	920	90	140	2491
				29.6	31.3	1.7	20	367	58	50	5374
				31.3	32.9	1.6	0.2	196	34	35	670
		NOTE: RECOVERY POOR OVER THIS INTERVAL 27.4-29.5 FAULT fine to rare fragments of qtz, strong oxidized dolomite, hematite-qtz breccia mixed with sand, fine crush									
		EOH 32.9m									

Toklat Resources Inc.

Drill Hole No.	Page 4 of 5

NOTE

DRILL HOLE LOG

RS95-M7

LOCATION: MIKE HILL ~~2400N/0+15E~~ 1+75N/0+15E

DRILL HOLE NO: ~~RS95-C~~

AZIMUTH: 130°	ELEVATION: 2300'	SURVEYS				PROPERTY:	
INCLINATION: -60°	LENGTH: 439m / 144'	METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.	CLAIM NO:	
RECOVERY	CORE SIZE: BGM 0-17.4 NQ 17.4-439.0 BQ					SECTION: 1+75N	
STARTED:						LOGGED BY: CCD	
COMPLETED:						DATED LOGGED:	
PURPOSE:						DRILLING CO.: FALCON	
						ASSAYED BY: ECO TECH	

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	14'	OVERBURDEN		0	5'	5'	<.2	247	72	45	-XT.
		angular to subangular, strongly fractured clasts		5'	10'	5'	0.4	367	156	40	1120
		of dolomite - dolomite breccia, moderate to strong		10'	14'	4'	<.2	245	140	40	846
		oxide on fractures, clasts mixed with sand									
		pebbles and clay with interval 5-10' having									
		abundant clay									
4.3	4.9	DOLOMITE BRECCIA fine to coarse strongly fractured		4.3	4.9	0.6	<.2	27	1414	45	251
		to finely milled clasts of strongly bleached light									
		grey dolomite; matrix well cemented with									
		dark blue matrix possibly indicating presence of									
		marcasite, weak oxide stain on fractures except									
		in core zone - vuggy, porous strongly altered									
		w orange to yellow pervasive staining, qtz vein near									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		top of interval 3 cm width qtz stkwk has euhedral tetragonal xtals dk brown vitreous - tetrahedrite & sphalerite, vein margins str oxidized.									
49	100	MULTILITHIC BRECCIA subangular medium to coarse breccia fragments with strong to moderate pervasive oxide stain strong alteration has destroyed much of original rock texture, colour ranges from yellow to rusty orange; mod to strongly fractured 45°CA; 9% mm-cm qtz vein 45-65°CA, white clay alteration on fractures		4.9	5.2	0.3	<.2	780	188	<5	.148
				5.2	5.9	0.7	<.2	460	<2	<5	1087
				5.9	6.9	1.0	<.2	193	178	<5	915
				6.9	8.1	1.2	<2	188	76	<5	2411
				8.1	9.3	1.2	<2	398	124	<5	974
				9.3	10.0	0.7	0.2	203	88	<5	665
		4.9-5.2 Gossan str pervasive rusty orange oxide on crumbly porous fragments; upper contact is boxwork of carbonate veins									
		5.2-5.9 as above washout str gossan overprint; white clay alteration on fractures; weakly oxidized; quartz visible at top of interval;									
		8.7 Quartz vein 1-3cm width qtz vein - quartz band with euhedral tabular to pyramidal deep brown crystals - sphalerite or tetrahedrite;									
		9.3-10.0 less altered multilith breccia clasts									

Toklat Resources Inc.

Drill Hole No. BSAS-07 | Page 2 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Zn
		become dominantly clerty shale; contact								
		with underlying clerty shale is sharp								
		w. thin gouge & contact zone fracture, looks								
		like a sedimentary contact;								
100	13.1	CHERTY SHALE - SILTSTONE dark grey blue		10.0	11.1	1.1	0.2	77	142	<5	104
		fine siltstone to shale, pervasive clerty		11.1	12.1	1.0	0.8	101	96	<5	226
		silica alteration; weak to moderate pin		12.1	13.1	1.0	1.6	540	38	5	512
		point vuggyness; 10% quartz in 1-3 cm									
		w. lith veinse 55 tca, as repl. in fractures									
		& gashes; fractures moderately to strongly									
		oxidized with rare oxide in vugs									
		11.4-13.1 BRECCIA fine, fractured subrounded									
		clasts of clerty shale in a matrix of white									
		quartz or weakly oxidized orange clay;									
		looks like a shatter type breccia with									
		little clast displacement and ~ 5% matrix									
		fractures @ 85 tca;									
13.1	13.4	MULTILITHIC BRECCIA similar to above with		13.1	13.7	0.6	6.2	1587	120	10	1851
		str red orange selective-pervasive oxide stain;									
		well cemented, mod silicious; 1% malachite replace-									
		ment									

Toklat Resources Inc.

Drill Hole No. PS95-07 | Page 2 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
13.4	13.7	QUARTZ BRECCIA / REPLACEMENT 40% white quartz in veins, fragments + repl in dk grey siliceous siltstone; vein contacts e 10-60°tca; fractures have weak green blue copper stain;									
13.7	15.6	SANDY DOLOMITE med to rusty brown sandy dolomite; high primary porosity, strongly altered with pervasive yellow-brown to rusty brown overprint, local texture suggest a collaform pattern; 14.1-14.5 low angle band of quartz fragments - quartz replacement; 15.1-15.3 BRECCIA strongly oxidized fragments of sandy dolomite and white qtz; green stain on fractures		13.7	14.5	0.8	3.4	970	152	<5	3354
				14.5	15.6	1.1	5.0	3960	356	<5	(1.36)
15.6	17.7	QUARTZ VEIN white quartz vein, moderate fine to medium grained; locally rusty and carry sphalerite-tetrahedrite; 5% angular clasts of sandy dolomite - dk grey shale;	REJECTED BGM AT 17.4m	15.6	16.7	1.1	0.8	120	358	5	26?
				16.7	17.7	1.0	0.4	51	250	35	1.29
17.7	19.1	BRECCIA strongly oxidized moderate to well consolidated breccia clasts, local mm qtz. veining e 60°tca		17.7	19.1	1.4	0.8	1256	3668	<5	2.48

Toklat Resources Inc.

Drill Hole No. RS95-07 | Page 4 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
191	217	QUARTZ VEIN-REPLACEMENT 95% white		19.1	20.3	1.2	5.4	1435	1060	20	1779			
		quartz veining, quartz rock, quartz breccia,		20.3	21.7	1.4	3.0	847	214	45	695			
		60% clasts of med grey to rusty orange												
		dolomite, 40% of interval has strong												
		yellowish oxide stain, rare (< 2%) sulphide												
		tetrahedrite-sphalerite in vugs in qtz; on												
		fractures, black dendritic mineral on fracture at												
		190° is possibly an oxide of native Cu or tetrahedrite												
		native Ag? pyrargyrite 1%, veins @ 40-65° tca												
217	439	MINERALIZED BRECCIA strong pervasive		21.7	22.5	0.8	11.6	4072	104	125	1720			
		alteration of breccia; alteration has destroyed		22.5	23.5	1.0	31.6	(7.78)	128	1845	5774			
		original textures except 21.7-22.3 with		23.5	24.5	1.0	8.6	(7.72)	102	360	5102			
		distinct angular to subangular fragments in		24.5	25.5	1.0	409.3	(1.44)	594	6850	7866			
		str. oxidized matrix, 5% quartz in low angle		25.5	26.6	1.1	31.2	(1.49)	150	2180	4115			
		(5-15 tca) veins and in angular subangular		26.6	27.6	1.0	111.2	.149	134	480	1333			
		replacement fragments; rock is porous-		27.6	28.6	1.0	11.2	936	38	410	1425			
		vuggy with local calcareous zones often		28.6	29.6	1.0	283.6	(1.33)	6442	7520	(2.06)			
		associated with malachite-azurite; rock has pervasive		29.6	30.6	1.0	760.4	(1.01)	6186	(1.02)	27L			
		stain to rusty brown overprint;		30.6	31.4	0.8	1384.0	(4.32)	2.28	(1.78)	780			
		MINERALIZATION 10% malachite-azurite		31.4	32.4	1.0	156.2	(6.14)	52	5535	7645			
		in fine to coarse dissemination on breccia		32.4	33.8	1.4	158.4	(2.52)	456	9750	5957			
		fragments, assoc. with qtz in low angle		33.8	34.8	1.0	397.4	4033	1898	8950	3584			
		veins (5% tca), qtz veins + repl. locally assoc		34.8	35.8	1.0	652.3	(4.48)	(1.22)	(1.15)	8257			

Toklat Resources Inc.

Drill Hole No. RSAS-07 | Page 5 2 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Cd	Zn
		with malachite, crse crystals of sphalerite, malachite		35.8	36.8	1.0	1198.2	(2.23)	(7.01)	(1.68)	(1.37)
		azurite range in colour from pale green to		36.8	37.8	1.0	2336	(1.36)	4760	8505	5772
		turquoise to deep metallic blue; pale green bladed crystals - calcite?		37.8	38.8	1.0	984.6	(8.46)	3986	(1.56)	(5.46)
		26.6-27.4 strongly fractured white qtz		38.8	40.5	1.7	1294	9032	870	2630	7684
		vein with perusive rusty oxide on fractures		40.5	41.1	0.6	33.4	96109	290	1020	8795
		in vugs, crse sphalerite crystals in vugs +		41.1	42.0	0.9	797.6	(4.27)	(7.03)	(1.02)	(1.44)
		in 0.2-0.5 cm rusty veinlets low angle		42.0	42.8	0.8	249.4	(2.18)	802	4530	(3.36)
		tcc, est 3-4% Zns over zone;		42.8	43.4	1.1	694.3	(7.29)	4854	8825	(7.60)
		30.5-32.4 well mineralized interval with									
		20-25% azurite + malachite, 50% white to									
		crystalline qtz, strongly fractured;									
		32.4-37.3 strongly oxidized zone, strong									
	★360 single large chip of galena.	perusive rusty orange stain; 15%									
		qtz - low angle (5-15°cal) veins carry									
		sphalerite-azurite;									
		37.8-40.5 25% deep blue to turquoise									
		azurite on low angle fractures and as repl.									
		of breccia clasts, deep purple colours									
		developed in places; strongly fractured									
		with local sand-crush - may be									
		FAULT related									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		40.5-43.9 alternating zones of strongly altered rusty orange moderately to poorly consolidated breccia and quartz rich strongly bleached light grey dolomite with azurite-malachite on fractures, as repl; interval is strongly fractured with sand and clay mixed with clasts; local white clay alteration on fractures					
		43.6-43.9 40% bright to deep blue fine to med grained azurite on fractures as repl					
		HQ3 HOLE LOST AT 43.9m DUE TO DRILLING PROBLEMS! 130' CASING & CORE BBL ASSBLY LEFT IN HOLE					
		EOH 43.9m					

Toklat Resources Inc.

DRILL HOLE LOG

RS95-M8

LOCATION: RUSTY SPRINGS MIKE HILL 1+75N/0+15E			DRILL HOLE NO.: RS95-M8
AZIMUTH: 130°	ELEVATION: 2300'		PROPERTY:
INCLINATION: -60°	LENGTH: 87.8m/288'		CLAIM NO:
RECOVERY: 74.6%	CORE SIZE: NQ		SECTION: 1+75N
STARTED: AUGUST 15 1995			LOGGED BY: CCD
COMPLETED:			DATED LOGGED:
PURPOSE: REDRILL NEAR RS95-M7			DRILLING CO.: FALCON
			ASSAYED BY: ECO TECH

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.
802m/263'			

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0'	25'	OVERBURDEN		0	5'	5'	<.2	251	228	45	1707
		0-15' brown to weakly orange-brown sand		5	10'	5'	0.2	441	136	50	1043
		& mixed = fragments of grey dolomite -		10'	15'	5'	0.2	5751	58	55	1549
		grey dolomite breccia, H core recovered		15'	20'	5'	<.2	432	124	<5	1815
		from 10-15' is grey moderately bleached		20'	25'	5'	<.2	210	64	<5	1199
		dolomite = microfractures healed =									
		crystalline, weak rusty stain some									
		fractures,									
		15-25' bright orange to red gossan;									
		original rock texture destroyed except									
		for quartz fragments; H core has									
		2 cm vein of clear to white quartz									
		@ tca									

Toklat Resources Inc.

Drill Hole No. RS95-M8 | Page 1 of 3

RECOVERY/SAMPLE ON BACK

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		20-25' dark brown fine, vuggy shale breccia, good H core over interval; moderate variable rust overprint; 0.5 cm calc veins @ 45° tca have mm euhedral terminated xtals									
7.9	8.5	RUBBLE / GROUND CORE									
		coarse rounded pebbles of quartz and vuggy shale		~7.9	8.5	0.6	0.4	110	20	<5	465
8.5	14.1	MIXED SHALE - MARL		8.5	9.9	1.4	0.2	115	120	5	587
		black fine grained shale; local fossil debris		9.9	10.9	1.0	1.4	207	622	15	315
		zones have white calcite replacement of bioclasts		10.9	11.9	1.0	1.0	131	92	5	149
		(coral, crinoid ossicles), in part fine vuggy zones		11.9	12.8	0.9	1.8	351	116	5	316
		developed after biodastic debris; moderate to strong variable pervasive oxide stain;		12.8	14.3	1.5	2.8	753	258	<5	761B
		moderately fractured; local microbreccia healed = clay, argillite ± calcite; 5%									
		calcite per interval; 3-5% quartz in 1-2cm width bands - replacement zones @ 60-80° tca, single 1cm width vein @ 10.3 m ° tca.									
		8.7 FAULT 3 cm width band of fine sandy orange crush; contacts sharp @ 55° tca.									

Toklat Resources Inc.

Drill Hole No. RS95-MB | Page 2 of 9

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		12.8-14.1 STRONG DEFORMATIVE RUSTY STAIN												
		brecciated-microfractured shale =												
		pervasive orange to orange-brown												
		oxide stain; 2% qtz in mm stringers												
		@ 0-25 tca; shale-dolomite contact												
		based on presence of $CaCO_3$												
14.1	16.4	DOLOMITE - DOLOMITIC SHALE		14.3	15.8	1.5	0.4	368	12	50	3172			
		medium to light grey fine grained		15.8	16.4	0.6	1.0	2645	46	40	774			
		dolomite - dolomitic shale												
		variable moderate bleaching, moderately												
		fractured = mm microfractures @ 45 tca,												
		fractures typically have black oxide												
		stain on surface; 4% quartz in 1-												
		2 cm width veins @ 15-45 tca; in												
		local fracture fill; 30% pervasive												
		orange to orange-brown oxide stain;												
16.4	17.6	GOSSAN		16.4	17.6	1.2	2.0	5428	2970	300	6835			
		pervasive deep orange-red oxide;												
		original rock is dolomite as above =												
		~85% of original rock texture masked												

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		strong clay alteration; zone tests positive for copper oxides;												
17.6	19.2	QUARTZ VEIN		17.6	19.2	1.6	5.8	1106	726	10	774			
		white bull quartz ± weak pervasive oxide alteration												
		18.7-19.0 RUBBLE - FAULT ZONE												
		fragments of vuggy ferruginous												
		shale mixed with sand; mud;												
		contacts indistinct;												
19.2	37.0	VARIABLY MINERALIZED BRECCIA		19.2	20.5	1.3	3.8	4224	182	40	8299			
		fine to course angular to subangular		20.5	22.0	1.5	9.2	3051	58	35	(2.26)			
		clasts of med. to fine grained dolomite;		22.0	23.8	1.8	6.4	854	188	15	9071			
		matrix is typically black weakly calcareous		23.8	25.3	1.5	0.8	563	58	120	1216			
		argillite; non oxidized intervals are typically		25.3	26.8	1.5	16.2	1361	60	750	1400			
		bleached; moderately to strongly fractured		26.8	28.0	1.2	98.9	6158	346	1995	1346			
		with orange to black oxide on fractures;		28.0	29.9	1.9	5.8	555	100	520	1059			
		5% quartz in 0.5-3cm width veins		29.9	31.2	1.3	18.8	3096	190	730	2698			
		& 0-2% fine quartz veins locally have		31.2	32.7	1.5	91.3	2811	822	1985	779			
		black dendritic mineral on fractures -		32.7	33.9	1.2	6.8	4732	106	575	2476			
		pyrolusite?; moderate to strong variable		33.9	34.9	1.0	6.4	(2.26)	<2	645	5059			
		pervasive orange to red-orange oxide		34.9	36.0	1.1	33.7	4269	230	1070	3535			
		alteration-staining;		36.0	37.0	1.0	11.0	1672	100	475	978			

Toklat Resources Inc.

Drill Hole No. R95-MB | Page 4 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Zn			
		MINERALIZATION											
		tr - 1% malachite azurite, azurcalcite in											
	⊕	positive f-case disseminations, local replacement											
		Mineralization is spotting, on fractures, 4mm vein of											
		indicates azurcalcite @ 88 to ca @ 19.5m, mineraliz-											
		ation occurs in variable concentrations											
		over interval, 26.8 - 28.0 5% mal/azurite #											
		28.0 - 29.9 QUARTZ VEIN - QUARTZ BRECCIA											
		mixture of white bull quartz with											
		weak pervasive oxide stain and											
		angular fragments of white to clear											
		quartz in a moderately oxidized,											
		weakly calcareous fine grained											
		argillaceous? matrix											
		30.6 - 31.2 RUBBLE - FAULT zone?											
		moderately to strongly oxidized fragments											
		of dolomite crush, contacts indistinct											
		32.7 - 32.9											
		white bull quartz vein, lower contact											
		sharp @ 48 to ca with malachite-azurite											
		spotting											
		32.9 - 37.0 STRONGLY OXIDIZED ZONE											
		pervasive orange yellow oxide alteration											
		of fine grained dolomite; interval is											

Toklat Resources Inc.

Drill Hole No. R995-M8 | Page 5 of 9

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		strongly fractured ≈ 30% fine to coarse									
		angular clasts mixed with clay, sand, rusty									
		zones test positive for zinc, copper. 1%									
		disseminated az. calcite, malachite, az. te vein									
		zone at 343 m 2cm width vein of azurite +									
		malachite at 50° tca;									
		35.5 m 15 cm width vein of rusty buff									
		quartz ± az. calcite on fractures; contact									
		@ 25° tca									
		35.6-37.0 RUBBLE-FAULT ZONE									
		Orange to grey sand mixed with fine to									
		coarse angular clasts of grey to orange									
		variably oxidized dolomite, clasts have									
		disseminated malachite, azurite;									
370	519	MINERALIZED BRECCIA / NODULAR DOLOMITE increase in silica content, subangular		37.0	38.0	1.0	6.8	933	54	480	1248
		clasts of grey dolomite breccia with		38.0	39.0	1.0	5.8	377	64	180	1027
		15% white to grey 0.2-1cm width		39.0	40.0	1.0	2.4	230	46	185	623
		quartz veins generally at low angle		40.0	41.0	1.0	2.4	327	36	205	4959
		tca (10-25°) interval is weakly silicified,		41.0	42.0	1.0	17.4	2765	144	610	1083
		weakly bleached, fine low angle fracturing		42.0	42.7	0.7	4.2	1363	16	170	(1.52)
		typically healed by rusty oxides, calcite;		42.7	43.3	0.6	23.6	(1.14)	78	1510	6131
		moderately fractured ± rusty to black		43.3	45.1	1.8	1.6	428	10	140	955
		oxides on fractures giving positive		45.1	46.6	1.5	0.6	372	<2	155	706
		Cu test, positive reaction to zinc zap		46.6	48.2	1.6	0.4	334	8	175	810
		to 52.9m									

Toklat Resources Inc.

Drill Hole No. R995-MB | Page 6 of 9

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		tr diss. azurite ± malachite ± auricalcite on fractures;		48.2	49.5	1.3	0.4	1,391	4	460	3318
		410-411.4 white weakly rusty ball quartz		49.5	50.9	1.4	0.4	339	<2	140	892
		vein ≈ 3% diss malachite, azurite; contacts		50.9	51.9	1.0	0.2	690	8	510	3764
		above; below are rubble zones → FAULT?									
		42.7-43.3 strong pervasive orange-brown									
		oxide alteration; 5% diss. malachite-									
		azurite also interval as repl. in breccia									
		matrix; breccia clasts;									
		48.3-49.5 strongly ox.dized. clay altered									
		dolomite, pervasive red-orange stain; single									
		large coral at 48.5m									
		49.7-49.8 FAULT									
		rusty grey sand mixed with clasts of									
		grey dolomite									
		51.6-51.9 FAULT									
		fine to medium strongly oxidized dolomite									
		sand; crush; contacts indistinct;									
519	878	NODULAR DOLOMITE		51.9	52.9	1.0	<.2	269	14	555	3815
		subrounded nodules - clasts of med.to		52.9	54.3	1.4	<.2	73	8	175	1099
		light grey fine grained dolomite in		54.3	55.8	1.5	<.2	40	12	110	502
		a dark grey argillaceous matrix; matrix		55.8	57.3	1.5	0.2	45	6	120	541
		locally carries fine brecciated debris;		57.3	58.8	1.5	<.2	111	10	125	616
		strongly fractured = orange oxide stain		58.8	60.4	1.6	0.4	105	20	165	909

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		on fractures; moderate to strong, variable,		60.4	61.9	1.5	0.4	155	26	200	1149			
		pervasive, orange-yellow to pink ox.de		61.9	63.4	1.5	1.2	86	10	120	910			
		altered on: 10% white dolspar as matrix		63.4	66.4	3.0	0.6	95	20	155	1384			
		replacement; rare low angle (10-45 to ca) 01-03		66.4	68.0	1.6	1.2	234	34	190	2124			
		cm white to clear qtz veining, argillaceous partings		68.0	69.5	1.5	0.6	118	28	140	1675			
		between nodules generally at high angle to ca		69.5	71.0	1.5	0.8	34	22	145	1195			
		suggesting near horizontal BEDDING, rare		71.0	72.5	1.5	0.4	8	60	130	1009			
		elongate vugs healed with quartz ± calcite;		72.5	74.0	1.5	0.6	8	110	195	1507			
				74.0	75.6	1.6	0.6	6	38	95	306			
		573-878 STRONGLY FRACTURED		75.6	77.1	1.5	0.2	6	72	100	387			
		MODERATE DOLOMITE - BUBBLE ZONE - FAULT?		77.1	78.6	1.5	<.2	3	44	85	337			
		med to coarse angular fragments		78.6	80.1	1.5	0.2	2	180	85	252			
		of rusty nodular dolomite; fractures		80.1	81.7	1.6	<.2	2	96	80	156			
		generally at low angle to ca with rusty		81.7	83.2	1.5	<.2	<1	44	70	104			
		brown to black ox.de stain; increase		83.2	84.7	1.5	<2	2	28	70	155			
		in dolspar content with 20-25%		84.7	87.8	3.1	0.6	7	26	10	238			
		white to pink spar in mm fracture												
		healing, as fossil repl as matrix in												
		local breccia features; local elongate												
		to round vugs healed ± spar, hematite,												
		ankerite?												
		664-714.8 FAULT fine to medium												
		fragments of rusty nodular dolomite												
		mixed w dolomite sand; contacts												

* 30 cm recovery

Toklat Resources Inc.

Drill Hole No. RS95-MB | Page 8 of 9

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		indistinct												
		84.7-87.8 RUBBLE ZONE - QUARTZ VEIN												
		fine to coarse dusts of rusty bull												
		quartz												
		EOH 878m / 283'												
		HOLE LOST DUE TO DRILLING PROBLEMS												
		SIMILAR TO CONDITIONS ENCOUNTERED IN												
		RS95-M7												
		ADDENDUM												
		71.5-84.7 SOLUTION BRECCIA												
		subrounded fine to coarse clasts of cryptocrystalline												
		dolomite in matrix of white sparry and fine												
		dolomite: 30% of clasts with ~15% matrix												
		replaced with sulphides. fractures are												
		also sulphide and typically have pyrrhotite												

Toklat Resources Inc.

Drill Hole No. RS95-M8 | Page 12 of 25

DRILL HOLE LOG

LOCATION: FUSSY SPRINGS - MIKE HILL 1475N/1015E

DRILL HOLE NO.: RSS-M

AZIMUTH: 130°	ELEVATION: 2300'	PROPERTY:	
INCLINATION: -85°	LENGTH: 154.3m	CLAIM NO:	
RECOVERY: 74 8 %	CORE SIZE: NQ	SECTION:	
STARTED: 19/08/95		LOGGED BY: CCD	
COMPLETED:		DATED LOGGED:	
PURPOSE:		DRILLING CO.: FALCON	
		ASSAYED BY: ECO TECH	

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0'	20'	OVERBURDEN		0	5'	5'	0.4	241	184	35	11626
		0-5'		5'	10'	5'	<.2	205	20	55	398
		red orange sand-clay mixed with quartz		10'	15'	5'	<.2	206	42	45	688
		chips fragments of grey dolomite		15'	20'	5'	<2	25	4	45	134
		5'-15'									
		grey-brown to weakly rusty sand mixed w/									
		fragments-chunks of grey dolomite									
		15'-20'									
		large angular fragments of dolomite as									
		below.									

Toklat Resources Inc.

RECOVERY/ SAMPLE ON BACK

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
6.1	7.6	Dolomite		6.1	7.6	1.5	<.2	29	2	50	408
		- ch- re- fine grained dolomite									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
7.6	15.3	Black Shale		7.6	9.6	2.0	0.4	63	36	<5	424
		- well - - - - - - - - - -		9.6	11.5	1.9	<.2	53	62	<5	165
		- - - - - - - - - - - -		11.5	13.4	1.9	0.6	55	58	<5	276
		- - - - - - - - - - - -		13.4	15.3	1.9	0.4	118	78	<5	1301
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									
		- - - - - - - - - - - -									

Toklat Resources Inc.

Drill Hole No. R95-M9 | Page 2 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
15.3	26.8	Quartz Vein		15.3	16.2	0.9	<.2	31	1418	<5	150
		- broken Bull Quartz vein									
		- upper and lower contacts sharp									
		- 4.0m core loss from 20.7-26.3									
		- fractures oxidized, minor local perva-									
		-sive alteration									
		16.2 20.5 Mixed Qtz / Dolomite		16.2	17.6	1.4	0.8	93	424	5	426
		- 1/2 Qtz - 1/2 fine grained Dolomite		17.6	20.5	2.9	<.2	135	10	40	1550
		- well veined with calcite -		20.5	23.8	3.3	<.2	12	64	10	88
		very strong siliceous alteration		23.8	26.8	3.0	0.2	111	150	<5	741
		- minor 2.5 m core loss									
26.8	29.0	Gossan		26.8	29.8	3.0	<.2	328	10	30	4270
		- extremely strong silica altered		29.8	31.0	1.2	1.4	1631	30	55	2358
		limonite breccia		31.0	32.0	1.0	0.4	19	<2	45	1548
		- core recovery from 26.8-31.0		32.0	33.1	1.1	<.2	558	<2	30	2575
		2.6 m core lost from 26.0-29.0		33.1	34.0	0.9	<.2	150	<2	60	1973
		- variable Zn mineralization throughout		34.0	36.0	2.0	<2	935	78	385	3670
		interval most notably @ 36.0		36.0	39.0	3.0	<.2	937	<2	75	3755

Toklat Resources Inc.

Drill Hole No. M9 | Page 3 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
39.0	1399	Dolomite		39.6	40.6	1.0	0.2	25	<2	55	1056
		[illegible] dolomite [illegible]		[illegible]	[illegible]	1.5	<2	4	<2	60	994
		[illegible]		[illegible]	45.1	2.8	<2	4	<2	65	759
		[illegible]		45.1	46.1	1.0	<2	6	<2	60	603
		[illegible]									
		[illegible]									
		[illegible]									
		[illegible]									
		[illegible]									
		46.0-50.0 Fault Zone 2.7m [illegible]		46.1	48.0	1.9	<2	213	14	45	2037
		- [illegible]		[illegible]	50.0	2.0	<2	22	<2	55	685
		- weak [illegible]		50.0	51.2	1.2	<2	8	<2	60	1297
		[illegible]		51.2	54.3	3.1	<2	151	8	55	2759
		51.2 - 54.3 well broken rubble zone		54.3	56.3	2.0	0.2	354	12	55	955
		- fault [illegible] (10cm) @ 54.1		56.3	57.3	1.0	<2	182	8	60	527
				57.3	58.3	1.0	<2	5847	42	35	5110
		57.3 - 59.1 Variably Mineralized Zone		58.3	59.1	0.8	<2	1266	12	55	1239
		clay gouge, rubble zone 60cm [illegible]									
		- well oxidized from 58.3 - 58.8									
		- strong zinc reaction from 57.3 - 58.3									
		in light grey-blue gouge zone									

Toklat Resources Inc.

Drill Hole No. M9 | Page 4 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Au	Cu	Pb	Sb	Zn
		61 5 - 619 shattered black shale		59.1	61 9	2.8	<.2	93	<2	60	245
		interlayer		61 9	64.4	2.5	<2	50	<2	55	981
		64.4 - 64.9 ordered fault zone		64 4	64.9	0.5	<2	210	4	55	1342
		66.9 - 69.8 moderate stringer recrystd		66 0	66.5	1.9	<.2	188	<2	55	1756
		broken - local silicification zone with Va		66 8	67.5	0.7	<2	76	<2	55	1756
		& Zn tenor		67 5	69 5	2 0	<.2	71	<2	60	1603
		70 5 - 75.6 gouge clay zone Fault ??)		69 5	69 8	0.3	0.2	257	10	55	1122
		- strong reaction to Zn tenor		69.8	70 5	0.7	0.4	373	6	65	1001
		from 70 5 - 71 3 in mostly		70.5	71.3	0.8	0.4	4151	<2	45	16346
		unordered dark grey clay		71 3	72 5	1.2	1.0	572	30	70	1196
		well ordered from 71 4 - 75.6		72 5	72 4	0.9	2.4	1071	136	70	3763
		silicified rock zone from 72 - 75		72 4	72 6	2.2	<.2	598	32	60	1728
				75 6	77.0	1.4	0.6	252	6	75	1332
		77.3 — 1399		77 0	80.1	3.1	0.4	480	34	60	1863
		Completely broken - variable zones		80.1	81 7	1.6	<.2	1994	80	40	8815
		of rubble cataclasite clay zones		81 7	84 -	2.3	0.6	83	18	65	542
		- alternating intervals of core		84 7	87 8	3.	0.4	280	26	50	1947
		and drill		87 8	89 8	2 0	1.2	154	28	55	1832
		Texture? Rock Type? Variable		89	92 9	3 1	1.2	252	30	65	1579
		with fresh		92 9	96.9	4 0	1.8	138	26	60	967
		- laminations - partings in relatively dolomite		96 9	100 0	3.1	1.0	115	32	60	695
		locally strongly hematite - calcitic & pyritic.									
		- variable white spar replacement of fossil debris.									
		white spar veining with up to 25% spar over									
		3m intervals									

Toklat Resources Inc.

Drill Hole No. M9 | Page 5 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Au	Cu	Pb	Sb	Zn
		77.4 15 cm width white quartz vein @ 30°/ca									
		77.5-79.0 grey to rusty dolomite sand									
		87.4-93.9 grey to rusty dolomite sand mixed with fragments - cluster of rusty		100.0	101.2	1.2	1.4	396	68	55	2344
		medium dolomite		101.2	102.7	1.5	0.8	1254	34	80	2245
		99.9-102.7 as above		102.7	106.0	3.3	4.2	1263	264	25	5651
		102.7-109.1 strongly rusty clay sand mixed		106.0	106.7	0.7	0.6	452	34	45	1342
		with 30% angular quartz chips;		106.7	107.5	0.8	0.2	1241	28	25	4407
		holes cuts quartz zone @ 10°ca		107.5	108.6	1.1	<.2	2431	142	35	4704
		from 106.1-106.4 m; moderate to		108.6	109.1	0.5	1.0	1120	84	60	1827
		strong fine reaction to zinc		109.1	110.6	1.5	1.6	526	46	60	1023
		zap from 106.7-108.6m, 27m		110.6	112.2	1.6	1.8	320	44	60	781
		core loss from 103.0-106.0 m		112.2	113.7	1.5	1.2	220	18	55	554
		109.1-112.4 as from 93.4-93.9		113.7	115.5	1.8	0.8	484	118	80	2332
		115.5-117.0 deep orange strongly oxidized		115.5	118.3	2.8	1.0	59	4	65	273
		clay sand, goethite on fractures-		118.3	119.8	1.5	2.0	314	56	50	1134
		veins?		119.8	121.0	1.2	1.0	176	50	70	923
		130.5-139.9 weakly to strongly oxidized		121.0	122.3	1.3	1.2	328	70	60	1051
		and clay rusty medium dolomite		122.3	122.8	0.5	0.4	31	<2	60	154
		fragments, colour ranges from		122.8	124.4	1.6	0.4	17	<2	65	116
		orange-rust-grey, dolomite frag-		124.4	126.4	2.0	0.4	79	14	60	491
		ments are strongly bleached;		126.4	127.5	1.1	0.2	21	8	60	561
		2% white qtz fragments.		127.5	130.5	3.0	0.6	97	60	65	1415

Toklat Resources Inc.

Drill Hole No. R595-M9 | Page 6 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
1399	1457	BRECCIA		130.5	132.0	1.5	<.2	65	62	75	1169
		fine to coarse angular to subrounded clasts		132.0	133.5	1.5	<.2	36	30	80	489
		of strongly bleached dolomite in a matrix of		133.5	134.8	1.3	0.2	72	82	65	1292
		white crystalline calcite breccia is a		134.8	136.6	1.8	0.4	21	12	65	296
		combination of both solution breccia		136.6	138.2	1.6	0.2	108	32	75	924
		approx 5% of clasts have ankeritic		138.2	139.9	1.7	0.4	46	10	65	1065
		rims and ankeritic staining 1-2%									
		hematite rind of clasts, weak oxide stain		139.9	142.6	2.7	0.6	21	10	60	619
		on fractures;		142.6	143.8	1.2	0.4	2	<2	60	152
		143.8 - 144.3 RUBBLE - FAULT		143.8	144.3	0.5	0.2	10	8	60	305
		clasts & fragments of dolomite breccia		144.3	145.7	1.4	0.6	8	8	60	213
		mixed with dolomite sand. Contacts									
		indistinct 70-90 tca;									
		145.5 - 145.7 SAND									
		clean fine grained weakly rusty									
		dolomite sand; irregular contacts									
		suggest open space deposition									
1457	1503	LIMESTONE		145.7	147.2	1.5	0.4	4	<2	60	181
		dark to medium grey limestone;		147.2	148.6	1.4	0.6	6	<2	60	321
		10% bioclastic debris - crinoid ossicles		148.6	149.6	1.0	0.2	3	<2	65	73
		moderately developed argillaceous lamin-		149.6	150.3	0.7	0.2	14	2	65	294
		ations; bedding 80-90 tca → BEDDING									

Toklat Resources Inc.

Drill Hole No. RS05-MQ | Page 7 of 8

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		weak ox dc stain on fractures, weak									
		increase ox dc stain from 1481-									
		1487 m									
		MF 1 1553 SOLUTION BRECCIA									
		clasts in a matrix of white calspar:									
1503	1548	RUBBLE ZONE		150.3	151.8	1.5	0.4	51	6	65	1015
		fine to coarse angular clasts of limestone		151.8	153.3	1.5	0.2	123	16	90	1294
		dolomitic limestone mixed with rusty		153.3	154.8	1.5	<2	157	36	110	2062
		fragments of carbonaceous and clay									
		EOH 1543m, 503'									

Toklat Resources Inc.

Drill Hole No. 595-MJ | Page 8 of 8

DRILL HOLE LOG

LOCATION: Mike 4.11 1+00N / 0+08E
DRILL HOLE NO.: RS95 M
AZIMUTH: 130° ELEVATION: 2380'
INCLINATION: - 65° LENGTH: 87.8 m / 288'
RECOVERY: 92.6% CORE SIZE: NQ
STARTED: Aug 24 / 95
COMPLETED: Aug 25 / 95
PURPOSE: TEST BELOW RS95-M2

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

PROPERTY: Kusti
CLAIM NO:
SECTION: 1+00N
LOGGED BY: CCD, SPK
DATED LOGGED:
DRILLING CO.: Falcon
ASSAYED BY: Eco Tech

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0'	10'	OVERBURDEN		0	5'	5'	<.2	12	26	65	298
		clean fragments, dusts of dolomitic limestone		5'	10'	5'	<.2	11	20	65	276
		as below									
30	36.4	DOLOMITIC LIMESTONE - LIMESTONE		3.0	4.2	1.2	<.2	10	8	65	251
		med. to light grey fine to medium recrystallized		4.2	5.5	1.3	<.2	9	10	65	212
		weakly to moderately dolomitized limestone,		5.5	7.0	1.5	<.2	12	18	60	212
		10% fine bioclastic debris including fragments		7.0	8.5	1.5	<.2	10	12	60	335
		of coral, crinoid ossicles, 15% white to grey		8.5	10.0	1.5	<.2	4	8	65	283
		calspar as result of bioclastic debris, in 1-3mm		10.0	11.6	1.6	<.2	6	10	60	238
		width fractures - anastomosing veins, 3-5%		11.6	12.8	1.2	0.6	35	62	70	527
		white calspar; interval is moderately fractured		12.8	14.2	1.4	0.2	29	60	65	429
		with moderate to weakly developed rust oxides		14.2	15.2	1.0	<.2	22	30	60	552
		on fractures; 3% white to clear quartz in		15.2	16.2	1.0	0.2	70	30	70	921

Toklat Resources Inc.

RECOVERY / SAMPLE ON BACK

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		lava sample 2-25cm with veins (0-10%ca)		16.2	17.5	1.3	0.4	29	38	70	746
		and on fractures.		17.5	18.5	1.0	<.2	15	48	70	493
		12.2-22.6 STRONGLY FRACTURED ZONE		18.5	19.5	1.0	<.2	41	40	60	615
		medium to course angular clasts of		19.5	20.7	1.2	<.2	13	54	65	201
		dolomitic limestone fractures have		20.7	22.2	1.5	1.4	42	406	65	522
		moderate rust oxide developed ranging		22.2	23.8	1.6	1.4	87	78	65	1444
		from pale yellow (ankerite) to		23.8	25.3	1.5	<.2	16	16	70	1766
		red-orange (calcite stained) from		25.3	26.8	1.5	1.8	32	18	85	1072
		zinc * 14.2-17.5 oxide fractures have moder-		26.8	28.3	1.5	<.2	7	<2	65	192
		ate to strong positive reaction to		28.3	29.9	1.6	0.4	14	16	65	352
		zinc zap		29.9	30.9	1.0	<.2	8	4	65	387
		22.6-30.0		30.9	31.9	1.0	10	51	28	60	1589
		moderate to strong fractured dolomitic		31.9	32.9	1.0	2.0	65	6	75	1085
		limestone as above fractures became		32.9	34.4	1.5	2.2	58	10	75	1252
		more strongly oxidized with brown		34.4	36.0	1.6	<.2	17	14	65	227
		red to blood red hematite common,		36.0	37.5	1.5	<.2	11	24	65	189
		local weak reaction to zinc zap		37.5	39.0	1.5	<.2	2	4	60	400
		from 23.8-24.1m, 25.6 25.8m		39.0	40.5	1.5	<.2	<1	10	60	141
		30.9-32.0 FAULT angular clasts									
		of dolomitic limestone mixed with									
		sand - dolomite limestone crush-									
		well consolidated sand from 30.9-									
		31.3 has positive reaction to zinc									
		zap, fault contacts indistinct									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		but fractures indicate low angle									
		(10-25°C) structure.									
		364 the mother of all fan corals									
634	818	BLEACHED DOLOMITE		634	650	1.6	<.2	21	<2	70	179
		light to medium grey fine grained mineral		650	665	1.5	0.4	60	14	75	395
		dolomite mixture and nodular dolomite		665	675	1.0	<.2	16	<2	75	322
		dolomite mixture has 15% brachiopod		675	685	1.0	<.2	20	8	70	309
		fragments - corals, crinoids, 10%		685	695	1.0	1.0	32	6	70	606
		white lamella dolspar as replacement of		695	705	1.0	0.2	18	4	70	362
		brachiopod debris as matrix in local solution		705	715	1.0	<.2	13	4	70	324
		breccia features, in 0.1-0.3 cm width		715	726	1.1	<2	190	14	70	1462
		cross-cutting veins, as vug healing (		726	736	1.0	0.4	58	18	70	476
		saddle dolomite); matrix dolomite		736	746	1.0	2.0	252	24	80	1219
		has argillaceous partings - laminations		746	756	1.0	1.6	671	28	85	1705
		thickness locally variable with		756	766	1.0	0.4	88	41	65	584
		calcite intercept is moderately to		766	776	1.0	<.2	20	4	65	4150
		strongly fractured with crumbly		776	787	1.1	<.2	4	24	65	217
		yellow brown fractures. local vugs-		787	802	1.5	<.2	51	10	65	404
		fractures have nice prismatic quartz		802	825	2.3	<.2	346	42	55	1043
		crystals often overgrown on saddle		825	833	0.8	<.2	34	<2	55	98
		dolomite.		833	848	1.5	0.2	47	<2	60	242
				848	863	1.5	<.2	9	<2	65	64
				863	878	1.5	0.4	20	<2	60	145

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		667-671 FAULT					
		strongly fractured clusts of rust, dk spar					
		solution breccia mixed w fine crush					
		contacts indistinct;					
		715-825 MINERALIZED ZONE					
		mixed nod bar dolomite - dolomitic limestone					
		with variable positive reaction to zinc					
		zap on thin smithsonite veneer on fractures					
		715 775 auricalcite band strongly					
		clay altered; strong positive reaction					
		to zinc zap, positive reaction to					
		copper test; barren quartz fragments;					
		731 BEDDING laminations @ 85° tca					
		736-741 FAULT					
		rusty dolomite crush, positive reaction					
		to zinc zap, contacts indistinct					
		751 755 FAULT					
		rusty to grey dolomite crush, strong					
		positive reaction to zinc zap;					
		762 764 QUARTZ VEIN - ALTERATION					
		1 cm width quartz vein @ 15° tca;					
		margins are strongly clay altered with					
		smithsonite and rusty clay;					

Toklat Resources Inc.

Drill Hole No. RG95-M10 | Page 4 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		77.1-77.8 nodular dolomite with weak reaction to zinc zap;					
		81.6-82.5 FAULT					
		mixed deep orange rusty dolomite gouge grading into grey clay; strong positive reaction to zinc zap; 05 cm core loss over interval;					
		83.4 BEDDING strong laminations 85° TCA;					
		EOH 87.3m / 288'					

Toklat Resources Inc.

Drill Hole No. RS95-M10 | Page 5 of 5

DRILL HOLE LOG

LOCATION: Mike Hill	1400N/0408E	DRILL HOLE NO.: RS95 M11	
AZIMUTH: 130	ELEVATION: 2380'	PROPERTY: Rusty Springs	
INCLINATION: -85°	LENGTH: 972m/3191'	CLAIM NO:	
RECOVERY: 94.9%	CORE SIZE: NQ	SECTION: 1400N	
STARTED: Aug 25		LOGGED BY: CCD/SPK	
COMPLETED:		DATED LOGGED:	
PURPOSE: TEST BENEATH RS95-M2		DRILLING CO.: Falcon	
		ASSAYED BY: EcoTech	

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE m FROM	METREAGE m TO	LENGTH m	ANALYSES ppm(%) Au	Cu	Pb	Sb	Zn
0'	10'	OVERBURDEN, CASING		0	2'	2'	-.2	110	88	55	877
		angular clasts of grey dolomite as below,		2'	3'	1'	<.2	24	42	65	729
				3'	4'	1'	<.2	25	44	60	448
3.0	9972	MIXED DOLOMITIC LIMESTONE - MODERATE		4'	5'	1'	<.2	5	20	65	251
		DOLOMITE		5'	6'	1'	<2	19	38	65	445
		med to light grey, moderately to strongly		6'	7'	1'	<.2	17	24	60	296
		bleached dolomite & limestone and		7'	8'	1'	<2	5	8	105	206
		weakly, moderate dolomite; scattered bio-		8'	9'	1'	<.2	6	2	60	202
		clastic debris throughout, medium dolomite		9'	10'	1'	<.2	4	16	60	240
		has corr. blebs, veinlets - lamellations, rare		13.6m	14.9	1.3m	<.2	16	28	60	512
		stylolites; moderately fractured to weakly		14.9	16.5	1.6	<.2	5	48	65	191
		developed rusty orange-brown oxides on fractures.		16.5	18.5	2.0	<.2	6	44	65	321
		15% white dolospar as replacement of bioclastic		18.5	19.5	1.0	<.2	4	44	65	205
		debris, in mm anastomosing veinsi fractures as		19.5	20.5	1.0	<.2	10	58	70	239

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		healing in vugs (typically saddle dolomite ± bitumen; 3-4% quartz in lai		20.5	21.5	1.0	<.2	23	80	70	381
		angle (5-25 tca) 01-05 cm veins, in		21.5	24.1	2.6	<.2	38	92	65	674
		prisms on fractures - in vugs;		24.1	25.1	1.0	<.2	4	104	65	748
		57 RUBBLE		25.1	26	1.0	<.2	5	184	60	905
		10 cm of subangular quartz pebbles		26	27.1	1.0	<.2	34	600	60	2510
		88-89 QUARTZ		27	28.1	1.0	<.2	24	298	55	2117
		vuggy bull quartz		28.1	29.1	1.0	<.2	56	2922	70	4672
				29.1	30.2	1.1	<.2	45	748	<5	5205
		136-337		30.2	31	1.0	<.2	8	234	5	857
		strongly fractured dolomitic mudstone-matrix		31	32	1.0	<.2	23	480	65	1829
		dolomite increase in oxides on fractures;		32	33	1.0	<.2	20	862	60	2600
		overall clean with local sand-gauge-fractures		33	33.7	0.5	3.4	6	768	70	1012
		generally at low angle tca (0-25)		33.7	34.7	1	10	14	238	65	1166
		167-337 weak to moderate fracturing		35.3	36.3	1.0	0.6	20	192	70	1120
		zinc zap on fractures indicates presence		36.3	37.3	1.0	<.2	14	64	65	430
		of sphalerite		37.3	38.3	1	0.2	57	52	70	672
		261-337 STRONGLY FRACTURED/CRUSH		38.3	39.3	1	2.0	538	58	95	9551
		mixed fine to coarse fragments of		39.3	40.8	1.5	2.4	85	50	70	472
		rusty dolomitic dolomite sand clay,		40.8	42.4	1.6	0.8	78	10	65	388
		appears to be a strongly altered-sheared?		42.4	43.9	1.5	1.0	47	4	65	374
		remnant of a vein system 25 tca;		43.9	45.4	1.5	1.0	45	20	70	469
		Very strong reaction to zinc zap from		45.4	46.9	1.5	<.2	41	2	25	631
		271 to 272: rubble becomes unaltered									

Toklat Resources Inc.

Drill Hole No. R95-M11 | Page 2 of 3

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Au	Cu	Pb	Zn				
		clean dd sample gravel @ 32.7												
		33.7 - 97.2												
		variable weak recrystallization zone on												
		or closed fractures (sample) and also on												
		white dd spar veins replacement textures and/or												
		breccia												
		47.9 - 49.1 - with vein = bands of												
		crystals,												
		51.4 - 51.6 FAULT, BUBBLES, QUARTZ VEIN												
		fine to course dd sample fragments -												
		dd sample crush zone with 2 cm												
		width low angle (15 to ca) quartz												
		vein												
		66.1 - 77.3 BRECCIA		66.6	66.9	5	0.6	58	46	80	231			
		strong recrystallized clasts of		66.9	67.4	1.5	1.0	102	36	100	499			
		grey dd sample in a matrix of		67.4	68.9	1.5	2.2	169	58	105	524			
		white to blue grey dd spar - epidote		68.9	70.4	1.5	0.4	30	14	70	176			
		appears to be combined as last		70.6	72.1	1.5	0.2	11	2	60	122			
		fracture - solution		72.1	73.6	1.5	0.2	15	6	60	141			
		replacement - spar is multi generat-		73.6	75.1	1.5	0.2	3	12	60	124			
		ational and has weak to mod-												
		erate reaction to zinc zap.												

Toklat Resources Inc.

Drill Hole No. RS05-MH1 Page 3 of 3

DRILL HOLE LOG

LOCATION: RUSTY SPRINGS 0+00/0+25W			DRILL HOLE NO.: RS95-M12
AZIMUTH: 130°	ELEVATION: 2400'		PROPERTY:
INCLINATION: -45°	LENGTH: 247'/75.3m	SURVEYS	CLAIM NO:
RECOVERY: 98%	CORE SIZE: NQ	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: 0+00/0+25W
STARTED: AUG 26/95			LOGGED BY: CCD/SPK
COMPLETED: AUG. 27/95			DATED LOGGED:
PURPOSE:			DRILLING CO.: FALCON
			ASSAYED BY: ECO TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (Au oz) Ag	Cu	Pb	Sb	Zn
00	10'	OVERBURDEN CASING		00'	20'	10'	4.4	79	3804	65	2575
		0-7' fragments, clasts of grey bleached dolomite		2.0'	3.0'	1.0'	2.8	67	1800	65	1538
		Mixed with org. clay		3.0'	4.0'	10'	0.4	17	174	70	1010
		7-10' clean fragments of grey bleached dolomite,		4.0'	5.0'	10'	0.6	36	436	65	850
				5.0'	6.0'	10'	3.6	27	2094	75	626
30	75.3m	BLEACHED DOLOMITE		6.0'	7.0'	10'	2.4	18	1512	70	558
		light to medium blue-grey, dense starting to		7.0'	8.0'	10'	0.6	17	204	65	304
		moderately bleached, nodular dolomite-clast		8.0'	10.0'	20'	1.0	37	174	80	426
		supported debris - fan corals, crinoid fragments,									
		rare brach fragments. blue grey colour		3.0	4.1	1.1	1.4	50	470	80	377
		may indicate presence of marcasite, 5% white		4.1	5.2	1.1	1.2	48	50	85	288
		dolospar as matrix in last sed. breccia		5.2	6.2	1.0	0.2	17	40	70	734
		fractures, in 0.1-2.0cm width veins with no		6.2	7.2	1.0	0.4	9	272	70	268
		preferred orientation, many fractures as		7.2	8.2	1.0	0.6	9	278	65	212

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		veinlet mineralization, as replacement stringers		8.2	9.2	1.0	1.2	35	92	70	170			
		fractured vein zone; 2% quartz in 0.2		9.2	10.2	1.0	2.2	41	1130	90	1369			
		0.5 cm width veinlet 20-40/cc in vugs		10.2	11.3	1.1	0.8	48	90	80	576			
		disseminated xtals, in rare open space		11.3	12.3	1.0	0.6	18	72	70	195			
		replacement textures, moderately fractured		12.3	13.3	1.0	0.4	53	56	70	178			
		with moderate to weakly developed zones		13.3	14.3	1.0	<.2	17	36	70	116			
		of fractures, oxide colour veins from		14.3	15.3	1.0	<.2	17	20	65	100			
		deep red Chocolate to Hematite		15.3	16.3	1.0	1.4	43	84	80	166			
		(sphalerite indicated by Zinc reactants		16.3	17.4	1.1	<.2	48	96	75	7168			
		Zinc Zap)		17.4	18.4	1.0	0.6	28	112	70	242			
		MINERALIZATION		18.4	19.4	1.0	0.4	29	94	65	256			
		sm thin veinlets or fracture controlled films, quartz		19.4	20.4	1.0	1.8	128	484	100	890			
		veins carry metallic minerals, blue/black,		20.4	21.4	1.0	0.4	31	110	70	184			
		as chalcite, calcite veins carry chalcite		21.4	22.4	1.0	1.0	78	226	95	1134			
		also in thin 1 or 2 cm mineralized		22.4	23.5	1.1	<.2	34	66	70	218			
		at 47m 91m 333m		23.5	24.5	1.0	0.6	42	376	75	4343			
		galena occurs replacement in 5 cm		24.5	25.5	1.0	<.2	72	34	65	2846			
		width quartz vein 20/cc to 78m;		25.5	26.5	1.0	0.4	16	30	70	114			
		chalcite noted at 41m 62m 81m 166-		26.5	27.5	1.0	0.2	10	36	65	81			
		167m 219m with tetrahedrite in 30/cc		27.5	28.5	1.0	<.2	12	14	65	97			
		quartz vein, 244m,		28.5	29.6	1.4	<.2	23	58	70	1496			
		346-480 BRECCIA		29.6	31.1	1.5	0.4	24	106	70	167			
		subangular to subrounded clasts		31.1	32.6	1.5	0.2	18	32	60	145			
		of bleached dolomite in a matrix of		32.6	33.6	1.0	1.2	84	92	90	170			

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
				33.6	34.6	1.0	0.2	58	60	75	205			
				34.6	35.7	1.1	0.4	183	14	100	567			
				35.7	36.7	1.0	25.8	1068	166	375	273			
				36.7	37.7	1.0	<.2	6	<2	60	79			
				37.7	38.7	1.0	<.2	9	<2	65	66			
				38.7	40.2	1.5	<.2	21	2	70	292			
				40.2	41.8	1.6	<.2	18	6	70	373			
				41.8	43.3	1.5	0.4	14	12	65	156			
				43.3	44.3	1.0	<.2	23	10	75	295			
				44.3	46.3	2.0	<.2	39	6	75	273			
				46.3	47.9	1.6	<.2	35	14	80	410			
				47.9	49.4	1.5	<.2	4	<2	60	93			
				49.4	50.9	1.5	<.2	3	<2	60	83			
				50.9	52.4	1.5	<.2	3	<2	65	81			
				52.4	53.9	1.5	<.2	13	14	65	387			
				53.9	55.4	1.5	<.2	14	10	70	258			
				55.4	57.0	1.6	<.2	15	14	70	264			
				57.0	58.5	1.5	<.2	13	2	70	268			
				58.5	59.5	1.0	<.2	154	26	155	779			
				59.5	61.0	1.5	14.0	1416	88	390	5833			
				61.0	62.5	1.5	0.6	47	22	95	572			
				62.5	63.5	1.0	1.6	77	12	100	438			
				63.5	64.5	1.0	0.4	40	38	95	407			
		EOH TD 3mm		64.5	65.5	1.0	0.6	185	52	135	9564			

INTERVAL FROM	INTERVAL TO	DESCRIPTION	SAMPLE NO.	INTERVAL FROM	INTERVAL TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
				65.5	67.0	1.5	1.0	44	10	85	265
				67.0	68.5	1.5	1.2	165	44	125	557
				68.5	70.0	1.5	5.8	608	52	385	(208)
				70.0	71.5	1.5	3.4	406	64	250	2707
				71.5	73.0	1.5	2.0	100	14	105	461
				73.0	74.5	1.5	<1.2	25	4	75	186
				74.5	75.3	0.8	7.6	6025	162	235	843

KEEWATIN ENGINEERING INC.

DRILL HOLE LOG

LOCATION: MIKE HILL 0400/1425W			DRILL HOLE NO.: RSS5-M13
AZIMUTH: 130°	ELEVATION: 2400'		PROPERTY:
INCLINATION: -45°	LENGTH: 110m / 361'	SURVEYS	CLAIM NO:
RECOVERY: 86.8%	CORE SIZE: NQ	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: 0400
STARTED:			LOGGED BY: CCD
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.: FALCON
			ASSAYED BY: ECO-TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH (m)	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0.0	100'	CASING		0'	5'	5'	58	158	2456	150	845
		[illegible]		5'	10'	5'	1.8	74	1052	95	2105
		[illegible]									
		[illegible]									
		[illegible]									
		[illegible]									
		[illegible]									
		3'-10' GREY DOLOMITE									
		as below									
30	98.3	BLEACHED GREY DOLOMITE		3.0	5.7	2.7	9.8	1417	370	205	(2.58)
		[illegible]		5.7	7.1	1.4	6.2	199	218	115	3134
		[illegible]		7.1	8.5	1.4	4.4	41	172	80	2844
		[illegible]		8.5	10.0	1.5	2.2	21	114	75	238
		[illegible]		10.0	11.6	1.6	<2	7	60	75	165

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		brown clayey calcareous fault gouge		11.6	13.1	1.5	<.2	5	54	75	128
		[illegible]		13.1	14.6	1.5	<.2	5	56	75	154
		dolomite and buff weathering limestone		14.6	16.1	1.5	<.2	8	62	80	126
		of mixed limestone dolomite and breccia		16.1	17.7	1.6	<.2	11	80	75	206
		[illegible]		17.7	19.2	1.5	<.2	12	106	75	211
		small fault with brecciated dolomite		19.2	20.7	1.5	0.4	12	112	80	171
		calcite and clay filled fault zone		20.7	21.7	1.0	<.2	11	130	70	302
		to fine grained dolomite and fault replacement ore		21.7	22.7	1.0	<.2	9	94	80	265
		vein healing in local microbreccia fracture		22.7	23.8	1.1	<.2	18	158	70	335
		mixed calcium carbonate and dolomite		23.8	24.2	0.4	0.2	10	242	80	228
		Calcareous 30-50 local 2% quartz in		24.2	25.2	1.0	0.2	5	192	75	243
		medium crystalline matrix		25.2	26.2	1.0	<.2	<1	98	75	237
				26.2	27.2	1.0	0.8	17	208	75	532
				27.2	28.2	1.0	0.8	27	812	80	1185
				28.2	29.9	1.7	<.2	22	648	75	4197
		MINERALIZATION		29.9	31.4	1.5	0.2	16	276	75	1663
		- variable weakly developed [illegible]		31.4	32.9	1.5	<.2	2	86	75	494
		replaces local dolomitization		32.9	34.4	1.5	<.2	5	62	80	566
		coarse dolomite replacing		34.4	36.0	1.6	<.2	18	36	75	985
		replacement [illegible]		36.0	37.5	1.5	<.2	27	74	75	682
				37.5	39.0	1.5	1.2	54	41	80	671
		30-50% RUBBLE, SILICIFIED FAULT		39.0	40.5	1.5	0.6	14	32	80	352
		and/or clasts of strongly bleached dolomite		40.5	42.1	1.6	0.4	8	28	85	613
		mixed with fine dolomite crush below		42.1	43.6	1.5	3.4	409	116	105	(2.06)

Toklat Resources Inc.

Drill Hole No. RS[illegible]-[illegible] | Page [illegible] of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		[illegible]		43.6	45.1	1.5	2.2	19	22	75	1190			
		[illegible]		45.1	46.6	1.5	0.6	49	24	75	3441			
		[illegible] bleached dolomite, rare		46.6	49.2	1.6	0.4	14	32	80	550			
		[illegible]		48.2	49.7	1.5	1.0	14	124	85	671			
				49.7	51.2	1.5	<.2	8	36	75	1128			
		[illegible]		51.2	54.2	3.0	<.2	8	6	85	264			
		[illegible]		54.2	54.8	0.6	0.8	32	110	80	1113			
		[illegible]		54.8	56.0	1.2	<.2	<1	36	85	144			
		[illegible]		56.0	57.3	1.3	<2	<1	10	75	148			
		[illegible]		57.3	58.8	1.5	<.2	6	40	85	616			
		[illegible]		58.8	60.4	1.6	<.2	3	36	90	227			
				60.4	61.9	1.5	0.4	15	36	90	290			
		[illegible]		61.9	63.4	1.5	0.4	19	14	90	309			
		[illegible]		63.4	64.9	1.5	0.6	35	56	95	293			
		[illegible]		64.9	66.4	1.5	5.0	147	252	110	2243			
		[illegible]		66.4	67.9	1.5	2.4	73	428	105	714			
		fractures have [illegible] and		67.9	69.5	1.6	12	75	122	125	219			
		[illegible]		69.5	71.0	1.5	0.6	34	46	105	148			
		dolomite [illegible] sand.		71.0	72.5	1.5	<.2	44	411	105	251			
		[illegible]												
		rubble												
		[illegible] bleached dolomite												
		with moderate [illegible]												
		[illegible]												

Toklat Resources Inc.

Drill Hole No. RSDS-M13 | Page 3 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		542-548 mixed grey to black to orange												
		coarse clasts												
		548-558 moderately to strongly bleached												
		dolomite with variable veinlets of												
		calcite - fractures have strong												
		bleaching with local weak reaction to												
		hydrochloric acid.												
		664 5cm width gravity vein with												
		coarse galena												
		858-883 Intense bleaching, pervasive												
		dark grey-red dolomite; increase in												
		calcite content as veins and local												
		dolomite breccia matrix; strong												
		fractures weakly mineralized, no reaction to												
		hydrochloric acid.												
883	110	DOLOMITE - DOLOMITIC LIMESTONE												
		fine grained, med grey blue dolomite -												
		dolomitic limestone more calcareous than												
		dolomite near bottom of hole - local weak												
		bleaching; 5% white calcspar along		106.1	107.6	1.5	<.2	<1	<2	80	31			
		vuggy veinlets as matrix in local		109.1	110.0	0.9	<.2	<1	2	85	43			

Toklat Resources Inc.

Drill Hole No. KS-13 | Page 4 of 5

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES							
		solution breccia BEDDING - local laminations												
		at SST/cg, fractures weak/moderately with												
		rare local positive reaction to HCl												
		EOH 110m 35°												

Toklat Resources Inc.

Drill Hole No. KSDS-1113 | Page 5 of 5

DRILL HOLE LOG

LOCATION: Mike Hill 0+00/1+25W			DRILL HOLE NO.: RS95-11
AZIMUTH: 130°	ELEVATION: 2400'		PROPERTY: Rusty Spires
INCLINATION: -70°	LENGTH: 130.5m	SURVEYS	CLAIM NO:
RECOVERY: 97.2%	CORE SIZE: NQ	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: 0+00
STARTED:			LOGGED BY: SPK
COMPLETED:			DATED LOGGED:
PURPOSE:			DRILLING CO.: Falcon
			ASSAYED BY: Eastech

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn			
0.0	10'	Overburden		0	5'	5'	0.2	23	106	50	185			
				5'	10'	5'	0.4	26	162	65	421			
30	30.5	Talcum -												
		- med dark grey massive, locally nodular												
		- relatively competent throughout, mi minor oxidized fractures at top of hole												
		- minor thin calcite veinlets												
		3.0 - 4.7 blended zone: no reaction to Talc-Top												

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		12.1-13.8 broken zone minor [illegible] oriented fractures												
		[illegible] slightly altered oriented zones.												
		25.6-28.1 brecciated with brittle healed veins												
		28.9-30.7 well broken and oriented zone rubble, minor clay from 30.2												
		31.5-33.7 vuggy bleached oriented fracture zone visible												
				34.4	35.9	1.5	0.4	13	86	65	427			
		36.0-36.5 hull quartz vein 2-3% sphal, Galena in vein rock from sharp broken contacts		35.9	36.5	0.6	1.8	16	496	60	138			
				36.5	37.5	1.0	0.8	14	30	65	186			
				37.5	39.0	1.5	<.2	7	20	65	322			
				39.0	40.5	1.5	<.2	2	8	60	409			
		37.5-45.0 solution breccia		40.5	42.0	1.5	<.2	1	12	60	230			
		- surrounded by [illegible] clasts		42.0	44.5	2.5	0.2	5	74	70	308			
				44.5	46.0	1.5	0.4	<1	42	65	130			
				46.0	47.5	1.5	0.4	11	114	65	307			

Toklat Resources Inc.

Drill Hole No. K595 M4 | Page 7 of 4

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		420 - 460 well bedded massive		475	490	1.5	0.2	3	42	70	120			
		Zone: cm scale/gouge		490	500	1.0	0.6	10	86	165	268			
				500	512	1.2	0.4	64	448	70	962			
		495 cm: Fault Zone		512	536	1.4	0.4	87	538	80	1139			
		cm scale/sharp/gouge		536	546	1.0	<.2	8	54	50	144			
		dark grey/black silicified sediment		546	573	2.6	4.4	27	1950	70	386			
		pink hydrothermal alteration		573	584	1.1	<.2	729	1514	145	3682			
		Zn-zone		584	600	1.6	0.6	100	172	80	704			
				600	612	1.2	0.8	186	142	85	1195			
		536 - 543 bull qtz vein,		612	634	2.2	06	55	44	70	402			
		lower contact @ 15° to CA		634	650	1.6	1.6	53	48	70	405			
		irregular, sulphides												
		543 - 573 bleached sediments												
		intercalated fine Zn-sup section												
		573 - 617 well mineralized fault												
		zone, sand + clay from 613 -												
		618 fault section to Zn zone												
		806 - 1916 dark grey - black interval												
		narrasitic(?) ; mid component												

Toklat Resources Inc.

Drill Hole No.	Page 3 of 4

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		101.3 101.5 fault bad												
				107.6	109.1	1.5	0.4	2	2	1.5	84			
107	130.5	Siliceous Islands		109.1	110.6	1.5	0.8	48	8	70	82			
		Light grey brown Islands		110.6	112.2	1.6	2.0	71	14	70	111			
		Light grey green altered		112.2	1137	1.5	<2	13	6	70	223			
		Silicified		1137	1152	1.5	0.4	4	40	100	423			
				1152	116.7	1.5	<.2	1	4	65	271			
130.5	EOH			116.7	118.3	1.6	<2	<1	<2	65	134			
				118.3	1198	1.5	0.4	6	6	60	376			
				119.8	121.3	1.5	<.2	<1	<2	60	152			
				121.3	122.8	1.5	0.4	2	<2	60	96			
				122.8	1244	1.6	0.4	4	<2	60	181			
				124.4	1259	1.5	0.6	4	<2	65	258			
				1259	127.4	1.5	0.4	3	<2	60	225			
				127.4	128.9	1.5	0.4	<1	<2	60	76			
				128.9	1305	1.6	0.2	<1	<2	65	59			

Toklat Resources Inc.

Drill Hole No. K595 M14	Page 4 of 4

DRILL HOLE LOG

LOCATION: RUSTY SPRINGS MIKE HILL 1475N/0450E			DRILL HOLE NO.: RSMS-M5
AZIMUTH: 310°	ELEVATION: 3m BELOW RSMS-M5		PROPERTY:
INCLINATION: -60°	LENGTH: 744m/244'	SURVEYS	CLAIM NO.
RECOVERY: 92.1%	CORE SIZE: NQ	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION: 1475N
STARTED: AUG 30/95			LOGGED BY: CCD
COMPLETED: AUG 31/95			DATED LOGGED:
PURPOSE: CCD-35E HOLE TO RSMS-M7			DRILLING CO.: FALCON
			ASSAYED BY: ECO TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
[illegible]	[illegible]	[illegible]		0	.9	0.9	27.4	2119	2524	385	(1.32)
				.9	1.2	0.3	142	1029	2138	270	6247
				1.2	1.8	0.6	112	1303	1358	190	5907
				1.8	2.1	0.3	3.6	492	1382	40	1502
61	95	RUBBLY CLAY ALTERATION / FAULT		2.1	2.4	0.3	4.4	1015	1424	115	3151
		strongly clay altered [illegible]		2.4	2.7	0.3	10.0	1219	2734	200	4116
		to sandy [illegible]		2.7	3.0	0.3	10.6	1321	2108	205	4185
		altered, moderate to strong [illegible]		3.0	3.3	0.3	248	2613	1918	165	4376
		sto moderate runs from dark brown to		3.3	6.0	2.7	23.2	2584	1888	155	4233
		red to pale yellow. 10% of interval is fault									
		grey dolomite sand-clay, moderate to strong		6.1	7.1	1.0	4.6	3318	646	325	(8.89)
		reaction to zinc 30%		7.1	8.1	1.0	5.4	1797	256	300	6169
		6370 FAULT		8.1	9.5	1.4	1.4	294	242	170	1252
		fine to medium chunks of dolomite									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		strongly altered dominantly carbonaceous												
		with strong relation to zinc												
		zone.												
95	458	STRONGLY BLEACHED SEDIMENTS		9.5	10.5	1.0	0.6	342	218	125	9222			
		fine to med grained light to med grey		10.5	11.5	1.0	0.8	260	192	90	3361			
		grey strongly bleached dominantly siliceous		11.5	11.7	0.2	1.8	427	280	160	(2.62)			
		to strongly iron oxide stained - yellow		11.7	12.7	1.0	0.6	156	78	90	1574			
		ranges from deep red (15.6-16.6m) to pale		12.7	13.7	1.0	0.6	188	70	85	521			
		red generally laminated 45-55°		13.7	14.7	1.0	7.2	654	120	200	1821			
		to laminations typically oxidized		14.7	15.7	1.0	0.8	214	104	100	1008			
		clots to strongly fractured zones in fine-		15.7	16.6	0.9	2.2	311	84	115	8567			
		clots to strongly altered laminated		16.6	17.6	1.0	6.8	1241	134	355	1518			
		brecciated intervals to 2cm.		17.6	18.5	0.9	0.2	85	8	80	421			
		fractures and indistinct laminations		18.5	19.5	1.0	4.8	459	158	165	1299			
		no trace of sulphosalts.		19.5	20.5	1.0	0.2	69	24	70	629			
				20.5	21.5	1.0	0.6	242	40	95	876			
		115-117 QUARTZ VEIN, FAULT		21.5	22.5	1.0	1.2	126	34	95	522			
		15 cm width, to be checked we-		22.5	23.5	1.0	7.4	29	34	75	203			
		e 55° to core, course crystalline		23.5	24.5	1.0	0.2	27	12	65	249			
		stibnite in veins and on fractures												
		lower contact is rusty sandy		25.4	25.5	0.1	2.2	20	6	70	161			
		siliceous zone over 5 cm.		25.5	26.5	1.0	0.8	97	8	100	266			

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		127-127 [illegible] grey coarse dolomitic clay		26.5	27.5	1.0	<.2	46	10	75	248
		altered dolomitic sand		27.5	28.5	1.0	<.2	11	6	65	179
		133-137 RUBBLE, FAULT		28.5	29.5	1.0	<.2	2	4	65	114
		[illegible] dolomitic clasts [illegible]		29.5	30.4	0.9	<.2	22	12	70	497
		clasts dolomitic sandy [illegible]		30.4	31.4	1.0	1.2	177	18	90	1940
		clast supported breccia (70-85% clasts)		31.4	32.4	1.0	<.2	8	12	65	933
		171-172 MINERALIZED VEIN		32.4	33.4	1.0	1.8	22	30	60	1912
		10 cm band of massive metallic		33.4	35.1	1.7	7.2	3235	100	3.15	3118
		cuprite-tetrahedrite-chrysocolla		35.1	35.7	0.6	1897.2	(7.59)	8928	(4.20)	(261)
		contact chrysocolla coated copper		35.7	36.8	1.1	215.6	(1.14)	1276	5390	(4.08)
		coated chrysocolla with [illegible]		36.8	38.1	1.3	4.2	263	24	195	548
		mineralized [illegible]		38.1	39.0	0.9	26.6	(2.31)	396	1610	2414
		[illegible] dolomite		39.0	40.0	1.0	2.0	5511	30	165	914
		[illegible]		40.0	40.5	0.5	3.0	6417	28	165	709
		abundant [illegible]		40.5	41.5	1.0	<.2	1617	104	130	1103
		139-141 RUBBLE [illegible]		41.5	42.5	1.0	0.2	3304	122	80	1373
		[illegible]		42.5	43.5	1.0	0.4	670	56	40	666
		[illegible]		43.5	44.2	0.7	<.2	1117	44	75	1407
		[illegible]		44.2	45.8	1.6	<.2	2388	<.2	<.5	4476
		[illegible]									
		[illegible]									
		[illegible]									

Toklat Resources Inc.

Drill Hole No. [illegible] Page 3 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES							
		206-208 white to grey clay and sand with intense vuggy texture												
		to 212 → sm chrysocolla hydro-zincite												
		304-309 325-330 Strong ferric red ox to stain												
		334-458 MINERALIZED ZONE RUBBLE												
		fine grained clasts of strongly altered												
		brecciated stained mixed with sand clay												
		[illegible] throughout												
		[illegible]												
		334-351 rusty to well cemented dolo-												
		[illegible]												
		[illegible]												
		[illegible]												
		[illegible]												
		351-357 60/0 malachite-az be- chrysocolla botryoidal to replacement clasts 25% each quartz - strongly bleached + stained.												
		357-360 Strongly altered bleached stained fractured brecciated												
		[illegible]												

Toklat Resources Inc.

Drill Hole No. RS95-M15 | Page 4 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES
		360-363 = DOUBLE					
		strong, pervasive chlorite-sericite					
		alteration of 25% malachite-rich					
		25% quartz, locally crackled to form					
		with overall average 80%					
		malachite-chrysocolla.					
		363-364 = strongly bleached-altered					
		dolomite, 15% white quartz replacement					
		364.1-402 = DOUBLE					
		fine to medium fragments of					
		strongly pervasively chlorite-sericite					
		altered dolomite with					
		patchy strong leached zones with					
		minor to moderate chrysocolla					
		filled fractures					
		402-415 = DOUBLE					
		similar to above with variable					
		pervasive chlorite alteration, increase					
		in clay content decrease in copper					
		content with veins and zones					
		barren					

Toklat Resources Inc.

Drill Hole No. KSS-11-15 | Page 5 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
45.3	79.9	BRECCIA		45.8	47.3	1.5	<.2	134	6	65	1470			
		med to l dkd grey calc lap to sl brn lap		47.3	48.1	0.8	<.2	123	4	70	989			
		frac'd, locally mod rubbly, to strongly		48.1	49.6	1.5	3.8	174	4	75	1047			
		bleached dolomitic matrix varies from		49.6	51.2	1.6	6.0	219	<2	75	1069			
		rusty, decomp to fractured but		51.2	52.7	1.5	2.6	273	34	100	1213			
		blocky to fissile, at bottom calcareous		52.7	53.7	1.0	6.2	637	212	140	2003			
		mod dkd grey - dk brn mod decomp		53.7	54.9	1.2	0.8	53	<2	65	560			
		to strongly decomp, rusty yellow		54.9	56.4	1.5	0.8	77	6	75	543			
		brn fissile from 45.3-51.0' under.		56.4	57.9	1.5	<.2	56	<2	70	562			
		calc. to strongly fractured with orange		57.9	59.1	1.2	0.6	69	<2	75	963			
		to red oxides on fractures, fractures have		59.1	59.5	0.4	0.8	37	<2	10	75			
		locally clay to moderate rubbly to		59.5	60.4	0.9	3.6	128	18	80	625			
		[illegible]		60.4	61.9	1.5	<.2	22	<2	65	655			
		[illegible]		61.9	63.4	1.5	<.2	9	<2	65	676			
		SILTSTONE RUBBLE SAND		63.4	64.9	1.5	<.2	3	<2	60	797			
		mixed fine to coarse clastic		64.9	66.4	1.5	<.2	19	<2	55	2524			
		clasts of siltstone, breccia and		66.4	68.0	1.6	0.8	42	2	65	1423			
		orange-brn and lamb shaped dk		68.0	69.5	1.5	<.2	33	2	60	1041			
		clay, moderately rubbly to fissile		69.5	71.0	1.5	0.2	54	<2	65	830			
		clay		71.0	72.5	1.5	0.4	24	22	65	507			
		SILTSTONE QUARTZ VEIN		72.5	74.4	1.9	104.8	1878	62	55	4307			
		white quartz with coarse												
		malachite-azurite-sphalerite												
		blebs [illegible] rock fragments.												

Toklat Resources Inc.

Drill Hole No: TSE-M15 | Page 6 of 7

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES							
		619-725 increase in breccia												
		rock is 1, 30-40% white dispers												
		-clasts supporting conglom to												
		-breccia clasts < 5 cm floated												
		dolomite matrix has weak to moder-												
		ately developed 2 to 3 cm												
		657-661 FAULT												
		[illegible]												
		[illegible]												
		725-744 & 384-												
		mixed dolomite sand.												
		do.												
		11 744m EOH												

Toklat Resources Inc.

Drill Hole No. R595-M15 | Page 7 of 7

DRILL HOLE LOG

LOCATION: Mike Hill 2+75N 10+15W			DRILL HOLE NO.: RS95 M16
AZIMUTH: 130°	ELEVATION: 690m (2260')		PROPERTY:
INCLINATION: -60°	LENGTH: 121.3m / 398'		CLAIM NO:
RECOVERY: 99.0%	CORE SIZE: NQ		SECTION: 2+75N
STARTED: Sept 1/95			LOGGED BY: SPK
COMPLETED: Sept 2/95			DATED LOGGED: Sept 2/95
PURPOSE:			DRILLING CO.: Falcon
			ASSAYED BY: EcoTech

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (o/o) Ag	Cu	Pb	Sb	Zn
0.0	3.0	Overburden									
3.0	111.3	Tuffaceous									
		- sedimentary dark grey, local clast									
		- fine grained sed									
		minor layers of lithoclastic debris		8.4	9.8	1.4	<2	<1	4	70	45
		locally recrystallized		9.8	11.3	1.5	<2	<1	6	60	69
		- minor faint lamination 50 60° to c/l		11.3	12.6	13	0.8	78	10	105	1777
		- several zones of internal sedimentation		12.6	14.0	1.4	0.2	14	4	70	77
				14.0	15.5	1.5	<2	<1	<2	65	15
		3.0 - 9.2 Solution Breccia		39.4	40.9	1.5	<2	<1	10	70	15
		- dolomite clasts (up to 3 cm, subang.		40.9	41.7	0.8	<2	<1	20	35	16
		angl in ankeritic Q-C matrix		41.7	43.2	1.5	<2	<1	10	70	16

Toklat Resources Inc.

DRILL HOLE LOG

FROM	TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		11.3 - 12.6 tr. qtz vein carrying py 10° to core axis									
		minor Azurite Tetrahedrite									
		vugs									
		30.7 - 42.1 broken zone no gouge minor calcite									
		40.0 - 41.1 Lower bull qtz vein minor Lower 15° to C.A									
		46.6 47.3 carbonate and Values in									
		66.7 - 77.1 intercal beds well bedded at 30° to C.A.									
		94.6 96.0 banded milky qtz vein 15° to core axis		93.1	94.6	1.5	<.2	<1	<2	55	51
				94.6	96.0	1.4	<2	1	<2	35	74
				96.0	97.3	1.3	<2	<1	<2	60	23
				110.5	112.0	1.5	<.2	1	6	60	52
				112.0	113.5	1.5	<2	<1	12	65	70
				118.3	119.8	1.5	<2	<1	14	65	10
				119.8	121.3	1.5	0.6	1 =	148	65	83

Toklat Resources Inc.

Drill Hole No. RS95M-4 | Page 2 of 2

DRILL HOLE LOG

OR95-1

LOCATION: ORMA HILL			DRILL HOLE NO.: [redacted]
AZIMUTH: 065	ELEVATION: 620m (2035')		PROPERTY:
INCLINATION: -45°	LENGTH: 98.1m / 322'	SURVEYS	CLAIM NO:
RECOVERY:	CORE SIZE: BGM	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY: CLO
COMPLETED:			DATED LOGGED:
PURPOSE: TEST MINERALIZATION IN AREA OF OUTCROP SHOWING			DRILLING CO.: FALCON
			ASSAYED BY: ECO TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	10	OVERBURDEN med to rusty brown dirt + clay		0	5'	5'	28.8	1827	9196	15	1649
		mixed with clasts of v fine gr. goethite altered		5'	10'	5'	41.4	1344	(1.82)	<5	2071
		rock, quartz, dolomite and 3% galena fragments									
3.0	6.2	GOETHITE ALTERED DOLOMITE fine to v		3.0	3.4	0.4	12.6	1440	1628	<5	2173
		fine grained to botryoidal, red-brown to silver		3.4	3.7	0.3	5.8	465	644	<5	2198
		pervasive goethite alteration of dolomite? original		3.7	5.0	1.3	8.8	2550	3192	<5	2123
		rock textures destroyed, 20% coarse vugs lined		5.0	6.2	1.2	3.8	3209	3870	<5	1784
		w hematite ± calcite, 5% 0.2-0.5cm qtz veins									
		@ is 30° tca; local brecciated textures; green +									
		" blue copper mineralization @ 5.4m reacts w									
		HCl; 10% sandy poorly consolidated rusty rubble.									

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
6.2	19.0	RUBBLE poorly to moderately consolidated sand		6.2	7.5	1.3	10.4	4786	5918	160	1182			
		and fine to medium fragments of str or brecc		7.5	8.7	1.2	15.0	9085	5806	385	1051			
		rock - quartz chips, colour varies from grey-brown		8.7	9.9	1.2	5.6	2954	9902	245	524			
		to rusty brown to yellow, qtz veins from 7.3-7.5,		9.9	10.7	0.8	2.4	226	368	45	418			
		9.9-10.7 are weakly to moderately vuggy = black		10.7	11.9	1.2	9.4	16366	8294	570	1214			
		oxides on fractures.		11.9	13.1	1.2	8.6	4430	5110	500	955			
		14.3-19.0 dominantly sand size material,		13.1	14.3	1.2	5.8	5269	8332	595	1125			
		local black streaks, pale yellow streaks; from		14.3	15.8	1.5	6.4	3134	5150	270	1018			
		17.6-17.8 large dense clasts of yellow-green		15.8	17.3	1.5	12.6	2330	11066	215	4170			
		altered rock may indicate presence of		17.3	19.0	1.7	439.3	(1.03)	(1880)	7110	591			
		kelyphite;												
		19.0 sharp contact with underlying												
		dolomite is irregular												
19.0	98.1	DOLOMITE, DOLOMITE BRECCIA medium to		19.0	20.5	1.5	1.6	45	292	100	9			
		light grey, mod to strongly bleached, fine grained												
		to sucrosic dolomite, 8% white calcite-qtz in												
		0.1-10 cm veins-gashes oriented generally												
		30-60° tca, 20% of interval has angular to												
		subangular dolomite clasts in matrix of												
		white spar, in places the matrix has marcasite												
		alteration-clouding, moderately fractured with												
		weak oxide stain on fractures to 33 cm												

Toklat Resources Inc.

Drill Hole No. RS95-08 | Page 2 of 3

FOOTAGE FROM	FOOTAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn			
		11.3 - 12.6 thin Qtz vein core lost at 10° to core axis												
		- minor Azurite Tetrahedrite												
		- vuggy												
		30.7 - 42.1 broken zone no gouge												
		- minor pyrite												
		40.0 - 41.7 barren bull Qtz vein												
		- vuggy barren 15° to C.A												
		42.1 - 47.3 recrystallized Dolomite												
		47.3 - 77.1 intercal rock, well fractured at 50° to C.A.												
		94.6 - 96.0 barren vuggy Qtz vein 10° to core axis		93.1	94.6	1.5	< 2	< 1	< 2	55	51			
				94.6	96.0	1.4	< 2	1	< 2	35	74			
				96.0	97.3	1.3	< 2	<	< 2	60	23			
				110.5	112.0	1.5	< .2	1	6	60	52			
				112.0	113.5	1.5	< 2	< 1	12	65	70			
				118.3	119.8	1.5	< .2	< 1	14	65	10			
				117.8	121.3	1.5	0.6	1	148	65	83			

Toklat Resources Inc.

Drill Hole No. RS95M16 | Page 2 of 2

DRILL HOLE LOG

OR95-2

LOCATION: OGMA HILL		DRILL HOLE NO.: ~~DDH95-09~~	
AZIMUTH: 065	ELEVATION: 620m (2035')	PROPERTY:	
INCLINATION: -70°	LENGTH: 38.4m, 126'	CLAIM NO:	
RECOVERY:	CORE SIZE: BGM	SECTION:	
STARTED:		LOGGED BY: CCD, TIM TERMUENDE LABELLED THE BD	
COMPLETED:		DATED LOGGED:	
PURPOSE: TEST DOWNDIP FOR ZONE IN RD95-08		DRILLING CO.: FALCON	
		ASSAYED BY: ECO TECH	

SURVEYS

METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	15'	OVERBURDEN medium to rusty-brown sand-		0	5'	5'	17.8	1177	3870	120	478
		dirt mixed with organic debris chips of qtz chunks of		5'	10'	5'	26.4	1521	5162	105	442
		underlying bedrock.		10'	15'	5'	15.8	4379	6122	75	2141
46	144	GOETHITE ALTERATION - GOSSAN ZONE similar		4.6	5.8	1.2	8.0	1076	1496	<5	1665
		top of hole #8, str pervasive replacement by vuggy		5.8	7.1	1.3	5.0	2356	4584	<5	1841
		to bottom of geotech, 50% of interval is poorly		7.1	8.2	1.1	7.0	3410	5098	150	1509
		consolidated rubble that appears to be alteration		8.2	9.8	1.6	8.8	4152	6280	240	1624
		product, rest fractured & blocky mn sand (soft, stains		9.8	11.0	1.2	7.6	4708	6516	170	1556
		(negris) and white clay alteration from 58 ?, 110-111		11.0	11.7	0.7	8.2	2617	5932	415	936
		qtz rubble 117-128m, str red-orange clay coating.		11.7	13.1	1.4	9.8	3819	5128	475	1121
				13.1	14.4	1.3	11.2	2895	4264	255	867

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
14.4	16.9	STRONG CLAY ALTERATION - DOLOMITE light		14.4	15.2	0.8	12.4	2,377	11082	275	6415
		grey fine grained dolomite with strong vella to		15.2	15.4	0.2	4.8	198	324	<5	142
		beige clay alteration, green clay bands last positive		15.4	16.9	1.5	135.8	(1.31)	(11.40)	4175	151
		for copper 165 16.9									
		15.8-16.5 FAULT, QUARTZ VEIN									
		angular clasts of white quartz mixed with									
		tan clay-sand; contacts indistinct at									
		10-25°CA.									
16.9	18.7	RUBBLE ZONE - FAULT angular to subrounded clasts		16.9	18.7	1.8	250.1	2147	(5.28)	1600	2241
		of quartz, sparkle altered dolomite grey dolomite									
		mixed with sand, clay, core loss over interval,									
		sharp contact with underlying dolomite									
18.7	38.4	DOLOMITE-DOLOMITE BRECCIA med to light grey		18.7	20.2	1.5	2.2	27	220	75	14
		med grained to microlic dolomite, 15% small		20.2	21.7	1.5	2.8	70	254	100	77
		(5-25 cm) breccia zones with stronglar dolomite		21.7	23.2	1.5	0.8	<1	14	60	6
		clasts in a matrix of white spar or marcasite altered									
		spar, breccias have general passive sedimentary									
		texture, interval is mod fractured, 10% white spar									
		qtz in 0.1-1cm veins cut gastes @ 10-45°CA;									
		local 5% black stain on fracture - mn? graphite?									
		21.5-21.7 Rubble str clay alteration,									
		margins have reversive weak oxide stain									

EOH 38.4m

Toklat Resources Inc.

Drill Hole No. RS95-09 | Page 2 of 2

DRILL HOLE LOG

OR95-3

LOCATION: ORMA HILL			DRILL HOLE NO.: ~~DDH-4~~
AZIMUTH: 065	ELEVATION: 620m (2030')		PROPERTY:
INCLINATION: -89°	LENGTH: 268m/88'	SURVEYS	CLAIM NO:
RECOVERY:	CORE SIZE: BGM	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY: CCD
COMPLETED:			DATED LOGGED:
PURPOSE: TEST DOWNDIP FOR GOSSAN ZONE SEEN IN RS95-89			DRILLING CO.: FALCON
			ASSAYED BY: ECO TECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH m	ANALYSES ppm (Ag) Ag	Cu	Pb	Sb	Zn
0	10'	OVERBURDEN medium to light brown sand clay-		0	5'	5'	14.8	716	1536	20	358
		dirt mixed with fragments of grey dolomite, occ silt chips		5'	10'	5'	19.0	721	1636	45	219
		and a large coral fragment									
30	104	GOETHITE ALTERATION ZONE as in hole 89, strong		3.0	3.9	0.9	10.4	391	548	<5	641
		oxidic alteration - rept of f-med grained dolomite		3.9	5.4	1.5	6.0	460	630	<5	1558
		CISS veins, 25% of interval is rusty orange rubble,		5.4	6.9	1.5	5.6	481	944	<5	1789
		clasts - fragments of med grey dolomite - dolomite		6.9	8.5	1.6	8.0	1741	3148	175	1414
		breccia scattered throughout,		8.5	10.0	1.5	4.4	1578	2758	50	1460
				10.0	11.6	1.6	9.2	3190	5044	380	1031
104	177	RUBBLE rusty orange sand mixed with chips -		10.0	11.6	1.6	9.2	3190	5044	380	1031
		fragments of silt, str altered dolomite		11.6	13.1	1.5	14.4	3934	5530	6085	1270
				13.1	14.6	1.5	6.4	1736	2856	270	965
177	268	RUBBLE - QUARTZ VEIN med. to coarse sacchroidal		14.6	16.1	1.5	16.2	429	784	15	276

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		clasts of white quartz = weak oxide staining on		16.1	17.7	1.6	10.2	279	4146	180	1155
		fractures. Local clay sand zones may be FAULT									
		related.		17.7	20.7	3.0	5.8	131	328	15	54
				20.7	23.8	3.1	107.3	1629	2950	290	489
		EOH 263m		23.8	26.8	3.0	49.3	511	(1.23)	900	29

Toklat Resources Inc.

Drill Hole No. R95-10 | Page 2 of 2

DRILL HOLE LOG

OR95-4

DRILL HOLE NO.: [illegible]

LOCATION: ORMA HILL			
AZIMUTH: 065°	ELEVATION: 610m (1000')		
INCLINATION: -45°	LENGTH: 317m/104'		
RECOVERY	CORE SIZE: BGM		
STARTED:			
COMPLETED:			
PURPOSE: TEST MINERALIZATION PROJECTED FROM SHOWINGS IN TRENCH #7			

SURVEYS			
METREAGE	AZIMUTH	INCLINATION	CORR. INCLIN.

PROPERTY:	
CLAIM NO:	
SECTION:	
LOGGED BY: CLD	
DATED LOGGED:	
DRILLING CO.: FALCON	
ASSAYED BY: ECO TECH	

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (Au oz) Au				Zn			
0	5'	OVERBURDEN med brown dirt and clay mixed with			5'	5'	261.5		2.88	625	1460			
		organic debris, cdz chips, fragments of blue												
		ddamite												
15	82	VARIABLY ALTERED DOLOMITE - DOLOMITE BRECCIA							4536	165	2593			
		med. to fine grained ddomite, altered on varies from							2800	175	1617			
		local pervasive specular alteration - replacement to					1.2		346	295	2297			
		pervasive orange to yellow gossan, from 50-65							1828	225	1162			
		rock is med grey-blue ddomite, fine, crackle breccia,							1138	165	511			
		with pervasive red-orange oxides on fractures,							1400	125	590			
									3794	125	1607			
82	9.8	RUBBLE - FAULT ZONE str. oxidized ddomite sand,							3794	125	1607			
		ddomite fragments, mod-poor, consolidated							4294	300	1156			
		94.98 SHALE? fine grained thinly laminated BB												

Toklat Resources Inc.

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
		tco, mod to str clay alteration									
99	127	QUARTZ VEIN - RUBBLE ZONE angular to subangular		9.8	11.6	1.8	6.2	1457	1614	155	374
		clasts of white quartz with pervasive orange stain on		11.6	12.7	1.1	6.6	317	802	55	183
		fractures in large vugs,									
127	161	RUBBLE ZONE fine dolomite sand, qtz fragments		12.7	13.4	0.7	11.4	2073	6188	295	1096
		poor, consolidated dolomite-cemented matrix at 15cm		13.4	14.6	1.2	8.8	3558	6276	500	1461
		band of quartz 153m		14.6	15.8	1.2	26.4	2703	8492	365	1167
		153-161 interval is mainly clay mixed with		15.8	16.1	0.3	21.2	(1.01)	(1.74)	700	1698
		rock fragments									
161	317	DOLOMITE - DOLOMITE BRECCIA med to light		16.1	17.1	1.0	2.6	78	100	65	158
		grey, light, bleached, med to fine grained dolomite,		17.1	18.5	1.4	0.8	64	82	70	60
		mod. fractured at low angle tco with white dolospar		18.5	19.5	1.0	0.8	7	14	60	22
		and marcasite in matrix, local medium vugs,									
		porosity									
		EOH 31.7m									
		HOLE STOPPED DUE TO DRILLING PROBLEMS									

Toklat Resources Inc.

OR95-4

Drill Hole No. ~~R95-11~~ | Page 2 of 2

DRILL HOLE LOG

OR95-5

LOCATION: ORMA HILL			DRILL HOLE NO.: DS95-5
AZIMUTH: 065°	ELEVATION: 6100m (2000')		PROPERTY:
INCLINATION: -90°	LENGTH: 28.0m, 92'	SURVEYS	CLAIM NO:
RECOVERY.	CORE SIZE: BGM	METREAGE / AZIMUTH / INCLINATION / CORR. INCLIN.	SECTION:
STARTED:			LOGGED BY: CCD
COMPLETED:			DATED LOGGED:
PURPOSE: TEST FOR MINERALIZATION IN TRENCH #7 AREA			DRILLING CO.: FALCON
			ASSAYED BY: I-COTECH

CORE RECOVERY:

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES ppm (%) Ag	Cu	Pb	Sb	Zn
0	7'	OVERBURDEN med brown dirt - clay mixed with		0	5'	5'	34.2	4979	(1.43)	275	2447
		fragments and clasts of variably altered grey		5'	7'	2'	7.4	3933	6212	250	2421
		dolomite									
21	131	VARIABLY ALTERED DOLOMITE-DOLOM-E		2.1	3.0	0.9	3.0	3176	.0416	200	2473
		BRECCIA med to f gr dolomite; strong to moderate		3.0	4.6	1.6	2.8	1758	.0213	50	1726
		pervasive red-orange gossan with lesser pervasive		4.6	6.1	1.5	2.4	883	1374	40	1727
		syntaxial replacement-alteration, from 64-109 is		6.1	7.6	1.5	3.0	796	1870	130	1275
		med grey-blue dolomite with fine crackle brecciation		7.6	9.1	1.5	2.8	1712	946	40	976
		vein brecciation healed with white spar, fractures		9.1	10.6	1.5	3.4	1116	1872	95	1271
		are strongly oxidized; 10% of interval is poorly		10.6	12.1	1.5	3.2	648	1438	50	1504
		consol. baked rubble;		12.1	131	1.0	2.0	784	2018	85	1819

Toklat Resources Inc.

OR95 5

Drill Hole No. ~~DS95-5~~ | Page 1 of 2

METREAGE FROM	METREAGE TO	DESCRIPTION	SAMPLE NO.	METREAGE FROM	METREAGE TO	LENGTH	ANALYSES Ag	Cu	Pb	Sb	Zn
13.1	18.0	QUARTZ VEIN- VEIN BRECCIA course to medium		13.1	14.0	0.9	3.0	82	290	<5	107
		fragments of white quartz, strong pervasive red-		14.0	14.9	0.9	3.4	1172	3288	100	1391
		orange gossan on fractures, in vugs, quartz		14.9	16.4	1.5	333.6	2197	6276	1690	1910
		carries strong marcasite altered dolomite clasts,		16.4	18.0	1.6	6.8	609	928	65	2116
		from 15.6-16.4 distinct green to turquoise									
		altered on on quartz flooded dolomite.									
18.0	23.6	RUBBLE ZONE poorly consolidated sand and		18.0	21.0	3.0	12.8	2188	5450	4165	11058
		clay mixed with clasts- fragments of str oxidized		21.0	22.1	1.1	16.6	1931	11802	250	4386
		dolomite scattered quartz fragments <5%;		22.1	23.6	1.5	15.6	758	3322	250	784
23.6	28.0	Dolomite medium to light grey to orange		23.6	25.0	1.4	0.4	10	20	60	76
		fine to med grained dolomite; moderate pervasive		25.0	25.9	0.9	0.6	<1	38	60	77
		orange-yellow oxide stain; mod-str fractured;		25.9	27.1	1.2	0.2	<1	16	60	82
		10% sandy rubble;		27.1	28.0	0.9	0.2	33	60	55	63
		EOH 23.0m									
		HOLE STOPPED DUE TO DRILLING PROBLEMS									

Toklat Resources Inc.

Drill Hole No. RSDS-12 | Page 2 of 2


APPENDIX IV

Statement of Expenditures

STATEMENT OF EXPENDITURES- RUSTY SPRINGS PROGRAM

The following expenses were incurred on the **Rusty Springs** property for the purpose of mineral exploration between the dates of June 4th to September 12th, 1995.

PERSONNEL	$ 59,770.00
EQUIPMENT RENTAL (including Bulldozer)	66,105.96
DIAMOND DRILLING	164,150.90
HELICOPTER CHARTER	43,921.76
FIXED-WING CHARTER	63,641.53
CONSULTANTS	67,300.64
ANALYTICAL	19,760.87
MEALS/GROCERY	15,064.07
ACCOMMODATION	6,976.65
AIRFARE	13,801.38
COMMUNICATIONS	10,463.58
FUEL	29,197.70
CAMP MATERIALS	14,100.48
TRAVEL EXPENSES	16,020.32
FILING FEES	1,728.00
COREBOXES	2,062.43
FIELD SUPPLY	286.76
SHIPPING	1,091.06
MISCELLANEOUS	2,815.40
Total :	**$538,549.26**



CORE STORAGE LOCATION

1. 95OR-1 TO 95OR-5
2. 80-1 TO 80-9; 80-22,80-23
3. 80-11
4. 80-12
5. 80-13
6. 80-14 TO 80-25; 82-1 TO 82-8; 83-1,83-2
7. 95-1 TO 95-16
8. 78-101 TO 78-106

140°24'00" W | 140°23'00" W | 140°22'00" W | 140°21'00" W | 140°20'00" W | 140°19'00" W

66°30'00" N

66°29'00" N

1995 PROPERTY BOUNDARY

CREEK

CARROL

RUSTY SPRINGS CAMP

MIKE GRID SOIL GEOCHEMICAL ANOMALY

MIKE ZONE

MIKE GRID COVERAGE AREA

Tim

Tip

Jackson

Galena Coral

Chivas

New Galena

Reef

Ma

Joe

Ullr

Geoff

Jennifer

Andrea

New

95-M2,M9-M11

95-M5-M8

95-M1

95-M3,M4

95-M3,14

95-M2

95-16

95-15

TRENCH 300

TRENCH 325

TRENCH 000

TRENCH 075

MIKE ZONE

MONUMENT 1

MIKE GRID ZERO BASELINE 0+00

MIKE HILL

BIG ONION ZONE

BIG ONION GRID ZERO BASELINE 0+00

Big Onion

Marilyn

White

Quartz

BIG ONION GRID SOIL GEOCHEMICAL ANOMALY

BIG ONION GRID COVERAGE AREA

ORMA CAMP

ORMA ZONE

Tetrahedrite

Pyrite

Orma

OR95-1

OR95-2

OR95-3

OR95-4

OR95-5

BULK SAMPLE

ORMA GRID SOIL GEOCHEMICAL ANOMALY

ORMA HILL

AIRSTRIP

Cole

Barite

N

0 250 500 750 1000m

LEGEND

- CAMP LOCATION
- CAT ROAD
- CREEK
- TRENCH LOCATION
- MONUMENT
- DRILLHOLE LOCATION
- SHOWING LOCATION
- CLAIM-POST LOCATION
- CORE SAMPLE LOCATION
- SOIL GEOCHEMICAL ANOMALY
- GRID BASE POINT

DIGITAL MAPPING & GPS SURVEY BY:

INTERIOR REFORESTATION CO. LTD.

P.O. BOX 487 CRANBROOK B.C. V1C 4J1
PHONE NO. 426-5300 FAX NO. 426-5311

EAGLE PLAINS RESOURCES
RUSTY SPRINGS PROJECT

PROPERTY COMPILATION MAP

NTS Reference: 116K/8,116K/9	Date: Feb./96
TOKLAT RESOURCES INC.	Scale: AS SHOWN

Cad File: TERM\JENDE\RUSTYSP.SOI

Marilyn

White Quartz

Big Onion

SOIL GEOCHEMICAL ANOMLY

BASELINE 1000 / 240°

SCALE
0 50m 100m 150m 200m

LEGEND

- CAT ROAD
- CREEK
- TRENCH LOCATION
- DRILLHOLE LOCATION
- SHOWING LOCATION
- CLAIM-POST LOCATION
- 1994 GRID DATA
- SOIL GEOCHEMICAL ANOMALY

DIGITAL MAPPING BY
INTERIOR REFORESTATION CO. LTD.
P.O. BOX 487 CRANBROOK B.C. V1C 4J1
PHONE NO. 426-5300 FAX NO. 426-5311

PROFESSIONAL GEOSCIENTIST
PROVINCE OF BRITISH COLUMBIA
J. TERMUENDE

EAGLE PLAINS RESOURCES
RUSTY SPRINGS PROJECT

BIG ONION GRID SOIL GEOCHEMISTRY
Ag IN SOILS

DATE:	DRAWN / MAPPED:	N.T.S.:
FEB. 1996	J. NICOLAJSEN/ T. TERMUENDE	116 K/8, 116 K/9

TOKLAT RESOURCES INC.

FIGURE No. 4

Marilyn

White

Quartz

Big Onion

SOIL GEOCHEMICAL ANOMLY

BASELINE 180/240°

SCALE
0 50m 100m 150m 200m

LEGEND

- CAT ROAD
- CREEK
- TRENCH LOCATION
- DRILLHOLE LOCATION
- SHOWING LOCATION
- CLAIM-POST LOCATION
- 1994 GRID DATA
- SOIL GEOCHEMICAL ANOMALY

DIGITAL MAPPING BY
INTERIOR REFORESTATION CO. LTD.
P.O. BOX 487 CRANBROOK B.C. V1C 4J1
PHONE NO. 426-5300 FAX NO. 426-5311

PROFESSIONAL GEOSCIENTIST
PROVINCE OF BRITISH COLUMBIA
J. TERMUENDE

EAGLE PLAINS RESOURCES
RUSTY SPRINGS PROJECT

BIG ONION GRID SOIL GEOCHEMISTRY
Pb IN SOILS

DATE:	DRAWN / MAPPED:	N.T.S.:
FEB. 1996	J. NICOLAJSEN/ T. TERMUENDE	116 K/8, 116 K/9
TOKLAT RESOURCES INC.		FIGURE No. 5

Marilyn

White

Quartz

Big Onion

SOIL GEOCHEMICAL ANOMLY

BASE LINE 160.730

SCALE
0 50m 100m 150m 200m

LEGEND

- CAT ROAD
- CREEK
- TRENCH LOCATION
- DRILLHOLE LOCATION
- SHOWING LOCATION
- CLAIM-POST LOCATION
- 1994 GRID DATA
- SOIL GEOCHEMICAL ANOMALY

DIGITAL MAPPING BY:
INTERIOR REFORESTATION CO. LTD.
P.O. BOX 487 CRANBROOK B.C. V1C 4J1
PHONE NO. 426-5300 FAX NO. 426-5311

PROFESSIONAL GEOSCIENTIST
PROVINCE OF BRITISH COLUMBIA

EAGLE PLAINS RESOURCES
RUSTY SPRINGS PROJECT

BIG ONION GRID SOIL GEOCHEMISTRY
Zn IN SOILS

DATE:	DRAWN / MAPPED:	N.T.S.:
FEB. 1996	J. NICOLAJSEN/ T. TERMUENDE	116 K/8, 116 K/9

TOKLAT RESOURCES INC.

FIGURE No. 6

WEST

EAST

ELEVATION 715m ASL

1+25W

1+00W

0.6, 60, 658, 347

0+75W

2.6, 48, 3114, 1308

0+50W

0.2, 26, 812, 225

0+25W

<0.2, 24, 146, 424

BASELINE

1.0, 28, 560, 853

0+25E

<0.2, 4, 4, 4

3.0m – 5.7m
2.7m @ 9.8, 1417, 370, 2.58%

24.2m – 54.8m
moderately oxidized rubble zone

42.1m – 43.6m
1.5m @ 3.4, 409, 116, 2.06%

RUBBLE ZONE

BLEACHED DOLOMITE
strongly fractured with weak oxide stain

3.0m – 75.3m
BLEACHED DOLOMITE
weak oxide stain on fractures;
local smithsonite on fractures

68.5m – 70.0m
1.5m @ 5.8, 608, 52, 2.08%

RS95 – M12
AZ 130°
DIP –45°
EOH 75.3m

APPROX. LIMIT OF BLEACHING AND SMITHSONITE ON FRACTURES

98.3m – 110m
MIXED DOLOMITIC LIMESTONE

RS95 – M13
AZ 130°
DIP –45°
EOH 110m

106.7m – 130.5m
SILICEOUS DOLOMITE

RS95 – M14
AZ 130°
DIP –70°
EOH 130.5m

LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 18.7, 2.55%, 234, 5668
UNLESS NOTED IN PERCENT (%)

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500


PROFESSIONAL GEOSCIENTIST
PROVINCE OF BRITISH COLUMBIA

EAGLE PLAINS RESOURCES LIMITED

RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – LINE 0+00
PLANE OF SECTION: 130° / 310°

DATE: FEBRUARY 1996	DRAWN / MAPPED: DWG FILE EP95-7 / TJT	N.T.S.: 116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 7



LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 18.7, 2.55%, 234, 5668
UNLESS NOTED IN PERCENT (%)

PROFESSIONAL ENGINEER
PROVINCE OF BRITISH COLUMBIA
T. J. TERMUENDE

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500

EAGLE PLAINS RESOURCES LIMITED


RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – LINE 1+00N
PLANE OF SECTION: 130° / 310°

DATE:	DRAWN / MAPPED:	N.T.S.:
FEBRUARY 1996	DWG FILE EP95-8 / TJT	116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 8

WEST

EAST



LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT _____

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 62.5m – 64.0m
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 18.7, 2.55%, 234, 5668
UNLESS NOTED IN PERCENT (%)

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500


PROFESSIONAL GEOSCIENTIST

EAGLE PLAINS RESOURCES LIMITED

RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – OFF SECTION 1+00N
PLANE OF SECTION: 070° / 250°

DATE:	DRAWN / MAPPED:	N.T.S.:
FEBRUARY 1996	DWG FILE #EP95-9 / TJT	116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 9



LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 18.7, 2.55%, 234, 5668
UNLESS NOTED IN PERCENT (%)

PROFESSIONAL ENGINEER
PROVINCE OF BRITISH COLUMBIA
J. J. TERMUENDE
GEOSCIENTIST

SCALE
0 10m 20m 30m 40m
SCALE = 1 : 500

EAGLE PLAINS RESOURCES LIMITED

RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – LINE 1+75N
PLANE OF SECTION: 130° / 310°

DATE:	DRAWN / MAPPED:	N.T.S.:
FEBRUARY 1996	DWG FILE EP95-10 / TJT	116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 10

WEST

EAST

0+25W

0+15W

BASELINE

0+25E

0+50E

1.6, 204, 178, 1193

0+75E

11.2, 483, 934, 3273

ELEVATION 690m ASL

3.0m – 121.3m
DOLOMITE
local bleaching and recrystallization

RS95 – M16
AZ 130°
DIP –60°
EOH 121.3m

LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 18.7, 2.55%, 234, 5668
UNLESS NOTED IN PERCENT (%)

PROFESSIONAL ENGINEER PROVINCE OF BRITISH COLUMBIA GEOSCIENTIST

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500

EAGLE PLAINS RESOURCES LIMITED


RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – LINE 2+75N
PLANE OF SECTION: 130° / 310°

DATE: FEBRUARY 1996	DRAWN / MAPPED: DWG FILE EP95-11 / TJT	N.T.S.: 116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 11

SOUTH

NORTH



LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), 25.4, 4182, 1.03%
UNLESS NOTED IN PERCENT (%)

PROFESSIONAL GEOSCIENTIST
PROVINCE OF BRITISH COLUMBIA
TERMUENDE

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500

EAGLE PLAINS RESOURCES LIMITED


RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE – TRENCH 6 AREA
PLANE OF SECTION: 245° / 065°

DATE:	DRAWN / MAPPED:	N.T.S.:
FEBRUARY 1996	DWG FILE EP95-12 / TJT	116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 12

SOUTH

NORTH



VARIABLY ALTERED DOLOMITE AND DOLOMITE BRECCIA
strong goethite alteration; strong pervasive oxide stain; numerous fault and rubble zones

LEGEND

OVERBURDEN

MINERALIZED ZONE

LITHOLOGIC CONTACT

FAULT/RUBBLE ZONE

GEOCHEMISTRY

STATION 18+00E
Ag(gm), Cu(ppm), Pb(ppm), Zn(ppm) 4.6, 1924, 2047, 246

DRILL INTERSECTION 14.6m – 16.1m
Ag(gm), Cu(ppm), Pb(ppm), 25.4, 4182, 1.03%
UNLESS NOTED IN PERCENT (%)

SCALE

0 10m 20m 30m 40m

SCALE = 1 : 500

PROFESSIONAL ENGINEER PROVINCE OF BRITISH COLUMBIA J. V. TERMUENDE GEOSCIENTIST

EAGLE PLAINS RESOURCES LIMITED

RUSTY SPRINGS PROJECT

DIAMOND DRILL PROFILE TRENCH 7 AREAS
PLANE OF SECTION: 245° / 065°

DATE: FEBRUARY 1996	DRAWN / MAPPED: DWG FILE EP95–13 / TJT	N.T.S.: 116 K8 / K9
TOKLAT RESOURCES INC.		FIGURE No. 13

CREEK

CARROL

MIKE GRID

BASELINE 45°/225°

ERIC 1 ERIC 4

ERIC 2 ERIC 5

ERIC 3 ERIC 6

ERIC 8 ERIC 7

JESSICA 1 JESSICA 4

JESSICA 2 JESSICA 5

JESSICA 3 JESSICA 6

JESSICA 7 JESSICA 8

SHELLY 1 SHELLY 2

SHELLY 3 SHELLY 4

SHELLY 5 SHELLY 6

SHELLY 7 SHELLY 8

SHELLY 9 SHELLY 10

SHELLY 11 SHELLY 12

SHELLY 15 SHELLY 13

SHELLY 16 SHELLY 14

Tetrahedrite Pyrite

Orma

Tip

Tim

Jackson

Mo

Joe

Ullr

Chivas

Reef

Galena Coral

New Galena

New

Geoff

Jennifer

Mike

Azurite

Andrea

Marilyn

White Quartz

ORMA HILL

AIRSTRIP

MIKE HILL

PROPERTY BOUNDARY

BIG ONION GRID

BASELINE 160°/340°

JOEL 1 JOEL 3 JOEL 4 JOEL 2

Big Onion

L0+00

L0+50 S

L1+00 S

L1+50 S

L2+00 S

L2+50 S

L3+00 S

2+00 W

1+00 W

0+00

1+00 E

3+00 E

LEGEND

- Camp Location
- Cat-Road
- Trench Location
- Diamond-Drillhole Location
- Showing Location
- Claim-Post Location

0 100m 200m 300m 400m 500m 1.0 km

PROFESSIONAL ENGINEER PROVINCE OF BRITISH COLUMBIA C. DOWNIE GEOSCIENTIST


EAGLE PLAINS RESOURCES LTD.

RUSTY SPRINGS PROJECT

95-004

Property Compilation Map

Scale: 1 : 5000	Date: SEPT. 1994
Mapped by: C. DOWNIE	N.T.S.: 116 K/8, 116 K/9
BIG CITY RESOURCES INC.	Map no.: 1



▲ LITHOGEOCHEMICAL SAMPLES

Tag #	Au ppb	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
TT94R-51	5	<.2	3.70	455	135	<5	0.17	15	138	50	445	>15	<10	<.01	430	35	<.01	866	1150	75	<5	<20	13	<.01	50	271	<10	13	2601
TT94R-52	5	<.2	1.93	130	105	<5	0.06	10	34	50	1734	14.70	<10	<.01	37	103	<.01	351	510	70	<5	<20	2	<.01	40	571	<10	24	1564
TT94R-53	5	4.0	0.09	520	35	<5	0.06	13	21	204	54	11.40	<10	<.01	124	17	<.01	47	410	205	<5	<20	2	<.01	20	9	<10	8	878
TT94R-54	10	<.2	8.11	355	130	<5	0.33	13	34	105	1140	10.90	<10	<.01	72	34	<.01	247	3050	138	<5	<20	2	<.01	50	1010	<10	36	1016
TT94R-59	5	>30	0.17	455	10	<5	0.05	37	<1	52	559	0.30	<10	0.02	11	8	<.01	10	240	>10000	1150	<20	7	<.01	<10	14	<10	2	2291
TT94R-60	15	>30	0.07	3310	25	<5	0.10	45	2	294	>10000	0.48	<10	0.04	38	20	<.01	11	950	7356	5625	<20	11	<.01	15	9	<10	<1	2134
TT94R-62	20	6.0	0.16	70	355	<5	0.01	3	5	205	128	6.18	<10	<.01	25	351	<.01	44	655	4418	50	<20	11	<.01	20	767	<10	41	406
TT94R-63	5	1.6	0.27	80	560	<5	0.05	2	5	101	86	4.61	20	<.01	18	83	<.01	84	2500	484	10	<20	43	<.01	20	157	<10	18	246
TT94R-64	35	>30	7.88	8815	100	<5	0.27	105	9	84	>10000	3.15	180	<.01	25	10	<.01	56	536	3610	>10000	3240	<20	<.01	<10	172	<10	47	3159
TT94R-65	5	6.6	0.22	75	100	<5	>15	27	57	4	188	9.04	>50	12.30	672	<1	0.01	436	370	566	80	<20	58	<.01	10	17	<10	54	5365
TT94R-66	10	1.0	1.26	145	175	<5	0.83	8	26	229	323	15.00	<10	0.41	100	110	<.01	232	4490	228	<5	<20	165	<.01	60	665	<10	24	1309
TT94R-67	5	1.8	0.22	60	95	<5	0.46	2	9	245	143	5.50	<10	0.23	187	64	<.01	84	840	156	<5	<20	20	<.01	20	111	<10	<1	272
TT94R-68	5	>30	0.70	1315	125	<5	0.54	22	4	147	1609	0.78	20	0.25	54	9	0.01	36	860	>10000	665	<20	18	<.01	<10	13	<10	12	700
TT94R-69	5	>30	0.53	955	75	<5	0.46	14	2	260	1543	0.81	60	0.06	33	16	<.01	50	960	6872	465	<20	35	<.01	<10	26	<10	10	462
TT94R-70	10	2.8	3.50	275	450	<5	0.42	31	34	194	1672	>15	<10	<.01	270	345	<.01	235	9900	236	<5	<20	35	<.01	170	790	<10	4	954
TT94R-71	150	>30	0.55	5370	360	<5	0.28	192	5	162	588	4.15	<10	<.01	31	9	<.01	38	2010	1584	>10000	<20	40	<.01	40	16	<10	35	1858
TT94R-72	25	>30	4.37	1810	105	<5	0.48	229	104	69	8057	5.78	<10	0.16	859	4	<.01	360	1800	>10000	4215	<20	8	<.01	20	146	<10	39	4376
TT94R-73	5	29.6	1.65	45	840	<5	0.18	144	883	8	1851	>15	<10	<.01	7856	<1	<.01	1506	100	2912	170	<20	5	<.01	140	53	<10	104	>10000
94ATR001	15	8.2	0.87	130	830	<5	0.12	13	27	165	244	8.55	<10	<.01	133	68	<.01	434	750	186	405	<20	7	<.01	30	344	<10	45	2677
94ATR002	10	2.8	0.93	445	1065	20	0.08	12	40	133	71	14.00	<10	<.01	143	38	<.01	682	340	94	150	<20	12	<.01	50	144	<10	11	1181
94ATR003	5	>30	0.03	3015	80	<5	0.08	39	2	304	4121	0.45	<10	0.01	35	15	0.01	17	320	1686	1750	<20	2	<.01	10	2	<10	<1	350
94ATR004	10	>30	0.01	2180	45	<5	0.25	37	1	157	9458	0.48	<10	0.10	70	5	<.01	9	550	412	3245	<20	2	<.01	<10	2	<10	<1	1372
G-11	10	7.8	0.12	715	185	<5	0.21	35	153	201	678	>15	<10	<.01	451	40	<.01	2092	890	116	200	<20	4	<.01	50	205	<10	76	3014
G-17	5	4.6	0.49	85	115	<5	0.22	4	15	274	209	4.92	<10	<.01	90	83	<.01	257	310	134	80	<20	2	<.01	<10	57	<10	26	1077
CDRS-R61	15	1.2	0.23	30	190	<5	0.04	<1	<1	38	41	1.01	<10	<.01	6	16	<.01	6	120	24	20	<20	10	<.01	<10	19	<10	2	21
CDRS-R73	5	0.6	0.03	15	65	<5	>15	<1	<1	27	18	0.24	<10	0.14	24	1	<.01	6	170	<2	25	<20	346	<.01	<10	5	<10	4	21
CDRS-R76	10	0.6	0.03	30	75	<5	>15	<1	<1	40	11	0.25	<10	13.00	352	2	0.01	4	310	6	65	<20	110	<.01	<10	10	<10	4	26
CDRS-R79	10	0.4	0.06	10	65	<5	0.23	<1	4	127	14	2.54	<10	0.35	92	6	<.01	19	570	22	5	<20	25	<.01	<10	15	<10	<1	54
CDRS-R80	10	<.2	2.89	30	705	<5	1.25	3	20	541	29	>15	<10	0.03	62	<1	<.01	52	715	7459	66	<5	271	<.01	70	577	<10	7	4812
CDRS-R81	5	0.2	0.11	5	30	<5	0.07	<1	5	276	9	1.29	<10	0.02	54	20	<.01	16	150	8	<5	<20	3	<.01	<10	7	<10	<1	42
CDRS-R82	140	0.4	0.22	10	65	<5	>15	<1	<1	40	16	1.43	<10	0.03	116	17	<.01	19	220	16	45	<20	14	<.01	<10	10	<10	4	42
CDRS-R83	315	0.2	0.07	5	50	<5	4.62	<1	3	281	9	1.54	<10	1.58	239	21	<.01	11	200	8	15	<20	82	<.01	<10	6	<10	<1	23
CDRS-R84	45	0.2	0.04	40	55	<5	>15	2	3	35	3	3.11	<10	8.28	234	2	0.01	12	20	36	40	<20	179	<.01	<10	12	<10	2	66
CDRS-R85	210	<.2	0.02	10	25	<5	10.00	<1	2	140	5	0.51	<10	3.95	173	8	<.01	8	90	10	35	<20	37	<.01	<10	10	<10	3	33
CDRS-R88	5	1.0	0.02	275	40	<5	20	12.90	3	6	85	7	7.69	<10	8.21	371	5	0.01	32	40	40	35	<20	58	<.01	<10	8	<10	<1	26
CDRS-R90	225	9.4	0.01	1345	80	<5	0.13	8	8	196	44	5.18	<10	0.02	40	17	<.01	58	30	66	15	<20	2	<.01	<10	13	<10	<1	245
CDRS-R91	15	2.4	0.03	60	35	<5	5.22	3	4	203	47	1.02	<10	1.76	134	14	0.01	47	70	52	35	<20	7	<.01	<10	16	<10	3	154
CDRS-R94	30	1.0	1.00	10	130	<5	0.26	3	19	75	22	>15	<10	0.03	68	6	<.01	51	1760	36	45	<20	21	<.01	70	78	<10	4	1077
CDRS-R94	210	5.6	0.08	115	20	<5	>15	623	47	6	2141	1.28	<10	12.60	610	<1	<.01	211	190	408	255	<20	37	<.01	<10	30	<10	42	>10000
CDRS-R95	535	1.2	0.13	15	20	<5	0.47	15	23	159	1118	0.66	<10	0.24	383	<1	<.01	113	110	1590	10	<20	2	<.01	<10	6	<10	9	>10000
CDRS-R97	325	1.2	0.10	10	40	<5	>15	50	14	8	157	1.26	<10	14.10	168	17	<.01	490	46	72	10	<20	2	<.01	<10	10	<10	3	1271
CDRS-R98	105	1.4	0.39	30	120	<5	0.23	5	104	282	295	9.17	<10	0.07	532	28	<.01	550	160	314	40	<20	41	<.01	<10	20	34	<10	16	2890
CDRS-R99	190	0.8	0.07	30	30	<5	>15	16	19	10	75	1.38	<10	14.30	265	<1	<.01	77	80	236	90	<20	37	<.01	<10	13	<10	12	787
CDRS-R100	90	>30	0.06	840	690	<5	0.22	14	3	243	262	1.06	<10	0.10	50	24	<.01	16	230	2008	835	<20	3	<.01	<10	22	<10	2	241
CDRS-R101	105	2.8	0.18	360	335	<5	0.37	16	15	103	85	8.03	<10	0.16	236	18	<.01	140	50	448	20	<20	3	<.01	10	11	<10	3	1571
CDRS-R102	435	>30	0.58	>10000	30	>10000	1.24	803	14	4	>10000	4.14	<10	0.14	46	<1	<.01	63	>10000	>10000	>10000	<20	4	<.01	20	31	<10	<1	>10000
CDRS-R103	225	>30	0.73	8150	90	<5	0.16	419	4	265	>10000	1.82	<10	0.03	37	19	<.01	41	1230	>10000	9595	<20	4	<.01	30	31	<10	2	3952
CDRS-R104	75	23.0	>15	300	410	<5	0.29	56	35	35	6049	0.35	10	0.07	111	<1	<.01	1562	880	5222	205	<20	11	<.01	<10	243	<10	214	7711
CDRS-R108	320	>30	0.17	3160	190	<5	0.25	61	2	112	>10000	0.28	<10	0.07	24	4	<.01	25	860	1204	6155	<20	1	<.01	<10	3	<10	2	1315
CDRS-R107	85	>30	6.66	>10000	210	<5	0.66	201	16	81	>10000	8.57	160	0.15	89	41	<.01	467	>10000	>10000	1810	<20	120	<.01	<10	102	<10	140	8853
CDRS-R108	165	>30	2.31	>10000	65	<5	0.54	332	6	116	>10000	2.58	290	0.09	53	17	<.01	44	5760	>10000	8010	<20	139	<.01	<10	44	<10	60	1353
CDRS-R109	560	25.6	0.07	255	80	<5	7	8	7	333	1.18	>10	14.90	168	<1	<.01	50	1145	1436	240	55	<20	56	<.01	<10	8	<10	5	431
CDRS-R110	125	4.4	0.02	45	30	<5	10.40	1	<1	167	55	0.28	<10	0.14	24	13	<.01	6	110	222	45	<20	290	<.01	<10	2	<10	12	25
CDRS-R111	20	1.8	0.06	15	40	<5	1.06	<1	1	83	30	0.30	<10	0.05	15	10	<.01	11	70	96	15	<20	22	<.01	<10	4	<10	2	45
CDRS-R113	165	5.8	2.01	30	115	<5	0.05	3	14	89	84	6.75	<10	<.01	160	5	<.01	90	210	250	20	<20	4	<.01	20	23	<10	11	304
CDRS-R114	505	1.2	0.09	10	65	10	0.05	2	6	175	49	7.44	<10	<.01	29	11	<.01	32	140	58	<5	<20	1	<.01	20	20	<10	1	155
CDRS-R117	515	8.0	0.30	75	110	<5	0.09	29	2	147	227	0.44	<10	0.04	43	4	<.01	25	70	490	25	<20	2	<.01	<10	10	<10	2	4547
CDRS-R118	210	2.6	0.41	75	110	<5	0.23	4	2	152	209	0.62	<10	0.10	30	7	0.01	38	230	384	35	<20	9	<.01	<10	7	<10	7	705
CDRS-R119	10	<.2	0.02	450	30	<5	0.54	>1000	5	3	>10000	0.19	40	0.07	91	<1	<.01	26	>10000	2012	755	<20	2	<.01	<10	10	<10	14	>10000
CDRS-R120	10	>30	<.01	1170	25	<5	6.70	82	<1	164	3108	0.23	10	0.18	63	11	0.02	5	230	5878	1550	<20	63	<.01	<10	3	<10	2	3128

● STREAM SEDIMENT SAMPLES

Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
94 ATL 001		<5	0.4	0.98	20	790	<5	1.52	2	12	19	41	2.61	<10	0.65	706	1	<.01	27	650	46	10	<20	40	0.01	10	42	<10	5	138
94 ATL 002		<5	<.2	0.94	20	150	5	0.20	<1	4	21	17	2.73	<10	0.24	65	<1	<.01	20	800	15	<5	<20	15	<.01	<10	12	<10	1	42
94 ATL 003		<5	<.2	0.87	15	85	<5	2.92	<1	10	42	25	3.08	<10	0.46	360	2	<.01	46	1930	10	<5	<20	105	<.01	<10	26	<10	15	138
94 ATL 004		<5	<.2	1.24	15	95	<5	2.90	<1	8	18	29	2.90	<10	0.30	724	1	<.01	30	1120	8	<5	<20	86	<.01	<10	24	<10	11	86
94 ATL 005		<5	<.2	0.91	15	215	5	0.90	<1	11	16	17	2.64	<10	0.26	517	<1	<.01	24	630	18	<5	<20	27	0.01	<10	41	<10	4	95
94 ATL 006		<5	0.4	1.21	20	395	<5	1.58	3	13	21	52	2.34	<10	0.56	449	9	<.01	50	930	68	10	<20	22	0.01	<10	74	<10	10	267
94 ATL 007		<5	<.2	0.81	<5	105	<5	0.46	<1	8	15	14	2.37	<10	0.31	175	1	<.01	24	500	14	<5	<20	30	<.01	<10	22	<10	2	86
94 ATL 008		<5	<.2	0.81	<5	105	<5	0.48	<1	8	15	14	2.37	<10	0.31	175	1	<.01	24	500	14	<5	<20	30	<.01	<10	22	<10	2	86
94 ATL 009		<5	<.2	0.29	10	110	<5	0.07	<1	3	8	7	0.78	<10	0.05	42	3	<.01	9	300	10	<5	<20	19	<.01	<10	14	<10	2	35
94 ATL 010		<5	0.7	1.15	20	300	<5	0.34	<1	2	7	19	1.42	<10	0.08	52	7	<.01	10	810	16	<5	<20	33	<.01	<10	29	<10	2	32
94 ATL 011		<5	<.2	0.72	10	115	<5	0.23	<1	4	9	11	1.07	<10	0.10	128	4	<.01	11	530	8	<5	<20	22	<.01	<10	18	<10	2	45
94 ATL 012		<5	0.4	0.44	5	105	<5	0.41	<1	3	8	9	0.98	<10	0.12	66	<1	<.01	10	620	10	<5	<20	22	<.01	<10	18	<10	4	42
94 ATL 013		<5	<.2	0.85	10	125	<5	1.57	<1	6	28	24	2.45	<10	0.30	76	<1	<.01	26	770	12	<5	<20	40	<.01	<10	41	<10	9	152
94 ATL 014		<5	<.2	0.72	<5	80	<5	0.36	<1	5	18	14	2.65	<10	0.26	536	<1	<.01	27	490	12	<5	<20	31	<.01	<10	17	<10	5	83
94 ATL 015		<5	<.2	0.84	10	80	<5	0.28	<1	11	15	17	3.00	<10	0.30	260	<1	<.01	27	660	16	<5	<20	45	<.01	<10	17	<10	3	80
94 ATL 016		<5	<.2	0.85	5	85	<5	1.23	<1	6	28	14	2.00	<10	0.30	76	<1	<.01	28	630	12	<5	<20	72	<.01	<10	21	<10	8	105
94 ATL 017		<5	<.2	0.80	10	85	<5	0.72	<1	9	18	16	2.63	<10	0.25	185	<1	<.01	32	570	12	<5	<20	24	<.01	<10	22	<10	4	118
94 ATL 018		<5	<.2	0.85	<5	85	<5	0.81	<1	9	18	14	2.48	<10	0.27	196	<1	<.01	29	510	12	<5	<20	45	<.01	<10	21	<10	4	88
94 ATL 019		<5	<.2	0.90	10	160	<5	0.17	<1	4	19	15	2.14	<10	0.21	53	<1	<.01	17	480	14	<5	<20	15	<.01	<10	35	<10	2	55
94 ATL 020		<5	<.2	0.81	5	125	<5	0.12	<1	2	19	12	2.10	<10	0.20	22	<1	<.01	17	640	16	<5	<20	28	<.01	<10	30	<10	<1	38
94 ATL 021		<5	<.2	0.79	10	85	<5	0.23	<1	12	15	18	3.10	<10	0.25	196	1	<.01	28	540	12	<5	<20	33	<.01	<10	22	<10	2	107
94 ATL 022		<5	<.2	0.81	10	160	<5	0.78	1	12	16	15	2.78	<10	0.25	273	1	<.01	29	610	14	<5	<20	27	<.01	<10	31	<10	3	95
G 9		<5	0.2	0.72	10	115	<5	0.11	<1	4	14	13	1.97	<10	0.17	40	<1	<.01	21	150	>10000	45	<20	17	<.01	<10	22	<10	2	57
G 10		<5	0.2	1.01	<5	175	10	0.41	<1	16	17	14	6.82	<10	0.22	338	<1	<.01	25	490	10	<5	<20	25	<.01	20	29	<10	<1	124
G 11		<5	<.2	0.74	10	100	<5	0.36	<1	11	14	15	2.38	<10	0.18	182	<1	<.01	33	400	12	<5	<20	18	<.01	<10	22	<10	2	129
G 14		<5	<.2	0.74	10	100	<5	0.36	<1	11	14	15	2.38	<10	0.18	182	<1	<.01	33	400	12	<5	<20	18	<.01	<10	22	<10	2	129
G 15		<5	<.2	0.87	10	110	<5	0.24	<1	6	18	9	2.26	<10	0.25	90	<1	<.01	14	370	14	<5	<20	10	0.02	<10	32	<10	1	62
G 20		<5	<.2	0.34	20	45	<5	6.30	1	9	40	25	3.68	<10	0.08	185	<1	<.01	72	1280	52	<5	<20	47	<.01	<10	22	<10	28	371
RSBBS-1		<5	<.2	0.43	10	55	<5	6.40	2	9	15	18	2.39	<10	0.60	1120	1	<.01	22	880	14	<5	<20	34	<.01	<10	22	<10	5	125
RSBBS-2		<5	<.2	0.42	10	95	<5	0.32	<1	6	13	15	2.18	<10	0.08	36	<1	<.01	30	310	16	<5	<20	16	<.01	<10	20	<10	1	105
RSBBS-3		<5	<.2	0.56	10	80	<5	0.40	2	20	13	16	2.32	<10	0.08	815	<1	<.01	189	360	20	<5	<20	11	<.01	<10	18	<10	3	836
RSBBS-4		<5	<.2	0.52	5	80	<5	0.39	<1	9	14	12	1.96	<10	0.12	64	<1	<.01	32	320	14	<5	<20	12	<.01	<10	19	<10	2	125
RSBBS-5		<5	<.2	0.50	5	80	<5	0.68	<1	7	14	12	2.07	<10	0.11	121	<1	<.01	24	400	14	<5	<20	15	<.01	<10	21	<10	2	116
CDRS-S62		<5	<.2	0.05	5	135	<5	0.03	<1	1	1	1	0.25	<10	<.01	5	1	<.01	4	40	24	<5	<20	2	<.01	<10	1	<10	<1	14
CDRS-S63		<5	0.8	1.45	40	710	<5	1.92	2	16	22	95	3.45	<10	0.74	1120	5	<.01	55	900	34	15	<20	34	0.01	10	54	<10	11	159
CDRS-S65		<5	<.2	1.00	20	105	<5	0.21	9	9	11	83	1.39	<10	4.89	313	4	<.01	69	1000	28	30	<20	33	<.01	<10	56	<10	12	288
CDRS-S66		<5	0.2	1.29	40	230	<5	0.80	6	8	19	80	2.18	<10	0.36	228	5	<.01	47	750	28	5	<20	25	0.02	<10	83	<10	7	109
CDRS-S67		<5	<.2	1.07	25	185	<5	0.39	<1	5	17	39	1.60	<10	0.21	126	4	<.01	28	780	28	<5	<20	24	0.01	<10	49	<10	3	50
CDRS-S68		<5	<.2	0.62	10	105	<5	0.45	4	6	19	19	2.45	<10	0.21	86	2	<.01	24	590	14	<5	<20	22	<.01	<10	34	<10	4	84
CDRS-S69		<5	<.2	1.03	15	185	<5	0.19	<1	6	21	18	2.46	<10	0.25	58	<1	<.01	24	510	14	<5	<20	14	<.01	<10	40	<10	4	78
CDRS-S70		<5	0.2	0.87	10	200	<5	0.46	3	7	18	16	2.29	<10	0.15	142	3	<.01	27	560	14	<5	<20	24	<.01	<10	34	<10	3	80
CDRS-S71		<5	0.2	0.48	10	115	<5	0.32	<1	4	11	15	1.33	<10	0.12	50	3	<.01	13	340	12	<5	<20	15	<.01	<10	22	<10	4	42
CDRS-S72		<5	<.2	0.54	10	105	<5	0.21	<1	5	13	23	1.51	<10	0.24	99	<1	<.01	12	470	12	<5	<20	20	0.02	<10	27	<10	3	60
CDRS-S73		<5	<.2	0.38	5	100	<5	0.72	<1	3	11	13	1.17	<10	0.10	148	1	<.01	14	350	10	<5	<20	23	<.01	<10	18	<10	4	45
CDRS-S74		<5	<.2	0.21	5	110	<5	0.16	<1	2	6	7	0.87	<10	0.07	33	<1	<.01	9	160	12	<5	<20	11	<.01	<10	11	<10	1	30
CDRS-S75		<5	<.2	0.71	10	160	<5	0.17	<1	8	37	23	2.77	<10	0.21	292	<1	<.01	47	1860