



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List
Receiving Lab: Canada-Whitehorse
Received: June 17, 2013
Report Date: August 09, 2013
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI13000038.1

CLIENT JOB INFORMATION

Project: Lucky Strike
Shipment ID: LSTR_13_003
P.O. Number
Number of Samples: 37

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3
CANADA

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	35	Crush, split and pulverize 250 g rock to 200 mesh			WHI
3B	37	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1DX	37	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

CERTIFICATE OF ANALYSIS

WHI13000038.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1243599	Rock	2.13	<2	0.8	22.7	9.7	38	<0.1	12.1	3.6	95	1.71	7.1	<0.5	4.4	8	0.1	0.6	0.1	23	0.06
1243600	Rock	2.96	5	3.6	27.0	20.4	72	0.2	31.6	21.1	1521	3.84	16.4	6.8	3.1	10	0.7	1.0	0.1	28	0.02
LS-REP-4	Rock Pulp	0.80	501	37.9	>10000	997.6	>10000	58.9	16.4	3.9	607	12.68	106.7	1405	<0.1	31	224.0	24.0	8.1	8	1.53
1243601	Rock	3.83	6	10.0	28.6	18.1	116	0.3	41.5	41.5	3449	5.10	22.1	3.6	3.5	9	1.1	2.0	<0.1	28	<0.01
1243602	Rock	2.16	<2	1.4	13.8	29.4	24	0.1	11.5	1.5	54	1.29	7.8	4.5	2.9	8	<0.1	1.2	<0.1	15	<0.01
1243603	Rock	2.67	3	1.6	17.5	7.8	20	<0.1	9.1	5.1	116	1.47	6.5	2.1	4.9	7	0.1	0.5	<0.1	16	0.01
1243604	Rock	2.91	2	0.6	15.3	6.9	20	<0.1	9.2	3.9	87	0.99	2.8	0.9	6.2	9	<0.1	0.3	<0.1	17	0.05
1243605	Rock	2.20	<2	1.6	50.9	7.1	51	0.1	21.2	10.8	259	2.86	13.9	1.4	6.2	10	0.1	0.7	0.2	35	0.05
1243606	Rock	2.17	<2	1.7	37.2	7.8	62	<0.1	21.5	8.3	284	2.96	12.3	3.8	7.9	8	<0.1	0.7	0.1	33	0.06
1243607	Rock	2.88	<2	1.2	49.0	5.9	39	<0.1	18.5	7.3	146	2.05	12.0	1.6	5.1	14	<0.1	0.8	0.1	35	0.05
1243608	Rock	2.36	<2	1.8	47.6	10.4	73	<0.1	29.4	8.1	285	3.67	11.1	1.4	6.8	13	0.1	0.6	0.2	38	0.08
1243609	Rock	2.28	<2	1.0	26.9	12.4	63	<0.1	24.8	7.6	533	1.70	8.7	1.3	6.1	9	0.2	0.5	0.4	23	0.06
1243610	Rock	2.34	<2	2.0	29.3	9.8	71	0.1	40.1	12.0	862	3.45	13.5	1.3	5.1	9	<0.1	0.8	0.2	22	0.05
1243611	Rock	2.60	<2	1.3	30.4	18.1	101	0.2	50.9	18.4	1192	3.34	17.2	<0.5	6.7	9	0.2	0.7	0.4	35	0.07
1243612	Rock	2.43	<2	1.6	33.9	16.8	151	0.1	58.8	19.8	940	3.97	24.8	2.5	8.9	10	0.2	0.8	0.3	30	0.10
1243613	Rock	2.79	<2	1.5	32.4	18.4	130	0.1	47.5	17.0	927	3.91	19.2	<0.5	6.4	13	0.2	1.3	0.2	27	0.06
1243614	Rock	2.24	11	0.9	27.5	11.6	77	<0.1	28.0	9.5	309	2.00	40.8	2.3	5.0	10	0.2	0.8	0.2	26	0.05
1243615	Rock	2.88	4	1.3	23.9	25.0	51	0.3	10.5	3.4	79	1.90	24.4	4.8	5.7	14	0.1	1.3	0.3	27	0.03
1243616	Rock	2.45	3	5.1	36.5	17.2	83	0.2	19.1	5.3	166	5.28	10.0	1.5	6.0	9	0.3	0.7	0.1	32	0.07
1243617	Rock	2.91	9	4.5	22.0	8.0	44	<0.1	11.7	3.4	109	3.12	4.7	2.0	4.5	11	<0.1	0.4	0.2	25	0.06
1243618	Rock	2.99	<2	6.9	18.2	7.0	33	<0.1	8.4	3.4	128	2.34	6.9	1.7	4.5	9	0.1	0.4	<0.1	21	0.02
1243619	Rock	2.51	2	5.4	22.2	9.3	51	<0.1	12.4	2.9	99	2.27	13.1	<0.5	4.4	13	0.1	0.9	<0.1	24	0.02
1243620	Rock	3.71	802	48.5	43.6	63.1	137	0.5	23.5	6.6	188	4.49	4.9	915.1	3.9	11	0.3	1.8	0.2	27	0.02
1243621	Rock	4.51	126	29.2	47.4	31.8	155	0.2	31.0	7.8	224	4.77	6.1	131.0	6.3	11	0.5	1.4	0.1	47	0.03
1243622	Rock	3.24	491	16.4	56.5	23.8	131	0.2	32.2	9.2	267	4.43	20.4	181.6	6.2	11	0.2	0.9	0.2	41	0.03
1243623	Rock	3.29	162	5.3	41.8	11.8	115	0.2	32.7	11.0	380	4.68	13.2	62.6	6.5	10	0.2	0.7	0.2	30	0.02
1243624	Rock	2.35	6	2.4	19.7	8.0	90	<0.1	23.8	8.0	319	3.08	9.3	6.9	5.7	12	0.1	0.4	<0.1	32	0.02
1243625	Rock	2.12	21	2.5	26.6	9.3	110	<0.1	27.0	8.7	323	3.47	9.8	10.2	6.4	17	0.2	0.5	<0.1	32	0.03
LS-REP-5	Rock Pulp	0.80	<2	3.3	22.9	2.4	36	0.5	18.2	9.4	313	1.99	3.0	<0.5	1.0	29	0.2	0.3	<0.1	47	0.69
1243626	Rock	2.47	8	2.9	34.7	10.2	129	0.1	27.3	9.0	272	3.82	13.3	8.0	5.8	13	0.3	0.4	0.1	29	0.02

CERTIFICATE OF ANALYSIS

WHI13000038.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	TI	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
1243599	Rock	0.027	9	13	0.13	92	0.030	<20	0.46	0.003	0.26	<0.1	0.38	0.2	<0.05	1.8	<0.5	2	<0.2
1243600	Rock	0.075	8	10	0.04	356	0.005	<20	0.33	0.002	0.14	0.5	2.22	0.3	<0.05	2.3	<0.5	<1	<0.2
LS-REP-4	Rock Pulp	0.037	<1	12	1.55	18	0.002	<20	0.63	0.022	0.06	0.3	2.83	0.8	>10	1.5	2.1	5	7.2
1243601	Rock	0.092	8	10	0.02	574	0.003	<20	0.24	0.002	0.11	<0.1	4.65	0.4	<0.05	2.2	0.6	<1	<0.2
1243602	Rock	0.026	6	6	0.01	66	0.001	<20	0.26	0.003	0.14	<0.1	0.94	<0.1	<0.05	1.5	<0.5	<1	<0.2
1243603	Rock	0.029	8	6	0.04	82	0.006	<20	0.28	0.003	0.16	0.3	0.42	0.1	<0.05	1.4	<0.5	<1	<0.2
1243604	Rock	0.017	11	9	0.09	123	0.017	<20	0.43	0.006	0.26	<0.1	0.23	0.1	<0.05	1.5	<0.5	1	<0.2
1243605	Rock	0.043	13	14	0.15	150	0.034	<20	0.57	0.003	0.31	<0.1	0.36	0.2	<0.05	2.6	0.7	2	0.3
1243606	Rock	0.036	20	14	0.18	199	0.052	<20	0.69	0.004	0.42	0.2	0.25	0.3	<0.05	2.8	<0.5	2	<0.2
1243607	Rock	0.028	12	18	0.17	130	0.036	<20	0.54	0.003	0.31	<0.1	0.29	0.2	<0.05	2.6	1.2	2	<0.2
1243608	Rock	0.050	15	20	0.17	203	0.036	<20	0.71	0.003	0.39	<0.1	0.61	0.2	<0.05	3.4	1.0	2	<0.2
1243609	Rock	0.025	9	12	0.11	201	0.025	<20	0.48	0.002	0.27	0.3	0.32	0.2	<0.05	1.9	<0.5	2	<0.2
1243610	Rock	0.048	9	11	0.08	170	0.017	<20	0.44	0.009	0.21	<0.1	0.38	0.1	<0.05	2.9	<0.5	2	<0.2
1243611	Rock	0.042	11	15	0.12	207	0.022	<20	0.52	0.008	0.26	<0.1	0.31	0.2	<0.05	3.3	<0.5	2	<0.2
1243612	Rock	0.068	13	15	0.12	263	0.025	<20	0.57	0.008	0.29	0.1	0.27	0.2	<0.05	3.2	<0.5	2	<0.2
1243613	Rock	0.055	13	13	0.06	210	0.008	<20	0.52	0.004	0.22	<0.1	0.32	0.1	<0.05	3.7	<0.5	2	<0.2
1243614	Rock	0.037	9	11	0.03	138	0.003	<20	0.38	0.004	0.13	0.1	0.38	0.1	<0.05	2.9	<0.5	1	<0.2
1243615	Rock	0.045	9	16	0.03	152	0.004	<20	0.37	0.007	0.18	<0.1	0.32	0.2	0.07	3.0	0.8	2	0.3
1243616	Rock	0.060	9	15	0.16	525	0.032	<20	0.68	0.004	0.35	<0.1	0.26	0.4	<0.05	3.1	2.5	2	<0.2
1243617	Rock	0.038	9	10	0.12	168	0.024	<20	0.58	0.003	0.28	<0.1	0.55	0.2	<0.05	2.9	1.1	2	<0.2
1243618	Rock	0.028	8	9	0.05	159	0.008	<20	0.45	0.008	0.18	<0.1	0.58	0.1	<0.05	3.1	<0.5	2	<0.2
1243619	Rock	0.031	8	10	0.04	327	0.005	<20	0.36	0.003	0.16	<0.1	0.35	<0.1	<0.05	2.7	0.8	1	<0.2
1243620	Rock	0.051	8	12	0.04	626	0.003	<20	0.43	0.002	0.16	0.2	0.75	<0.1	<0.05	3.7	2.6	1	<0.2
1243621	Rock	0.074	17	17	0.05	648	0.007	<20	0.43	0.008	0.16	<0.1	0.40	0.1	<0.05	6.3	1.4	1	<0.2
1243622	Rock	0.080	12	19	0.04	368	0.004	<20	0.42	0.003	0.14	<0.1	0.44	<0.1	<0.05	6.8	0.6	2	<0.2
1243623	Rock	0.083	15	13	0.06	302	0.011	<20	0.42	0.004	0.21	0.2	0.29	0.2	<0.05	3.8	0.8	1	<0.2
1243624	Rock	0.043	11	21	0.05	258	0.006	<20	0.51	0.003	0.16	<0.1	0.33	0.2	<0.05	4.6	<0.5	2	<0.2
1243625	Rock	0.057	13	18	0.08	237	0.008	<20	0.47	0.003	0.18	<0.1	0.20	0.1	<0.05	4.9	<0.5	2	<0.2
LS-REP-5	Rock Pulp	0.049	5	22	0.53	90	0.107	<20	1.12	0.065	0.09	17.0	0.02	<0.1	<0.05	3.7	<0.5	4	<0.2
1243626	Rock	0.058	11	18	0.05	188	0.004	<20	0.45	0.003	0.15	0.3	0.15	<0.1	<0.05	4.0	0.9	2	<0.2



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 3 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI13000038.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1243627	Rock	2.22	9	3.7	35.6	12.3	99	0.1	23.8	7.9	243	3.80	18.1	6.5	6.8	9	0.2	0.6	0.2	32	0.02
1243628	Rock	2.67	2	2.5	41.5	14.3	81	<0.1	21.1	6.6	225	3.69	24.5	1.1	5.0	12	0.3	1.0	0.2	22	0.01
1243629	Rock	2.67	10	1.9	40.9	31.7	93	0.1	26.1	7.5	160	3.43	20.8	8.7	8.8	12	0.2	1.3	0.2	25	0.01
1243630	Rock	2.52	417	5.6	38.3	18.1	107	0.2	23.8	9.8	399	3.08	30.1	234.6	6.9	27	0.3	3.5	0.3	26	0.02
1243631	Rock	2.99	2251	24.5	63.1	102.7	80	2.1	25.6	7.2	267	3.49	35.1	1704	5.4	13	0.3	21.6	0.3	30	0.02
1243632	Rock	3.30	97	2.7	57.8	17.2	72	<0.1	24.8	8.0	219	3.48	21.8	21.3	5.9	12	0.3	0.8	0.3	31	0.02
1243633	Rock	3.70	<2	1.7	42.6	15.9	65	<0.1	16.1	7.5	179	2.64	29.4	2.4	5.6	14	0.2	0.9	0.3	30	0.01



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI13000038.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
1243627	Rock	0.063	13	16	0.06	283	0.009	<20	0.44	0.003	0.18	<0.1	0.14	<0.1	<0.05	3.3	0.6	2	<0.2
1243628	Rock	0.077	11	13	0.02	145	0.002	<20	0.30	0.002	0.13	<0.1	0.08	<0.1	<0.05	2.3	<0.5	<1	<0.2
1243629	Rock	0.064	22	18	0.02	149	0.003	<20	0.29	0.003	0.15	0.1	0.07	<0.1	<0.05	4.9	1.4	<1	<0.2
1243630	Rock	0.043	11	16	0.03	2234	0.004	<20	0.37	0.003	0.15	<0.1	1.26	0.1	<0.05	3.1	0.5	1	<0.2
1243631	Rock	0.057	11	15	0.04	937	0.010	<20	0.35	0.003	0.15	<0.1	0.83	0.1	<0.05	3.5	1.8	1	<0.2
1243632	Rock	0.058	12	15	0.05	418	0.008	<20	0.44	0.003	0.18	0.2	0.09	0.1	<0.05	3.2	0.5	2	<0.2
1243633	Rock	0.049	11	14	0.03	175	0.005	<20	0.37	0.003	0.15	<0.1	0.10	<0.1	<0.05	3.1	0.8	1	<0.2

QUALITY CONTROL REPORT

WHI13000038.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1243606	Rock	2.17	<2	1.7	37.2	7.8	62	<0.1	21.5	8.3	284	2.96	12.3	3.8	7.9	8	<0.1	0.7	0.1	33	0.06
REP 1243606	QC			1.6	35.2	8.0	61	0.1	21.2	8.7	280	2.91	12.6	2.8	7.4	8	0.1	0.7	<0.1	33	0.06
1243611	Rock	2.60	<2	1.3	30.4	18.1	101	0.2	50.9	18.4	1192	3.34	17.2	<0.5	6.7	9	0.2	0.7	0.4	35	0.07
REP 1243611	QC		<2																		
Core Reject Duplicates																					
1243612	Rock	2.43	<2	1.6	33.9	16.8	151	0.1	58.8	19.8	940	3.97	24.8	2.5	8.9	10	0.2	0.8	0.3	30	0.10
DUP 1243612	QC		<2	1.4	31.1	15.9	137	0.1	56.2	18.0	885	3.68	23.1	1.3	8.1	10	0.1	0.9	0.2	29	0.08
Reference Materials																					
STD DS9	Standard			14.4	109.8	128.5	321	1.8	38.8	7.7	594	2.42	25.0	103.9	6.9	69	2.7	4.6	5.6	41	0.70
STD DS9	Standard			15.1	122.4	137.6	328	1.9	44.9	8.4	633	2.54	25.4	96.1	6.6	74	2.2	4.9	6.8	42	0.76
STD OREAS45EA	Standard			1.6	690.4	15.4	32	0.3	386.7	53.1	412	24.53	10.1	67.4	11.5	4	<0.1	0.2	0.2	301	0.04
STD OREAS45EA	Standard			1.6	730.8	17.0	30	0.3	407.4	54.8	413	25.21	9.8	61.8	11.6	4	<0.1	0.2	0.3	309	0.03
STD OXK94	Standard			3719																	
STD OXK94	Standard			3858																	
STD OXK94	Standard			3615																	
STD SH55	Standard			1393																	
STD SH55	Standard			1413																	
STD SH55	Standard			1426																	
STD SH55 Expected				1375																	
STD OXK94 Expected				3562																	
STD DS9 Expected				12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201
STD OREAS45EA Expected				1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI13000038.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
Pulp Duplicates																			
1243606	Rock	0.036	20	14	0.18	199	0.052	<20	0.69	0.004	0.42	0.2	0.25	0.3	<0.05	2.8	<0.5	2	<0.2
REP 1243606	QC	0.036	19	14	0.18	194	0.051	<20	0.68	0.003	0.41	0.3	0.24	0.3	<0.05	2.5	<0.5	2	<0.2
1243611	Rock	0.042	11	15	0.12	207	0.022	<20	0.52	0.008	0.26	<0.1	0.31	0.2	<0.05	3.3	<0.5	2	<0.2
REP 1243611	QC																		
Core Reject Duplicates																			
1243612	Rock	0.068	13	15	0.12	263	0.025	<20	0.57	0.008	0.29	0.1	0.27	0.2	<0.05	3.2	<0.5	2	<0.2
DUP 1243612	QC	0.061	13	14	0.12	249	0.023	<20	0.54	0.008	0.28	<0.1	0.24	0.2	<0.05	3.0	<0.5	2	<0.2
Reference Materials																			
STD DS9	Standard	0.087	13	121	0.63	331	0.110	<20	0.97	0.088	0.42	2.5	0.18	5.2	0.16	2.3	5.4	4	5.4
STD DS9	Standard	0.082	14	135	0.68	335	0.122	<20	1.04	0.092	0.43	3.0	0.23	5.5	0.18	2.4	6.8	5	5.0
STD OREAS45EA	Standard	0.029	7	839	0.11	149	0.092	<20	3.29	0.022	0.06	<0.1	<0.01	<0.1	<0.05	78.7	<0.5	12	<0.2
STD OREAS45EA	Standard	0.026	8	894	0.09	157	0.092	<20	3.34	0.026	0.06	<0.1	0.01	<0.1	<0.05	75.5	0.9	13	<0.2
STD OXK94	Standard																		
STD OXK94	Standard																		
STD OXK94	Standard																		
STD SH55	Standard																		
STD SH55	Standard																		
STD SH55	Standard																		
STD SH55 Expected																			
STD OXK94 Expected																			
STD DS9 Expected		0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59	5.02
STD OREAS45EA Expected		0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7	0.11
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
Report Date: August 09, 2013

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI13000038.1

	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																				
G1-WHI	Prep Blank	<2	<0.1	1.8	3.0	48	<0.1	3.5	4.3	555	1.92	<0.5	<0.5	4.2	49	<0.1	<0.1	<0.1	37	0.45
G1-WHI	Prep Blank	<2	0.1	2.0	3.5	47	<0.1	3.9	4.4	555	1.97	<0.5	1.7	4.1	51	<0.1	<0.1	<0.1	36	0.46



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
Report Date: August 09, 2013

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI1300038.1

		1DX P %	1DX La ppm	1DX Cr ppm	1DX Mg %	1DX Ba ppm	1DX Ti %	1DX B ppm	1DX Al %	1DX Na %	1DX K %	1DX W ppm	1DX Hg ppm	1DX Tl ppm	1DX S %	1DX Sc ppm	1DX Se ppm	1DX Ga ppm	1DX Te ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.082	8	5	0.58	234	0.123	<20	0.94	0.071	0.50	0.7	<0.01	0.3	<0.05	1.9	<0.5	5	<0.2
G1-WHI	Prep Blank	0.078	8	7	0.58	225	0.125	<20	0.96	0.078	0.49	<0.1	<0.01	0.3	<0.05	2.1	<0.5	5	<0.2