



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List
Receiving Lab: Canada-Whitehorse
Received: June 17, 2013
Report Date: August 09, 2013
Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI13000039.1

CLIENT JOB INFORMATION

Project: Lucky Strike
Shipment ID: LSTR_13_004
P.O. Number
Number of Samples: 26

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.


Invoice To: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3
CANADA

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	25	Crush, split and pulverize 250 g rock to 200 mesh			WHI
3B	26	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1DX	26	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

CERTIFICATE OF ANALYSIS

WHI13000039.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1243634	Rock	2.24	<2	1.2	39.4	8.1	30	<0.1	21.7	8.4	453	1.98	6.3	1.0	4.3	10	<0.1	0.5	0.1	32	0.02
1243635	Rock	3.82	<2	1.2	30.6	6.5	44	<0.1	27.9	14.7	1400	2.24	8.5	1.8	3.9	10	0.2	1.0	0.1	21	0.02
1243636	Rock	2.88	<2	2.5	64.1	10.5	110	0.2	73.4	40.2	3887	5.43	14.7	1.0	4.5	16	0.4	2.8	0.1	28	0.02
1243637	Rock	2.82	<2	1.4	53.6	14.1	121	0.2	41.5	15.0	576	4.38	9.5	1.3	4.7	13	0.2	1.7	0.2	33	0.03
1243638	Rock	2.70	<2	2.6	59.9	9.2	75	0.1	24.7	7.3	135	3.56	10.2	1.0	3.5	9	0.2	1.1	<0.1	30	0.04
1243639	Rock	2.29	6	3.2	50.9	7.4	35	0.1	11.6	4.2	155	2.18	5.0	5.0	3.8	13	<0.1	0.8	0.2	19	0.03
1243640	Rock	2.44	<2	2.4	75.5	6.0	55	<0.1	14.0	4.2	113	3.09	6.4	1.8	4.5	15	0.2	0.9	<0.1	14	0.03
1243641	Rock	3.16	<2	5.9	62.7	8.9	57	<0.1	18.5	4.9	189	3.49	8.3	2.9	6.9	14	0.2	0.7	0.1	40	0.06
1243642	Rock	3.54	8	23.3	54.1	11.1	142	0.1	62.6	21.5	1337	4.77	6.6	8.9	7.5	12	0.5	1.1	<0.1	43	0.04
1243643	Rock	4.14	325	288.3	41.3	22.7	121	0.2	25.0	9.5	598	5.75	7.5	149.3	13.2	9	0.1	2.5	0.2	47	0.02
1243644	Rock	4.12	164	197.4	17.1	29.5	86	0.4	26.5	13.8	524	4.01	3.7	126.7	5.6	6	<0.1	1.3	0.2	22	0.02
1243645	Rock	1.97	293	452.2	36.4	22.2	88	0.5	22.3	10.0	285	4.12	5.6	164.5	6.1	6	<0.1	2.3	0.2	28	0.01
1243646	Rock	2.71	121	36.5	18.8	5.1	68	0.2	17.9	8.9	520	3.74	3.5	171.3	8.8	7	<0.1	0.5	<0.1	19	0.02
1243647	Rock	2.60	14	27.8	34.6	28.7	52	0.1	17.0	9.0	418	3.30	14.5	8.7	4.8	13	0.2	0.8	0.2	23	0.02
1243648	Rock	2.90	<2	6.8	24.9	25.7	35	0.1	9.0	3.0	71	1.23	18.0	1.4	2.7	27	0.3	1.8	0.2	18	0.02
1243649	Rock	2.51	<2	5.4	39.0	30.6	28	0.1	8.7	3.2	91	1.96	34.4	3.9	3.2	21	0.2	3.4	0.2	21	0.02
1243650	Rock	2.42	140	194.6	45.7	46.9	126	0.3	28.0	8.1	265	4.43	17.5	47.4	4.4	11	<0.1	2.2	0.2	25	0.02
LS-REP-6	Rock Pulp	0.08	6464	1.3	15.2	22.4	56	0.1	12.0	1.3	924	0.53	4407	6808	1.3	193	0.4	18.9	0.4	19	25.38
1243651	Rock	3.09	229	72.7	49.6	21.5	69	0.3	19.1	5.9	260	3.68	19.3	203.1	4.8	16	0.2	2.3	0.1	29	0.02
1243652	Rock	3.43	45	83.1	35.1	37.4	57	0.2	16.5	5.6	163	2.28	9.8	33.5	3.6	14	0.1	1.8	0.4	18	0.02
1243653	Rock	3.08	149	197.9	24.9	110.3	55	0.4	17.2	5.8	192	2.13	7.6	101.7	3.2	12	<0.1	1.7	1.2	17	0.01
1243654	Rock	2.68	26	5.1	39.9	13.4	118	0.1	37.7	11.4	487	4.10	13.1	29.0	8.3	11	0.2	0.7	0.2	30	0.02
1243655	Rock	2.71	215	6.2	42.2	17.2	195	0.2	55.9	17.1	501	5.78	19.2	175.9	5.8	12	0.5	1.3	0.2	30	0.03
1243656	Rock	2.53	4	3.6	31.9	15.6	82	0.1	24.5	7.4	219	2.95	11.7	18.1	4.9	12	0.1	0.5	0.1	24	0.02
1243657	Rock	2.98	109	4.4	43.4	43.8	67	0.2	20.0	5.1	138	3.13	17.6	107.5	5.3	13	0.1	0.9	0.4	22	0.02
1243658	Rock	3.58	17	1.8	43.0	15.2	111	<0.1	33.7	9.9	252	3.71	25.0	17.4	6.5	15	0.2	1.2	0.2	32	0.03



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 2 of 2

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI13000039.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	TI	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
1243634	Rock	0.033	9	14	0.08	167	0.015	<20	0.43	0.002	0.17	<0.1	0.30	<0.1	<0.05	3.4	<0.5	2	<0.2
1243635	Rock	0.032	8	10	0.05	234	0.010	<20	0.35	0.003	0.15	<0.1	0.38	<0.1	<0.05	2.5	<0.5	1	<0.2
1243636	Rock	0.075	12	12	0.06	469	0.010	<20	0.38	0.005	0.20	2.3	0.57	0.1	<0.05	3.1	<0.5	1	<0.2
1243637	Rock	0.065	10	16	0.04	198	0.008	<20	0.35	0.002	0.16	<0.1	0.45	0.1	<0.05	3.1	0.6	1	<0.2
1243638	Rock	0.058	7	11	0.03	127	0.005	<20	0.37	0.011	0.14	<0.1	0.64	<0.1	<0.05	3.0	1.1	1	<0.2
1243639	Rock	0.041	9	7	0.07	183	0.015	<20	0.41	0.016	0.19	0.9	0.62	0.2	0.06	3.3	1.1	2	<0.2
1243640	Rock	0.058	11	5	0.06	255	0.008	<20	0.45	0.018	0.21	<0.1	1.59	0.1	0.06	4.7	0.6	1	<0.2
1243641	Rock	0.069	14	22	0.15	249	0.026	<20	0.69	0.004	0.32	<0.1	3.33	0.2	<0.05	5.1	1.2	2	<0.2
1243642	Rock	0.073	22	27	0.16	476	0.030	<20	0.78	0.005	0.37	0.5	3.68	0.3	<0.05	6.3	2.1	2	<0.2
1243643	Rock	0.107	46	19	0.03	233	0.004	<20	0.47	0.002	0.10	0.2	3.89	0.1	<0.05	12.1	2.4	1	0.4
1243644	Rock	0.060	18	10	0.02	209	0.003	<20	0.50	0.003	0.08	<0.1	1.92	0.2	<0.05	6.3	1.5	1	<0.2
1243645	Rock	0.055	18	13	0.05	158	0.008	<20	0.45	0.003	0.13	0.4	2.12	0.1	<0.05	5.8	1.7	1	0.4
1243646	Rock	0.044	21	6	0.03	274	0.005	<20	0.41	0.004	0.12	<0.1	7.43	0.2	<0.05	5.4	0.9	1	<0.2
1243647	Rock	0.045	11	10	0.02	271	0.002	<20	0.36	0.002	0.11	<0.1	2.07	0.1	<0.05	3.9	1.0	1	<0.2
1243648	Rock	0.022	7	9	0.02	420	0.003	<20	0.36	0.002	0.13	0.5	0.94	<0.1	<0.05	2.3	<0.5	<1	<0.2
1243649	Rock	0.044	7	11	0.01	346	0.002	<20	0.31	0.002	0.10	<0.1	1.02	<0.1	<0.05	1.9	1.7	<1	<0.2
1243650	Rock	0.047	11	13	0.02	206	0.002	<20	0.38	0.004	0.13	<0.1	0.56	0.1	<0.05	3.1	1.5	<1	0.3
LS-REP-6	Rock Pulp	0.015	7	24	6.74	41	0.001	<20	0.22	0.016	0.06	3.9	4.53	16.5	<0.05	1.9	<0.5	<1	<0.2
1243651	Rock	0.048	13	14	0.03	233	0.004	<20	0.34	0.003	0.13	0.4	0.63	0.2	<0.05	3.4	1.4	1	<0.2
1243652	Rock	0.033	9	12	0.03	398	0.005	<20	0.33	0.003	0.15	<0.1	0.47	0.1	<0.05	2.7	0.7	1	0.2
1243653	Rock	0.029	7	11	0.02	198	0.003	<20	0.31	0.002	0.10	<0.1	0.42	0.1	<0.05	2.3	0.7	<1	0.6
1243654	Rock	0.061	19	16	0.06	241	0.011	<20	0.41	0.003	0.21	<0.1	0.24	0.2	<0.05	3.9	1.1	1	<0.2
1243655	Rock	0.084	15	14	0.03	236	0.005	<20	0.42	0.003	0.18	<0.1	0.45	0.1	<0.05	3.7	1.0	1	<0.2
1243656	Rock	0.038	12	13	0.03	344	0.004	<20	0.33	0.003	0.14	0.4	0.36	<0.1	<0.05	2.9	<0.5	1	<0.2
1243657	Rock	0.047	13	11	0.03	146	0.003	<20	0.35	0.003	0.15	<0.1	0.36	<0.1	<0.05	2.7	0.8	1	<0.2
1243658	Rock	0.054	15	14	0.04	522	0.005	<20	0.41	0.003	0.17	<0.1	0.14	0.1	<0.05	4.6	0.9	1	<0.2

QUALITY CONTROL REPORT

WHI13000039.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1243637	Rock	2.82	<2	1.4	53.6	14.1	121	0.2	41.5	15.0	576	4.38	9.5	1.3	4.7	13	0.2	1.7	0.2	33	0.03
REP 1243637	QC			1.7	57.9	14.5	126	0.2	43.7	15.1	608	4.57	10.0	2.4	4.9	13	0.2	1.6	0.2	35	0.03
1243642	Rock	3.54	8	23.3	54.1	11.1	142	0.1	62.6	21.5	1337	4.77	6.6	8.9	7.5	12	0.5	1.1	<0.1	43	0.04
REP 1243642	QC		6																		
Core Reject Duplicates																					
1243653	Rock	3.08	149	197.9	24.9	110.3	55	0.4	17.2	5.8	192	2.13	7.6	101.7	3.2	12	<0.1	1.7	1.2	17	0.01
DUP 1243653	QC		144	209.3	27.6	117.2	60	0.4	17.0	6.4	212	2.27	7.7	180.0	3.5	13	<0.1	1.7	1.3	18	0.01
Reference Materials																					
STD DS9	Standard			15.1	122.4	137.6	328	1.9	44.9	8.4	633	2.54	25.4	96.1	6.6	74	2.2	4.9	6.8	42	0.76
STD OREAS45EA	Standard			1.6	730.8	17.0	30	0.3	407.4	54.8	413	25.21	9.8	61.8	11.6	4	<0.1	0.2	0.3	309	0.03
STD OXK94	Standard		3615																		
STD OXK94	Standard		3595																		
STD SH55	Standard		1426																		
STD SH55	Standard		1382																		
STD SH55 Expected			1375																		
STD OXK94 Expected			3562																		
STD DS9 Expected			12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201	
STD OREAS45EA Expected			1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032	
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1-WHI	Prep Blank		<2	0.1	2.1	3.7	53	<0.1	5.1	5.1	616	2.11	<0.5	2.7	5.4	62	<0.1	<0.1	<0.1	39	0.49
G1-WHI	Prep Blank		<2	0.1	1.9	5.7	51	<0.1	4.4	5.4	607	2.09	<0.5	<0.5	4.9	72	<0.1	<0.1	<0.1	38	0.52

QUALITY CONTROL REPORT

WHI13000039.1

Method		1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
Pulp Duplicates																			
1243637	Rock	0.065	10	16	0.04	198	0.008	<20	0.35	0.002	0.16	<0.1	0.45	0.1	<0.05	3.1	0.6	1	<0.2
REP 1243637	QC	0.063	10	16	0.05	203	0.008	<20	0.36	0.004	0.17	<0.1	0.47	0.1	<0.05	3.3	<0.5	1	<0.2
1243642	Rock	0.073	22	27	0.16	476	0.030	<20	0.78	0.005	0.37	0.5	3.68	0.3	<0.05	6.3	2.1	2	<0.2
REP 1243642	QC																		
Core Reject Duplicates																			
1243653	Rock	0.029	7	11	0.02	198	0.003	<20	0.31	0.002	0.10	<0.1	0.42	0.1	<0.05	2.3	0.7	<1	0.6
DUP 1243653	QC	0.031	8	11	0.02	215	0.003	<20	0.32	0.003	0.12	0.7	0.48	0.1	<0.05	2.7	1.0	1	0.7
Reference Materials																			
STD DS9	Standard	0.082	14	135	0.68	335	0.122	<20	1.04	0.092	0.43	3.0	0.23	5.5	0.18	2.4	6.8	5	5.0
STD OREAS45EA	Standard	0.026	8	894	0.09	157	0.092	<20	3.34	0.026	0.06	<0.1	0.01	<0.1	<0.05	75.5	0.9	13	<0.2
STD OXK94	Standard																		
STD OXK94	Standard																		
STD SH55	Standard																		
STD SH55	Standard																		
STD SH55 Expected																			
STD OXK94 Expected																			
STD DS9 Expected		0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59	5.02
STD OREAS45EA Expected		0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7	0.11
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.082	11	8	0.64	254	0.148	<20	1.03	0.074	0.53	<0.1	<0.01	0.3	<0.05	2.3	<0.5	5	<0.2
G1-WHI	Prep Blank	0.076	11	8	0.64	244	0.146	<20	1.05	0.091	0.53	3.3	<0.01	0.3	<0.05	2.3	<0.5	5	<0.2