



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List
Receiving Lab: Canada-Whitehorse
Received: June 17, 2013
Report Date: August 09, 2013
Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI13000041.1

CLIENT JOB INFORMATION

Project: Lucky Strike
Shipment ID: LUC_ROCK_2013_1
P.O. Number
Number of Samples: 9

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3
CANADA

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Table with 6 columns: Procedure Code, Number of Samples, Code Description, Test Wgt (g), Report Status, Lab. Rows include R200-250, 3B, and 1DX.

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
Report Date: August 09, 2013

Page: 2 of 2

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI1300041.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1232101	Rock	1.31	4	1.5	29.1	10.8	16	0.1	8.7	5.7	147	1.34	12.8	2.8	4.7	6	<0.1	1.5	0.3	18	0.01
1232102	Rock	2.77	4	5.6	56.3	20.4	85	0.1	44.4	10.4	257	4.74	6.8	2.1	6.4	10	0.2	0.6	0.1	36	0.05
1232103	Rock	1.49	98	53.6	22.6	15.5	170	0.2	32.6	11.7	360	7.27	8.7	51.9	3.3	21	0.2	2.1	<0.1	39	0.02
1227801	Rock	1.01	3	1.9	42.0	18.3	93	0.1	48.3	11.6	329	2.88	14.4	1.5	7.4	9	<0.1	0.3	<0.1	24	0.02
1227802	Rock	1.02	12	0.9	39.0	24.9	14	0.3	4.9	0.8	42	1.47	28.4	8.5	4.7	20	<0.1	1.2	<0.1	9	<0.01
1227803	Rock	3.41	95	1.3	44.6	17.3	101	0.2	25.9	6.9	206	3.75	21.3	71.1	4.5	8	0.2	0.6	<0.1	19	<0.01
1227804	Rock	1.08	9	3.1	47.7	13.0	39	<0.1	12.6	6.6	145	3.17	28.8	4.6	6.1	11	0.1	0.3	0.1	33	0.02
1227805	Rock	1.02	8	0.7	28.3	12.2	122	0.1	39.8	8.6	176	3.68	1.3	5.2	12.2	7	0.1	0.2	0.1	45	0.07
1227806	Rock	1.41	5389	11.9	29.1	20.3	38	0.6	13.1	2.1	63	2.83	16.0	1647	3.0	6	<0.1	2.2	0.4	8	0.02



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 2 of 2

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI1300041.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
1232101	Rock	0.026	10	9	0.03	83	0.003	<20	0.25	0.003	0.17	<0.1	0.51	<0.1	<0.05	1.8	1.9	<1	<0.2
1232102	Rock	0.082	14	15	0.08	109	0.010	<20	0.39	0.004	0.19	<0.1	0.57	0.1	<0.05	3.4	1.2	1	<0.2
1232103	Rock	0.062	5	18	0.01	238	0.001	<20	0.28	0.001	0.09	<0.1	0.46	<0.1	<0.05	5.0	1.5	<1	<0.2
1227801	Rock	0.034	12	12	0.06	141	0.010	<20	0.36	0.003	0.18	<0.1	0.07	0.1	<0.05	2.6	0.6	1	<0.2
1227802	Rock	0.042	7	9	<0.01	400	0.002	<20	0.18	<0.001	0.06	<0.1	0.13	<0.1	<0.05	0.9	1.8	<1	0.3
1227803	Rock	0.091	10	8	0.07	230	0.015	<20	0.31	0.002	0.17	<0.1	0.06	0.1	<0.05	1.6	<0.5	<1	<0.2
1227804	Rock	0.070	12	13	0.04	142	0.006	<20	0.33	0.002	0.13	<0.1	0.10	<0.1	<0.05	3.2	0.8	<1	<0.2
1227805	Rock	0.043	21	27	0.31	225	0.077	<20	0.98	0.004	0.63	<0.1	0.02	0.4	<0.05	3.6	1.2	3	<0.2
1227806	Rock	0.034	7	7	<0.01	507	0.001	<20	0.21	<0.001	0.05	<0.1	0.11	<0.1	<0.05	4.1	2.5	<1	0.3

QUALITY CONTROL REPORT

WHI13000041.1

Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1227806	Rock	1.41	5389	11.9	29.1	20.3	38	0.6	13.1	2.1	63	2.83	16.0	1647	3.0	6	<0.1	2.2	0.4	8	0.02
REP 1227806	QC		5282																		
Reference Materials																					
STD DS9	Standard			13.1	115.2	141.4	322	1.8	42.8	7.8	628	2.51	27.3	122.8	6.8	81	2.7	4.6	6.2	42	0.76
STD OREAS45EA	Standard			1.4	727.4	16.7	30	0.3	406.2	55.1	438	24.14	9.8	59.0	12.4	4	<0.1	0.2	0.3	316	0.04
STD OXK94	Standard		3653																		
STD SH55	Standard		1423																		
STD SH55	Standard		1388																		
STD OXK94 Expected			3562																		
STD SH55 Expected			1375																		
STD DS9 Expected				12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201
STD OREAS45EA Expected				1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		2																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1-WHI	Prep Blank		<2	<0.1	2.0	16.5	51	0.1	4.2	4.4	622	2.12	<0.5	0.8	4.9	66	<0.1	<0.1	<0.1	40	0.53



www.acmelab.com

Acme Analytical Laboratories (Vancouver) Ltd.
 9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
 PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
 1300 - 1111 West Georgia Street
 Vancouver BC V6E 4M3 CANADA

Project: Lucky Strike
 Report Date: August 09, 2013

Page: 1 of 1

Part: 2 of 2

QUALITY CONTROL REPORT

WHI13000041.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2	
Pulp Duplicates																			
1227806	Rock	0.034	7	7	<0.01	507	0.001	<20	0.21	<0.001	0.05	<0.1	0.11	<0.1	<0.05	4.1	2.5	<1	0.3
REP 1227806	QC																		
Reference Materials																			
STD DS9	Standard	0.085	14	132	0.67	340	0.115	<20	1.03	0.085	0.42	3.2	0.20	5.4	0.18	2.3	4.7	5	5.6
STD OREAS45EA	Standard	0.028	7	840	0.11	154	0.096	<20	3.23	0.019	0.05	<0.1	0.02	<0.1	<0.05	83.7	<0.5	13	<0.2
STD OXK94	Standard																		
STD SH55	Standard																		
STD SH55	Standard																		
STD OXK94 Expected																			
STD SH55 Expected																			
STD DS9 Expected		0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59	5.02
STD OREAS45EA Expected		0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7	0.11
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.081	11	8	0.64	248	0.135	<20	1.06	0.085	0.53	<0.1	<0.01	0.3	<0.05	2.2	<0.5	5	<0.2