



Sample ID	Au (g/t)	As (ppm)	Ag (g/t)	Pb (%)	Cu (%)	Zn (%)	Mo (ppm)	Sb (ppm)	Bi (ppm)
K291402*	0.00	13	17.4	0.22	0.29	0.00	1.23	13	7
K291403*	0.02	37	8.2	0.24	0.47	0.01	0.98	25	0
K291408*	0.06	885	11.2	0.09	0.32	0.02	3070	8	250
K291411*	0.13	126	26.1	0.15	0.01	0.01	3.79	80	32
R503951*	0.18	98	1470	1.75	0.03	0.06	5.02	1730	109
R503952*	0.13	447	65.8	0.23	0.02	0.12	1.81	455	2
R503953*	0.13	201	6.9	0.16	0.02	0.10	2.95	245	0
R503954*	0.27	770	251	2.02	0.03	0.07	11.35	830	5
R503955*	0.54	217	2490	45.78	0.21	0.09	1.18	7410	9
R503958*	0.03	16	35.9	0.42	0.75	0.02	2.75	92	6
R503959*	0.00	19	5.4	0.01	0.42	0.01	3.31	6	1
R503961*	0.00	13	11.1	0.30	0.21	0.01	1.98	19	1
R503962*	0.06	22	13.7	0.02	0.25	0.00	25.80	9	18
R503964*	0.00	2	54.5	0.18	0.01	0.03	0.12	96	0
R503965*	1.53	1235	564	13.95	0.10	0.19	6.00	1585	3
R503966*	0.21	250	677	2.87	0.03	0.38	24.50	101	25100
R503967*	0.00	23	2.5	0.01	0.15	0.02	1.92	7	53
R503968*	2.25	973	11.4	0.04	0.00	0.01	96.00	140	36
R503970*	3.13	55	0.7	0.01	0.00	0.00	2.75	4	103
R503971*	0.19	40	1510	57.31	0.09	2.39	0.36	1710	34
R503972*	0.17	91	1635	51.93	0.21	5.42	2.30	2010	59
R503974*	0.82	269	59.3	0.47	0.03	0.05	4.34	127	59
R503976*	0.27	268	52.1	0.90	0.03	0.01	2.87	179	38
R503977*	1.81	16	1370	75.18	0.53	0.04	0.51	732	414
R503978*	1.09	3110	59.7	2.60	0.05	0.11	2.98	94	15
R503983*	0.15	98	3.6	0.01	0.19	0.04	0.44	2	141
R503990*	2.16	12350	388	17.15	0.43	0.16	26.70	1125	24
K283895	0.10	490	8.2	0.12	0.00	0.08	0.90	31	3
K283896	1.06	740	319	22.77	0.01	0.30	7.79	300	80
K283897	0.11	360	7.2	0.61	0.01	0.68	7.24	50	2
K283898	0.06	239	11.3	0.58	0.01	3.43	2.91	35	5
K283899	0.02	102	384	4.95	0.11	0.38	0.58	796	2
K283900	0.20	149	2950	19.70	0.51	0.16	2.11	5850	20
Q934551	0.89	82	2390	58.36	0.32	0.35	0.56	3410	49
Q934553	0.08	228	704	6.62	0.10	0.05	47.00	1725	19
Q934554	0.80	1015	6680	30.22	0.26	0.02	30.40	9060	32
Q934555	0.09	413	425	0.73	0.11	0.09	130	1195	24
R608477	0.06	211	23.3	0.03	1.58	0.02	1.92	16	208
R608489	0.13	288	2.8	0.02	0.00	0.09	1.60	34	1
R608490	0.21	845	7.2	0.15	0.01	0.23	9.23	69	4
R608491	0.00	27	1.1	0.00	0.40	0.04	4.74	13	1
R608492	0.01	110	3.2	0.01	0.48	0.01	0.71	8	103
R608493	0.05	272	26.7	0.01	0.67	0.02	2.09	16	91
H005	0.01	200	53.0	1.38	NA	NA	NA	NA	NA
H007	5.01	640	0.5	0.03	NA	NA	NA	NA	NA
H010	0.46	300	33.1	35.40	NA	NA	NA	NA	NA
H011	3.64	50	90.0	2.03	NA	NA	NA	NA	NA
H012	0.00	750	10.0	22.10	NA	NA	NA	NA	NA
H014	6.55	0	34.0	0.04	NA	NA	NA	NA	NA
H015	0.79	46	0.9	0.03	NA	NA	NA	NA	NA
H017	0.79	46	56.5	65.10	NA	NA	NA	NA	NA
H021	0.24	501	140	0.09	NA	NA	NA	NA	NA

**MESOZOIC**

- Weakly to moderately clay altered hornblende-biotite granodiorite and dacite dykes (Blonde gossan).
- Pyritiferous and silicified/clay altered hornblende-biotite granodiorite (Orange gossan).
- Massive and thinly bedded fine grained dark green andesite flows, hornblende or augite porphyritic andesite +/- feldspar phenocrysts and fine grained basalt.
- Medium to coarse grained hornblende-biotite syenite, quartz-monzonite and hornblende-biotite granodiorite with feldspar phenocrysts up to 2 cm.

Linear  
 Outcrop  
 Subcrop  
 Felsenmeer/talus  
 Limit of 2016 mapping  
 Inferred Contact

Significant Ag-Pb+/-Zn+/-Cu+/-Au+/-Mo rock sample with assay in table  
 Significant Au (> 1.0 g/t) rock sample with assay in table  
 2016 Hand trench

Rock Samples K291458 - K291464  
60.5 g/t silver and 0.79% lead over 2.1 m

Rock Samples K291478 - K291483  
9.4 g/t silver, 0.18 g/t gold, 0.4% lead and 0.3% zinc over 8.4 m

Rock Samples K291465 - K291477  
570 g/t silver, 2.76% lead, 0.08 g/t gold over 6.4 m and 106 g/t silver, 0.84% lead and 0.03 g/t gold over 9.6 m

Rock Samples K291451 - K291457  
375 g/t silver and 8.33% lead over 0.9 m

**STRATEGIC METALS LTD.**

FIGURE 7  
ARCHER, CATHRO & ASSOCIATES (1981) LIMITED  
**MINERALIZATION**  
OOO PROPERTY

0 1 km  
UTM ZONE 7, NAD 83, 115J08

FILE: ...2016/OOO DATE: OCTOBER 2016